

Specification for Automotive Weld Quality—Laser Beam Welding of Steel



Documents

Document Sharing Hub

AWS D8.10M:2021
An American National Standard

Approved by the
American National Standards Institute
September 8, 2020

Specification for Automotive Weld Quality—Laser Beam Welding of Steel

1st Edition

Prepared by the
American Welding Society (AWS) D8 Committee on Automotive Welding

Under the Direction of the
AWS Technical Activities Committee

Approved by the
AWS Board of Directors

Abstract

This document contains both visual and measurable acceptance criteria for laser beam welds in steels. The information contained herein may be used as an aid by designers, laser beam welding equipment manufacturers, welded product producers, and others involved in the automotive industry and laser beam welding of steels.



ISBN Print: 978-1-64322-149-6
ISBN PDF: 978-1-64322-150-2
© 2020 by American Welding Society
All rights reserved
Printed in the United States of America

Photocopy Rights. No portion of this standard may be reproduced, stored in a retrieval system, or transmitted in any form, including mechanical, photocopying, recording, or otherwise, without the prior written permission of the copyright owner.

Authorization to photocopy items for internal, personal, or educational classroom use only or the internal, personal, or educational classroom use only of specific clients is granted by the American Welding Society provided that the appropriate fee is paid to the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, tel: (978) 750-8400; Internet: <www.copyright.com>.

Statement on the Use of American Welding Society Standards

All standards (codes, specifications, recommended practices, methods, classifications, and guides) of the American Welding Society (AWS) are voluntary consensus standards that have been developed in accordance with the rules of the American National Standards Institute (ANSI). When AWS American National Standards are either incorporated in, or made part of, documents that are included in federal or state laws and regulations, or the regulations of other governmental bodies, their provisions carry the full legal authority of the statute. In such cases, any changes in those AWS standards must be approved by the governmental body having statutory jurisdiction before they can become a part of those laws and regulations. In all cases, these standards carry the full legal authority of the contract or other document that invokes the AWS standards. Where this contractual relationship exists, changes in or deviations from requirements of an AWS standard must be by agreement between the contracting parties.

AWS American National Standards are developed through a consensus standards development process that brings together volunteers representing varied viewpoints and interests to achieve consensus. While AWS administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in its standards.

AWS disclaims liability for any injury to persons or to property, or other damages of any nature whatsoever, whether special, indirect, consequential, or compensatory, directly or indirectly resulting from the publication, use of, or reliance on this standard. AWS also makes no guarantee or warranty as to the accuracy or completeness of any information published herein.

In issuing and making this standard available, AWS is neither undertaking to render professional or other services for or on behalf of any person or entity, nor is AWS undertaking to perform any duty owed by any person or entity to someone else. Anyone using these documents should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances. It is assumed that the use of this standard and its provisions is entrusted to appropriately qualified and competent personnel.

This standard may be superseded by new editions. This standard may also be corrected through publication of amendments or errata, or supplemented by publication of addenda. Information on the latest editions of AWS standards including amendments, errata, and addenda is posted on the AWS web page (www.aws.org). Users should ensure that they have the latest edition, amendments, errata, and addenda.

Publication of this standard does not authorize infringement of any patent or trade name. Users of this standard accept any and all liabilities for infringement of any patent or trade name items. AWS disclaims liability for the infringement of any patent or product trade name resulting from the use of this standard.

AWS does not monitor, police, or enforce compliance with this standard, nor does it have the power to do so.

Official interpretations of any of the technical requirements of this standard may only be obtained by sending a request, in writing, to the appropriate technical committee. Such requests should be addressed to the American Welding Society, Attention: Managing Director, Standards Development Division, 8669 NW 36 St, # 130, Miami, FL 33166 (see Annex B). With regard to technical inquiries made concerning AWS standards, oral opinions on AWS standards may be rendered. These opinions are offered solely as a convenience to users of this standard, and they do not constitute professional advice. Such opinions represent only the personal opinions of the particular individuals giving them. These individuals do not speak on behalf of AWS, nor do these oral opinions constitute official or unofficial opinions or interpretations of AWS. In addition, oral opinions are informal and should not be used as a substitute for an official interpretation.

This standard is subject to revision at any time by the AWS D8 Committee on Automotive Welding. It must be reviewed every five years, and if not revised, it must be either reaffirmed or withdrawn. Comments (recommendations, additions, or deletions) and any pertinent data that may be of use in improving this standard are requested and should be addressed to AWS Headquarters. Such comments will receive careful consideration by the AWS D8 Committee on Automotive Welding and the author of the comments will be informed of the Committee's response to the comments. Guests are invited to attend all meetings of the AWS D8 Committee on Automotive Welding to express their comments verbally. Procedures for appeal of an adverse decision concerning all such comments are provided in the Rules of Operation of the Technical Activities Committee. A copy of these Rules can be obtained from the American Welding Society, 8669 NW 36 St, # 130, Miami, FL 33166.

This page is intentionally blank.

Personnel

AWS D8 Committee on Automotive Welding

R. Ruokolainen, Chair	<i>FCA USA LLC</i>
H. Ghassemi-Armaki, Vice Chair	<i>ArcelorMittal—USA LLC</i>
A. Orr, 2nd Vice Chair	<i>Ford Motor Company</i>
M. Diaz, Secretary	<i>American Welding Society</i>
J. Beckham	<i>Fiat Chrysler Automobiles US LLC</i>
D. Bellish	<i>Obara Corporation</i>
T. Coon	<i>Ford Motor Company</i>
E. Cross	<i>Meggitt Aircraft Braking Systems</i>
M. Gugel	<i>US Steel</i>
F. W. Hunt	<i>Hitachi Automotive Systems Americas</i>
J. G. Hunt	<i>Fiat Chrysler Automobiles US LLC</i>
D. R. Kolodziej	<i>Ford Motor Company (Retired)</i>
D. F. Maatz	<i>R & E Engineering Services</i>
J. S. Noruk	<i>Servo Robot Corporation</i>
W. F. Qualls	<i>Consultant</i>
M. D. Tumuluru	<i>Consultant</i>
Z. Wang	<i>ArcelorMittal—USA LLC</i>
A. Young	<i>KUKA Robotics</i>

Advisors to the AWS D8 Committee on Automotive Welding

W. H. Brafford	<i>Consultant</i>
J. W. Dolfi	<i>Consultant</i>
W. W. Doneth	<i>Fronius USA LLC</i>
D. L. Galiher	<i>Tower International (Retired)</i>
S. C. Kelley	<i>ArcelorMittal—USA LLC (Retired)</i>
D. P. Kelly	<i>Fusion Welding Solutions</i>
T. W. Morrissett	<i>Consultant</i>

AWS D8E Subcommittee on Automotive Laser Welding

T. Coon, Chair	<i>Ford Motor Company</i>
M. Diaz, Secretary	<i>American Welding Society</i>
J. Beckham	<i>Fiat Chrysler Automobiles US LLC</i>
E. Biro	<i>University of Waterloo</i>
E. Cross	<i>Meggitt Aircraft Braking Systems</i>
K. Erickson	<i>Abbott</i>
M. Gugel	<i>United States Steel Corporation</i>
D. Kolodziej	<i>Ford Motor Company (Retired)</i>
N. Lun	<i>ArcelorMittal—USA LLC</i>
E. Miller	<i>Miller Electric</i>
J. S. Noruk	<i>Servo Robot Corporation</i>
F. Reed	<i>IHCC</i>
R. Ruokolainen	<i>FCA USA LLC</i>
S. Tate	<i>EPRI, formerly AK Steel</i>
M. D. Tumuluru	<i>Consultant</i>

Advisor to the AWS D8E Subcommittee on Automotive Laser Welding

S. L. Engel	<i>HDE Technologies, Incorporated</i>
-------------	---------------------------------------

This page is intentionally blank.

Foreword

This foreword is not part of this standard but is included for informational purposes only.

This publication is the first edition of the AWS D8.10M:2021, *Specification for Automotive Weld Quality—Laser Beam Welding of Steel*.

This document has been prepared to establish acceptance criteria for laser beam welds in automotive structures fabricated from steels including the Advanced High Strength Steels (AHSS). As a specification, the criteria and techniques contained are obligatory when cited as a normative reference on a drawing or in a contract.

This specification was prepared by the AWS D8E Subcommittee on Automotive Laser Beam Welding of the AWS D8 Committee on Automotive Welding. This publication is issued under the auspices of the AWS D8 Committee on Automotive Welding.

This page is intentionally blank.

Table of Contents

	Page No.
<i>Personnel</i>	v
<i>Foreword</i>	vii
<i>List of Tables</i>	x
<i>List of Figures</i>	x
1. General Requirements	1
1.1 Scope	1
1.2 Units of Measurement	1
1.3 Safety	2
2. Normative References	2
3. Terms and Definitions	2
4. Weld Process Control	3
5. General Provisions	3
5.1 Application	3
5.2 Welding Process	4
5.3 Limitations	4
5.4 Equipment Qualification	4
5.5 Weld Identification and Inspection	4
5.6 Types of Weld Joints and Applicable Welds	4
6. Laser Beam Welding Acceptance Criteria	5
6.1 Visual Requirements	6
6.2 Light Source	6
6.3 Surface Inspection—Manual Visual	7
6.4 Surface Inspection—Automated	7
6.5 Destructive Inspection—Metallographic	7
6.6 Destructive Inspection—Peel and Chisel	7
6.7 Destructive Inspection—Shear and Cross Tension	9
Annex A (Informative)—Informative References	23
Annex B (Informative)—Requesting an Official Interpretation on an AWS Standard	25
List of AWS Documents on Automotive Welding	27

List of Tables

Table		Page No.
1	Classification of Steels for Laser Beam Welding Purposes	6
2	Surface Inspection Acceptability Limits	8
3	Metallographic Inspection Acceptability Limits	9
4	Shear Tension Sample Dimensions	18
5	Cross Tension Sample Dimensions	19

List of Figures

Figure		Page No.
1	Joint Configurations for Laser Beam Welds	5
2	Top Sheet Burn-Through	10
3	Complete Burn-Through	10
4	Skip	11
5	Porosity	11
6	Concavity—Surface and Metallographic Views	11
7	Undercut—Surface and Metallographic Views	12
8	Crack	12
9	Splatter	12
10	Weld Penetration	13
11	S-Value Determination	13
12	Concavity	14
13	Undercut	14
14	Pores, Pits, and Inclusions	15
15	Crack	16
16	Complete Burn-Through	17
17A	Schematic for Lap Joint Shear Tension Samples	17
17B	Schematic for Fillet Joint Shear Tension Samples	18
18	Schematic for Cross Tension Samples	18
19	Metrics Monitored in Shear and Cross Tension Tests	19
20	Interfacial Fracture	20
21	Partial Thickness Fracture (Surface View)	21
22	Full Thickness Fracture (Cross Tension Sample)	22

Specification for Automotive Weld Quality— Laser Beam Welding of Steel

1. General Requirements

1.1 Scope. This specification defines quality characteristics and metrics pertinent to laser beam welding used in automotive body applications, exclusive of butt joint configurations. Laser beam welds may be applied as intermittent (stitch) or continuous and either linear or shaped. The evaluation methods and inspection criteria specified herein can be used to evaluate the effectiveness of particular welding equipment and procedures used to weld a particular base material combination. The criteria and metrics are the same for all welds regardless of the service load. The quality standards established by this specification do not constitute a lower bound of suitability for service; welds that do not meet the weld quality criteria of this specification may be satisfactory for certain applications. The acceptance criteria of this standard are not intended for applications outside this scope (such as post-crash weld quality assessment); attempts to do so may lead to an erroneous result.

1.1.1 Applicability and Limitations. Laser beam welding processes are generally limited to weldable steels. The American Welding Society (AWS) defines weldability as “the relative ease with which a material may be welded to meet an applicable standard.” A term known as “Carbon Equivalent” is used to quantify weldability of steels. Several formulas are available to calculate the carbon equivalent for steels. Users should apply the equation that best suits their application. One of the most commonly used is the one developed by the International Institute of Welding (IIW) (Ref. *ASM Handbook*, Volume 6A: *Welding Fundamentals and Processes*, page 133, 2011). The IIW equation is as follows:

$$Ceq_{IIW} = C + \frac{(Mn + Si)}{6} + \frac{(Cr + Mo + V)}{5} + \frac{(Ni + Cu)}{15}$$

It should be noted that the carbon equivalent should be used as a guideline to indicate the weldability of a given grade of steel, but not as an absolute parameter. If the above equation is used to calculate the carbon equivalent, it is recommended that the same equation continues to be used so as to avoid obtaining a different carbon equivalent value for the same or similar materials.

1.1.2 Advanced High Strength Steels Considerations. With the introduction of Advanced High Strength Steels (AHSS) (Reference: WorldAutoSteel Joining Guidelines, WorldAutoSteel.org) in automotive applications, steels with a carbon equivalent greater than 0.3 have been successfully welded using the laser beam welding processes. Generation 3 (GEN3) steels that possess higher elongation and tensile strengths than the generation 1 AHSS (such as dual phase steels) are also being welded using laser beam welding processes. GEN3 steels possess significant amounts of alloying additions and tend to have carbon equivalents greater than 0.3. While these newer steel grades with higher carbon equivalents have been welded successfully, users are advised to assess their weldability using suitable test methods and develop their own welding procedures to verify that acceptable welds are achieved for their intended application.

1.1.3 Additional Considerations. The items listed below are examples of factors that need to be considered when welding steels with high carbon equivalents:

- (1) High cooling rates may induce cracking in some steels.
- (2) Vaporization of some alloying elements can occur leading to alterations in fusion zone and heat-affected zone (HAZ) properties.
- (3) Welding of thin sections requires precision fixturing and close fit-up tolerances to achieve acceptable welds.
- (4) Joints which are highly constrained during welding may induce cracking in some steels.

1.2 Units of Measurement. This standard makes sole use of the International System of Units (SI).