



- Categoria: A DIN -ISO 4759/1.
- Materiali: Classe di resistenza 4.6 - 5.6 ISO 898.
- Tolleranze: 6g DIN 13.
- Filettatura metrica ISO a passo grosso e fine.
- Stato fornitura: grezza o zincata.

- Grade: A DIN -ISO 4759/1.
- Material: Strength class 4.6 - 5.6 ISO 898.
- Allowance: 6g DIN 13.
- ISO metric coarse and fine thread.
- Manufacture: rough or zinc coated.

Es. di design.:
0.050218.T Barra filettata DIN 975
M 20 x 1000 - 4.6
Cat. A - Grezza

Ex. of design.:
0.050218.T Threaded rod DIN 975
M 20 x 1000 - 4.6
Gr. A - Rough



Sconsigliato
Not recommended

	d	Massa Kg/m	CODICE - CODE		
			Class 4.6	Class 5.6	zincate 4.6
Passo grosso - Course thread	M5	0,12	0.050912.C	0.160953.Q	0.163645.H
	M6	0,18	0.050213.N	0.160954.H	0.163646.K
	M8	0,32	0.050214.P	0.160955.K	0.163647.L
	M10	0,5	0.050215.Q	0.160829.L	0.163648.R
	M12	0,72	0.050216.H	0.160830.H	0.163649.V
	(M14)	0,97	0.150508.Z	0.160831.E	0.163650.T
	M16	1,33	0.050217.K	0.160832.F	0.161835.X
	(M18)	1,65	0.160949.R	0.160833.G	0.163651.P
	M20	2,08	0.050218.T	0.160834.A	0.161836.Z
	(M22)	2,54	0.160950.S	0.160835.B	0.163652.Q
	M24	3	0.050219.R	0.160836.C	0.161837.S
	(M27)	3,85	0.160951.N	0.160837.D	0.161838.A
	M30	4,75	0.050220.S	0.160838.M	0.163653.H
	(M33)	5,9	0.160952.P	0.160839.N	0.163654.K
	M36	6,9	0.014684.X	0.160840.T	0.163655.L
	M42	9,4	0.014685.Z	0.160960.R	0.163656.M
	M48	12,4	0.014686.S	0.160961.Q	0.163657.N

	d	Massa Kg/m	CODICE - CODE		
			Class 4.6	Class 5.6	zincate 4.6
Passo fine - Fine thread	M8 x 1	0,32	0.160962.H	0.160956.L	0.163658.W
	M10 x 1,25	0,5	0.160963.K	0.160971.K	0.163659.X
	M12 x 1,25	0,72	0.160964.L	0.160972.L	0.163660.V
	(M14 x 1,5)	0,97	0.160965.M	0.160948.T	0.163661.H
	M16 x 1,5	1,33	0.160966.N	0.160973.M	0.163662.K
	(M18 x 1,5)	1,65	0.160967.P	0.160957.M	0.163663.L
	M20 x 1,5	2,08	0.014687.T	0.160974.N	0.163664.M
	(M22 x 1,5)	2,54	0.160968.X	0.160958.V	0.163665.N
	M24 x 2	3	0.054589.G	0.160975.P	0.163666.P
	(M27 x 2)	3,8	0.160969.Z	0.160976.Q	0.163667.Q
	M30 x2	4,75	0.058878.V	0.160977.H	0.163668.Z
	(M33 x2)	5,9	0.160970.W	0.160959.W	0.163669.S
	M36 x 3	6,9	0.054590.E	0.160978.S	0.163670.X
	M42 x 3	9,4	0.014688.B	0.160979.T	0.163671.L
	M48 x 3	12,4	0.060785.P	0.160980.Q	0.163672.M

Note:

- Barre filettate a passo fine sono di difficile approvvigionam.
- Utilizzare classe 5.6 per unioni flangiate.

Notes:

- Fine threaded rods are of difficult purchasing.
- Use 5.6 strength class only for jointed flanges.