

+

document details: DANIEL 5.100.101 0

Document Approved Hub




STANDARDIZATION

BARRE QUADRE LAMINATE A CALDO DIN 1014
HOT ROLLED SQUARE STEEL BARS DIN 1014

FOGLIO SHEET	2	DI OF	2	EDIZ. ISSUED	01/94
STANDARD N° 5.100.101					
REVIS.	1				
SOSTITUISCE REPLACE					

BARRE QUADRE LAMINATE A CALDO DI USO GENERALE DIN 1014 - (ISO/R 1035/II - EU 59)
HOT ROLLED SQUARE STEEL BARS FOR GENERAL PURPOSES DIN 1014 - (ISO/R 1035/II - EU 59)



Mat.: St 44.2 DIN 17100 Grezzo
Ck 45 DIN 17200 Normalizz. - Certif.: DIN 50049/2.2

Mat.: St 44.2 DIN 17100 Rough
Ck 45 DIN 17200 Normal. - Test report: DIN 50049/2.2

Toll. di rettilineità: d $\geq 25 \div \leq 80 = 0,004 L$
Straightness $d > 80 = 0,0025 L$

Es. di design.:
0.310432.C Quadro 20 DIN 1014
Ck 45 DIN 17200 Norm.
DIN 50049/2.2

Ex. of design.:
0.310432.C Square 20 DIN 1014
Ck 45 DIN 17200 Norm.
DIN 50049/2.2

Sconsigliato
Not recommended

d	Toll. Tol. d	r	Sezione Section cm ²	Massa Mass Kg/m	CODICE St 44.2 Grezzo Rough	CODE Ck 45 Normal.
8	± 0,4	≤ 1	0,64	0,5	0.310402.N	0.310425.D
10			1	0,78	0.310403.P	0.310426.E
12			1,44	1,13	0.310404.Q	0.310427.F
14			1,96	1,54	0.310405.H	0.310428.P
15	± 0,5	≤ 1,5	2,25	1,77	0.310406.K	0.310429.Q
16			2,56	2,01	0.310407.L	0.310430.N
18			3,24	2,54	0.310408.R	0.310431.B
20			4	3,14	0.310409.V	0.310432.C
22	± 0,6	≤ 2	4,84	3,8	0.310410.H	0.310433.D
25			6,25	4,91	0.310411.E	0.310434.E
30			9	7,07	0.310412.F	0.310435.F
32			10,2	8,04	0.310413.G	0.310436.G
35	± 0,8	≤ 2,5	12,3	9,62	0.310414.A	0.310437.A
40			16	12,6	0.310415.B	0.310438.H
45			20,3	15,9	0.310416.C	0.310439.K
50			25	19,6	0.310417.D	0.310440.X
55	± 1	≤ 3	30,3	23,7	0.310418.M	0.310441.L
60			36	28,3	0.310419.N	0.310442.M
70			49	38,5	0.310420.L	0.310443.N
80			64	50,2	0.310421.G	0.310444.P
90	± 1,3	≤ 3	81	63,6	0.310422.A	0.310445.Q
100			100	78,5	0.310423.B	0.310446.H
120	± 1,5	≤ 4	144	113	0.310424.C	0.310447.