

+

document details: DANIELI 7.000.102 0

REDATTO
 COMPILE


According to law Danieli&C. considers this document to be a company secret and therefore prohibits any person to reproduce it or make it known in whole or in part to other parties or to competitors without specific written authorization of Danieli's Management



STANDARDIZATION


**BUSSOLE CEMENTATE
CASE-HARDENED BUSHES**

FOGLIO SHEET	2	DI OF	2	EDIZ. ISSUED	06/95
STANDARD N° 7.000.102					
REVIS.	1				
SOSTITUISCE REPLACES	7.400.001				



Materiale: 16CrNi4 UNI 7846
Cementato e temprato
Durezza: HRC 58 ± 2
Prof. di cementazione: 0,5 ÷ 0,8 mm

Material: 16CrNi4 UNI 7846
Case-hardened
Hardness: HRC 58 ± 2
Case-hardening depth: 0,5 ÷ 0,8 mm



Es. di design.:
0.007735.D Bussola cementata
40H7x 50p6x63 - HRC 58
16CrNi4 UNI 7846
N 7.000.102

Ex. of design.:
0.007735.D Case-hardened bush
40H7x 50p6x63 - HRC 58
16CrNi4 UNI 7846
N 7.000.102

D H7	d p6	L ± 0,5	Massa Kg	CODICE CODE
20	30	33	0,1	0.007731.G
25	35	43	0,16	0.007732.A
30	40	53	0,23	0.007733.B
35	45	53	0,26	0.007734.C
40	50	63	0,35	0.007735.D
45	55	73	0,45	0.007736.E
50	60	73	0,49	0.007737.F
60	70	84	0,67	0.007738.P
70	85	105	1,5	0.007739.Q
80	95	115	1,85	0.007740.V
90	110	125	3,05	0.007741.H
100	120	135	3,65	0.007742.K

Descrizione - Description

Date

Rev