

Methods of test for evaluating the resistance of insulating materials against the initiation of electrical trees

UDC 621.315.6:620.1

NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW



Document Sharing Hub

Committees responsible for this Draft for Development

The preparation of this Draft for Development was entrusted to Technical Committee GEL/15, Insulating material, upon which the following bodies were represented:

- British Ceramic Research Ltd.
- British Industrial Ceramic Manufacturers' Association
- Electrical and Electronic Insulation Association (BEAMA Ltd.)
- Electricity Association
- Federation of the Electronics Industry
- Rotating Electrical Machines Association (BEAMA Ltd.)
- Transmission and Distribution Association (BEAMA Ltd.)

This Draft for Development, having been prepared under the direction of the Electrotechnical Sector Board, was published under the authority of the Standards Board and comes into effect on 15 September 1995

© BSI 02-2000

The following BSI references relate to the work on this Draft for Development:
Committee reference GEL/15
Draft announced *BSI News* April 1995

ISBN 0 580 24635 3

Amendments issued since publication

Amd. No.	Date	Comments

Contents

	Page
Committees responsible	Inside front cover
National foreword	ii
Foreword	2
Text of ENV 61072	3
List of references	Inside back cover

National foreword

This Draft for Development has been prepared by Technical Committee GEL/15 and is the English language version of ENV 61072:1993 *Methods of test for evaluating the resistance of insulating materials against the initiation of electrical trees*, published by the European Committee for Electrotechnical Standardization (CENELEC). It is identical with IEC 1072:1991 published by the International Electrotechnical Commission (IEC).

This publication is not to be regarded as a British Standard.

It is being issued in the Draft for Development series of publications and is of a provisional nature because it is identical with IEC 1072:1991 which has the status of a Technical Report (type 2) and is subject to review by IEC Technical Committee TC15.

The UK participation in the preparation of ENV 61072 is through Technical Committee GEL/15 and any observations should be sent to the Secretary of GEL/15, BSI, 389 Chiswick High Road, London W4 4AL, for consideration by the committee.

Cross-references

Publication referred to	Corresponding British Standard
	BS 923 <i>Guide on high-voltage testing techniques</i>
HD 588.1 S1:1991 (IEC 60-1:1989)	Part 1:1990 <i>General</i>
IEC 60-3:1976	Part 3:1980 <i>Measuring devices</i>
IEC 270:1981	BS 4828:1985 <i>Guide for partial discharge measurements</i>

Summary of pages

This document comprises a front cover, an inside front cover, pages i and ii, the ENV title page, pages 2 to 22, an inside back cover and a back cover.

This standard has been updated (see copyright date) and may have had amendments incorporated. This will be indicated in the amendment table on the inside front cover.

UDC 621.315.6:620.1

Descriptors: Electrical insulating materials, solid electrical insulating materials, test, endurance electrical test, electrical resistance, ambient test, electrical discharge, electrical trees

English version

Methods of test for evaluating the resistance of insulating materials against the initiation of electrical trees

(IEC 1072:1991)

Méthodes d'essais pour évaluer la résistance des matériaux isolants à la formation d'arborescences électriques
(CEI 1072:1991)

Prüfverfahren zur Bewertung der Widerstandsfestigkeit von Isolierstoffen gegen die Entstehung von elektrischem "Treeing"
(IEC 1072:1991)

This European Prestandard (ENV) was approved by CENELEC on 1993-09-22 as a prospective standard for provisional application. The period of validity of this ENV is limited initially to three years. After two years the members of CENELEC will be requested to submit their comments, particularly on the question whether the ENV can be converted into a European Standard (EN).

CENELEC members are required to announce the existence of this ENV in the same way as for an EN and to make the ENV available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the ENV) until the final decision about the possible conversion of the ENV into an EN is reached.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

Central Secretariat: rue de Stassart 35, B-1050 Brussels

© 1993 Copyright reserved to CENELEC members

Foreword

The CENELEC questionnaire procedure, performed for finding out whether or not the International Standard IEC 1072:1991 could be accepted without textual changes, has shown that no common modifications were necessary for acceptance as a European Prestandard.

The reference document was submitted to the CENELEC members for formal vote and was approved by CENELEC as ENV 61072 on 22 September 1993.

The following date was fixed:

- latest date of announcement
of the ENV at national level (doa) 1994-03-01

Annexes designated “normative” are part of the body of the standard. Annexes designated “informative” are given only for information. In this standard, Annex A and Annex B are informative and Annex ZA is normative.

Contents

	Page
Foreword	2
Introduction	3
Section 1. General	
1.1 Scope and object	5
1.2 Normative references	5
1.3 Definitions	5
Section 2. Method A — The single-needle test: needle to plane geometry	
2.1 Summary of method	6
2.2 Apparatus	6
2.3 Test procedure	7
2.4 Analysis of test results	8
2.5 Report	8
2.6 Precision and bias	8
Section 3. Method B — The double-needle test: needle to needle geometry	
3.1 Summary of method	9
3.2 Significance and use	9
3.3 Terminology	9
3.4 Apparatus	9
3.5 Sampling	9
3.6 Test specimens	9
3.7 Conditioning	11
3.8 Procedure	11
3.9 Presentation of results	11
3.10 Report	12
3.11 Precision and bias	12

Annex A (informative) Preparation of needle electrodes	16
Annex B (informative) Results and discussion of round robin treeing tests	16
Annex ZA (normative) Other international publications quoted in this standard with the references of the relevant European publications	21
Figure 1 — Size of specimens and position of needle electrode	13
Figure 2 — Possible arrangement of specimens	14
Figure 3 — Needle insertion jig	14
Figure 4 — Finished specimen	15
Figure 5 — Mould for preparation of specimens containing electrodes	15
Table B1a — Tree inception voltage in the single-needle treeing test with PE-LD; test results and statistical evaluation (Stressing conditions: Consecutive 1 kV/min steps, see method A in section 2)	18
Table B1b — Tree inception voltage in the single-needle treeing test with epoxy resin; test results and statistical evaluation (Stressing conditions: consecutive 1 kV/min steps, see method A in section 2)	19
Table B2 — Tree inception voltage in the double-needle treeing test with PE-LD; test results and statistical evaluation (Stressing conditions-consecutive 1 kV/min steps, see method A in section 2)	20

Introduction

a) *General remarks*

A preparatory working group has been set up on electrical endurance. One of the given tasks was to prepare methods for assessing the electrical treeing endurance of insulating materials and simple combinations thereof.

Two treeing tests are generally used to compare the resistance of solid insulating materials against the initiation of electrical trees under dry conditions and using short-time stressing. They are described in this report. The methods differ mainly in the electrode arrangement and in the time intervals during which voltage is applied:

- method A, the single-needle test, described in section 2 of this report, employs a point-to-plane geometry and consecutive voltage steps of 1 min duration until tree initiation has occurred;
- method B, the double-needle test, described in section 3, employs two opposing cylindrical electrodes, one sharpened to a point, the other with a hemispherical end. The voltage is applied to virgin specimens for a period of 1 h at different stress levels.

As a first step towards testing of resistance against electrical treeing, the electrode arrangements described in sections 2 and 3 have been evaluated in a round robin test under conditions of short-time (1 min) stressing. The test results and a short discussion of the same are given in Annex B.

In summary, it can be concluded that treeing tests to determine the resistance to initiation of electrical trees under short-time stressing and performed under well-defined conditions using commercial needle electrodes give statistically valid and reproducible results. Since there is no obvious advantage to either one of the two tests, both methods can be recommended without preference.

It should be pointed out that endurance against treeing does not necessarily correlate with the short-time tree inception voltage. Therefore treeing tests using the above-mentioned electrode arrangements have been performed to find out whether, or how closely, an elevated tree inception voltage corresponds to a prolonged tree inception time at constant lower stresses. The results are such that at the present stage of knowledge, the extension of the methods described in sections 2 and 3 to testing the long-term endurance of insulating materials against treeing is far too operator-dependent to meet IEC needs. It was decided that, at present, there is no justification for continuing the attempt to prepare an IEC test method for the long-term treeing endurance of insulating materials. Further research in this field is required. It was emphasized that such work should certainly be continued elsewhere, as the importance of the long-term treeing endurance of insulating materials is recognized, and methods to assess it under laboratory conditions would certainly be useful.

b) *Test methods for evaluating resistance to tree inception*

When solid organic dielectrics are subjected to sufficiently high and non-uniform electrical gradients, failure generally occurs through a mechanism called treeing.

In materials with different molecular structures, this electrical treeing process initiates at different levels of stress, indicating different degrees of resistance to tree initiation.

Trees that grow by a degradation mechanism resulting from high and non-uniform electrical gradients or from partial discharges are called electrical trees to distinguish them from electrochemical and water trees which are quite different.

Electrical treeing, when it occurs in high voltage insulation, often starts at corners of electrodes, asperities and conducting particles which are regions of intense localized electrical stress. Treeing tests use needle electrodes to simulate such field enhancements.

The reproducibility of measured characteristic properties, in this case the characteristic voltage and the divergent field life, depends on many factors. Some of these have been identified as follows:

- differences in the geometry of the needle point;
- residual strains or orientation in the specimen produced by needle insertion;
- inclusions or voids in the specimen;

- agents included in the specimens which may exude or spread out on the surface producing a film which is sufficiently conductive to alter the electric field around the needle point;
- differences in thermal history or processing, specifically for materials containing volatile components which can affect the susceptibility to treeing.

Section 1. General

1.1 Scope and object

This Technical Report describes two methods for evaluating and comparing the resistance of solid dielectric materials to the initiation of tree-like patterns, i.e. a network of tubular channels wherein partial discharges may occur, during short-time stressing, with a highly divergent electric field.

The tests are primarily used at power frequencies (48 Hz – 62 Hz).

The tests are generally carried out at room temperature. If other temperatures are desired, these should not exceed the range of normal use of the material to be tested.

1.2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this Technical Report. At the time of publication of this Technical Report, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this Technical Report are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

IEC 60-1:1989, *High-voltage test techniques — General definitions and test requirements*.

IEC 60-3:1976, *High-voltage test techniques — Part 3: Measuring devices*.

IEC 270:1981, *Partial discharge measurements*.

1.3 Definitions

For the purpose of this Technical Report, the following definitions apply:

electrical tree

tree-like network of tubular channels in a solid dielectric material formed by a degradation mechanism resulting from high and non-uniform electrical gradients or partial discharges

electrical treeing

formation of electrical trees

treed (adjective)

presenting tree-like patterns