

DIN EN ISO 13503-5

ICS 75.180.99

**Erdöl- und Erdgasindustrie –
Komplettierungsflüssigkeiten und Materialien –
Teil 5: Verfahren zur Messung der Langzeitleitfähigkeit von
Stützmaterialien (ISO 13503-5:2006);
Englische Fassung EN ISO 13503-5:2006**

Petroleum and natural gas industries –
Completion fluids and materials –
Part 5: Procedures for measuring the long-term conductivity of proppants
(ISO 13503-5:2006);
English version EN ISO 13503-5:2006

Industries du pétrole et du gaz naturel –
Fluides de complétion et matériaux –
Partie 5: Modes opératoires pour mesurer la conductivité à long terme des agents de
soutènement (ISO 13503-5:2006);
Version anglaise EN ISO 13503-5:2006

Gesamtumfang 31 Seiten

Normenausschuss Erdöl- und Erdgasgewinnung (NÖG) im DIN

Nationales Vorwort

Diese Europäische Norm wurde vom Technischen Komitee CEN/TC 12 „Materialien, Ausrüstungen und Offshore-Bauwerke für die Erdöl-, petrochemische und Erdgasindustrie“ (Sekretariat: Frankreich) erstellt. Es handelt sich dabei um die unveränderte Übernahme von ISO 13503-5:2006, erarbeitet von ISO/TC 67 „Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries“, Subkomitee SC 3 „Drilling and completion fluids, and well cements“.

Für Deutschland hat hieran der Arbeitskreis NÖG 12/67 AK 3 „Bohrspülung und Zemente“ im Normenausschuss Erdöl- und Erdgasgewinnung (NÖG) mitgearbeitet.

Diese Europäische Norm enthält unter Berücksichtigung des DIN-Präsidialbeschlusses 13/1983 nur die englische Originalfassung der ISO-Norm.

English Version

Petroleum and natural gas industries - Completion fluids and materials - Part 5: Procedures for measuring the long-term conductivity of proppants (ISO 13503-5:2006)

Industries du pétrole et du gaz naturel - Fluides de complétion et matériaux - Partie 5: Modes opératoires pour mesurer la conductivité à long terme des agents de soutènement (ISO 13503-5:2006)

Erdöl- und Erdgasindustrie - Komplettierungsflüssigkeiten und Materialien - Teil 5: Verfahren zur Messung der Langzeitleitfähigkeit von Stützmaterialien (ISO 13503-5:2006)

This European Standard was approved by CEN on 24 May 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword	3
Introduction	4
1 Scope	5
2 Normative reference	5
3 Terms and definitions.....	5
4 Abbreviations	6
5 Procedures for evaluating long-term proppant pack conductivity	6
5.1 Objective	6
5.2 Discussion	6
6 Reagents and materials	7
6.1 Test fluid	7
6.2 Sandstone.....	7
7 Long-term conductivity test apparatus	7
7.1 Test unit	7
7.2 Hydraulic load frame	7
7.3 Pack width measurement device(s)	7
7.4 Test fluid drive system.....	7
7.5 Differential pressure transducers	8
7.6 Back-pressure regulators	8
7.7 Balance	8
7.8 Oxygen removal	8
7.9 Temperature control	8
7.10 Silica saturation and monitoring.....	9
8 Equipment calibration	9
8.1 Pressure indicators and flow rates	9
8.2 Zero pack width measurement	9
8.3 Determination of cell width	10
8.4 Hydraulic load frame	10
9 Leak tests	10
9.1 Hydraulic load frame	10
9.2 Test fluid system.....	10
10 Procedure for loading the cells	10
10.1 Preparation of the test unit	10
10.2 Cell setup	11
11 Loading cell(s) in the press	13
12 Acquiring data	13
13 Calculation of permeability and conductivity	14
14 Data reporting	15
Annex A (informative) Conversion factors	16
Annex B (normative) Silica-saturation vessel setup	17
Annex C (informative) Figures	19
Bibliography	28

Foreword

This document (EN ISO 13503-5:2006) has been prepared by Technical Committee ISO/TC 67 "Materials, equipment and offshore structures for petroleum and natural gas industries" in collaboration with Technical Committee CEN/TC 12 "Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2007, and conflicting national standards shall be withdrawn at the latest by January 2007.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Endorsement notice

The text of ISO 13503-5:2006 has been approved by CEN as EN ISO 13503-5:2006 without any modifications.

Introduction

This part of ISO 13503 is largely based on API RP 61^[1]. Informative references are also included in the Bibliography, References [2] to [15].

The tests and test apparatus herein have been developed to establish standard procedures and conditions for use in evaluating the long-term conductivity of various hydraulic fracture proppant materials under laboratory conditions. This procedure enables users to compare the conductivity characteristics under the specifically described test conditions. The test results can aid users in comparing proppant materials for use in hydraulic fracturing operations.

The procedures presented in this publication are not intended to inhibit the development of new technology, materials improvements, or improved operational procedures. Qualified engineering analysis and sound judgment is required for their application to fit a specific situation.

This part of ISO 13503 may be used by anyone desiring to do so. Every effort has been made by ISO and API to ensure the accuracy and reliability of the data contained in it. However, ISO and API make no representation, warranty, or guarantee in connection with this part of ISO 13503, and hereby expressly disclaim any liability or responsibility for loss or damage resulting from its use or for the violation of any federal, state, or municipal regulation with which this part of ISO may conflict.

In this part of ISO 13503, where practical, U.S. customary units are included in parentheses for information.

CAUTION — The testing procedures in this part of ISO 13503 are not designed to provide absolute values of proppant conductivity under downhole reservoir conditions. Long-term test data have shown that time, elevated temperatures, fracturing fluid residues, cyclic stress loading, embedment, formation fines and other factors further reduce fracture proppant pack conductivity. Also, this reference test is designed to measure only the frictional energy losses corresponding to laminar flow within a pack. It is recognized that fluid velocity within an actual fracture can be significantly higher than in these laboratory tests, and can be dominated by inertial effects.

1 Scope

This part of ISO 13503 provides standard testing procedures for evaluating proppants used in hydraulic fracturing and gravel-packing operations.

NOTE The “proppants” mentioned henceforth in this part of ISO 13503 refer to sand, ceramic media, resin-coated proppants, gravel packing media, and other materials used for hydraulic fracturing and gravel-packing operations.

The objective of this part of ISO 13503 is to provide consistent methodology for testing performed on hydraulic-fracturing and/or gravel-packing proppants. It is not intended for use in obtaining absolute values of proppant pack conductivities under downhole reservoir conditions.

2 Normative reference

The following referenced document is indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced standard (including any amendments) applies.

ISO 3506-1, *Mechanical properties of corrosion-resistant stainless-steel fasteners — Part 1: Bolts, screws and studs*

3 Terms and definitions

3.1 conductivity

width of the fracture multiplied by the permeability of the proppant pack

3.2 laminar flow

type of streamlined flow for single-phase fluids in which the fluid moves in parallel layers, or laminae, such that the layers flow smoothly over each other with instabilities being dampened by the viscosity

3.3

Ohio sandstone

fine-grained sandstone found in the United States from the Scioto Formation in southern Ohio

3.4

permeability

a measure of the ability of media to transmit fluid through pore spaces

4 Abbreviations

API	American Petroleum Institute
ASTM	American Society for Testing and Materials
RTV	Room temperature vulcanizing
ANSI	American National Standards Institute
PID	Proportional-integral device

5 Procedures for evaluating long-term proppant pack conductivity

5.1 Objective

The objective is to establish a standard test procedure, using a standard apparatus, under standard test conditions to evaluate the long-term conductivity of proppants under laboratory conditions. This procedure is used to evaluate the conductivity of proppants under laboratory conditions but is not intended for use in obtaining absolute values of proppant pack conductivities under downhole reservoir conditions. The effects of fines, formation hardness, resident fluids, time, and/or other factors are beyond the scope of this procedure.

5.2 Discussion

In this part of ISO 13503 procedure, a closure stress is applied across a test unit for $50 \text{ h} \pm 2 \text{ h}$ to allow the proppant sample bed to reach a semi-steady state condition. As the fluid is forced through the proppant bed, the proppant pack width, differential pressure, temperature and flow rates are measured at each stress level. Proppant pack permeability and conductivity are calculated.

Multiple flow rates are used to verify the performance of the transducers, and to determine darcy flow regime at each stress; an average of the data at these flow rates is reported. A minimum pressure drop of 0,01 kPa (0,002 0 psi) is recommended; otherwise, flow rates shall be increased. At stipulated flow rates and temperature conditions, no appreciable non-darcy flow or inertial effects are encountered. After completing the rates at a closure stress level in all cells, the closure stress is increased to a new level; $50 \text{ h} \pm 2 \text{ h}$ is allowed for the proppant bed to reach a semi-steady state condition, and multiple flow rates in all cells are introduced to gather data required to determine proppant pack conductivity at this stress level. The procedure is repeated until all desired closure stresses and flow rates have been evaluated. To achieve accurate conductivity measurements, it is essential that single-phase flow occurs.

Test condition parameters, such as test fluid, temperature, loading, sandstone and time, at each stress shall be reported along with long-term conductivity and permeability data. Other conditions can be used to evaluate different characteristics of proppants and, therefore, can be expected to produce differing results.

6 Reagents and materials

6.1 Test fluid

The test fluid is 2 % by mass potassium chloride (KCl) in a deionized or distilled-water solution filtered to at least 7 μm . The potassium chloride shall be at least 99,0 % by mass pure.

6.2 Sandstone

Ohio sandstone cores should have dimensions of 17,70 cm to 17,78 cm (6,96 in to 7,00 in) in length, 3,71 cm to 3,81 cm (1,46 in to 1,50 in) wide, and a minimum of 0,9 cm (0,35 in) thick. The ends of the sandstone cores shall be rounded to fit into the test unit (see 7.1). Parallel thickness shall be maintained within $\pm 0,008$ cm ($\pm 0,003$ in).

7 Long-term conductivity test apparatus

7.1 Test unit

The test unit shall be a linear flow design with a 64,5 cm² (10 in²) proppant and bed area. Figure C.1 illustrates the details of the test unit and an example of how cells can be stacked. The pistons and test chamber(s) shall be constructed of 316 stainless steel (e.g. ISO 3506-1, Grade A4), Monel¹⁾ or Hastalloy material. Filters for the test unit may be constructed using Monel wire cloth with an opening of 150 μm or equivalent (100 US mesh). Nominal particle retention sizes are greater than 114 μm .

7.2 Hydraulic load frame

The hydraulic load frame shall have sufficient capacity to develop 667 kN (150 000 lbf). To ensure uniform stress distribution, the platens shall be parallel to each other. It is recommended that the hydraulic load frame be of a four-post design that minimizes warping that can be transmitted to the test cell. Each post should have a minimum diameter of 6,35 cm (2,5 in).

The hydraulic pressurization source shall be capable of holding any desired closure stress [$\pm 1,0$ % or 345 kPa (50 psi), whichever is greater] for 50 h. The hydraulic load frame shall be capable of loading rate changes of 4 448 N/min (1 000 lbf/min) or 690 kPa/min (100 psi/min) on a 64,5 cm² (10 in²) cell. A calibrated electronic load cell shall be used to calibrate the stress between the hydraulic ram and the opposing platen of the load frame.

7.3 Pack width measurement device(s)

Pack width measurements shall be made at each end of the test unit. A measuring device capable of measuring to 0,002 5 cm (0,001 in) accuracy or better shall be used. Figure C.4 shows an example of width slats allowing for the measurement of pack widths.

7.4 Test fluid drive system

Some constant-flow-rate pumps (e.g. chromatographic pumps) have been found satisfactory for this application. Pulsation dampening can be necessary and can be accomplished by use of a piston, bladder accumulator or other effective means. Pressure fluctuations during differential pressure and flow rate measurements (for conductivity calculations) shall be maintained at less than 1,0 %. Each laboratory shall determine the best technique for pulsation dampening. Large pressure spikes can be indicative of pump problems or trapped gas in the flow system and shall be corrected before recording data.

1) Monel and Hastalloy are examples of suitable products available commercially. This information is given for the convenience of users of this part of ISO 13503 and does not constitute an endorsement by ISO of this product.

7.5 Differential pressure transducers

Differential pressure transducers with a range of 0 kPa to 7 kPa (0 psi to 1,0 psi) are satisfactory. The transducer shall be capable of measuring the differential pressure to $\pm 0,1$ % of full scale.

7.6 Back-pressure regulators

The back-pressure regulator shall be capable of maintaining a pressure of 2,07 MPa to 3,45 MPa (300 psi to 500 psi). The stress applied to the cells shall take into account the back-pressure. For example, if the back-pressure is 3,45 MPa (500 psi), then the applied stress shall be 3,45 MPa (500 psi) greater to take into account the pressure exerted outward from the pistons.

7.7 Balance

The balance shall be capable of accommodating a minimum capacity of 100 g with a precision greater than 0,01 g.

7.8 Oxygen removal

The conductivity test fluid shall have the oxygen content reduced to simulate reservoir fluids and to minimize corrosion of test equipment. De-oxygenation can be accomplished with a two-reservoir system for the fluid. The first reservoir holds fluid for oxygen removal. This is connected to nitrogen gas that is bubbled through the fluid at low pressure below 103 kPa (15 psi) and at low rate. The nitrogen supply is first passed through an oxygen/moisture trap such as Agilent Model OT3-4²⁾ that has an efficiency to remove oxygen to less than 15 µg/l. An equivalent system can be made; this system allows nitrogen to pass through heated copper shavings at 370 °C (698 °F), where the copper reacts with the trace amounts of oxygen in the system forming copper oxide. An indicating trap, such as the oxygen trap by Chrom Tech, Inc. part # 10T-4-HP³⁾, after the oxygen-removal process allows for visual confirmation that oxygen has been removed. When the visual indicating trap is oxygen-saturated, both traps shall be replaced to maintain the efficiency of oxygen removal. The second reservoir holds the oxygen-free fluid; this is the supply reservoir for the pumping system.

All fluids in each reservoir are held in sealed, inert-gas pressurized containers to eliminate oxygen contamination from the air.

7.9 Temperature control

The test cell and proppant pack shall be maintained at the desired temperature ± 1 °C (± 3 °F). The temperature for the test conditions is measured in the temperature port of the conductivity cell (Figure C.1). This temperature is used to determine the fluid viscosity from Table C.1. The thermocouple assembly is split into a temperature-control device and a data-acquisition system or equivalent. The temperature control devices shall be programmable PID controllers and capable of self-tuning for different temperature conditions and flow rates.

A temperature of 121 °C (250 °F) is employed in the test for ceramics and resin-coated proppants and 66 °C (150 °F) for naturally occurring sands. The temperature for the silica-saturation vessel (see Annex B) should be 11 °C (20 °F) above testing temperature of 66 °C (150 °F) for naturally occurring sands. Sand 20 °C (35 °F) above 121 °C (250 °F) is used for resin-coated and ceramic proppants to ensure that the fluid is saturated with silica prior to reaching the cell. Care shall be taken to ensure that the fluid arriving to the cell is at the appropriate temperature. Tests using other fluids or temperatures can be of value in evaluating proppant pack conductivity.

2) Agilent Model OT3-4 is an example of a suitable product available commercially. This information is given for the convenience of users of this part of ISO 13503 and does not constitute an endorsement by ISO of this product.

3) Chrom Tech, Inc. part # 10T-4-HP is an example of a suitable product available commercially. This information is given for the convenience of users of this part of ISO 13503 and does not constitute an endorsement by ISO of this product.