



# ESDU 71027

Issued September 1971

With Amendment A

September 1974

Re-issued January 2013

## Endurance of high strength steels (in bending)



**ROYAL  
AERONAUTICAL  
SOCIETY**

Endorsed by  
The Royal Aeronautical Society

## ESDU DATA ITEMS

Data Items provide validated information in engineering design and analysis for use by, or under the supervision of, professionally qualified engineers. The data are founded on an evaluation of all the relevant information, both published and unpublished, and are invariably supported by original work of ESDU staff engineers or consultants. The whole process is subject to independent review for which crucial support is provided by industrial companies, government research laboratories, universities and others from around the world through the participation of some of their leading experts on ESDU Technical Committees. This process ensures that the results of much valuable work (theoretical, experimental and operational), which may not be widely available or in a readily usable form, can be communicated concisely and accurately to the engineering community.

We are constantly striving to develop new work and review data already issued. Any comments arising out of your use of our data, or any suggestions for new topics or information that might lead to improvements, will help us to provide a better service.

## THE PREPARATION OF THIS DATA ITEM

The work on this particular Data Item was monitored and guided by the Fatigue Committee. This Committee first met in 1955 and now has the following membership:

|                   |                                                            |
|-------------------|------------------------------------------------------------|
| Chairman          |                                                            |
| Mr K.E. Cheverton | — Rolls Royce (1971) Ltd, Bristol Engine Division, Filton  |
| Vice Chairman     |                                                            |
| Dr W.J. Harris    | — Rolls Royce (1971) Ltd, Small Engine Division, Leavesden |
| Members           |                                                            |
| Mr R.A. Clare     | — Ministry of Defence (Aviation Supply)                    |
| Mr H.L. Cox       | — Independent                                              |
| Mr A.J. Fenner    | — Ministry of Defence (Aviation Supply)                    |
| Mr W.T. Kirkby    | — Royal Aircraft Establishment                             |
| Mr J.A.B. Lambert | — Hawker Siddeley Aviation Ltd, Hatfield                   |
| Mr N.H. Mason     | — Consulting Engineer                                      |
| Mr H.E. Parish    | — British Aircraft Corporation (Preston) Ltd               |
| Mr V.A.B. Rogers  | — Westland Aircraft Ltd                                    |
| Mr J.B. Sanders   | — Ministry of Defence (Aviation Supply)                    |
| Mr R.H. Sandifier | — Independent.                                             |

The construction and subsequent development of the Data Item was undertaken by

|                 |                                   |
|-----------------|-----------------------------------|
| Mr M.E. Grayley | — Head of Strength Analysis Group |
| Mr R.L. Penning | — Strength Analysis Group.        |

## ENDURANCE OF HIGH STRENGTH STEELS (IN BENDING)

### CONTENTS

|                              | Page    |
|------------------------------|---------|
| 1. NOTATION                  | 1       |
| 2. NOTES                     | 1       |
| 3. REFERENCES AND DERIVATION | 3       |
| 3.1 Derivation               | 3       |
| 3.2 References               | 3       |
| 4. TYPES OF STEEL            | 4       |
| FIGURES 1 to 9               | 5 to 13 |

ESDU Copyright material. For current status contact ESDU.

Copyright Engineering Sciences Data Unit

## ENDURANCE OF HIGH STRENGTH STEELS (IN BENDING)

### 1. NOTATION

|       |                                                                       |                  |                     |
|-------|-----------------------------------------------------------------------|------------------|---------------------|
| $f_t$ | tensile strength of material                                          | N/m <sup>2</sup> | lbf/in <sup>2</sup> |
| $K_t$ | elastic stress concentration factor based on net cross-sectional area |                  |                     |
| $N$   | endurance                                                             |                  |                     |
| $S_a$ | maximum alternating stress based on net cross-sectional area          | N/m <sup>2</sup> | lbf/in <sup>2</sup> |

Both SI and British units are quoted but any coherent system of units may be used.

### 2. NOTES

The results of approximately 1100 fatigue tests on plain and notched specimens of a number of types of high strength steel have been analysed to give curves of  $K_t S_a / f_t$  against  $N$ . The data have been grouped according to the type of steel as shown in Table 4.1 and are presented in Figures 1 to 8.

In Figure 9  $S_a$  is plotted against  $N$  for various values of  $f_t$  to give a correlation of endurance with ultimate tensile strength for low alloy steels only. The curves given in Figure 9 have been obtained by considering all the results shown in Figures 1 to 4, and are not therefore necessarily the best fit for any one particular steel; they do not apply to the stainless or maraging steels of Figures 5 to 8.

All the results were obtained on specimens with  $1.0 \leq K_t \leq 3.2$  tested either as a rotating cantilever (single- or two-point loading) or as a rotating beam (4-point loading), except those results for the austenitic stainless steel DTD 166B (Figure 7) which were obtained on specimens tested in reverse bending.

The diameter at the critical section for most of the specimens was in the range 0.2 to 0.32 in (5.08 to 8.13 mm) though about 60 were bigger, up to 1.0 in (25.4 mm) diameter, and about 10 were smaller, 0.125 in (3.18 mm) diameter. The surface finish was fine turned, ground or polished (normally Centre Line Average Index range 0 to 32  $\mu$ in (0.813  $\mu$ m)). No subsequent chemical, thermal or mechanical treatment was applied, except for stress relief *in vacuo* in a few instances.

The values of  $f_t$  used in plotting the data points shown were those obtained from control tests on specimens of the same batch of material, whenever available. When such a value was not available an average value taken from the appropriate specification was used.

In each figure a mean curve has been drawn through the results for plain specimens. Test results, whenever available, for notched specimens are plotted on the figures as maximum alternating stress at the notch against endurance. An estimate of the allowable alternating stress at any required endurance in any other notched specimen may be made by treating the mean curve for plain specimens as  $K_t S_a / f_t$ , that is, using the maximum stress at the notch for the notched specimens. For specimens in the range of sizes on which the figures are based, the extent to which the alternating stress estimated in this way is low may be judged by the difference between the actual notched specimen results and the points from which the mean curve was constructed. For notched specimens larger than those tested the difference between the estimate and

Issued September 1971  
With Amendment A, September 1974  
Re-issued January 2013

the results of an actual test is likely to be less. Comparison of the plotted results in order to ascertain the magnitude of any size effect is inadvisable because factors other than size will affect the comparison, for example, surface finish, variation in composition. Conservative estimate of fatigue endurance would be obtained by using a curve through the results lower than the mean curve given.

This Item applies to stress concentrations due simply to change of form and does not relate to stress concentrations forming part of the loading system (for example, interference fits) nor to the fretting that may occur in such cases. Guidance on the latter subject may be obtained from ESDU 90031 "Fretting fatigue".

The fatigue endurance of steels is strongly influenced by surface conditions and treatments which may have a negligible effect on tensile strength. The endurance values may therefore increase or decrease in relation to those indicated by the figures according to the nature of the surface treatment. The fatigue endurance may be reduced by processes that induce a residual tensile stress in the specimen surface, for example, harsh grinding or heavy machining. A reduced fatigue endurance is also associated with surface decarburisation, oxidation and chromium plating. The fatigue endurance may be increased by processes that induce residual compressive stress, for example, shot peening or rolling, and there is evidence to suggest that case hardening, nitriding and grit blasting (before cadmium plating) are beneficial in this respect.

This Item does not cover low strength steels, that is, steels with tensile strengths below 123 000 lbf/in<sup>2</sup> (55 tonf/in<sup>2</sup>, 848 MN/m<sup>2</sup>), which are usually designed to the fatigue limit. Guidance on the fatigue limits that may be assumed for such steels is to be found in ESDU 88008 "Fatigue limit of unnotched steels (related to tensile strength)" and the references given in Section 3 of this Item.

## 3. REFERENCES AND DERIVATION

### 3.1 Derivation

1. PHILLIPS, C.E.  
HEYWOOD, R.B. The size effect on fatigue of plain and notched steel specimens loaded under reversed direct stress. Dept Sci. Indust Res., P.M. 57, April 1950.
2. GUNN, N.J.F. The fatigue strength of two materials under different types of stressing. RAE tech. Note MET 231, November 1955.
3. – *Aircraft fatigue handbook*, Vol. 3., Aircraft Industries Assoc., January 1957.
4. – DTD 166 – Type austenitic chromium-nickel steel sheet: a summary of properties. Ministry of Supply, S and T Memo. 12/57, September 1957.
5. RATCLIFFE, M.E. Corrosion fatigue and air fatigue tests on 85 ton aircraft steel to BSS 99. Ministry of Aviation, S and T Memo. 38/60, 1960.
6. WRIGHT, D.H.  
WILLN, J.E.  
LOVE, R.J. The effects of heat cycling and ageing on the fatigue strength of fillet rolled components. The Motor Industry Research Association, Rep. 1962/5, March 1962.
7. FROST, N.E. The alternating stress required to propagate edge cracks in copper and nickel chromium alloy steel plates. NEL Rep. 35, June 1962.
8. IMRIE, W.M. An examination of a maraging steel die forging. Dowty Rotol Ltd, Rep. 64/9006, April 1964.
9. HAYNES, A.G. A survey of developments in maraging steels. The International Nickel Company (Mond) Ltd, June 1964.
10. SHIVES, T.R.  
BENNETT, J.A. The effect of environment on the fatigue strength of four selected alloys. NASA Contract Rep. CR-267, August 1965.
11. – Unpublished work at the British Aircraft Corporation (Weybridge Division), English Electric Aviation Ltd, Hawker Siddeley Aviation Co. Ltd and The Fairey Aviation Co. Ltd.
12. – Unpublished work at the British Steel Corporation, River Don and Associated Works.
13. SMITH, D.  
JOHNSON, R.F. Unpublished work at the British Steel Corporation, Swindon Laboratories, January 1971.

### 3.2 References

14. CAZAUD, R. *La fatigue des metaux*, 1948, translated as *Fatigue of metals* by A.J. Fenner, Chapman and Hall, London, 1953.
15. FORREST, P.G. *Fatigue of metals*. Pergamon Press, London, 1962.
16. HEYWOOD, R.B. *Designing against fatigue*. Chapman and Hall, London, 1962.
17. WOOLMAN, J.  
MOTTRAM, R.A. *The mechanical and physical properties of the British Standard En steels*, Vols 1, 2 and 3. Pergamon Press, 1964.