



ESDU 73004

Issued July 1973
With Amendment A
May 1985
Re-issued January 2013

Criteria of yielding for ductile materials under static loading

ESDU Copyright material. For current status contact ESDU.

Institution of
**MECHANICAL
ENGINEERS**

Endorsed by
The Institution of Mechanical Engineers

AVA Documents
Document Sharing Hub

ESDU DATA ITEMS

Data Items provide validated information in engineering design and analysis for use by, or under the supervision of, professionally qualified engineers. The data are founded on an evaluation of all the relevant information, both published and unpublished, and are invariably supported by original work of ESDU staff engineers or consultants. The whole process is subject to independent review for which crucial support is provided by industrial companies, government research laboratories, universities and others from around the world through the participation of some of their leading experts on ESDU Technical Committees. This process ensures that the results of much valuable work (theoretical, experimental and operational), which may not be widely available or in a readily usable form, can be communicated concisely and accurately to the engineering community.

We are constantly striving to develop new work and review data already issued. Any comments arising out of your use of our data, or any suggestions for new topics or information that might lead to improvements, will help us to provide a better service.

THE PREPARATION OF THIS DATA ITEM

The work on this particular Data Item was monitored and guided by the Stress Analysis and Strength of Components Committee. This Committee first met in 1964 and now has the following membership:

Chairman	
Mr H.L. Cox	— Independent
Vice-Chairman	
Mr G.P. Smedley	— Lloyd's Register of Shipping
Members	
Mr A.J. Batchelor	— Imperial Chemical Industries Ltd
Mr C.E. Day	— Independent
Dr J.R. Dixon	— National Engineering Laboratory
Mr N.E. Frost	— National Engineering Laboratory
Dr R.B. Heywood	— A. Macklow-Smith Ltd
Mr M.J. Kemper	— A.P.V. Company Ltd
Dr L.C. Laming	— Imperial College of Science and Technology
Dr J. Spence	— University of Strathclyde
Dr C.E. Turner	— Imperial College of Science and Technology
Mr J.V. Vint	— C.A. Parsons and Company Ltd.

The construction and subsequent development of the Data Item was undertaken by

Mr M.E. Grayley	— Head of Strength Analysis Group
Mr N. Gregory	— Strength Analysis Group.

The ESDU Stress and Strength Series is recognised as a valuable source of validated data and methods by the Institution of Mechanical Engineers and its Structural Technology and Materials Group is involved in continually reassessing the scope and focus of the content of this Series.

CRITERIA OF YIELDING FOR DUCTILE MATERIALS UNDER STATIC LOADING

CONTENTS

	Page
1. NOTATION	1
2. NOTES	1
3. DUCTILE MATERIAL CRITERIA	1
3.1 Maximum Shear Stress Criterion (Tresca)	1
3.2 Shear Strain Energy Criterion (Von Mises and Hencky)	2
3.3 General Comments	2
4. CHOICE OF YIELD STRESS AND MATERIAL BEHAVIOUR	3
5. FACTORS AFFECTING MATERIAL BEHAVIOUR	4
5.1 Bauschinger Effect	4
5.2 Stress Concentration	4
5.3 Shakedown	4
6. REFERENCES	4
7. EXAMPLE	4
FIGURE 1	6

CRITERIA OF YIELDING FOR DUCTILE MATERIALS UNDER STATIC LOADING

1. NOTATION

f_e	equivalent uniaxial tensile stress	N/m ²	lbf/in ²
f_y	uniaxial tensile yield stress	N/m ²	lbf/in ²
f_1, f_2, f_3	principal stresses ($f_1 > f_2 > f_3$)	N/m ²	lbf/in ²
Convention:	Tensile stresses positive. Compressive stresses negative.		

Both SI and British units are quoted but any coherent system of units may be used.

2. NOTES

The strength of a homogeneous isotropic material is generally obtained from simple uniaxial tensile tests. In such tests a noticeable departure from the linear stress-strain relationship often occurs well before the tensile strength is reached. The stress at which this non-linearity reaches a prescribed value is termed the yield stress*. This stress is often used as a design criterion for components that have to maintain their form. However, the stresses to which engineering components are subjected are usually more complex than simple tension. It is therefore necessary to predict the point of yielding under multiaxial stresses from a knowledge of the material yield stress provided by the simple uniaxial tensile test. This is done by expressing any combination of the principal stresses acting at a point as an equivalent uniaxial tensile stress, f_e . Yielding occurs when this value of f_e reaches the uniaxial yield stress. Thus, f_e may be termed the yield criterion.

3. DUCTILE MATERIAL CRITERIA

Since yielding is in essence a shear phenomenon, it is appropriate that the criteria should be based on either the shear stresses or shear strains present in the material. Of the various yield criteria developed only two, termed the maximum shear stress criterion and the shear strain energy criterion, follow this principle and correspond closely to the material behaviour. Table 3.1 provides a synopsis of these two criteria for systems of both two- and three-dimensional principal stresses. The merits of these criteria are discussed in the following section.

For two-dimensional stress systems Figure 1 provides the yield boundary represented by the two criteria in terms of the ratios of the principal stresses to the uniaxial yield stress, f_y . Provided that a point defined by these ratios lies within the bounds of a yield criterion curve, the material is below the state of yield according to that criterion. Also shown are the regions in which experimental results typically fall.

3.1 Maximum Shear Stress Criterion (Tresca)

The criterion, formulated by Tresca and Guest, states that yielding occurs when the maximum shear stress reaches the same value as in the case of uniaxial tension at yield, that is, half the tensile yield stress. This criterion is widely used since f_e , which is simply given by the largest difference between the principal stresses, is usually conservative with respect to experimental results.

* The general behaviour of a material as it approaches and passes this stress is discussed in Section 4.