



ESDU 83036

Issued November 1983
With Amendments A and B
December 1992
Re-issued December 2012

Natural frequencies of rectangular, specially orthotropic laminated plates

Associated software: ESDUpac A8336



Endorsed by
The Royal Aeronautical Society

AVA Documents
Document Sharing Hub

ESDU DATA ITEMS

Data Items provide validated information in engineering design and analysis for use by, or under the supervision of, professionally qualified engineers. The data are founded on an evaluation of all the relevant information, both published and unpublished, and are invariably supported by original work of ESDU staff engineers or consultants. The whole process is subject to independent review for which crucial support is provided by industrial companies, government research laboratories, universities and others from around the world through the participation of some of their leading experts on ESDU Technical Committees. This process ensures that the results of much valuable work (theoretical, experimental and operational), which may not be widely available or in a readily usable form, can be communicated concisely and accurately to the engineering community.

We are constantly striving to develop new work and review data already issued. Any comments arising out of your use of our data, or any suggestions for new topics or information that might lead to improvements, will help us to provide a better service.

THE PREPARATION OF THIS DATA ITEM

The work on this particular Item was monitored and guided by the Acoustic Fatigue Panel which had the following membership:

Chairman	
Mr J.A. Hay	— British Aerospace plc, Aircraft Group, Weybridge – Bristol Division
Members	
Dr R.D. Adams	— University of Bristol
Mr B.P. Broadley	— Rolls-Royce Ltd, Derby
Mr R.J. Cummins	— British Aerospace plc, Aircraft Group, Weybridge – Bristol Division
Mr D.C.G. Eaton*	— The European Space Research and Technology Centre, Domeinweg, The Netherlands
Mr J.E. Marshall	— Short Brothers Ltd, Belfast
Mr W.B. Roberts	— British Aerospace plc, Dynamics Group, Hatfield Division
Prof. R.G. White	— Institute of Sound and Vibration Research, University of Southampton.

* Corresponding Member

The Item was accepted for inclusion in the Acoustic Fatigue series by the Vibration and Structural Dynamics Steering Group which first met in July 1976 and now has the following membership:

Chairman	
Mr D.C.G. Eaton	— The European Space Research and Technology Centre, Domeinweg, The Netherlands
Members	
Mr T.V. Lawson	— University of Bristol
Dr M.R. Smith	— University of Newcastle-upon-Tyne
Dr H.H.B.M. Thomas	— Independent.

The work on this Item was carried out in the Aircraft Noise and Structural Dynamics Group of ESDU. The member of staff who undertook the technical work involved in the initial assessment of the available information and the construction and subsequent development of the Item was

Mr R.F. Lambert — Group Head.

NATURAL FREQUENCIES OF RECTANGULAR, SPECIALLY ORTHOTROPIC LAMINATED PLATES

CONTENTS

	Page
1. NOTATION AND UNITS	1
2. NOTES	2
2.1 General	2
2.2 Specially Orthotropic Laminated Plates	3
2.3 Mode Numbers	3
2.4 Effect of Plate Curvature	3
2.5 Accuracy and Limitations on Data	4
3. COMPUTATION OF NATURAL FREQUENCIES	4
3.1 Data Input	5
3.1.1 General	5
3.1.2 Plate stiffness data	5
3.1.3 Data for calculation of D-matrix	5
3.1.4 Natural frequency case data	6
3.2 Data Output	6
4. DERIVATION AND REFERENCE	7
4.1 Derivation	7
4.2 Reference	7
5. EXAMPLES	7
5.1 Estimation of Flat Plate Natural Frequencies Using the Computer Program Described in Section 3	7
5.2 Effect of Curvature on Clamped Plate Fundamental Natural Frequency	11
FIGURES 1 TO 3	12 TO 14

NATURAL FREQUENCIES OF RECTANGULAR, SPECIALLY ORTHOTROPIC LAMINATED PLATES


1. NOTATION AND UNITS

a	length of plate in x -direction (see Sketch 1.1)	m	in
b	length of plate in y -direction, or arc length of curved plate (see Sketch 1.1)	m	in
$\mathbf{D}$	flexural stiffness sub-matrix for plate [see Equation (2.2)]	N m	lbf in
E_α, E_β	lamina modulus of elasticity in α -, β -directions, respectively	N/m ²	lbf/in ²
f	natural frequency	Hz	Hz
$G_{\alpha\beta}$	shear stiffness of lamina in (α , β) direction	N/m ²	lbf/in ²
$\mathbf{K}$	$\begin{bmatrix} \partial^2 w / \partial x^2 \\ \partial^2 w / \partial y^2 \\ 2 \partial^2 w / \partial x \partial y \end{bmatrix}$ column sub-matrix of curvature components of plate [see Equation (2.2)]	m ⁻¹	in ⁻¹
$\mathbf{M}$	$\begin{bmatrix} M_x \\ M_y \\ M_{xy} \end{bmatrix}$ column sub-matrix of bending moment intensities acting in xz - and yz -planes and twisting moment intensities acting about x - and y -axes, respectively	N m/m	lbf in/in
m	mode number in x -direction		
N	number of layers in plate		
n	mode number in y -direction		
R	plate mean radius	m	in
t	laminated plate thickness	m	in
w	deflection of plate normal to xy -plane	m	in
x, y	plate coordinate system (see Sketch 1.1)		
α, β	lamina coordinates aligned with principal axes of orthotropy of lamina (see Sketch 1.2)		
$\nu_{\alpha\beta}$	Poisson's ratio for lamina resulting from load applied in α -direction		


Issued November 1983
With Amendments A and B, December 1992 – 14 pages
Re-issued December 2012 – 14 pages

$\nu_{\beta\alpha}$	Poisson's ratio for lamina resulting from load applied in β -direction		
ρ	mean density of plate	kg/m ³	*
ψ	angle of principal axis of orthotropy, α , of lamina measured from plate principal axis, x (see Sketch 1.2)	degree	degree

* A density value expressed in British units as lb/in³ has to be divided by 386.4 before being input into the computer program. (A force of 1 lbf acting on a mass of 1 lb produces an acceleration of 386.4 in/s².) For example, if the material density is 0.097 lb/in³, the value input into the computer program should be 2.51×10^{-4} lb s²/in⁴.



Sketch 1.1 Plate dimensions



Sketch 1.2 Relationship between plate and layer axes

2. NOTES

2.1 General

This Data Item provides a means of estimating the lower natural frequencies of initially unstressed, specially orthotropic (see Section 2.2), rectangular plates. The data are particularly applicable to fibre reinforced composite laminated plates. Because of the large number of lay-up configurations that may be used in laminated plates it is not practical to provide natural frequency data in graphical form. Data are provided in the form of a computer program, known as ESDUpac A8336.

The programs in this Item allow the estimation of the natural frequencies of plates having any combination of simply-supported and clamped edge conditions. These boundary conditions are illustrated in Figure 1.

An appropriate procedure is provided (Section 2.4) for the estimation of the fundamental natural frequency of slightly curved plates having all edges clamped. These singly-curved plate natural frequencies are obtained by factoring the computed flat plate fundamental natural frequencies.

2.2 Specially Orthotropic Laminated Plates

Specially orthotropic plates are balanced laminates having layers of equal thickness, elastic properties and orientation that are symmetrically arranged about the plate central plane. The conditions for special orthotropy are detailed in ESDU 83035. In specially orthotropic plates, direct and shear stiffnesses are uncoupled; further, bending and twisting stiffnesses are uncoupled so that plane sections normal to the reference plane remain plane and normal to the reference plane during small amplitude deflections. Also, the in-plane and flexural stiffnesses are uncoupled so that for specially orthotropic laminates the flexural load deformation relationship (used in determining the plate natural frequencies) is

$$[\mathbf{M}] = [\mathbf{D}][\mathbf{K}] , \quad (2.1)$$

which, in its expanded form, becomes

$$\begin{bmatrix} M_x \\ M_y \\ M_{xy} \end{bmatrix} = \begin{bmatrix} D_{11} & D_{12} & 0 \\ D_{21} & D_{22} & 0 \\ 0 & 0 & D_{33} \end{bmatrix} \begin{bmatrix} \partial^2 w / \partial x^2 \\ \partial^2 w / \partial y^2 \\ 2 \partial^2 w / \partial x \partial y \end{bmatrix} . \quad (2.2)$$

The $\mathbf{D}$ -matrix in Equation (2.2) is symmetric so that $D_{12} = D_{21}$.

In this Item the principal axes of orthotropy of the specially orthotropic plates are assumed to be parallel to the xy -axes. In ESDU 82013 (Reference 5) the stacking sequence of layer angles to achieve specially orthotropic laminates is given for laminates with even or odd number of layers for both symmetric and anti-symmetric ply orientations about the central plane. In practice it is difficult to manufacture laminated plates that exactly conform to the conditions of special orthotropy, but many multilayered composite laminates approximate to those conditions which allows simple analysis procedures to be used to determine natural frequencies.

2.3 Mode Numbers

For any mode of vibration, the mode numbers m and n may be related to the nodal lines provided that these lines are parallel, or approximately parallel, to the plate sides. For these cases m and n are one plus the number of nodal lines crossing any line parallel to the x -axis and y -axis, respectively. In this definition plate edges, clamped or simply-supported, are not counted as nodal lines.

2.4 Effect of Plate Curvature

An approximate means of estimating the fundamental natural frequency ($m = n = 1$ mode) of slightly curved, rectangular laminated plates with all edges clamped is presented in Figure 2. On that Figure, the ratio of curved plate frequency to flat plate frequency is plotted against the curvature parameters b^2/Rt , where b is the arc length of the plate curved side. The curve is an empirical relationship but is based on the theoretical isotropic plate frequency ratios. It is applicable to all panel a/b ratios ($a/b > 1.0$) over the plotted range of b^2/Rt .