

SOILING & CLEANABILITY TEST FOR INTERIOR TRIM MATERIALS**Application**

This procedure is used to evaluate the cleanability of automotive interior trim materials.

Apparatus Required**White Paper Towels****White Cheesecloth****Soiling Agents**

- NLGI 2 Grease: Motorcraft Lead-Free Multi-Purpose Grease, Part Number XG-4 (previous recommendation: part #D0AZ-19584-AA)(4-ounce tube) or equivalent meeting Ford Material Specification ESR-M1C159-A

Available From:

Ford Motor Dealerships in US and Canada

- or -

Excelda Manufacturing
Brian Carter: (248) 486-3800

- or -

Ford Motor Company recommended equivalents

- Orange Juice (premium brand, not from concentrate)
- Coffee *

Concentration

Instant coffee 3 grams
Boiling water 100 ml

*Apply coffee solution immediately, heated to 65 °C minimum, to the material specimen

Date	Action	Revisions
2001 07 06	Revised	Updated Apparatus &Addresses, rev para 1.2 R. Moore
2000 08 02	Revised	Editorial – no technical change A. Cockman
1996 03 19		

Printed copies are uncontrolled

Page 1 of 5

Copyright © 2001, Ford Global Technologies, Inc.

- Synthetic Soil ; AATCC Composition
Grade: Method 123 Carpet Soil (available 500 g and 1 kg)

Available from:

SDL America Inc
1900A Center Park Dr.
Charlotte, NC 28217-2956 USA
(704) 329-0911 Phone
(704) 329-0914 FAX
test@sdiamerica.com E-mail

<u>Ingredients</u>	<u>% by weight</u>
Peat moss (dark)	38.00
Portland cement	17.00
Kaolin clay	17.00
Silica	17.00
Furnace black	1.75
Red iron oxide	0.50
Mineral oil (medicinal grade)	8.75

- Ketchup

Cleaning Agents

- Carpets and Fabrics - Ford Extra Strength Upholstery Cleaner, Part number E8AZ-19523-AA

Available from Ford dealers in US

Canadian suppliers should contact the
manufacturer representative:

Chris Hilton
Currie Associates, Incorporated
Phone no.: (248) 332-9900

Or contact:

Ford Customer Service Division
Service Chemicals and Lubricants
Repair Product Planning
Phone no.: (313) 337-5441

-or-

Ford Motor Company Recommended Equivalents