



**FABRIC, MAX PATTERN, FLAT WOVEN,
100% VIRGIN WITH SOIL REPELLANT**

WSS-M1H1054-A11

**FABRIC, MAX PATTERN, FLAT WOVEN,
RECYCLED, PIR/PCR CONTENT WITH SOIL REPELLANT**

WRS-M1H1054-A21

1. SCOPE

The materials defined by these specifications are a flat woven polyester face fabric made from 100% virgin yarn or with a minimum of 25% PIR/PCR (Post industrial/post consumer) recycled yarn.

2. APPLICATION

This specification was released originally for material used as an interior trim fabric for 2006 MY seat bolster. The fabric was originally approved as tri-laminated with foam and a backing scrim.

3. REQUIREMENTS

3.1 APPROVED SOURCES

This specification requires the use of approved sources. Only the sources identified on the Ford Approved Source List (ASL) can be used when this specification is listed on the drawing, CAD file, or other documents. The list of approved sources is located within Ford at www.mats.ford.com or available externally through a Ford Materials Engineer.

3.2 APPEARANCE

The color, pattern, and finish shall match the approved Corporate Design master sample.

3.3 FABRIC PERFORMANCE

In addition to the requirements listed herein, the fabric shall meet all requirements of WSS-M8P18-B1/B2/B3/B4/latest as applicable.

3.4 VEHICLE INTERIOR ENVIRONMENTAL PERFORMANCE

Materials used in interior applications must meet the requirements outlined in WSS-M99P2222-D1/latest, *Performance, Vehicle Interior Environmental Quality Material/Component Requirements*. Data must be included in material submission package.

3.5 CONDITIONING AND TEST CONDITIONS

All test values are based on material conditioned for not less than 24 h prior to testing in a controlled environment of 23 +/- 2 °C and 50 +/- 5% relative humidity. Testing of the material should occur in the conditioning environment or soon after removal.

Date	Action	Revisions	Rev. 0
2016 06 27	Released		



Documents

R. Kyle FOE

Document Sharing Hub



3.6 FABRIC CONSTRUCTION

3.6.1 Fabric Count, $\pm 5\%$ tolerance
(ASTM D3775)

Warp
Weft

125 ends / 10 cm
110 picks / 10 cm

3.6.2 Fabric Weight, $\pm 5\%$ tolerance
(FLTM BN 106-01)

290 g/m²

3.7 COMPOSITION (ASTM D629)

Fabric

100% polyester

3.8 YARN CONSTRUCTION (ASTM D1244)

Warp

A11
1150 Dtex f320,
(Air textured)

A21
1150 Dtex f320
(Air textured)

Weft

1150 Dtex f320,
(Air textured)

1150 Dtex f320 ,
(Air textured, 100% recycled yarn)

3.9 RECYCLED CONTENT

Recycled yarn must contain a minimum of 25% recycled content PIR/PCR (Postindustrial/post consumer) as defined by WRS-M99P42-A2. The remaining portion of the material can come from virgin sources. Refer to the Approved Source List (ASL), for specific regional recycled levels for this material. Virgin yarn contains 100% virgin material.

3.10 METHOD OF DYEING

Yarn dyed for Passenger Vehicle
Solution dyed for Commercial Vehicle

3.11 FINISHED OPERATIONS

Washing, drying, Pad SR, Framing.

Any changes to the above process must
be approved by Materials Engineering.

4. GENERAL INFORMATION

The information given below is provided for clarification and assistance in meeting the requirements of this specification. Contact gmfs@ford.com for questions concerning Engineering Material Specifications.

4.1 Purchase departments will ensure that the material defined in this specification and shipped to any one assembly plant will be produced by one supplier only. In the event of a Global Program or regional duplication, each regional location of the supplier for this specification must provide a construction package and be approved to meet this specification.

