



FABRIC, LANE PATTERN, FLAT WOVEN,  
100% VIRGIN WITH SOIL REPELLANT

WSS-M1H1068-A11

FABRIC, LANE PATTERN, FLAT WOVEN,  
RECYCLED, PIR/PCR CONTENT WITH SOIL REPELLANT

WRS-M1H1068-A21

## 1. SCOPE

The materials defined by these specifications are a flat woven polyester face fabric made from 100% virgin yarn or with a minimum of 25% PIR/PCR (Post industrial/post consumer) recycled yarn.

## 2. APPLICATION

This specification was released originally for material used as an interior trim fabric for 2013 MY seat Insert. The fabric was originally approved as tri-laminated with foam and a backing scrim.

## 3. REQUIREMENTS

### 3.1 APPROVED SOURCES

This specification requires the use of approved sources. Only the sources identified on the Ford Approved Source List (ASL) can be used when this specification is listed on the drawing, CAD file, or other documents. The list of approved sources is located within Ford at [www.mats.ford.com](http://www.mats.ford.com) or available externally through a Ford Materials Engineer.

### 3.2 APPEARANCE

The color, pattern, and finish shall match the approved Corporate Design master sample.

### 3.3 FABRIC PERFORMANCE

In addition to the requirements listed herein, the fabric shall meet all requirements of WSS-M8P18-B1/B2/B3/B4/latest as applicable.

### 3.4 VEHICLE INTERIOR ENVIRONMENTAL PERFORMANCE

Materials used in interior applications must meet the requirements outlined in WSS-M99P2222-D1/latest, *Performance, Vehicle Interior Environmental Quality Material/Component Requirements*. Data must be included in material submission package.

### 3.5 CONDITIONING AND TEST CONDITIONS

All test values are based on material conditioned for not less than 24 h prior to testing in a controlled environment of 23 +/- 2 °C and 50 +/- 5% relative humidity. Testing of the material should occur in the conditioning environment or soon after removal.

| Date       | Action   | Revisions | Rev. 0 |
|------------|----------|-----------|--------|
|            |          |           |        |
|            |          |           |        |
| 2016 06 27 | Released |           |        |



Documents

R. Kyle, FQE

Document Sharing Hub

**3.6 FABRIC CONSTRUCTION**

3.6.1 Fabric Count,  $\pm 5\%$  tolerance  
(ASTM D3775)

Warp  
Weft

230 ends / 10 cm  
135 picks / 10 cm

3.6.2 Fabric Weight,  $\pm 5\%$  tolerance  
(FLTM BN 106-01)

325 g/m<sup>2</sup>

**3.7 COMPOSITION**  
(ASTM D629)

Fabric

100% polyester

**3.8 YARN CONSTRUCTION**  
(ASTM D1244)

Warp  
A11  
830 Dtex f188,  
(Air textured)

A21  
830 Dtex f188  
(Air textured)

Weft  
830 Dtex f188,  
(Air textured)

830 Dtex f188 ,  
(Air textured, 100% recycled yarn)

**3.9 RECYCLED CONTENT**

Recycled yarn must contain a minimum of 25% recycled content PIR/PCR (Postindustrial/post consumer) as defined by WRS-M99P42-A2. The remaining portion of the material can come from virgin sources. Refer to the Approved Source List (ASL), for specific regional recycled levels for this material. Virgin yarn contains 100% virgin material.

**3.10 METHOD OF DYEING**

Yarn dyed

**3.11 FINISHED OPERATIONS**

Washing, drying, Pad SR, Framing.

Any changes to the above process must  
be approved by Materials Engineering.

**4. GENERAL INFORMATION**

The information given below is provided for clarification and assistance in meeting the requirements of this specification. Contact [gmfs@ford.com](mailto:gmfs@ford.com) for questions concerning Engineering Material Specifications.

**4.1** Purchase departments will ensure that the material defined in this specification and shipped to any one assembly plant will be produced by one supplier only. In the event of a Global Program or regional duplication, each regional location of the supplier for this specification must provide a construction package and be approved to meet this specification.

**4.2** If yarn is locally sourced it must meet the above fabric construction, composition and yarn construction. The fabric must also meet the requirements of WSS-M8P18-B1/B2/B3/B4/latest.

**4.3** Global strategy for this fabric is to use tri-laminate/foam & scrim construction in all regions.