FABRIC, CAPITOL PATTERN, FLAT WOVEN, 100% VIRGIN WITH SOIL REPELLANT — **WSS-M1H1266-A11**

FABRIC, CAPITOL PATTERN, FLAT WOVEN, RECYCLED, PIR/PCR CONTENT WITH SOIL REPELLANT — **WRS-M1H1266-A21**

1. SCOPE

The material defined by this specification is a flat woven polyester face fabric made from 100% virgin yarn or with a minimum of 25% PIR/PCR (Post industrial/post consumer) recycled yarn.

2. APPLICATION

This specification was released originally for material used as an interior trim fabric for Transit 2019 MY seat insert. The fabric was originally approved as tri-laminated with foam and a backing scrim.

3. REQUIREMENTS

3.1 APPROVED SOURCES

This specification requires the use of approved sources. Only the sources identified on the Ford Approved Source List (ASL) can be used when this specification is listed on the drawing, CAD file, or other documents. The list of approved sources is located within Ford at www.mats.ford.com or available externally through a Ford Materials Engineer.

3.2 APPPEARANCE

The color, pattern, and finish shall match the approved Corporate Design master sample.

3.3 FABRIC PERFORMANCE

In addition to the requirements listed herein, the fabric shall meet all requirements of WSS-M8P18-B1/B2/B3/B4/latest as applicable.

3.4 CONDITIONING AND TEST CONDITIONS

All test values are based on material conditioned for not less than 24 h prior to testing in a controlled environment of 23 +/- 2 °C and 50 +/- 5% relative humidity. Testing of the material should occur in the conditioning environment or soon after removal.

3.5 FABRIC CONSTRUCTION

3.5.1 Fabric Count, - /+ 5% tolerance (ASTM D3775)

Warp	300 / 10 cm
Weft	200 / 10 cm

3.5.2 Fabric Weight, -/+5 % tolerance (FLTM BN 106-01) — 321 g/m^2

Date	Action	Revisions	Rev. 01
2018 05 03	Released	Released –A21	L. Pollard, NA
2017 02 16	Released	Released -A11	R.Kyle, EU

Copyright Ford Motor Company
Provided by IHS Markit under license with FORD
No reproduction or networking permitted without license from IHS
Full document details: FORD WRS-M1H1266-A21 2018
Copyright © 2018, Ford Global Technologies, LLC
Licensee=/, User=,
Not for Resale,
Documents Document Sharing Hub

3.6 COMPOSITION
(ASTM D629)

Fabric	100% Polyester

3.8 YARN CONSTRUCTION
(ASTM D1244)

	A11	A21
Warp	340 Dtex f68 x 2, (Polyester, False Twist)	340 Dtex f68 x 2, (Polyester, False Twist, with 100% recycled yarn)
Fill	167 Dtex f34 x 2, (Polyester, False Twist)	167 Dtex f34 x 2 , (Polyester, False Twist, 100% recycled yarn)
Fill	650 Dtex f144, (Polyester, Air Textured)	650 Dtex f144 , (Polyester, Air Textured, 100% recycled yarn)

3.9 METHOD OF DYEING Solution dyed

3.10 FINISHED OPERATIONS Washing, drying, Pad SR, framing

Any changes to the above process
must be approved by Materials Engineering.

4. GENERAL INFORMATION

The information given below is provided for clarification and assistance in meeting the requirements of this specification. Contact gmfs@ford.com for questions concerning Engineering Material Specifications.

4.1 Purchase departments will ensure that the material defined in this specification and shipped to any one assembly plant will be produced by one supplier only. In the event of a Global Program or Regional duplication, each regional location of the supplier for this specification must provide a Construction package and be approved to meet this specification.

4.2 If yarn is locally sourced it must meet the above fabric construction, composition and yarn construction. The fabric must also meet the requirements of WSS-M8P18-B1/B2/B3/B4/latest.

4.3 Global strategy for this fabric is to use tri-laminate/foam & scrim construction in all regions.

4.4 APPROVAL OF MATERIALS

Suppliers desiring approval of their materials shall first obtain an expression of interest from Purchasing, Design or Product Development, and Materials Engineering. The supplier shall submit a completed copy of their laboratory test reports, signed by a qualified and authorized representative of the test facility, demonstrating full compliance with all the requirements of the Material Specification. Tested material samples must be available for review upon request and kept for a minimum of one year. Upon request, the supplier will review the associated quality control documents (Process Failure Mode and Effects Analysis, Control Plans, Certification testing) with Ford.

Documents
Document Sharing Hub

Copyright Ford Motor Company
Provided by IHS Markit under license with FORD
No reproduction or networking permitted without license from IHS
Full document details: FORD WRS-M1H1266-A21 2018

Copyright © 2018, Ford Global Technologies, LLC
Licensee=/, User=,
Not for Resale,