



ENGINEERING MATERIAL SPECIFICATION

Material Name

Specification Number

FABRIC, PAROS PLAIN DESIGN, KNITTED, UNLAMINATED	WSD-M1H664-A
FABRIC, PAROS PLAIN DESIGN, KNITTED, 3 mm	WSD-M1H664-B1
FABRIC, PAROS PLAIN DESIGN, KNITTED, 6 mm	WSD-M1H664-B2
FABRIC, PAROS PLAIN DESIGN, KNITTED, 3 mm	WSD-M1H664-C1
FABRIC, PAROS PLAIN DESIGN, KNITTED, 6 mm	WSD-M1H664-C2
FABRIC, PAROS PLAIN DESIGN, KNITTED, 6 mm	WSD-M1H664-D2
FABRIC, PAROS PLAIN DESIGN, KNITTED, 3 mm PU	WSD-M1H664-F1
FABRIC, PAROS PLAIN DESIGN, KNITTED, 6 mm PU	WSD-M1H664-F2
FABRIC, PAROS PLAIN DESIGN, KNITTED, HFW	WSD-M1H664-G
FABRIC, PAROS PLAIN DESIGN, KNITTED, HFW	WSD-M1H664-H
FABRIC, PAROS PLAIN DESIGN, KNITTED, HFW	WSD-M1H664-J
FABRIC, PAROS PLAIN DESIGN, KNITTED, HFW	WSD-M1H664-K

1. SCOPE

The material defined by this specification is a 3 bar 28 gauge, warp knitted, polyester bodycloth with Fluorocarbon anti-soil finish.

2. APPLICATION

WSD-M1H664-A is used for moulded headrests and also adhesive coated for use on inner door panels.

WSD-M1H664-B1, B2, C1, C2, F1, F2 are used for seat wearing surfaces.

WSD-M1H664-D2 is used for adhesively bonded door and quarter trim panel applications.

WSD-M1H664-G, H, J, K, are used for inner door and quarter trim panels and/or as specified on Engineering Drawings.

PAROS PLAIN DESIGN

WSD-M1H664-A	Unlaminated
WSD-M1H664-B1	3.0 mm, flame laminated to polyether foam and knitted fabric.
WSD-M1H664-B2	6.0 mm, flame laminated to polyether foam and knitted fabric.
WSD-M1H664-C1	3.0 mm, flame laminated to polyester foam and knitted fabric (EAO use only).
WSD-M1H664-C2	6.0 mm, flame laminated to polyester foam and knitted fabric (EAO use only).
WSD-M1H664-D2	6.0 mm, flame laminated to polyether foam.
WSS-M1H664-F1	3.0 mm, flame laminated to polyester foam and polyurethane film (EAO use only).
WSS-M1H664-F2	6.0 mm, flame laminated to polyester foam and polyurethane film (EAO use only).

Date	Action	Changes
1995 08 08	Revised	C10531287, Revised para 1 N. J. Komatsu
1995 06 30	C10460391	Added F1, F2, updated N. J. Komatsu
1994 09 30	C10348613	Released N. J. Komatsu

WP 3948-a

Page 1 of 6

9009160 0012181 614



WSD-M1H664-G	HF-weldable vinyl film, adhesive bonded, or an engineering approved alternative.
WSD-M1H664-H	HF-weldable acrylic backcoating applied by the doctor-knife spreading technique, or an engineering approved alternative.
WSD-M1H664-J	HF-weldable vinyl backcoating applied by the doctor-knife spreading technique, or an engineering approved alternative.
WSD-M1H664-K	HF-weldable polyurethane backcoating applied by the doctor-knife spreading technique, or an engineering approved alternative.

3. REQUIREMENTS

In addition to the requirements listed herein, the fabric or laminate shall meet all requirements of WSB-M8Pl-H.

3.1 QUALITY SYSTEM REQUIREMENTS

Material suppliers and part producers must conform to Quality System Requirements, QS-9000. Material specification requirements are to be used for initial qualification of materials. A Control Plan for ongoing production verification is required. This plan must be reviewed and approved by the relevant Ford Materials activity and/or Ford Supplier Technical Assistance (STA) prior to production parts submission. Appropriate statistical tools must be used to analyze process/product data and assure consistent processing of the materials.

Part producers using this material in their products, must use Ford approved materials and must conform to a process control plan which has been approved by STA and/or the relevant Materials Activity.

3.2 INFRARED SPECTROPHOTOMETRY AND/OR THERMAL ANALYSIS

Ford Motor Company, at its option, may conduct infrared and/or thermal analysis of material/parts supplied to this specification. The IR spectra and thermograms established for initial approval shall constitute the reference standard and shall be kept on file at the designated material laboratory. All samples shall produce IR spectra and thermograms that correspond to the reference standard when tested under the same conditions.

3.3 CONDITIONING AND TEST CONDITIONS

All test values indicated herein are based on material conditioned in a controlled atmosphere of 23 +/- 2 C and 50 +/- 5 % relative humidity for not less than 24 h prior to testing and tested under the same conditions unless otherwise specified.