Ford Motor Company

ENGINEERING MATERIAL SPECIFICATION

Material Name	Specification Number
ADHESIVES, CYANOACRYLATE, (CA), METHYL	**WSK-M2G401-A1/A4**
ADHESIVES, CYANOACRYLATE, (CA), ETHYL	**WSK-M2G402-A1/A11**
ADHESIVES, CYANOACRYLATE, (CA), SURFACE INSENSITIVE	**WSK-M2G403-A1/A4**
ADHESIVES, CYANOACRYLATE, (CA), THICKENED, TOUGHENED	**WSK-M2G404-A1/A5**
ADHESIVES, CYANOACRYLATE, (CA), ALKOXY, LOW ODOR, LOW BLOOM	**WSK-M2G405-A1/A4**

1. SCOPE

The materials defined by these specifications are a series of solventless, room temperature curing cyanoacrylate adhesives.

2. APPLICATION

These specifications were released originally for single component industrial quality adhesives formulated for bonding all metals, most rubbers and many plastics.

WSK-M2G401 - Methyl Cyanoacrylates

A1 A thin penetrating methyl cyanoacrylate adhesive for use in gaps up to 0.05 mm, fast fixturing on metal surfaces, 82 °C continuous use temperature.

A2 A low viscosity methyl cyanoacrylate adhesive for use in gaps up to 0.10 mm, similar to A1 in all other respects.

A3 A medium viscosity methyl cyanoacrylate adhesive for use in gaps up to 0.20 mm, slightly slower fixturing allows 15 second alignment time, similar to A1 in all other respects.

A4 A low viscosity methyl cyanoacrylate adhesive for use in gaps up to 0.10 mm, slightly slower fixturing, similar to A1.

WSK-M2G402 - Ethyl Cyanoacrylates

A1 A penetrating ethyl cyanoacrylate adhesive for use in gaps up to 0.05 mm, fast fixturing on plastic and rubber surfaces, 82 °C continuous use temperature.

Date	Action	Revisions	
2003 02 28	Revised	Para 3.0 inserted; Para 3.1, 3.2, 3.3, 3.7, 3.8, 4 deleted	
1992 10 01	EP00E10176308000	Revised, added suffixes	N. Adamowicz B. Lange
1990 08 01	EP00E01031538000	Released	F.O. Swanson J.Schult

Documents
Document Sharing Hub

Copyright Ford Motor Company
Provided by IHS Markit under license with FORD
No reproduction or networking permitted without license from IHS
Full document details: FORD WSK-M2G405-A4 2003

Copyright © 2003, Ford Global Technologies, Inc.
Licensee=, User=,
Not for Resale,

A2 A low viscosity ethyl cyanoacrylate adhesive for use in gaps up to 0.10 mm, similar to A1 in all other respects.

A3 A low viscosity ethyl cyanoacrylate adhesive for use in gaps up to 0.13 mm, somewhat higher strength, similar to A1 in all other respects.

A4 A medium viscosity ethyl cyanoacrylate adhesive for use in gaps up to 0.10 mm.

A5 A medium viscosity ethyl cyanoacrylate adhesive for use in gaps up to 0.18 mm, slower fixturing, similar to A1.

A6 A medium viscosity ethyl cyanoacrylate adhesive for use in gaps up to0.20 mm, similar to A5 in all other respects.

A7 A gel-like ethyl cyanoacrylate adhesive for use in gaps up to 0.25 mm, for porous or rough surfaces, somewhat slower fixturing, 80 +/-2 °C continuous service temperature.

A8 A penetrating, low strength, ethyl cyanoacrylate adhesive for use in gaps up to 0.05 mm where a temporary bond is desired.

A9 A medium viscosity ethyl cyanoacrylate adhesive for use in gaps up to 0.15 mm, slower fixturing, similar to A1.

A10 A medium viscosity ethyl cyanoacrylate adhesive designed for resisting thermal cycling from - 40 to + 120 °C. Maximum continuous temperature 100 °C. Exhibits better humidity resistance than standard instant adhesives.

A11 A gel-like ethyl cyanoacrylate for use in gaps up to 0.25 mm, similar to A10 in all other respects.

WSK-M2G403 - Surface Insensitive Cyanoacrylates

A1 A penetrating ethyl cyanoacrylate adhesive for gaps up to 0.05 mm and for plated parts, 80 +/- 2 °C continuous service temperature.

A2 A low viscosity ethyl cyanoacrylate adhesive for gaps up to 0.10 mm and for low humidity during assembly, 80+/- 2 °C continuous use temperature.

A3 A medium viscosity ethyl cyanoacrylate adhesive for gaps up to 0.15 mm and for mildly contaminated surfaces, 80 +/- 2 °C continuous use temperature.

A4 A gel-like ethyl cyanoacrylate adhesive for gaps up to 0.25 mm, and for porous or rough parts, 80+/- 2 °C continuous use temperature.

--`,,```,,,,````-`-`,,`,,`,`,,`---

Documents
Document Sharing Hub

Copyright Ford Motor Company
Provided by IHS Markit under license with FORD
No reproduction or networking permitted without license from IHS
Full document details: FORD WSK-M2G405-A4 2003

Copyright © 2003, Ford Global Technologies, Inc.
Licensee=/, User=,
Not for Resale,

WSK-M2G404 - Thickened/Toughened Cyanoacrylates

A1 A medium viscosity toughened ethyl cyanoacrylate adhesive for gaps up to 0.15 mm, reasonably fast fixturing and good moisture resistance, approximately 105 °C continuous use temperature.

A2 A medium viscosity toughened ethyl cyanoacrylate adhesive for gaps up to 0.15 mm, for high stress, and for environmental durability, slow fixturing, approximately 105 °C continuous use temperature.

A3 A high viscosity toughened ethyl cyanoacrylate adhesive for gaps up to 0.20 mm, similar to A2 in all other respects.

A4 A high viscosity toughened ethyl cyanoacrylate adhesive for gaps up to 0.25 mm and for porous or rough parts, approximately 100 °C continuous use temperature.

A5 A gel-like toughened ethyl cyanoacrylate adhesive for gaps up to 0.25 mm, similar to A2 in all other respects.

WSK-M2G405 - Alkoxy Alkyl Cyanoacrylates

A1 A penetrating cyanoacrylate adhesive for gaps up to 0.05 mm, use where low odor and low blooming is desirable, use for bonding plastic and rubber substrates, approximately 70 °C continuous temperature.

A2 A low viscosity cyanoacrylate adhesive for gaps up to 0.10 mm, similar to A1 in all other respects.

A3 A medium viscosity cyanoacrylate adhesive for gaps up to 0.15 mm, similar to A1 in all other respects.

A4 A gel-like cyanoacrylate adhesive for gaps up to 0.25 mm, similar to A1 in all other respects.

3. REQUIREMENTS

3.0 STANDARD REQUIREMENTS FOR PRODUCTION MATERIALS

Material suppliers and part producers must conform to the Company's Standard Requirements For Production Materials (WSS-M99P1111-A).

--`,,```,,,,````-`-`,,`,,`,`,,`---

Documents
Document Sharing Hub

Copyright Ford Motor Company
Provided by IHS Markit under license with FORD
No reproduction or networking permitted without license from IHS
Full document details: FORD WSK-M2G405-A4 2003

Copyright © 2003, Ford Global Technologies, Inc.
Licensee=/, User=,
Not for Resale,