POLYVINYL CHLORIDE (PVC), FLEXIBLE 80 A HARDNESS, EXTERIOR — **WSK-M4D689-A1**

POLYVINYL CHLORIDE (PVC), FLEXIBLE 85 A HARDNESS, EXTERIOR — **WSK-M4D689-A2**

POLYVINYL CHLORIDE (PVC), FLEXIBLE 90 A HARDNESS, EXTERIOR — **WSK-M4D689-A3**

POLYVINYL CHLORIDE (PVC), FLEXIBLE 95 A HARDNESS, EXTERIOR — **WSK-M4D689-A4**

POLYVINYL CHLORIDE (PVC), FLEXIBLE 75 A HARDNESS, EXTERIOR — **WSK-M4D689-A5**

POLYVINYL CHLORIDE (PVC), FLEXIBLE 65 A HARDNESS, EXTERIOR — **WSK-M4D689-A6**

POLYVINYL CHLORIDE (PVC), FLEXIBLE 60 A HARDNESS, EXTERIOR — **WSK-M4D689-A7**

1. SCOPE

The materials defined by these specifications are flexible polyvinyl chloride injection and/or extrusion molding compound.

2. APPLICATION

These specifications were released originally for materials used for exterior garnish moldings.

3. REQUIREMENTS

3.0 STANDARD REQUIREMENTS FOR PRODUCTION MATERIALS

Material suppliers and part producers must conform to the Company's Standard Requirements For Production Materials (WSS-M99P1111-A).

3.4 MOLDED TEST SPECIMEN

3.4.1 Preparation of Test Specimens

Unless otherwise specified, all test shall be conducted on specimens die cut from ungrained compression molded plaques 150 x 150 x 2.0 +/- 0.2 mm molded according to ISO 293.

3.4.2 Density, g/cm^3, max
(ISO 1183, Method A/ASTM D 792, Method A)

A1	A2	A3	A4	A5	A6	A7
1.35	1.40	1.45	1.45	1.35	1.35	1.35

Date	Action	Revisions	
2007 05 11	Revised	Revised paragraph 3.5.1	M. Mehandru
2005 11 17	Revised	Inserted 3.0; Deleted 3.1, 3.2, 3.3, 3.7, 3.8 & 4	
1992 04 01		Added A5 to A7 EP00E10176266000	L. Rodigas

Copyright Ford Motor Company
Provided by IHS Markit under license with IHS
No reproduction or networking permitted without license from IHS
Full document details: FORD WSK-M4D689-A7 2007
Printed copies are uncontrolled
Copyright © 2007, Ford Global Technologies, LLC
Not for Resale,
Documents
Document Sharing Hub

3.4.3 Hardness, Durometer A
(ISO 868/ASTM D 2240, 6 mm thick plied-up specimens, 15 s delay)

A1	A2	A3	A4	A5	A6	A7
80 +/- 5	85 +/- 5	90 +/- 5	95 +3/-5	75 +/- 5	65 +/- 5	60 +/- 5

3.4.4 Tensile Strength at Break, MPa, min
(ISO R 527, type 2/ASTM D 638M, type M-II, 500 mm/min test speed)

A1	A2	A3	A4	A5	A6	A7
12	14	15	16	11	10	10

3.4.4.1 Elongation at Break, %, min
(Test Method according to para 3.4.4)

A1	A2	A3	A4	A5	A6	A7
220	180	160	150	240	250	250

3.4.5 Tear Strength, kN/m, min
(ISO 34, Method B, Procedure a/ASTM D 624, Die C)

A1	A2	A3	A4	A5	A6	A7
50	55	60	70	40	30	25

3.4.6 Cold Flexibility at -30 °C (A1 - A7) No cracks
(FLTM BN 102-01, except specimen 25 x 150 mm, minimum and 19-20 mm mandrel)

3.4.7 Color Stability (A1 - A7)
(ISO 188/ASTM D 573, 150 +/- 50 air changes/h, 168 h at 80 +/- 2 °C)

After exposure the material shall not exhibit color change in excess of AATCC rating 4 (AATCC Gray Scale for Evaluating Change in Color, 10 step).

In addition there shall be not be any staining, spewing, loss of gloss.

3.4.8 Heat Aging Performance (A1 - A7)
(ISO 188/ASTM D 573, 150 +/- 50 air changes/h, 1000 h at 80 +/- 2 °C. Unaged property values shall be determined at the time of the aged properties determination)

3.4.8.1 Tensile Strength Change +/- 25%
(Test Method per para 3.4.4)

3.4.8.2 Elongation Change +/- 25%
(Test Method per para 3.4.4)

3.4.8.3 Weight Change, max 10%
(50 x 25 x 2 +/- 0.2 mm specimen)

3.4.9 H2S Staining (A1 - A7) Rating 5
(FLTM AN 102-01)

Documents
Document Sharing Hub

Copyright Ford Motor Company
Provided by IHS Markit under license with FORD
No reproduction or networking permitted without license from IHS
Printed copies are uncontrolled
Full document details: FORD WSK-M4D689-A7 2007

Copyright © 2007, Ford Global Technologies, LLC
Licensee = Ford
Not for Resale,