



ENGINEERING MATERIAL SPECIFICATION

Material Name

Specification Number

PAINT, WATERBASED, BASECOAT, LOW BAKE, METALLIC
PAINT, WATERBASED, BASECOAT, LOW BAKE, NONMETALLIC

WSK-M62J30-A1
WSK-M62J30-A2

1. SCOPE

The materials defined by these specifications are waterbased one pack low bake basecoats for 90 C baking temperature. They must be coated with an additional clear coat.

2. APPLICATION

These specifications were released originally for materials used as two coat basecoat on primed plastic bumpers. The materials may also be used for other exterior plastic applications such as radiator grilles or body side moldings, (see 5.1).

3. REQUIREMENTS

3.1 STATISTICAL PROCESS

Suppliers must conform to the requirements of Ford Quality System Standard Q-101. A mutually acceptable Control Plan as described therein is required for material/source approval. Appropriate statistical tools must be used to analyze process/product data so that variation in the final product is continuously reduced.

3.2 INFRARED SPECTROPHOTOMETRY AND/OR THERMAL ANALYSIS

Ford Motor Company, at its option, may conduct infrared and/or thermal analysis of material/parts supplied to this specification. The IR spectra and thermograms established for initial approval shall constitute the reference standard and shall be kept on file at the designated material laboratory. All samples shall produce IR spectra and thermograms that correspond to the reference standard when tested under the same conditions.

3.3 CONDITIONING AND TEST CONDITIONS

All test values indicated herein are based on material conditioned in a controlled atmosphere of 23 +/- 2 C and 50 +/- 5 % relative humidity for not less than 24 h prior to testing and tested under the same conditions unless otherwise specified.

3.4 COMPOSITION

3.4.1 Resin

Water based synthetic resins.

3.4.2 Pigments

Pigments to obtain the desired colour and properties.

Date	Release No.	Release/Revision
1991-06-03	EP00E01089485000	Released KW

WP 3948-a

Page 1 of 5

9009160 0014241 7T3



- 3.4.3 Solvent Emissions See Initial Sample +/- 1 %
(ASTM D 3960)

This requirement is as determined by the United States Environmental Protection Agency Reference Method #24 and is only applicable to materials used in the USA.

3.5 MATERIAL PROPERTIES

- 3.5.1 Nonvolatile See Initial Sample +/- 1 %
(FLTM BI 102-01)

WSK-M62J30-A1, min	16 %
WSK-M62J30-A2, min	20 %

The nonvolatile content shall be determined at spray viscosity of 35 s per para 3.5.4.

- 3.5.2 Density See Initial Sample +/- 0.02 g/mL
(ASTM D 1475)

- 3.5.3 Viscosity as supplied See Initial Sample +/- 5 s
(FLTM BI 111-01)

- 3.5.4 Spray Viscosity As specified by the supplier
(FLTM BI 111-01, FC #4)

The material can be reduced with deionized water.

- 3.5.5 Organic Solvent Content, max 17 %

The content of organic solvents is defined as:
Weight-% of organic solvents at spray viscosity.

- 3.5.6 Dry Hiding Power
(FLTM BI 158-01)

WSK-M62J30-A1, max	15 micrometre
WSK-M62J30-A2, light red, max	40 micrometre
WSK-M62J30-A2, other colours, max	25 micrometre

- 3.5.7 Storage Stability 90 days

During the storage between 5 and 32 C temperature, the material as supplied shall not settle up or cake insoluble. After the storage the material must pass all specification requirements.