



FABRIC, INFLUENCE PATTERN, WARP KNIT

WSS-M1H1106-A

1. SCOPE

The material defined by this specification is a INFLUENCE PATTERN, 3 bars, 56 Gauge, Single Needle bar, body cloth of good quality and uniform composition. The base fabric is embossed to create the pattern.

2. APPLICATION

This specification was released originally for material used as an interior trim fabric for 2008 D219 seat insert.

3. REQUIREMENTS

In addition, to the requirements listed herein, the fabric shall meet all requirements of WSS-M8P18-A1/A4 as applicable.

3.1 STANDARD REQUIREMENTS FOR PRODUCTION MATERIALS

Material suppliers and part producers must conform to the Company's Standard Requirements For Production Materials (WSS-M99P1111-A).

3.2 FABRIC CONSTRUCTION**3.2.1 Fabric Count, +/- 5% tolerance
(ASTM D 3887)**

Wales	146 wales/10 cm
Courses	181 courses/10 cm

**3.2.2 Fabric Weight, +/- 5%, g/m²
(FLTM BN 106-01)**

Face w/no Backcoat	344
Laminated to 3 mm foam	463

**3.3 COMPOSITION
(ASTM D 629)**

Tolerance as specified in WSS-M8P18-A1/A4

Fabric	100% Polyester
Backcoat	No backcoat

Date	Action	Revisions
2006 12 20	Activated	



Documents

M. Dumitrescu

Document Sharing Hub



3.4 YARN CONSTRUCTION (ASTM D 1244)

Face	11.1 tex f34 (textured yarn)
Middle	11.1 tex f34 (textured yarn)
Back	7.77 tex f36 (wd yarn)

3.5 METHOD OF DYEING

Piece Dye

3.6 FINISHING OPERATIONS

Knit, Heat set, Setmake, Dye,
Dry, Emboss, Inspect

