



FABRIC, MASON PATTERN, FLAT WOVEN, 100% VIRGIN WITH SOIL REPELLANT AND BACKCOATING

WSS-M1H1278-A13

1. SCOPE

The material defined by this specification is a flat woven polyester face fabric made from 100% virgin yarn.

2. APPLICATION

This specification was released originally for material used as an interior trim fabric for Everest 2018MY seat insert. The fabric was originally approved as tri-laminated with foam and a backing scrim.

3. REQUIREMENTS

3.1 APPROVED SOURCES

This specification requires the use of approved sources. Only the sources identified on the Ford Approved Source List (ASL) can be used when this specification is listed on the drawing, CAD file, or other documents. The list of approved sources is located within Ford at www.mats.ford.com or available externally through a Ford Materials Engineer.

3.2 APPEARANCE

The color, pattern, and finish shall match the approved Corporate Design master sample.

3.3 FABRIC PERFORMANCE

In addition to the requirements listed herein, the fabric shall meet all requirements of WSS-M8P18-B1/B2/B3/B4/latest as applicable.

3.4 VEHICLE INTERIOR ENVIRONMENTAL PERFORMANCE

Materials used in interior applications must meet the requirements outlined in WSS-M99P2222-D1/latest, *Performance, Vehicle Interior Environmental Quality Material/Component Requirements*. Data must be included in material submission package.

3.5 CONDITIONING AND TEST CONDITIONS

All test values are based on material conditioned for not less than 24 h prior to testing in a controlled environment of 23 +/- 2 °C and 50 +/- 5% relative humidity. Testing of the material should occur in the conditioning environment or soon after removal.

3.6 FABRIC CONSTRUCTION

3.6.1 Fabric Count, +/- 5 % tolerance
(ASTM D3775)

Warp
Fill

670 / 10 cm
270 / 10 cm

Date	Action	Revisions	Rev. 0
2017 02 27	Released		



Documents

J. Wang, APA



3.6.2 Fabric Weight, - /+10 % tolerance 355 g/m²
(FLTM BN 106-01)

Face fabric	270 g/m ²
Back coating	85 g/m ²
Total Weight	355 g/m ²

3.7 COMPOSITION (ASTM D629)

Fabric	100% polyester
Backcoating	Acrylic

3.8 YARN CONSTRUCTION (ASTM D1244)

Warp	167 Dtex f48, (polyester, false twist texturized)
------	--

Fill 1	330 Dtex f96, (polyester, false twist texturized)
--------	--

Fill 2	167 Dtex f48 /3, (polyester, false twist texturized)
--------	---

Fill 3	330 Dtex f72 /2, (polyester, false twist texturized)
--------	---

3.10 METHOD OF DYEING

Yarn Dyed

3.11 FINISHED OPERATIONS

Dipping, Soil Repellent , Drying, Back Coating, Setting

4. GENERAL INFORMATION

The information given below is provided for clarification and assistance in meeting the requirements of this specification. Contact gmfs@ford.com for questions concerning Engineering Material Specifications.

4.1 Purchase departments will ensure that the material defined in this specification and shipped to any one assembly plant will be produced by one supplier only. In the event of a Global Program or regional duplication, each regional location of the supplier for this specification must provide a construction package and be approved to meet this specification.

4.2 If yarn is locally sourced it must meet the above fabric construction, composition and yarn construction. The fabric must also meet the requirements of WSS-M8P18-B1/B2/B3/B4/latest.

4.3 Global strategy for this fabric is to use tri-laminate/foam & scrim construction in all regions.