



## FABRIC, JACARANDA EMBOSSED PATTERN, WARP KNIT, 100% VIRGIN WITH SOIL REPELLANT

WSS-M1H1309-A11

### 1. SCOPE

The material defined by this specification is a warp knit polyester face fabric made from 100% virgin yarn. View is the base fabric for this embossed pattern.

### 2. APPLICATION

This specification was released originally for material used as an interior trim fabric for New Fiesta South America 2018MY seat insert. The fabric was originally approved as tri-laminated with foam and a backing scrim.

### 3. REQUIREMENTS

#### 3.1 APPROVED SOURCES

This specification requires the use of approved sources. Only the sources identified on the Ford Approved Source List (ASL) can be used when this specification is listed on the drawing, CAD file, or other documents. The list of approved sources is located within Ford at [www.mats.ford.com](http://www.mats.ford.com) or available externally through a Ford Materials Engineer.

#### 3.2 APPEARANCE

The color, pattern, and finish shall match the approved Corporate Design master sample.

#### 3.3 FABRIC PERFORMANCE

In addition to the requirements listed herein, the fabric shall meet all requirements of WSS-M8P18-B1/B2/B3/B4/latest as applicable.

#### 3.4 CONDITIONING AND TEST CONDITIONS

All test values are based on material conditioned for not less than 24 h prior to testing in a controlled environment of 23 +/- 2 °C and 50 +/- 5% relative humidity. Testing of the material should occur in the conditioning environment or soon after removal.

#### 3.5 FABRIC CONSTRUCTION

3.5.1 Fabric Count, -5/+ 10 % tolerance  
(ASTM D3775)

Warp  
Fill

130 / 10 cm  
240 / 10 cm

3.5.2 Fabric Weight, +/-10 % tolerance  
(FLTM BN 106-01)

260 g/m<sup>2</sup>

| Date       | Action   | Revisions | Rev. 0 |
|------------|----------|-----------|--------|
|            |          |           |        |
|            |          |           |        |
| 2017 06 14 | Released |           |        |



Documents

Document Sharing Hub



### 3.6 COMPOSITION (ASTM D629)

Fabric 100% polyester

### 3.7 YARN CONSTRUCTION (ASTM D1244)

Warp 78 Dtex f36  
(Polyester, false twist, texturized)

Fill 76 Dtex f24,  
(Polyester, flat yarn)  
  
76 Dtex f24  
(Polyester, flat yarn made)

### 3.8 METHOD OF DYEING

Solution Dyed

### 3.9 FINISHED OPERATIONS

Washing, Drying, Framing, Embossing

Any changes to the above process  
must be approved by Materials Engineering.

## 4. GENERAL INFORMATION

The information given below is provided for clarification and assistance in meeting the requirements of this specification. Contact [gmfs@ford.com](mailto:gmfs@ford.com) for questions concerning Engineering Material Specifications.

**4.1** Purchase departments will ensure that the material defined in this specification and shipped to any one assembly plant will be produced by one supplier only. In the event of a Global Program or Regional duplication, each regional location of the supplier for this specification must provide a Construction package and be approved to meet this specification.

**4.2** If yarn is locally sourced it must meet the above fabric construction, composition and yarn construction. The fabric must also meet the requirements of WSS-M8P18-B1/B2/B3/B4/latest.

**4.3** Global strategy for this fabric is to use tri-laminate/foam & scrim construction in all regions.

### 4.4 APPROVAL OF MATERIALS

Suppliers desiring approval of their materials shall first obtain an expression of interest from Purchasing, Design or Product Development, and Materials Engineering. The supplier shall submit a completed copy of their laboratory test reports, signed by a qualified and authorized representative of the test facility, demonstrating full compliance with all the requirements of the Material Specification. Tested material samples must be available for review upon request and kept for a minimum of one year. Upon request, the supplier will review the associated quality control documents (Process Failure Mode and Effects Analysis, Control Plans, Certification testing) with Ford.

### 4.5 SUPPLIER'S ONGOING RESPONSIBILITY

All materials must be equivalent in all characteristics to the material upon which approval was originally granted.