ENAMEL, WATERBORNE, THERMOSET BASECOAT, BASE-COAT/CLEARCOAT WET-ON-WET PROCESS, EXTERIOR — **WSS-M33J6-A1**

ENAMEL, COMPLIANCE VOC, MEDIUM SOLIDS, THERMOSET CLEARCOAT, BASECOAT/CLEARCOAT WET-ON-WET PROCESS, EXTERIOR — **WSS-M33J6-B1**

ENAMEL, COMPLIANCE VOC, MEDIUM SOLIDS, THERMOSET CLEARCOAT, BASECOAT/CLEARCOAT WET-ON-WET PROCESS, ETCH RESISTANT, EXTERIOR — **WSS-M33J6-B3**

ENAMEL, COMPLIANCE VOC, HIGH SOLIDS, THERMOSET CLEARCOAT, BASECOAT/CLEARCOAT WET-ON-WET PROCESS, ETCH RESISTANT, EXTERIOR — **WSS-M33J6-C3**

ENAMEL, COMPLIANCE VOC, HIGH SOLIDS, THERMOSET TINTED CLEARCOAT, BASECOAT/CLEARCOAT WET-ON-WET PROCESS, ETCH RESISTANT, EXTERIOR — **WSS-M33J6-C4**

1. SCOPE

The materials defined by this specification are coatings which consist of a pigmented waterborne thermoset basecoat enamel over which is applied a clear or tinted clear thermoset clearcoat in a wet-on-wet process. These materials are monobaked. Unique tricoat colors are also included in this specification. Tricoat colors consist of a pigmented basecoat followed by a non-hiding midcoat over which is applied a clear or tinted clear. Tricoat colors may be processed wet-on-wet-on-wet application and monobaked or in a wet on bake operation. WSS-M33J6-A1/C4 replaces WSB-M33J5-A1/B3.

2. APPLICATION

These specifications were released originally for materials used as the topcoat finish on automobile bodies, hoods, fenders and other exterior parts, and shall be satisfactory for use over specified primers or over previously baked enamel, as in paint repair or two toning operations. The basecoat portion is used alone, without clearcoat, as an interior baking enamel for some applications

3. REQUIREMENTS

3.1 APPROVED SOURCES

This specification requires the use of approved sources. Only the sources identified on the Ford Approved Source List (ASL) can be used when this specification is listed on the drawing, CAD file, or other documents. The list of approved sources is located within Ford at www.mats.ford.com or available externally through a Ford Materials Engineer.

3.2 CONDITIONING AND TEST CONDITIONS

Date	Action	Revisions	Rev. 1
2017 01 27	Revised	See Summary of Revisions	M. Jones, NA
1997 09 25	Released		E. M. Mancin

Copyright © 2017, Ford Global Technologies, LLC

Documents
Document Sharing Hub
Copyright Ford Motor Company
Provided by IHS Markit under license with FORD
No reproduction or networking permitted without license from IHS
Licensee=/, User=,
Not for Resale,
Full document details: FORD WSS-M33J6-B1 2017

All test values are based on material conditioned for not less than 24 h prior to testing in a controlled environment of 23 +/- 2 °C and 50 +/- 5% relative humidity. Testing of the material should occur in the conditioning environment or soon after removal.

3.3 INFRARED SPECTROPHOTOMETRY AND/OR THERMAL ANALYSIS

Ford Motor Company, at its option, may conduct infrared and/or thermal analysis of material/parts supplied to this specification. The IR spectra and thermograms established for initial approval shall constitute the reference standard and shall be kept on file at the designated material laboratory. All samples shall produce IR spectra and thermograms that correspond to the reference standard when tested under the same conditions.

3.4 COMPOSITION

Test shall be made on the basis of comparison with approved production material, to be chosen by approving materials engineer.

Note: For purposes of the specification, paint systems which utilize a standard basecoat/clearcoat, a basecoat/midcoat/clearcoat and/or a system with a tinted clearcoat shall be considered the "complete basecoat/clearcoat enamel system". For basecoat-only applications refer to para 3.12.

3.4.1 Resin

Basecoats shall be thermosetting, waterbased synthetic resins, and clearcoats will be thermosetting, acrylic-modified synthetic resins. Each will be appropriately fortified so as to meet the durability requirement of 10 years.

3.4.2 Pigments

Pigments are exterior quality automotive grade selected to meet durability requirements.

3.4.3 Solvents

The volatility of the solvents will be such that there shall be no paint sagging, pin-holing, roughness or dry spray at specified film thicknesses.

3.5 PHYSICAL PROPERTIES LIQUID STATE

At application viscosity, material shall be in compliance with local emissions regulations.

3.5.1	Non-Volatile Content (ASTM D1353)	See initial sample +/- 1 %
3.5.2	Volatile Organic Content(VOC) (ASTM D3960)	See initial sample +/- 1 %
3.5.3	Weight per Volume (ASTM D1475)	See initial sample +/- 0.03 g/ml
3.5.4.	Volume Solids (ASTM D2697)	See initial sample +/- 1 %
3.5.4.1	Pigment Content in Tinted Clearcoat (ASTM D2371)	0.5 % max

Copyright © 2017, Ford Global Technologies, LLC

Documents
Document Sharing Hub

Copyright Ford Motor Company
Provided by IHS Markit under license with FORD
No reproduction or networking permitted without license from IHS
Licensee=/, User=,
Not for Resale,
Full document details: FORD WSS-M33J6-B1 2017

3.5.5 Viscosity
(ASTM D2196 - Non-Newtonian)
(ASTM D1200)

Supplier shall report value at application reduction. Supplier shall present viscosity versus shear rate curves.

3.5.6 Stability
(ASTM D1849)

After test, the material shall pass all specification requirements.

3.5.6.1 Shelf Stability 90 days

No more than 30 % increase in viscosity permitted.

3.5.6.2 Accelerated Stability
(60 °C, 16 h)

No more than 30 % increase in viscosity permitted when tested per para 3.5.5.

3.5.7 Resistivity-Clearcoat Only 0.05 to 2.00 megohms
(ASTM D5682)

Volatile solvents and other components affecting electrical conductivity shall be adjusted such that the resistivity at application viscosity shall be within specified limits.

3.6 PREPARATION OF TEST PANELS

Substrate: Current production phosphated galvanized steel and current production primed exterior thermosetting plastic. Record all substrate information. See para 4.1.

Electrocoat: Current production medium build gray cathodic electrocoat, applied at 20 - 23 micrometers and baked 10 minutes at 182 °C metal temperature (MT). Record electrocoat and oven type used.

Primer: Current production primer surfacer in a color consistent with production, applied at 25 - 28 micrometers and baked 10 minutes at 150 °C (metal temperature). Record primer and oven type used.

Enamel: Apply basecoat to required dry film thickness by (OEM) spray under conditions appropriate for waterborne basecoats, and flash (or prebake) as required. Apply clearcoat to required dry film thickness. Bake using appropriate bake schedule. Record enamel and oven type used.

Catalyzed Low Bake Repair: (LBR) For catalyzed low-bake repair, a current production basecoat/clearcoat system from the same manufacturer that has been approved for use may be substituted, provided that it meets all the catalyzed repair systems criteria. Catalyze enamel as per manufacturer's recommendations. Prepare panels at target conditions (# 3). Wipe panels using naphtha and mask half of panel vertically. Apply low bake system, remove masking, flash and bake 10 minutes at 100 °C metal temperature.

See Table 1 for Topcoat Processing Matrix, Table 2 and 3 for New Technology Test Matrices, and Table 4 for New Pigments/New Colors Test Matrix.

Copyright © 2017, Ford Global Technologies, LLC

Documents
Document Sharing Hub

Copyright Ford Motor Company
Provided by IHS Markit under license with FORD
No reproduction or networking permitted without license from IHS
Licensee=/, User=,
Not for Resale,
Full document details: FORD WSS-M33J6-B1 2017

3.7 PROCESS WINDOW DEFINITION - NEW TECHNOLOGIES ONLY

The supplier shall perform a Design of Experiments (DOE) (Response Surface Analysis is recommended) to determine the process window of the control and candidate materials. The three variables/parameters to be included in the design are bake temperature, bake time, and clearcoat film thickness (basecoats applied at hiding). An initial screening experiment should be run to determine what levels should be tested for the variables/parameters. This screening experiment should be reviewed with the materials engineer to set up the final DOE. Responses to the DOE will be based on the materials tested and will be chosen from tests listed within the specification. Minimal critical testing required: cross-hatch adhesion, condensing humidity, acid/alkali resistance, mar resistance, stone chip (SAE J400 and Erichsen), intercoat adhesion (ICA). Information will be used by materials engineer to determine acceptable plant processing conditions. See also para 4.2.

3.8 APPEARANCE

Note: Appearance panels will be sprayed using standard plant processing parameters.

3.8.1 Color
(FLTM BI 109-01)
(SAE J1545 X-Rite MA58 Three-Angle CMC)

Shall match the Master Appearance Standard color panel.

3.8.2 Distinctness of Image (DOI) — 70 min
(FLTM BI 110-03)

3.8.3 Gloss — 90 min
(ASTM D 523, 20 degree Glossmeter)

3.8.3.1 Gloss After Rebake — 4 unit decrease max

Rebake panel at target bake conditions.

Copyright © 2017, Ford Global Technologies, LLC

Documents
Document Sharing Hub

Copyright Ford Motor Company
Provided by IHS Markit under license with FORD
No reproduction or networking permitted without license from IHS
Licensee=/, User=,
Not for Resale,
Full document details: FORD WSS-M33J6-B1 2017

3.8.4 Leveling

The surface of material under test shall be equal to or better than currently approved production material for smoothness when applied and baked under identical conditions. Orange peel values taken from Quality Measurement System (QMS) data obtained using Autospect shall be reported.

3.8.5 Sanding

3.8.5.1 Holdout

There shall be no evidence of dulling, gloss loss or change of image clarity when enamel color coat is applied over sanded (P400 and P800 grit sandpaper) or unsanded primer surfacer. There shall be no prominence of sand scratches.

3.8.5.2 Telegraphing

There shall be no evidence of color shift when enamel color coat is applied over sanded (P400 and P800 grit sandpaper) or unsanded primer surfacer.

3.8.6 General

The enamel shall cure to a presentable, serviceable, mar-resistant film showing no craters, pinholing, seediness, abnormal roughness or excessive metallic mottling. It shall have reasonable tolerance for ordinary cleaning (such as automatic car washes) and exhibit excellent polishing characteristics when wheel polished with a wide range of various compounds and cleaners.

3.9 FILM PROPERTIES

3.9.1 Film Thickness
(ASTM D1186)

Target values shall be defined from process window (para 3.7).

3.9.2 Dry Hiding - Pigmented Basecoat 15 – 30 micrometers
(FLTM BI 158-01)

The basecoat is required to provide complete visual hiding over black and gray hiding chart.

When an exception to this hiding requirement is needed for special colors, concurrence must be obtained from all affected Ford activities.

3.9.2.1 Pigmented Midcoat

The pigmentation of the midcoat shall be such that hiding of the basecoat does not occur.

3.9.3 Ultraviolet Light Transmittance

Maximum light transmission through basecoat applied at 80 % of dry hiding directly over epoxy-free spray primer shall be no more than 0.1 % at 360 nm and 5 % at 400 nm. The equipment used for this measurement is a Lambda 6 Integrating Sphere spectrophotometer or equivalent. Non-fortified (without UV pkg) clearcoat is used for this evaluation.

Copyright © 2017, Ford Global Technologies, LLC

Documents
Document Sharing Hub

Copyright Ford Motor Company
Provided by IHS Markit under license with FORD
No reproduction or networking permitted without license from IHS
Licensee=/, User=,
Not for Resale,
Full document details: FORD WSS-M33J6-B1 2017

3.9.4	Bleeding of Pigments (ASTM D279)	None Permitted

3.9.5 Hardness
(ASTM D1474)

Record value at target film and bake conditions. Coating shall be sufficiently cured after baking so that it can meet the polishing requirements of para 3.9.7.

3.9.6 Adhesion

3.9.6.1	Scratch Test (FLTM BI 106-01, Part A)	No chipping or loss of adhesion permitted
3.9.6.2	Scribe Test (FLTM BI 106-01, Part B)	Grade 2 max

3.9.7 Polishing

Shall be capable of being sanded with 1200 grit sandpaper and polished in accordance with current plant processes to minimize orange peel or to remove defects. No noticeable change in gloss or appearance except for a minimum of swirl marks is permitted. Deep polishing lines or swirl marks are unacceptable.

3.10 RESISTANCE PROPERTIES

3.10.1	Condensing Humidity (ASTM D4585, 43 °C)	240 h

No blistering, dulling, wrinkling, softening and/or loss of adhesion permitted. Within 15 - 20 minutes of removal from water resistance test, panels will be checked for adhesion and meet the requirements of para 3.9.6.2.

3.10.2	Acid/Alkali Resistance	Equal or better than control

The Gradient Bar Method shall be used. The following solutions shall be tested on candidate materials: Solutions of sulfuric acid (H_2SO_4) adjusted to pH of 2, 3, 4; a solution in water of 0.75 % by weight $CaSO_4$ adjusted to a pH of 4; deionized water (DI) and tap water, Bee Dropping (Ford Method 24).

Apply 0.05 ml of specified solutions along entire length of 2 test panels. Place on gradient bar (38 - 82 °C, calibrated for heat-up rate of 2 minutes or less for 0.09 mm steel substrate). Remove 1 panel after 15 minutes at temperature, other after 30 minutes. Rinse any remaining solution with water. Examine panels for etching, dis-coloration, pitting, etc. Report etch-free temperature for test material and control.

NOTE: Process window evaluation will be done using 2 solutions: (1) Sulfuric Acid pH3, 15 minute exposure; and (2) $CaSO_4$ pH4, 30 minute exposure.

Copyright © 2017, Ford Global Technologies, LLC

Documents
Document Sharing Hub

Copyright Ford Motor Company
Provided by IHS Markit under license with FORD
No reproduction or networking permitted without license from IHS
Licensee=/, User=,
Not for Resale,
Full document details: FORD WSS-M33J6-B1 2017