**CARPET, POLYESTER, NON WOVEN, FLAT NEEDLED, LATEX 342 g/m$^2$ (10 oz/yd$^2$)** **WSS-M3H158-A1**

## 1. SCOPE

The materials defined by this specification are flat needled, virgin polyester, non-woven carpets of good quality and uniform composition. The face fiber is 100% 6 denier polyester and it is back coated with the appropriate weight of latex.

## 2. APPLICATION

This specification was originally released for cut and sew applications on the China Transit seat back carpet.

## 3. REQUIREMENTS

### 3.1 APPROVED SOURCES

This specification requires the use of approved sources. Only the sources identified on the Ford Approved Source List (ASL) can be used when this specification is listed on the drawing, CAD file, or other documents. The list of approved sources is located within Ford at www.mats.ford.com or available externally through a Ford Materials Engineer.

### 3.2 CONDITIONING AND TEST CONDITIONS

All test values are based on material conditioned for not less than 24 h prior to testing in a controlled environment of 23 +/- 2 °C and 50 +/- 5% relative humidity. Testing of the material should occur in the conditioning environment or soon after removal.

### 3.3 PERFORMANCE CRITERIA

3.3.1 In addition to the requirements listed herein, the end-item carpet shall be tested to WSS-M8P16-B and any additional SDS requirements. The details for each of the supplier specific constructions shall be documented in the supplement attached and uploaded into the scanned data package.

3.3.2 Vehicle Interior Environment Quality Materials/Component Performance Requirements

Materials used in interior applications must meet the requirements outlined in WSS-M99P2222-D1/ latest. Data must be provided at the appropriate program milestone.

### 3.4 SAMPLE SELECTION

All evaluations shall be conducted on test specimens taken from finished roll good.

### 3.5 APPEARANCE

The color, pattern, and gloss shall match the approved Corporate Design master sample.

| Date | Action | Revisions | Rev. 00 |
|---|---|---|---|
| | | | |
| | | | |
| 2016 04 11 | Released | | R. Kyle, EU |


Copyright © 2016, Ford Global Technologies, LLC
Licensee=/, User=,
Not for Resale,

Copyright Ford Motor Company
Provided by IHS Markit under license with FORD
No reproduction or networking permitted without license from IHS
Full document details: FORD WSS-M3H158-A1 2016
Documents Document Sharing Hub

**3.6 COMPOSITION**

| | | |
|---|---|---|
| 3.6.1 | Face Fiber (ASTM D276) | 100% Polyester |
| 3.6.2 | Primary Backing (ASTM D276) | Latex |

**3.7 METHOD OF DYEING** — Solution Dyed

**3.8 CONSTRUCTION**

| | | |
|---|---|---|
| 3.8.1 | Fiber Size and Description (ASTM D 1244) | 6 Denier (Polyester) |

**3.9 THICKNESS** (ISO 1765) — 2.0 +/- 0.3 mm

**3.10 WEIGHT**

| | | |
|---|---|---|
| 3.10.1 | Face Fiber (ASTM D5848) | 342 - 418 g/m$^2$ (10.0 – 12.3) oz/yd$^2$ |
| 3.10.2 | Primary Backing (ASTM D5848) | (15-25) g/m$^2$ (0.4 – 0.7) oz/yd$^2$ |

Weight tolerances approved for each supplier's construction can be found in the scanned data package. Approved moldable substrate weights can also be found on the Approved Source Listing.

## 4. GENERAL INFORMATION

This information given below is provided for clarification and assistance in meeting the requirements of this specification. Contact gmfs@ford.com for questions concerning Engineering Material Specifications.

### 4.1 DRAWING CALL OUT

The following shall be called out on the Engineering drawing to correctly designate the approved material.

WSS-M3H158-1A
Supplier Name and Product Code (As it appears on the Approved Source Listing)
WSS-M8P16-B

### 4.2 APPROVAL OF MATERIALS

Suppliers desiring approval of their materials shall first obtain an expression of interest from Purchasing, Design or Product Development, and Materials Engineering. The supplier shall submit a completed copy of their laboratory test reports, signed by a qualified and authorized representative of the test facility, demonstrating full compliance with all the requirements of the Material Specification. Tested material samples must be available for review upon request and kept for a minimum of one year. Upon request, the supplier will review the associated quality control documents (Process Failure Mode and Effects Analysis, Control Plans, Certification testing) with Ford.

Documents
Document Sharing Hub



Copyright Ford Motor Company
Provided by IHS Markit under license with FORD
No reproduction or networking permitted without license from IHS
Full document details: FORD WSS-M3H158-A1 2016

Copyright © 2016, Ford Global Technologies, LLC
Licensee=/, User=,
Not for Resale,