GM WORLDWIDE ENGINEERING STANDARDS	**Material Specification**	**GMW16900**

Polypropylene, Long Glass Fiber Reinforced, Compression Molded

1 Scope

1.1 Material Description. This standard covers the properties of a long glass fiber mat, pre-impregnated with polypropylene, homopolymer, and used in a compression molding process.

1.2 Symbols. The material abbreviation according to ISO 11469 is > PP – GFXX <. The symbol shall be completed by the supplier according to the Glass Fiber (GF) content of the material.

1.3 Typical Applications. Typical applications include non-Class "A" surface appearance structural components such as the following: underbody panels, chassis shields, radiator support brackets, seat backs, bumper beams, battery trays, header panels.

1.4 Remarks. The classification into groups is according to the different ranges of glass fiber content.

2 References

Note: Only the latest approved standards are applicable unless otherwise specified.

2.1 External Standards/Specifications.

ISO 75	ISO 1183	ISO 6603-1/2	ISO 11469
ISO 178	ISO 3451-1	ISO 11359-2	SAE J1686
ISO 527-1/2			

2.2 GM Standards/Specifications.

GMW3013	GMW3221	GMW14650	GMW15725
GMW3059	GMW14444		

2.3 Additional References.

TMC003 Material Safety Data Sheet guidance documents (available at www.gmsupplypower.com).

3 Requirements

Materials approved to this specification shall meet the requirements of GMW3013, **General Requirements for Handling of Technical Terms of Delivery for Plastics.**

3.1 Requirements on Delivery. The physical, mechanical and thermal properties that characterize the material are summarized in Table 1.

Note: The requirements to Table 1 shall be documented for self-certification of the product according to GMW3013. The color shall be specified on drawings, in material specifications, and otherwise.

3.1.1 Requirements on Test Specimens. Unless otherwise specified, all specimens for test shall be obtained from molded plaques with a thickness of 2.5 mm ± 0.5 mm. The specimens shall be molded using temperatures and pressures typical of those used in production.

All tests shall be performed on specimens 40 h minimum after molding and immediately following a conditioning period of 24 h minimum in a controlled atmosphere per GMW3221, Code A, unless otherwise specified. All tests shall be performed on unannealed specimens. Five coupons minimum shall be tested. The average value is the material property value.

3.1.2 Chemical Requirements. All parts manufactured from molding compounds shall be resistant to the media they contact at their place of use.

3.2 Requirements on Materials. See Table 1.

3.3 Performance Requirements. All finished parts for Interior applications shall meet the requirements according to GMW14444. All finished parts for Exterior applications shall meet the requirements according to

© Copyright 2013 General Motors Company All Rights Reserved

Documents Document Sharing Hub

Copyright General Motors Company
Provided by IHS Markit under license with General Motors Company
Reproduction, distribution or publication of these standards is expressly prohib
Licensee=/, User=,
Not for Resale,
Full document details: GM GMW16900 2013

GMW14650. All finished parts for Engine Compartment applications shall meet the requirements according to GMW15725.

3.3.1 Limitations. Parts made of this material are subject to the following limitations.

3.3.1.1 Maximum continuous use temperature shall not exceed 125 °C.

3.3.1.2 Maximum short term use, <30 minutes, shall not exceed 145 °C.

3.4 Compound Properties. The following are also required for full specification approval. The minimum number of lots per test required is one: Poisson's Ratio, Stress Strain Curve at +23 °C, +85 °C, -30 °C; Differential Scanning Calorimetry (DSC) Curve; and Infrared Spectroscopy Curve.

Table 1: Compound Properties Note 1, Note 2

Property	Standard	Unit	Type 1	Type 2
Ash	ISO 3451-1, Method A	% by Mass	30 ± 3	40 ± 3
Specific Gravity	ISO 1183, Method A	g/cm^3	1.14 ± 0.04	1.22 ± 0.04
Tensile Strength at Break	ISO 527-1, ISO 527-2, Specimen A, test speed 5 mm/minute	MPa	65	84
Tensile Elongation at Yield	ISO 527-1/2	%	1.8	1.6
Tensile Modulus	ISO 527-1/2	MPa	5100	5500
Flexural Modulus At 23 °C At 80 °C	ISO 178, Method 1	MPa	3550 2300	4100 2400
Multiaxial Impact at +23 °C, 2.2 m/s	ISO 6603-1/2 Energy at maximum load, Sample Size 60 mm x 60 mm	J	12	16
Multiaxial Impact at -30 °C, 2.2 m/s	ISO 6603-1/2 Energy at maximum load, Sample size 60 mm x 60 mm	J	10	12
Tensile Strength after Heat Aging 1000 h at 100 °C	ISO 527-1, ISO 527-2, specimen A, test speed 5 mm/minute	% retention	75	75
Deflection Temperature Under Load, 1800 kPa, Method A	ISO 75 (refer to SAE J1686), flatwise	°C	155	155
Coefficient of Linear Thermal Expansion (CLTE) Parallel to flow Transverse to flow	ISO 11359-2 Thermal Mechanical Analysis (TMA), mean secant value over the temperature range -40 °C to 85 °C	mm/mm/°C	Report	Report

Note 1: Minimum requirements are listed unless otherwise stated.
Note 2: Unless otherwise stated, requirements are for samples obtained from plaques irrespective of flow direction.

© Copyright 2012 General Motors Company All Rights Reserved

Documents
Document Sharing Hub
Copyright General Motors Company
Provided by IHS Markit under license with General Motors Company
Reproduction, distribution or publication of these standards is expressly prohib
Licensee=/, User=,
Not for Resale,
Full document details: GM GMW16900 2013