



PA66+PPE (Polyamide 66 + Polyphenylene Ether) – 10% Glass Fiber Reinforced, Heat Stabilized

1 Scope

1.1 Material Description. This specification covers the properties of a 10% glass fiber reinforced, heat stabilized PA66+PPE (polyamide 66 + polyphenylene ether) blend which is used in injected form for molded components.

1.2 Symbols. The material abbreviation according to ISO 11469 is >PA66+PPE-GF10<.

1.3 Applicability. Typical applications include the following: wiring harness components, lamp sockets.

1.4 Remarks. Not applicable.

2 References

Note: Only the latest approved standards are applicable unless otherwise specified.

2.1 External Standards/Specifications.

ASTM D6869	ISO 294	ISO 1874-2	ISO 11469
ISO 75-2	ISO 294-3/4	ISO 3146	ISO 15512
ISO 179/1eA	ISO 527	ISO 3451	
ISO 188	ISO 1183	ISO 11357-3	

2.2 GM Standards/Specifications.

GMW3013	GMW3059	GMW3221	GMW14335
---------	---------	---------	----------

2.3 Additional References.

TMC003 Material Safety Data Sheet guidance documents (available at www.gmsupplypower.com).

3 Requirements

Materials approved to this specification shall meet the requirements of GMW3013, **General Requirements for Handling of Technical Terms of Delivery for Plastics.**

3.1 Requirements on Test Specimens. Reference GMW3221.

Unless otherwise specified, injection molding of test specimens shall be accomplished per ISO 294 with the conditions for injection molding from ISO 1874-2. Test methods and specimen dimensions are also to be in accordance with ISO 1874-2.

All values indicated herein are based on material considered to be in the dry-as-molded state with moisture content of 0.2% maximum (ASTM D6869, ISO 15512, Method A or B, or GMW14335). Immediately after molding, per ISO 1874-2, specimens shall be sealed in moisture-proof containers and stored at $22\text{ }^{\circ}\text{C} \pm 3\text{ }^{\circ}\text{C}$ for at least 24 h. All tests shall be performed on unannealed specimens immediately after their removal from the containers in a controlled atmosphere per GMW3221, Code A, unless otherwise specified. In addition, tests specified at temperatures below or above $22\text{ }^{\circ}\text{C} \pm 3\text{ }^{\circ}\text{C}$ shall be conducted at the specified temperature using specimens conditioned at the specified temperature for 4 h minimum.

The values specified in Table 1 shall be met by test specimens in natural, black or in a standard sampled color if natural or black are not available.

3.2 Compound Properties. See Table 1. The following are also required for full standard approval. The minimum number of lots per test required for the following properties is one in natural: Poisson's Ratio, Coefficient of Linear Thermal Expansion (CLTE), Mold Shrinkage, Stress Strain Curve at multiple temperatures (for example $-30\text{ }^{\circ}\text{C}$, $23\text{ }^{\circ}\text{C}$, $85\text{ }^{\circ}\text{C}$). See GMW3013 for all test procedures and parameters.

3.3 Performance Requirements. Performance requirements shall be specified on part drawings or in component specifications. All parts manufactured from molding compounds shall be resistant to the media they contact, such as aliphatic and aromatic hydrocarbons, fuels, lubricants, oils, greases and alcohols, at their places of use.

3.4 Requirements on Delivery. Important physical, mechanical and thermal properties that characterize the material are summarized in Table 1. The color shall be specified on drawings, in material specifications and otherwise.

Table 1: Compound Properties (Natural and Black)

Property	Standard	Unit	Value
Density	ISO 1183	g/cm ³	Target Range 1.13 to 1.22
Ash	ISO 3451 (+950 °C)	% by mass	8 to 12
Moisture Content	ISO 15512, Method A or B or GMW14335	%	≤ 0.2
Tensile Modulus	ISO 527	MPa	3700 to 5100
Tensile Stress at Break	ISO 527	MPa	≥ 74
Tensile Stress at Break after Heat Aging, 1000 h at 140 °C	ISO 527 ISO 188	% Retention	≥ 75
Notched Charpy Impact Strength at +22 °C at -30 °C	ISO 179/1eA	kJ/m ²	≥ 5 ≥ 2
Notched Charpy Impact Strength after Heat Aging, 1000 h at 140 °C, Notch specimens prior to aging	ISO 179/1eA ISO 188	% Retention	≥ 75
Melting Temperature	ISO 3146 or ISO 11357-3	°C	Target Range 250 to 270
Heat Deflection Temperature Under Load, 1.8 MPa	ISO 75-2	°C	≥ 180
Mold Shrinkage (for reference only) after 48 h at 23 °C Parallel to Flow Perpendicular to Flow	ISO 294-3/4	%	Target Range 0.8 to 1.0 0.9 to 1.1

4 Manufacturing Process

Not applicable.