GM	WORLDWIDE ENGINEERING STANDARDS	Material Specification	GMW18126

Polyamide 66 - Glass Fiber Reinforced, Heat Stabilized, Post-Industrial Recycled or Post-Consumer Recycled

1 Scope

Note: Nothing in this standard supercedes applicable laws and regulations.

Note: In the event of conflict between the English and domestic language, the English language shall take precedence.

1.1 Purpose/Material Description. This standard describes material types of glass fiber reinforced, heat stabilized Post Industrial Recycled (PIR) and Post-Consumer Recycled (PCR) Polyamide 66 (nylon 66) which are used in injected form for molded components.

1.2 Symbols. The material abbreviations according to ISO 11469 are shown in Table 1.

1.3 Applicability. Applicable for a GMW3038 replacement provided the materials pass part validation. Typical applications: Fans and Fan Shroud.

1.4 Remarks. The classification into groups is according to percentage of glass fiber reinforcement and recyclate source:

- Type 1 (T1) = PIR
- Type 2 (T2) = PCR

2 References

Note: Only the latest approved standards are applicable unless otherwise specified.

2.1 External Standards/Specifications.

ISO 75-1	ISO 527-1	ISO 3146	ISO 11357-3
ISO 179-1/1eA	ISO 527-2	ISO 3451-1	ISO 11469
ISO 188	ISO 1183-1	ISO 3451-4	ISO 15512
ISO 294-1	ISO 1183-2	ISO 3795	ISO 16396-2

2.2 GM Standards/Specifications.

GMW3013	GMW3221	GMW14335	GMW16172
GMW3038	GMW3232	GMW14444	GMW16853
GMW3059	GMW3235	GMW14797	
GMW3205	GMW14270	GMW15634	

2.3 Additional References. Not applicable.

3 Requirements

3.1 Requirements on Test Specimens. Materials approved to this specification shall meet the requirements of GMW3013.

Unless otherwise specified, injection molding of test specimens shall be accomplished per ISO 294-1 with the conditions for injection molding from ISO 16396-2. Test methods and specimen dimensions are also to be in accordance with ISO 16396-2.

© Copyright 2021

Documents
Document Sharing Hub

Copyright General Motors
Provided by IHS Markit under license with General Motors

Full document details: GM GMW18126 2021

All values indicated herein are based on material considered to be in the dry-as-molded state with moisture content of 0.2% maximum (ISO 15512 Method A or Method B, or GMW14335). Immediately after molding, per ISO 16396-2, specimens shall be sealed in moisture-proof containers and stored at 23 °C ± 2 °C for at least 24 h. All tests shall be performed on unannealed specimens immediately after their removal from the containers in a controlled atmosphere per GMW3221, Code A, unless otherwise specified. In addition, tests specified at temperatures below or above 23 °C ± 2 °C shall be conducted at the specified temperature using specimens conditioned at the specified temperature for 4 h minimum.

The values specified in Table 1 shall be met by test specimens in natural, black or in a standard sampled color if natural or black are not available. See the Polyamide tab on the Plastics Submission Template and GMW3013 for test details and parameters.

3.2 Requirements on Delivery. Important physical, mechanical and thermal properties that characterize the material are summarized in Table 1. The color shall be black.

3.3 Compound Properties (Black). See Table 1. The following are also required for full approval. The minimum number of lots per test required is one (1) in black unless otherwise specified. See the Polyamide tab on the Plastics Submission Template and GMW3013 for test details and parameters.

- Poisson's Ratio
- Stress/strain data points and curves at the following temperatures:

  -30 °C, +23 °C, +85 °C, +110 °C, +125 °C, +150 °C, Conditioned to +23 °C /50% Relative Humidity (RH)

  Note: See GM Material Property Database (GMMPD) tab on Plastics Submission Template (located in GM SupplyPower) for test details.
- Coefficient of Linear Thermal Expansion (CLTE) data

  Note: See GMMPD tab on Plastics Submission Template (located in GM SupplyPower) for test details.
- Differential Scanning Calorimetry (DSC) curve
- Fourier Transform Infrared (FTIR) spectroscopy curve
- Mold shrinkage

3.4 Initial Source Approval. No shipments shall be made by any supplier until representative initial production samples have been approved by the appropriate Materials Engineering department(s) as meeting the requirements of this specification.

3.5 Performance Requirements. Performance requirements shall be specified on part drawings or in component specifications. All parts manufactured from these materials shall be resistant to the media contacted, such as aliphatic and aromatic hydrocarbons, fuels, lubricants, oils, greases and alcohols, at their place of use.

3.6 Emissions Testing of Interior Materials and Parts. For all Code E designated parts per GMW14444, reference GMW16853 for emissions testing of interior materials and parts.

3.7 Paintability. Plastics used for painted applications are required to meet Paint Performance Requirements for New Plastic Materials per GMW16172. Additionally, painted plastic parts are required to meet Painted Plastic Parts Performance Requirements per GMW14797.

3.8 All materials supplied to this standard must comply with GMW3059, Restricted and Reportable Substances. For raw materials, non-dimensional materials (e.g., fluids, greases) and/or bulk materials that require approval into the GM Materials Approved Source List (GMMASL), an International Material Data System (IMDS) submission must be made by the material supplier as a material Material Data Sheet (mMDS). After the mMDS is approved by the GM IMDS team, the materials supplier is to provide a "Header only report" to the responsible GM Materials Engineer. Further guidance can be found in the GM-specific instructions on the IMDS website.

© Copyright 2021

Documents
Document Sharing Hub

Copyright General Motors
Provided by IHS Markit under license with General Motors

Full document details: GM GMW18126 2021