GM	WORLDWIDE ENGINEERING STANDARDS	Material Specification	GMW17192

Polyamide 66 - Impact Modified, Heat Stabilized, Extrusion Grade

1 Scope

1.1 Material Description. This specification covers the properties of an impact modified, heat stabilized, and extrusion grade polyamide 66.

1.2 Symbols. The material abbreviation according to ISO 11469 is >PA66-I<.

1.3 Applicability. Typical applications include the following: Transmission cable housing.

1.4 Remarks. The specification is classified by level of impact modifiers. Additional impact modifier levels will be added as they become necessary.

2 References

Note: Only the latest approved standards are applicable unless otherwise specified.

2.1 External Standards/Specifications.

ASTM D6869	ISO 188	ISO 1183	ISO 11357-3
ISO 75-2	ISO 294	ISO 1874-2	ISO 11469
ISO 179/1eA	ISO 527	ISO 3146	ISO 15512

2.2 GM Standards/Specifications.

GMW3013	GMW3059	GMW3221	GMW14335

3 Requirements

Materials approved to this specification shall meet the requirements of GMW3013, **General Requirements for Handling of Technical Terms of Delivery for Plastics.**

3.1 Requirements on Test Specimens. Unless otherwise specified, injection molding of test specimens shall be accomplished per ISO 294 with the conditions for injection molding from ISO 1874-2. Test methods and specimen dimensions are also to be in accordance with ISO 1874-2.

All values indicated herein are based on material considered to be in the dry-as-molded state with moisture content of 0.2% maximum (ASTM D6869, ISO 15512, Method A or B, or GMW14335). Immediately after molding, per ISO 1874-2, specimens shall be sealed in moisture-proof containers and stored at 22 °C ± 3 °C for at least 24 h. All tests shall be performed on unannealed specimens immediately after their removal from the containers in a controlled atmosphere per GMW3221, Code A, unless otherwise specified. In addition, tests specified at temperatures below or above 22 °C ± 3 °C shall be conducted at the specified temperature using specimens conditioned at the specified temperature for 4 h minimum.

The values specified in Table 1 shall be met by test specimens in natural, black or in a standard sampled color if natural or black are not available.

3.2 Requirements on Delivery. Important physical, mechanical and thermal properties that characterize the material are summarized in Table 1. The color shall be specified on drawings, in material specifications and otherwise.

3.3 Compound Properties. See Table 1. The following are also required for full standard approval. The minimum number of lots per test required for the following properties is one in natural: Poisson's Ratio, Coefficient of Linear Thermal Expansion (CLTE), Mold Shrinkage, Stress Strain Curve at multiple temperatures (for example -30 °C, 23 °C, 110 °C). See GMW3013 for all test procedures and parameters.

3.4 Performance Requirements. Performance requirements shall be specified on part drawings or in component specifications. All parts manufactured from molding compounds shall be resistant to the media they

© Copyright 2015 General Motors Company All Rights Reserved

Documents
Document Sharing Hub
Copyright General Motors Company
Provided by IHS Markit under license with General Motors Company
Reproduction, distribution or publication of these standards is expressly prohib
Licensee=/, User=,
Not for Resale,
Full document details: GMW GMW17192 2015

contact, such as aliphatic and aromatic hydrocarbons, fuels, lubricants, oils, greases and alcohols, at their places of use.

Table 1: Compound Properties (Natural and Black)

Property	Standard	Unit	Value
Density	ISO 1183	g/cm^3	Target Range 1.03 to 1.09
Moisture Content	ISO 15512, Method A or B or GMW14335	%	≤0.2
Tensile Modulus	ISO 527	MPa	1600 to 2200
Tensile Stress at Yield	ISO 527	MPa	≥45
Tensile Strain at Yield	ISO 527	%	Report
Tensile Stress at Break after Heat Aging, 1000 h at 140 °C	ISO 527 ISO 188	% Retention	≥75
Notched Charpy Impact Strength at +22 °C at -30 °C	ISO 179/1eA	kJ/m^2	≥45 ≥11
Notched Charpy Impact Strength after Heat Aging, 1000 h at 140 °C, Notch Specimens Prior to Aging	ISO 179/1eA ISO 188	% Retention	≥75
Melting Temperature	ISO 3146 or ISO 11357-3	°C	Target Range 258 to 264
Heat Deflection Temperature Under Load, 1.8 MPa	ISO 75-2	°C	≥40

4 Manufacturing Process

Not applicable.

5 Rules and Regulations

5.1 Legal Regulations. All materials must satisfy applicable laws, rules, regulations and recommendations valid in the country of usage.

5.2 Language. In the event of conflict between the English and domestic language, the English language shall take precedence.

5.3 Inspection and Rejection. Samples of components or materials released to a GM material specification shall be tested for conformity with the requirements of this material specification and approved by the responsible Engineering department prior to commencement of delivery of bulk supplies.

A new approval must be received for any changes, e.g., properties, manufacturing process, location of manufacture, etc. If not otherwise agreed, all testing and documentation normally required for initial release must be completed.

It is the responsibility of the supplier to inform the customer in a timely manner, without solicitation, and to include documentation of all modifications of materials and/or processes and to apply for a new release.

© Copyright 2015 General Motors Company All Rights Reserved

Documents
Document Sharing Hub

Copyright General Motors Company
Provided by IHS Markit under license with General Motors Company
Reproduction, distribution or publication of these standards is expressly prohib
Licensee=/, User=,
Not for Resale,
Full document details: GMW GMW17192 2015