

**TABLES OF PHYSICAL AND ELECTRICAL
PROPERTIES OF CONDUCTORS USED
ON OVERHEAD LINES**

PUBLICATION P-50-431 ALUMINIUM CONDUCTORS
PUBLICATION P-51-432 COPPER CONDUCTORS
PUBLICATION P-52-469 COPPER COVERED STEEL CONDUCTORS

MAY 1970



INSULATED POWER CABLE ENGINEERS ASSOCIATION

Price \$4.00 per copy

LIST OF TABLES

Table		Page
	P-50-431	
I	Physical Characteristics of Bare ACSR Conductors	2
II	Physical Characteristics of Bare All-Aluminum Conductors	4
III	Electrical Characteristics of Single-Layer ACSR	5
IV	Electrical Characteristics of Multi-Layer ACSR	6
V	Electrical Characteristics of Bare All-Aluminum Conductors	8
VI	Physical Characteristics of Weather-Resistant Aluminum Conductors-Neoprene Covered	9
VII	Physical Characteristics of Weather-Resistant Aluminum Conductors-Polyethylene Covered	10
VIII	Physical Characteristics of Weather-Resistant ACSR	11
IX	Ampacity of Weather-Resistant All-Aluminum Conductors Normally Used in Overhead Lines	12
X	Ampacity of Weather-Resistant ACSR Conductors Normally Used in Overhead Lines	13
	P-51-432	
XI	Physical Characteristics of Bare Copper Conductors Normally Used in Overhead Lines	15
XII	Stress-Strain Characteristics for Calculating Initial Sags and Tensions Hard and Medium Hard Drawn Copper Conductors	16
XIII	Electrical Characteristics of Copper Conductors Used on Overhead Lines	17
XIV	Ampacity of Weather-Resistant Hard Drawn Copper Conductors Normally Used in Overhead Lines	18
	P-52-469	
XV	Physical Characteristics of Bare Copper and Copper Covered Steel Composite Conductors Normally Used in Overhead Lines	20

LIST OF TABLES (cont)

XVI	Resistance of Bare Copper and Copper Covered Steel Composite Conductors Normally Used in Overhead Lines	22
XVII	GMR and Reactance of Bare Copper and Copper Covered Steel Composite Conductors Normally Used in Overhead Lines	24
XVIII	Stress-Strain Characteristics for Calculating Initial Sags and Tensions of Bare Copper and Copper Covered Steel Composite Conductors	26

INSULATED POWER **IPCEA** CABLE ENGINEERS ASSOCIATION
HAND BOOK

May 1970
DATE

P-50-431
P-51-432
P-52-469
NUMBER

FOREWORD

This Project consolidates material which was developed in three separate Projects over several years.

Together they cover the Physical and Electrical Properties of Conductors Used on Overhead Lines.

Because the bases for calculation apply to several tables equally, all notes and applicable formulae are consolidated in a section at the end of the tables, P. 30, et. seq.

TABLE I

PHYSICAL CHARACTERISTICS OF BARE ACSR CONDUCTORS

Code Word	Size of Conductor			Stranding			Outside Diameter Complete Cable In.	Steel Core In.	WEIGHT PER 1000 FEET			ULTIMATE STRENGTH - POUNDS		
	Circular Mils or Avg	Cross Section		Aluminum		Steel			Total lbs	Aluminum		Steel lbs	Type Zinc Coating or Core	
		Square Inches	Total	Aluminum	Steel					Standard Weight	B		C	
														num
Turkey	6	0.0206	0.0240	6 x .0661	1 x .0661	0.198	0.0661	11.6	24.5	11.6	1,170	1,170		
Thrush	5	.0260	.0303	6 x .0743	1 x .0743	.223	.0743	14.6	30.9	14.6	1,460	1,460		
Swan	4	.0328	.0383	6 x .0834	1 x .0834	.250	.0834	18.0	39.0	18.0	1,830	1,830		
Swanate	4	.0328	.0411	7 x .0772	1 x .1029	.257	.1029	28.4	39.0	28.4	2,288	2,245		
Swallow	3	.0413	.0482	6 x .0937	1 x .0937	.281	.0937	23.3	49.2	23.3	2,250	2,220		
Sparrow	2	.0521	.0608	6 x .1052	1 x .1052	.316	.1052	29.3	62.0	29.3	2,790	2,745		
Sparate	2	.0521	.0653	7 x .0974	1 x .1299	.325	.1299	44.7	62.0	44.7	3,525	3,385		
Robin	1	.0657	.0767	6 x .1182	1 x .1182	.355	.1182	37.0	78.2	37.0	3,480	3,430		
Raven	1/0	.0829	.0967	6 x .1327	1 x .1327	.398	.1327	46.6	98.6	46.6	4,280	4,140		
Quail	2/0	.1045	.1219	6 x .1490	1 x .1490	.447	.1490	58.8	124.3	58.8	5,345	4,910		
Pigeon	3/0	.1318	.1538	6 x .1672	1 x .1672	.502	.1672	74.0	156.8	74.0	6,675	6,020		
Penquin	4/0	.1682	.1939	6 x .1878	1 x .1878	.563	.1878	93.4	197.7	93.4	7,730	7,590		
Waxwing	266,800	.2095	.2211	18 x .1217	1 x .1217	.609	.1217	39.2	250.5	39.2	6,830	6,600		
Partridge	266,800	.2095	.2436	26 x .1013	7 x .0788	.642	.2356	115.6	251.7	115.6	11,250	11,075		
Ostrich	300,000	.2356	.2740	26 x .1074	7 x .0835	.680	.2505	129.8	283.0	129.8	12,650	12,450		
Merlin	336,400	.2642	.2789	18 x .1367	1 x .1367	.684	.1367	49.5	315.8	49.5	8,470	8,330		
Linnet	336,400	.2642	.3072	26 x .1138	7 x .0885	.721	.2655	145.8	317.3	145.8	14,050	13,830		
Ortola	336,400	.2642	.3259	30 x .1059	7 x .1059	.741	.3177	209	318.1	209	17,040	16,430		
Chickadee	397,500	.3122	.3295	18 x .1486	1 x .1486	.743	.1486	58.5	373.2	58.5	9,605	9,520		
Ibis	397,500	.3122	.3630	26 x .1236	7 x .0961	.783	.2883	171.9	375.0	171.9	15,930	15,680		
Lark	397,500	.3122	.3850	30 x .1151	7 x .1151	.806	.3453	246.9	375.9	246.9	19,600	19,240		
Pelican	477,000	.3746	.3984	18 x .1628	1 x .1628	.844	.1628	70.2	447.8	70.2	11,870	11,245		
Flicker	477,000	.3746	.4232	24 x .1410	7 x .0940	.846	.2820	164.5	450.0	164.5	17,200	16,700		
Hawk	477,000	.3746	.4356	26 x .1355	7 x .1054	.858	.3162	206.8	450.0	206.8	19,430	18,820		
Hen	477,000	.3746	.4620	30 x .1261	7 x .1261	.883	.3783	296.3	451.1	296.3	23,300	21,600		
Osprey	556,500	.4371	.4614	18 x .1758	1 x .1758	.879	.1758	81.9	522.4	81.9	13,850	13,120		
Parakeet	556,500	.4371	.4938	24 x .1523	7 x .1015	.944	.3045	191.8	525.0	191.8	19,850	19,270		
Dove	556,500	.4371	.5083	26 x .1463	7 x .1138	.927	.341	241.1	525.0	241.1	22,400	21,700		
Eagle	556,500	.4371	.5391	30 x .1362	7 x .1362	.953	.409	345.7	526.3	345.7	26,200	25,200		
Pearcock	605,000	.4752	.5368	24 x .1588	7 x .1059	.953	.318	208.8	570.7	208.8	21,500	20,950		
Squab	605,000	.4752	.5526	26 x .1525	7 x .1186	.966	.356	261.9	570.7	261.9	24,100	23,400		
Teal	605,000	.4752	.5835	30 x .1420	19 x .0852	.994	.426	367.6	572.1	367.6	30,000	29,500		
Book	636,000	.4955	.5643	24 x .1628	7 x .1085	.977	.326	219.2	600.0	22,600	22,300	22,300		
Grosbeak	636,000	.4995	.5809	26 x .1564	7 x .1216	.990	.365	275.3	600.0	25,000	24,200	23,400		

TABLE I (cont.)

PHYSICAL CHARACTERISTICS OF BARE ACSSR CONDUCTORS

Code Word	Size of Conductors			Stranding	Core	Outside Diameter Complete Cable In.	WEIGHT PER 1000 FEET			ULTIMATE STRENGTH - POUNDS		
	Circular Mils or Avg	Square Inches	Total				Aluminum	Steel	Type	Zinc Coating or Core	C	
												Total
Egret	636,000	0.6134	0.4995	30 x .1456	19 x .0874	1.019	988	601.4	386.8	31,500	31,500	31,000
Flamingo	666,000	.5914	.5235	24 x .1667	7 x .1111	1.000	859	628.8	229.8	23,700	23,400	23,000
Gow	715,500	.6348	.5620	54 x .1151	7 x .1151	1.036	921	675.0	246.4	26,300	25,900	25,600
Starling	715,500	.6535	.5620	26 x .1659	7 x .1290	1.051	985	675.0	309.8	27,100	27,200	26,300
Redwing	715,500	.6901	.5620	30 x .1544	19 x .0926	1.081	1111	676.6	434.2	34,600	34,000	33,300
Drake	795,000	.7261	.6244	26 x .1749	7 x .1366	1.108	1094	750.0	344.3	31,200	30,200	29,200
Mallard	795,000	.7668	.6244	30 x .1628	19 x .0977	1.110	1235	751.8	483.3	38,400	37,700	37,000
Tern	795,000	.6676	.6244	45 x .1329	7 x .0886	1.063	896	750.0	146.0	22,900	22,900	22,700
Condor	795,000	.7053	.6244	54 x .1214	7 x .1214	1.093	1024	750.0	274.1	28,500	27,700	26,900
Crane	874,500	.7759	.6868	54 x .1273	7 x .1273	1.146	1126	825.0	301.4	31,400	30,500	29,600
Canary	900,000	.7985	.7069	54 x .1291	7 x .1291	1.162	1159	849.0	310.0	32,300	31,400	30,500
Rail	954,000	.8011	.7493	45 x .1456	7 x .0971	1.165	1075	900.0	175.0	26,900	26,600	26,400
Cardinal	954,000	.8464	.7493	54 x .1329	7 x .1329	1.196	1229	900.0	328.5	34,200	33,300	32,300
Ortolan	1,033,500	.8117	.8678	45 x .1516	7 x .1011	1.213	1165	975.0	190.0	28,900	28,600	28,300
Curlew	1,033,500	.8117	.9169	54 x .1384	7 x .1384	1.246	1331	975.0	356.3	37,100	36,000	35,000
Bluejay	1,113,000	.9346	.8741	45 x .1573	7 x .1049	1.259	1255	1050	205	30,900	30,600	30,300
Finch	1,113,000	.9819	.8741	54 x .1436	19 x .0862	1.293	1431	1055	376	40,200	40,200	39,700
Bunting	1,192,500	.9367	1.001	45 x .1628	7 x .1085	1.302	1344	1125	219	33,200	32,800	32,500
Grackle	1,192,500	.9366	1.055	54 x .1486	19 x .0892	1.338	1533	1130	403	43,100	43,000	43,000
Bittern	1,272,000	.9990	1.068	45 x .1681	7 x .1121	1.345	1434	1200	234	35,400	35,000	34,700
Pheasant	1,272,000	.9990	1.126	54 x .1535	19 x .0921	1.382	1635	1205.8	429.5	44,800	44,200	43,600
Dipper	1,351,500	1.062	1.135	45 x .1733	7 x .1151	1.386	1523	1275	248	37,600	37,200	36,800
Martin	1,351,500	1.0625	1.196	54 x .1582	19 x .0949	1.424	1737	1281.2	456	47,600	47,000	46,300
Bobolink	1,431,000	1.124	1.202	45 x .1783	7 x .1189	1.427	1613	1350	263	39,800	39,400	39,000
Plover	1,431,000	1.124	1.266	54 x .1628	19 x .0977	1.465	1840	1356.5	483.3	50,400	49,700	49,000
Nuthatch	1,510,500	1.186	1.268	45 x .1832	7 x .1221	1.466	1702	1425	277	41,600	40,700	39,900
Parrot	1,510,500	1.186	1.337	54 x .1673	19 x .1004	1.506	1942	1432	510	53,200	52,500	51,800
Lapwing	1,590,000	1.249	1.335	45 x .1878	7 x .1252	1.502	1792	1500	292	43,800	42,700	41,800
Falcon	1,590,000	1.249	1.407	54 x .1716	19 x .1030	1.545	2044	1507	537	56,000	55,300	54,500
Chukar	1,780,000	1.398	1.512	84 x .1456	19 x .0874	1.602	2074	1687	387	53,600	53,600	53,000
Grouse	80,000	.0628	.0817	8 x .1000	1 x .1670	.367	149.0	75.1	73.9	5,200	4,655	4,550
Petrel	101,800	.0800	.1266	12 x .0921	7 x .0921	.461	254.1	96.1	158.1	9,860	9,615	9,385
Minorca	110,800	.0878	.1378	12 x .0961	7 x .0961	.481	276.6	104.5	172.1	10,730	10,470	10,220
Leghorn	134,600	.1057	.1674	12 x .1059	7 x .1059	.530	336.0	127.0	209.0	12,920	12,620	12,310
Quinea	159,000	.1249	.1977	12 x .1151	7 x .1151	.576	396.8	150.0	246.8	15,200	14,850	14,470
Dottrel	176,900	.1389	.2200	12 x .1214	7 x .1214	.607	441.4	166.9	274.5	16,440	15,640	14,830
Dorking	190,800	.1499	.2373	12 x .1261	7 x .1261	.631	476.3	180.0	296.3	17,730	16,860	16,000
Cochin	211,300	.1660	.2628	12 x .1327	7 x .1327	.663	527.5	199.3	328.2	19,640	18,700	17,700
Brahma	203,200	.1596	.3020	16 x .1127	19 x .0977	.714	676.8	191.7	485.1	27,500	26,800	26,100

TABLE II

PHYSICAL CHARACTERISTICS OF BARE ALL-ALUMINUM CONDUCTORS

Code Word	Conductor Size Mils or Avg	Stranding Class	Total Number of Wires	Wire Diameter Inch	Cable Diameter Inch	Gross Sectional Area Square Inch	Weight per 1000 Ft. lbs	Ultimate Strength Hard Drawn lbs
Peachbell	6	A	7	0.0612	0.184	0.0206	24.6	528
Rose	4	A	7	.0772	.232	.0328	39.2	826
Lily	3	A	7	.0867	.260	.0413	49.4	1,023
Iris	2	AA	7	.0974	.292	.0521	62.3	1,266
Pansy	1	AA	7	.1093	.328	.0657	78.6	1,538
Poppy	1/0	AA	7	.1228	.368	.0829	99.1	1,865
Aster	2/0	AA	7	.1379	.414	.1045	124.9	2,350
Phlox	3/0	AA	7	.1548	.464	.1318	157.5	2,845
Oxlip	4/0	AA	7	.1739	.522	.1662	198.6	3,590
Daisy	266,800	AA	7	.1953	.566	.2095	250.5	4,525
Laurel	266,800	A	19	.1185	.593	.2095	250.5	4,810
Tulip	366,400	AA	19	.1331	.666	.2642	315.8	5,940
Canna	397,500	AA	19	.1447	.724	.3122	373.1	6,880
Cosmos	477,000	AA	19	.1585	.793	.3746	447.8	8,090
Syringa	477,000	A	37	.1135	.795	.3746	447.8	8,600
Dahlia	556,500	A	19	.1711	.856	.4371	522	9,440
Mistletoe	556,500	A & AA	37	.1226	.858	.4371	522	9,830
Orchid	636,000	AA	37	.1311	.918	.4995	597	11,240
Violet	715,500	AA	37	.1391	.974	.5620	672	12,640
Nasturtium	715,500	A	61	.1083	.975	.5620	672	13,150
Arbutus	795,000	AA	37	.1466	1.026	.6244	746	13,770
Lilac	795,000	A	61	.1142	1.028	.6244	746	14,330
Anemone	874,500	AA	37	.1538	1.077	.6868	821	14,830
Crocus	874,500	A	61	.1198	1.078	.6868	821	15,760
Magnolia	954,000	AA	37	.1606	1.124	.7493	896	16,180
Goldenrod	954,000	A	61	.1251	1.126	.7493	896	16,860
Bluebell	1,033,500	AA	37	.1672	1.170	.8117	970	17,530
Larkspur	1,033,500	A	61	.1302	1.172	.8117	970	18,260
Marigold	1,113,000	AA	61	.1351	1.216	.8741	1045	19,660
Harthorn	1,192,500	AA	61	.1398	1.258	.9366	1119	21,000
Narcissus	1,272,000	AA	61	.1444	1.300	.9990	1194	22,000
Columbine	1,351,500	AA	61	.1489	1.340	1.062	1269	23,400
Carnation	1,431,000	AA	61	.1532	1.379	1.124	1343	24,300
Gladiolus	1,510,500	AA	61	.1574	1.417	1.186	1418	25,600
Coreopsis	1,590,000	AA	61	.1615	1.454	1.249	1493	27,000
Dogwood	1,590,000	A	91	.1322	1.454	1.249	1493	28,100

TABLE III

ELECTRICAL CHARACTERISTICS - SINGLE LAYER ACSR

Code Word	Size Avg or Nom	STRANDING	RESISTANCE						INDUCTIVE REACTANCE			CAPACITIVE REACTANCE 1 ft Equivalent Spacing-60 cps megohms-miles
			DC (1) 20 C			AC-60 CYCLES (2)			1 ft. Equivalent Spacing			
			ohms/1000'	25 C ohms/mile	50 C ohms/mile	75 C ohms/mile	25 C ohms/mile	50 C ohms/mile	75 C ohms/mile			
Turkey	6	6	1	0.6577	3.459	3.940	4.320	104	0.636	0.728	0.774	0.1423
Swan	4	6	1	.4134	2.176	2.518	2.763	139	.604	.691	.723	.1354
Swanate	4	7	1	.4134	2.154	2.523	2.797	139	.608	.710	.746	.1346
Sparrow	2	6	1	.2601	1.372	1.628	1.783	183	.578	.642	.673	.1284
Sparate	2	7	1	.2601	1.357	1.635	1.799	184	.579	.661	.683	.1276
Robin	1	6	1	.2062	1.089	1.305	1.433	210	.564	.629	.645	.1250
Raven	1/0	6	1	.1634	0.864	1.052	1.153	240	.550	.607	.621	.1216
Quail	2/0	6	1	.1297	.686	.853	.934	275	.536	.590	.601	.1182
Pigeon	3/0	6	1	.1028	.545	.690	.757	316	.520	.572	.579	.1147
Penguin	4/0	6	1	.08155	.434	.569	.617	360	.508	.555	.557	.1113
Grouse	80.0	8	1	.2168	1.120	1.404	1.549	204	.570	.666	.677	.1240
Petrel	101.8	12	7	.1712	.851	1.084	1.261	240	.540	.622	.674	.1172
Minorca	110.8	12	7	.1573	.801	1.024	1.194	249	.535	.612	.664	.1160
Leghorn	134.6	12	7	.1295	.646	.845	.995	285	.525	.598	.641	.1131
Guinea	159.0	12	7	.1096	.547	.731	.865	307	.516	.584	.624	.1106
Dotterel	176.9	12	7	.09851	.493	.667	.791	324	.509	.574	.610	.1091
Dorking	190.8	12	7	.09134	.457	.625	.743	338	.504	.568	.601	.1079
Cochin	211.3	12	7	.08248	.413	.575	.684	363	.498	.561	.590	.1065
Brahma	203.2	16	19	.08576	.412	.553	.691	357	.489	.551	.587	.1043

ELECTRICAL CHARACTERISTICS - MULTILAYER ACSR

Table IV

Code Word	Size Mcm	Stranding Al./St.	Number of Aluminum Layers	RESISTANCE				AMPACITY(3) Amperes	GMR Feet	INDUCTIVE REACTANCE 1 FT. EQUIVALENT SPACING-60 CPS(4) ohms/mile	CAPACITIVE REACTANCE 1 FT. EQUIVALENT SPACING-60 CPS(4) megohm-miles
				AC - 60 CPS (2)							
				DC(1) 20 C ohms/ 1000'	25 C ohms/ Mile	50 C ohms/ Mile	75 C ohms/ Mile				
Waxwing	266.8	18/1	2	0.06500	0.348	0.382	0.416	448	0.0198	0.476	0.1090
Partridge	266.8	26/7	2	0.06532	.344	.378	.412	457	.0217	.465	.1074
Ostrich	300.0	26/7	2	.05809	.306	.336	.366	492	.0229	.458	.1057
Merlin	336.4	18/1	2	.05155	.276	.304	.331	518	.0222	.462	.1055
Linnet	336.4	26/7	2	.05181	.273	.300	.327	528	.0243	.451	.1040
Oriole	336.4	30/7	2	.05193	.271	.297	.324	534	.0255	.445	.1032
Chickadee	397.5	18/1	2	.04363	.234	.257	.280	575	.0241	.452	.1031
Ibis	397.5	26/7	2	.04384	.231	.254	.277	586	.0264	.441	.1015
Lark	397.5	30/7	2	.04395	.229	.252	.275	593	.0277	.435	.1007
Pelican	477.0	18/1	2	.03636	.196	.215	.234	644	.0264	.441	.1004
Flicker	477.0	24/7	2	.03654	.194	.213	.232	654	.0284	.432	.0992
Hawk	477.0	26/7	2	.03654	.193	.212	.231	658	.0289	.430	.0988
Hen	477.0	30/7	2	.03662	.191	.210	.229	665	.0304	.424	.0980
Osprey	556.5	18/1	2	.03116	.168	.185	.202	708	.0284	.432	.0981
Parakeet	556.5	24/7	2	.03132	.167	.183	.200	718	.0306	.423	.0969
Dove	556.5	26/7	2	.03132	.166	.182	.198	725	.0314	.420	.0965
Eagle	556.5	30/7	2	.03139	.164	.180	.197	732	.0327	.415	.0957
Peacock	605.0	24/7	2	.02880	.153	.169	.184	757	.0319	.418	.0957
Squab	605.0	26/7	2	.02880	.153	.168	.183	762	.0327	.415	.0953
Teal	605.0	30/19	2	.02887	.151	.166	.181	772	.0341	.410	.0944
Rook	636.0	24/7	2	.02740	.146	.161	.175	782	.0327	.415	.0950
Grosbeak	636.0	26/7	2	.02740	.145	.160	.174	787	.0335	.412	.0946
Egret	636.0	30/19	2	.02747	.144	.158	.172	797	.0352	.406	.0937
Flamingo	666.6	24/7	2	.02614	.139	.153	.167	805	.0335	.412	.0943
Crow	715.5	54/7	3	.02436	.130	.146	.162	825	.0349	.407	.0932
Starling	715.5	26/7	2	.02436	.130	.142	.155	847	.0355	.405	.0948
Redwing	715.5	30/19	2	.02442	.128	.141	.153	858	.0373	.399	.0920
Drake	795.0	26/7	2	.02192	.117	.128	.140	903	.0373	.399	.0912
Mallard	795.0	30/19	2	.02197	.116	.128	.139	913	.0392	.393	.0904
Tern	795.0	45/7	3	.02192	.119	.132	.146	875	.0352	.406	.0925
Condor	795.0	54/7	3	.02192	.117	.131	.146	881	.0370	.400	.0916
Crane	874.5	54/7	3	.01993	.107	.120	.133	935	.0386	.395	.0902
Canary	900.0	54/7	3	.01936	.104	.117	.130	926	.0392	.393	.0898
Rail	954.0	45/7	3	.01827	.100	.111	.123	953	.0386	.395	.0897
Cardinal	954.0	54/7	3	.01827	.098	.110	.123	960	.0402	.390	.0890

TABLE IV (Cont.)

ELECTRICAL CHARACTERISTICS - MULTILAYER ACSR

Code Word	Size Mcm	Stranding Al./St.	Number of Aluminum Layers	RESISTANCE						AMPACITY(3) amperes	GMR feet	INDUCTIVE REACTANCE 1 FT. EQUIVALENT SPACING-60CPS(4) ohms/mile	CAPACITIVE REACTANCE 1 FT. EQUIVALENT SPACING-60CPS(4) megohm-miles
				AC - 60 CPS (2)									
				DC(1) 20 C ohms/ 1000'	25 C ohms/ Mile	50 C ohms/ Mile	75 C ohms/ Mile						
Ortolan	1033.5	45/7	3	0.01686	0.092	0.103	0.113	1005	0.0402	0.390	0.0885		
Curlew	1033.5	54/7	3	.01686	.091	.102	.114	1010	.0420	.385	.0877		
Bluejay	1113.0	45/7	3	.01566	.086	.096	.106	1051	.0415	.386	.0874		
Finch	1113.0	54/19	3	.01573	.085	.095	.106	1060	.0436	.380	.0866		
Bunting	1192.5	45/7	3	.01461	.081	.089	.099	1099	.0429	.382	.0864		
Grackle	1192.5	54/19	3	.01469	.080	.089	.099	1108	.0451	.376	.0856		
Bittern	1272.0	45/7	3	.01370	.076	.084	.093	1145	.0444	.378	.0855		
Pheasant	1272.0	54/19	3	.01377	.075	.085	.094	1148	.0466	.372	.0847		
Dipper	1351.5	45/7	3	.01290	.072	.080	.088	1188	.0459	.374	.0846		
Martin	1351.5	54/19	3	.01296	.071	.079	.088	1198	.0482	.368	.0838		
Bobolink	1431.0	45/7	3	.01218	.068	.076	.084	1227	.0470	.371	.0837		
Flower	1431.0	54/19	3	.01224	.067	.075	.084	1237	.0494	.365	.0829		
Nuthatch	1510.5	45/7	3	.01154	.065	.072	.080	1268	.0486	.367	.0829		
Parrot	1510.5	54/19	3	.01159	.064	.072	.080	1278	.0506	.362	.0821		
Lapwing	1590.0	45/7	3	.01096	.061	.069	.076	1310	.0498	.364	.0822		
Falcon	1590.0	54/19	3	.01101	.061	.068	.077	1313	.0523	.358	.0814		
Chukar	1780.0	84/19	4	.00984	.056	.061	.066	1434	.0536	.355	.0803		

TABLE V
ELECTRICAL CHARACTERISTICS - BARE ALL-ALUMINUM CONDUCTORS

Code Word	Size Avg or Mcm	Stranding No. Wires	RESISTANCE						CAPACITY (3) amperes	GMR feet	Inductive Reactance 1 Ft. Equivalent Spacing - 60 CPS ohms/mile	Capacitive Reactance 1 Ft. Equivalent Spacing - 60 CPS megohms-mile
			DC (1) 20 C ohms/ 1000'	AC - 60 CPS (2)								
				25 C ohms/ Mile	50 C ohms/ Mile	75 C ohms/ Mile						
Peachbell	6	7	0.6609	3.561	3.912	4.264		103	.00556	0.630	0.1445	
Rose	4	7	.4155	2.239	2.460	2.681		138	.00700	.602	.1376	
Lily	3	7	.3296	1.776	1.951	2.127		159	.00786	.588	.1342	
Iris	2	7	.2613	1.408	1.547	1.687		185	.00882	.574	.1308	
Pansy	1	7	.2072	1.117	1.227	1.337		214	.00990	.560	.1273	
Poppy	1/0	7	.1642	0.885	0.973	1.060		247	.0111	.546	.1239	
Aster	2/0	7	.1303	.689	.772	.841		286	.0125	.532	.1204	
Phlox	3/0	7	.1033	.558	.613	.668		330	.0140	.518	.1171	
Oxlip	4/0	7	.08196	.442	.486	.529		382	.0158	.503	.1136	
Daisy	266.8	7	.06500	.351	.386	.420		442	.0177	.489	.1101	
Laurel	266.8	19	.06500	.351	.386	.420		444	.0187	.483	.1098	
Tulip	336.4	19	.05155	.279	.306	.334		513	.0210	.469	.1063	
Garna	397.5	19	.04363	.237	.259	.283		570	.0230	.458	.1038	
Cosmos	477.0	19	.03636	.197	.217	.236		639	.0249	.448	.1011	
Syringa	477.0	37	.03636	.197	.217	.236		640	.0253	.446	.1011	
Dahlia	556.5	19	.03116	.170	.186	.203		703	.0271	.438	.0989	
Mistletoe	556.5	37	.03116	.170	.186	.203		704	.0275	.436	.0988	
Orchid	636.0	37	.02727	.149	.164	.178		765	.0294	.428	.0968	
Violet	715.5	37	.02424	.133	.146	.158		823	.0311	.421	.0951	
Nasturtium	715.5	61	.02424	.133	.146	.158		824	.0314	.420	.0950	
Arbutus	795.0	37	.02181	.120	.131	.143		874	.0327	.415	.0935	
Lilac	795.0	61	.02181	.120	.131	.143		878	.0330	.414	.0935	
Anemone	874.5	37	.01983	.110	.120	.130		932	.0344	.409	.0921	
Crocus	874.5	61	.01983	.110	.120	.130		932	.0346	.408	.0920	
Magnolia	954.0	37	.01818	.101	.110	.120		982	.0358	.404	.0908	
Goldenrod	954.0	61	.01818	.1012	.1103	.1201		982	.0361	.403	.0907	
Bluebell	1033.5	37	.01678	.0938	.1024	.1111		1031	.0373	.399	.0896	
Larkspur	1033.5	61	.01678	.0938	.1024	.1111		1032	.0376	.398	.0896	
Marigold	1113.0	61	.01558	.0878	.0956	.1036		1079	.0392	.393	.0885	
Hawthorn	1192.5	61	.01454	.0824	.0896	.0971		1125	.0405	.389	.0875	
Narcissus	1272.0	61	.01363	.0775	.0844	.0913		1170	.0419	.385	.0865	
Columbine	1351.5	61	.01283	.0734	.0800	.0865		1212	.0429	.382	.0856	
Carnation	1431.0	61	.01212	.0699	.0759	.0821		1254	.0444	.378	.0847	
Gladiolus	1510.5	61	.01148	.0665	.0724	.0781		1295	.0445	.375	.0839	
Coreopsis	1590.0	61	.01091	.0637	.0691	.0746		1334	.0466	.372	.0832	
Dogwood	1590.0	91	.01091	.0637	.0691	.0746		1334	.0470	.371	.0832	