IEC 60092-350

Edition 5.0 2020-01
REDLINE VERSION

INTERNATIONAL STANDARD

colour inside

Electrical installations in ships –
Part 350: General construction and test methods of power, control and instrumentation cables for shipboard and offshore applications

IEC 60092-350:2020-01 RLV(en)

Documents
Document Sharing Hub

Full document details: IEC 60092-350 2020 RLV

THIS PUBLICATION IS COPYRIGHT PROTECTED
Copyright © 2020 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembé
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC
The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications
The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform
The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,…). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished
Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc
If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

Electropedia - www.electropedia.org
The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary
67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

Documents
Document Sharing Hub

Full document details: IEC 60092-350 2020 RLV

IEC 60092-350

Edition 5.0 2020-01
REDLINE VERSION

INTERNATIONAL STANDARD

colour inside

Electrical installations in ships –
Part 350: General construction and test methods of power, control and instrumentation cables for shipboard and offshore applications

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 29.060.20; 47.020.60

ISBN 978-2-8322-7819-2

Warning! Make sure that you obtained this publication from an authorized distributor.

® Registered trademark of the International Electrotechnical Commission

Documents
Document Sharing Hub

Full document details: IEC 60092-350 2020 RLV

CONTENTS

FOREWORD 7
1 Scope 9
2 Normative references 9
3 Terms and definitions 11
3.31 tests 15
4 Constructional requirements 16
4.1 General requirements 16
4.1.1 General 16
4.1.2 Voltage designation 16
4.1.3 Cable marking 16
4.1.4 Core identification 17
4.1.5 Halogen-free cables 18
4.2 Conductors 18
4.2.1 Material 18
4.2.2 Metal coating and separator 18
4.2.3 Class and form 18
4.2.4 Resistance 19
4.3 Insulation system 19
4.3.1 Material 19
4.3.2 Application 19
4.3.3 Insulation thickness 19
4.4 Screens 20
4.4.1 Conductor and insulation screens for high-voltage cables 20
4.4.2 Screens (shields) for low voltage cables 20
4.5 Cabling 21
4.5.1 Multi-core cables 21
4.5.2 Multi-unit cables 21
4.6 Inner coverings, fillers and binders 21
4.7 Inner sheath 21
4.7.1 Material 21
4.7.2 Application 21
4.7.3 Thickness of inner sheath 22
4.8 Metal braid armour 22
4.8.1 Material 22
4.8.2 Application 22
4.9 Outer sheath 23
4.9.1 Material 23
4.9.2 Application 23
4.9.3 Thickness of outer sheath 23
4.9.4 Calculation of lower and upper limits for the outer dimensions of cables 23
5 Test methods 23
5.1 Test conditions 23
5.1.1 Ambient temperature 23
5.1.2 Frequency, waveform and magnitude of power-frequency test voltages 23
5.2 Routine tests 23
5.2.1 General 23

AVA Documents
Document Sharing Hub

Full document details: IEC 60092-350 2020 RLV

5.2.2 Measurement of the electrical resistance of the conductors 24
5.2.3 Voltage test 24
5.2.4 Partial discharge test 26
6 Sample tests 26
6.1 General 26
6.2 Frequency of sample tests 26
6.3 Repetition of tests 27
6.4 Conductor examination 27
6.5 Measurement of thickness of insulation 27
6.5.1 General 27
6.5.2 Procedure 27
6.5.3 Requirements 27
6.6 Measurements of thickness of non-metallic sheaths 28
6.6.1 General 28
6.6.2 Procedure 28
6.6.3 Requirements 28
6.7 Measurement of external diameter 28
6.8 Hot-set test for insulations and sheaths 28
6.8.1 General procedure 28
6.8.2 Requirements 28
6.9 Insulation resistance test (volume resistivity determination) 28
7 Type tests, electrical 29
7.1 General 29
7.2 Insulation resistance measurement 29
7.2.1 Measurement at ambient temperature 29
7.2.2 Measurement at maximum rated temperature 30
7.3 Increase in AC capacitance after immersion in water 30
7.3.1 General 30
7.3.2 Preparation of test specimens 30
7.3.3 Apparatus 30
7.3.4 Procedure 31
7.3.5 Requirements 31
7.4 High-voltage test for 4 h for cables rated up to 1,8/3 kV 31
7.4.1 General 31
7.4.2 Requirement 31
7.5 Mutual capacitance (control and instrumentation cables only) 31
7.6 Inductance to resistance ratio (control and instrumentation cables only) 31
7.7 High voltage sequence test (cables having a voltage rating higher than 3,6/6 (7,2) kV) 32
7.7.1 General 32
7.7.2 Special provisions 32
7.7.3 Partial discharge test 32
7.7.4 Bending test 32
7.7.5 Tan δ measurement as a function of the voltage 33
7.7.6 Tan δ measurement as a function of the temperature 33
7.7.7 Heating cycle test plus partial discharge test 33
7.7.8 Impulse withstand test, followed by a power-frequency voltage test 33
7.7.9 High-voltage test for 4 h 34
8 Type tests (non-electrical) 34

Documents
Document Sharing Hub
Full document details: IEC 60092-350 2020 RLV

8.1 General 34
8.2 Measurement of thickness of insulation 34
8.3 Measurement of thickness of non-metallic sheaths (excluding inner coverings) 34
8.4 Tests for determining the mechanical properties of insulation before and after ageing 34
8.4.1 Sampling 34
8.4.2 Ageing treatments 34
8.4.3 Conditioning and mechanical tests 34
8.4.4 Requirements 35
8.5 Tests for determining the mechanical properties of sheaths before and after ageing 35
8.5.1 Sampling 35
8.5.2 Ageing treatments 35
8.5.3 Conditioning and mechanical tests 35
8.5.4 Requirements 35
8.6 Additional ageing test on pieces of completed cables (compatibility test) 35
8.6.1 General 35
8.6.2 Sampling 35
8.6.3 Ageing treatment 35
8.6.4 Mechanical tests 35
8.6.5 Requirements 36
8.7 Loss of mass test on PVC ST 2 sheath 36
8.7.1 Procedure 36
8.7.2 Requirements 36
8.8 Test for the behaviour of PVC ST 2 and halogen-free SHF 1 sheaths at high temperature (hot pressure test) 36
8.8.1 Procedure 36
8.8.2 Requirements 36
8.9 Test for the behaviour of PVC sheath ST 2 and halogen-free SHF 1 and SHF 2 sheaths at low temperature 36
8.9.1 Procedure 36
8.9.2 Requirements 36
8.10 Special test for low temperature behaviour (when required) 36
8.11 Test of the metal coating of copper wires 36
8.12 Galvanizing test 37
8.13 Test for resistance of PVC ST 2 and halogen-free SHF 1 sheaths to cracking (heat shock test) 37
8.13.1 Procedure 37
8.13.2 Requirements 37
8.14 Ozone resistance test for insulation and for sheaths 37
8.14.1 Procedure 37
8.14.2 Requirements 37
8.15 Hot oil immersion test and enhanced hot oil immersion test for sheaths 37
8.15.1 Hot oil immersion test 37
8.15.2 Enhanced hot oil immersion test (when required) 37
8.16 Mud drilling fluid test (when required) 37
8.17 Fire tests 37
8.17.1 Flame-spread test on single cables 37
8.17.2 Flame-spread test on bunched cables 38

AVA Documents
Document Sharing Hub

Full document details: IEC 60092-350 2020 RLV

8.17.3 Smoke emission test 38
8.17.4 Acid gas emission test 38
8.17.5 pH and conductivity test 38
8.17.6 Fluorine content test 38
8.17.7 Fire-resistance test (test for circuit integrity cables) 39
8.18 Determination of hardness for HEPR 39
8.19 Determination of elastic modulus for HEPR 39
8.20 Durability of print 39
Annex A (normative) Fictitious calculation method for determination of dimensions of protective coverings 40
A.1 Overview 40
A.2 General 40
A.3 Method 40
A.3.1 Conductors 40
A.3.2 Cores 41
A.3.3 Diameter over laid-up cores 42
A.3.4 Inner coverings 44
A.3.5 Sheath 44
A.3.6 Braid armour 45
Annex B (informative) Recommended minimum spark test voltage levels (according to IEC 62230) 46
B.1 General 46
B.2 Test voltages 46
B.2.1 General 46
B.2.2 Contact electrodes 46
B.2.3 Non-contact electrodes 47
Annex C (normative) Rounding of numbers 48
C.1 Rounding of numbers for the purpose of the fictitious calculation method 48
C.1.1 Rules 48
C.1.2 Illustrations 48
C.2 Rounding of numbers for other purposes 48
Annex D (normative) Calculation of the lower and upper limits for the outer dimensions of cables with circular copper conductors 49
D.1 General 49
D.2 Lower limit for the outer diameter 49
D.3 Upper limit for the outer diameter 49
D.4 Thickness of the mandatory or optional coverings other than the insulation and the sheath(s) 50
Annex E (normative) Cold bend test and impact test for low temperature behaviour 52
E.1 Cold bend test at any specified low temperature 52
E.1.1 Method no. 1 52
E.1.2 Method no. 2 52
E.1.3 Examination and requirements 53
E.2 Impact test at any specified low temperature 53
E.2.1 Apparatus 53
E.2.2 Procedures 53
E.2.3 Requirements 53
Bibliography 54

Documents
Document Sharing Hub
Full document details: IEC 60092-350 2020 RLV

Table 1 – Minimum size of conductors 18
Table 2 – Routine test voltage 25
Table 3 – Number of samples according to cable length 27
Table 4 – Tan δ versus voltage 33
Table 5 – Tan δ versus temperature 33
Table 6 – Impulse withstand voltages 34
Table 7 – Test methods and requirements for halogen-free components 39
Table A.1 – Fictitious diameter of conductor 41
Table A.2 – Increase of diameter for concentric conductors and metallic screens made of tape or wire 41
Table A.3 – Assembly coefficient k for laid-up 43
Table A.4 – Coefficient c_f 44
Table B.1 – Recommended minimum spark-test voltages for cables having rated voltage (U_0) between 150 V and 1 800 V 46
Table D.1 – Lower and upper limits of circular copper conductors for cables for fixed installations 51
Table E.1 – Details of low temperature bending test 52

Documents
Document Sharing Hub
Full document details: IEC 60092-350 2020 RLV

INTERNATIONAL ELECTROTECHNICAL COMMISSION

_____

ELECTRICAL INSTALLATIONS IN SHIPS –

Part 350: General construction and test methods of power, control and instrumentation cables for shipboard and offshore applications

FOREWORD

1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
6) All users should ensure that they have the latest edition of this publication.
7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.

Documents
Document Sharing Hub

Full document details: IEC 60092-350 2020 RLV

International Standard IEC 60092-350 has been prepared by subcommittee 18A: Electric cables for ships and mobile and fixed offshore units, of IEC technical committee 18: Electrical installations of ships and of mobile and fixed offshore units.

This fifth edition cancels and replaces the fourth edition published in 2014 and constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

a) more detailed description of the test procedures in 7.7.6 and 7.7.7;

b) description of the relationship between Annex A and Annex D.

The text of this International Standard is based on the following documents:

CDV	Report on voting
18A/420/FDIS	18A/423/RVC

Full information on the voting for the approval of this document can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

The list of all the parts of the IEC 60092 series, under the general title *Electrical installations in ships*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "http://webstore.iec.ch" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

Documents
Document Sharing Hub

Full document details: IEC 60092-350 2020 RLV

ELECTRICAL INSTALLATIONS IN SHIPS –

Part 350: General construction and test methods of power, control and instrumentation cables for shipboard and offshore applications

1 Scope

This part of IEC 60092 provides the general constructional requirements and test methods for use in the manufacture of electric power, control and instrumentation cables with copper conductors intended for fixed electrical systems at voltages up to and including 18/30(36) kV on board ships and offshore (mobile and fixed) units.

The reference to fixed systems includes those that are subjected to vibration (due to the movement of the ship or installation) or movement (due to motion of the ship or installation) and not to those that are intended for frequent flexing. Cables suitable for frequent or continual flexing use are detailed in other IEC standards, for example IEC 60227 (all parts) and IEC 60245 (all parts), and their uses are restricted to those situations which do not directly involve exposure to a marine environment, for example, portable tools and domestic appliances.

The following types of cables are not included:

– optical fibre;
– sub-sea and umbilical cables;
– data and communication cables;
– coaxial cables.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-461, *International Electrotechnical Vocabulary – Part 461: Electric cables* (available at www.electropedia.org)

~~IEC 60092-353, *Electrical installations in ships – Part 353: Power cables for rated voltages 1 kV and 3 kV*~~

IEC 60092-360:2014, *Electrical installations in ships – Part 360: Insulating and sheathing materials for shipboard and offshore units, power, control, instrumentation~~,~~ and telecommunication ~~and data~~ cables*

IEC 60228, *Conductors of insulated cables*

IEC 60230, *Impulse tests on cables and their accessories*

IEC 60331-1, *Tests for electric cables under fire conditions – Circuit integrity – Part 1: Test method for fire with shock at a temperature of at least 830 °C for cables of rated voltage up to and including 0,6/1,0 kV and with an overall diameter exceeding 20 mm*

AVA Documents
Document Sharing Hub
Full document details: IEC 60092-350 2020 RLV

IEC 60331-2, *Tests for electric cables under fire conditions – Circuit integrity – Part 2: Test method for fire with shock at a temperature of at least 830 °C for cables of rated voltage up to and including 0,6/1,0 kV and with an overall diameter not exceeding 20 mm*

IEC 60331-11, *Tests for electric cables under fire conditions – Circuit integrity – Part 11: Apparatus – Fire alone at a flame temperature of at least 750 °C*

IEC 60331-21, *Tests for electric cables under fire conditions – Circuit integrity – Part 21: Procedures and requirements – Cables of rated voltage up to and including 0,6/1,0 kV*

IEC 60332-1-2, *Tests on electric and optical fibre cables under fire conditions – Part 1-2: Test for vertical flame propagation for a single insulated wire or cable – Procedure for 1 kW pre-mixed flame*

IEC 60332-3-22, *Tests on electric and optical fibre cables under fire conditions – Part 3-22: Test for vertical flame spread of vertically-mounted bunched wires or cables – Category A*

IEC 60684-2, *Flexible insulating sleeving – Part 2: Methods of test*

IEC 60754-1, *Test on gases evolved during combustion of materials from cables – Part 1: Determination of the halogen acid gas content*

IEC 60754-2, *Test on gases evolved during combustion of materials from cables – Part 2: Determination of acidity (by pH measurement) and conductivity*

IEC 60811-201, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 201: General tests – Measurement of insulation thickness*

IEC 60811-202, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 202: General tests – Measurement of thickness of non-metallic sheath*

IEC 60811-203, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 203: General tests – Measurement of overall dimensions*

IEC 60811-401, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 401: Miscellaneous tests – Thermal ageing methods – Ageing in an air oven*

IEC 60811-403, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 403: Miscellaneous tests – Ozone resistance test on cross-linked compounds*

IEC 60811-404, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 404: Miscellaneous tests – Mineral oil immersion tests for sheaths*

IEC 60811-409, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 409: Miscellaneous tests – Loss of mass test for thermoplastic insulations and sheaths*

IEC 60811-501, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 501: Mechanical tests – Tests for determining the mechanical properties of insulating and sheathing compounds*

IEC 60811-504, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 505: Mechanical tests – Bending tests at low temperature for insulations and sheaths*

IEC 60811-505, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 505: Mechanical tests – Elongation at low temperature for insulations and sheaths*

Documents
Document Sharing Hub
Full document details: IEC 60092-350 2020 RLV

IEC 60811-506, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 505: Mechanical tests – Impact test at low temperature for insulations and sheaths*

IEC 60811-507, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 507: Mechanical tests – Hot set test for cross-linked materials*

IEC 60811-508, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 508: Mechanical tests – Pressure test at high temperature for insulation and sheaths*

IEC 60811-509, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 509: Mechanical tests – Test for resistance of insulations and sheaths to cracking (heat shock test)*

~~IEC 60885-2, *Electrical test methods for electric cables. Part 2: partial discharge tests*~~

IEC 60885-3, *Electrical test methods for electric cables – Part 3: Test methods for partial discharge measurements on lengths of extruded power cables*

IEC 61034-1, *Measurement of smoke density of cables burning under defined conditions – Part 1: Test apparatus*

IEC 61034-2, *Measurement of smoke density of cables burning under defined conditions – Part 2: Test procedure and requirements*

ISO 7989-2:2007, *Steel wire and wire products – Non-ferrous metallic coatings on steel wire – Part 2: Zinc or zinc-alloy coating*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60050-461 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at http://www.electropedia.org/
- ISO Online browsing platform: available at http://www.iso.org/obp

3.1
approximate value
value which is neither guaranteed nor checked

Note 1 to entry: It is used, for example, for the calculation of other dimensional values.

3.2
braid
covering formed from braided metallic or non-metallic material

[SOURCE: IEC 60050-461:2008, 461-05-10~~, modified ("plaited" replaced by "braided")~~]

3.3
braid armour
covering formed from braided metal wires used to protect a cable from external mechanical effects

Note 1 to entry: Where the rules of the applicable national, regulatory or approval body permit the practice, it is also possible to use the braid armour as an earth conductor.

AVA Documents Document Sharing Hub

Full document details: IEC 60092-350 2020 RLV

Note 2 to entry: Copper-wire braid armour may also provide a limited function of an electrostatic collective screen, provided it is effectively earthed.

3.4
compatibility test
test intended to check that the insulation and sheath are not liable to deteriorate in operation due to contact either with each other or with other components in the cable

3.5
conductor
<of a cable> part of a cable which has the specific function of carrying current

[SOURCE: IEC 60050-461:2008, 461-01-01]

3.6
conductor screen
non-metallic conducting layer applied between the conductor and insulation to equalise the electrical stress between these components

Note 1 to entry: It may also provide smooth surfaces at the boundaries of the insulation and assist in the elimination of spaces at these boundaries

3.7
core-insulated conductor, US
assembly comprising a conductor and its own insulation (and screens, if any)

Note 1 to entry: In North American usage, the core of a cable has been defined as the assembly of components of a cable lying under a common covering such as the sheath (jacket).

3.8
drain wire
un-insulated wire laid in contact with an electrical screen or an electrical shield which has the specific function of earthing an electrostatic screen by ensuring a low resistive path throughout the length of the cable

~~[SOURCE: IEC 60050-461:2008, 461-03-07, modified (addition of text from "... which has ...")]~~

3.9
electrostatic screen
electrostatic shield, US
earthed metallic layer surrounding a cable which confines the electric field generated by the cable within the cable cores, pair(s), triples(s) or quad(s), and/or protects the core(s), pair(s), triple(s) or quad(s) from external influence

Note 1 to entry: Metallic sheaths, foils, braids, armours and earthed concentric conductors may also serve as an electrostatic screen, provided they are effectively grounded or earthed.

3.10
fictitious value
value calculated according to the "fictitious method" described in Annex A

~~[SOURCE: IEC 60502-2:2005, definition 3.1.4]~~

3.11
filler
material used to fill the interstices between the cores of a multi-conductor cable

[SOURCE: IEC 60050-461:2008, 461-04-05]

Documents
Document Sharing Hub
Full document details: IEC 60092-350 2020 RLV

3.12
fire resistance
circuit integrity
ability of an electric cable to continue to operate in ~~the~~ a designated manner whilst subjected to a specified flame source for a specified period of time under specified conditions

~~[SOURCE: IEC 60331-11:2009, definition 3.1, modified (addition of "fire resistance")]~~

3.13
flexible cable
cable which is required to be capable of being flexed while in service and of which the structure and materials are such as to fulfil this requirement

[SOURCE: IEC 60050-461:2008, 461-06-14]

3.14
individually screened cable
radial field cable
cable in which each core is covered with an individual screen

[SOURCE: IEC 60050-461:2008, 461-06-12]

3.15
inner covering
non-metallic covering which surrounds the core or the assembly of the cores or the cabling elements (and fillers, if any) of a multi-conductor cable and over which further layers are applied and which has no mechanical or electrical functions

Note 1 to entry: The inner covering can be either extruded or taped, and in either case forms a continuous layer, which has only an approximate value of thickness and no defined mechanical requirements.

Note 2 to entry: Taped inner coverings are also sometimes called "lapped beddings".

~~[SOURCE: IEC 60050-461:2008, 461-05-02, modified (addition of "further layers ..." and Notes 1 and 2 to entry)]~~

3.16
inner sheath
inner jacket, US
non-metallic sheath generally applied under a metallic sheath, reinforcement or armour ~~It should be extruded~~

Note 1 to entry: The inner sheath shall have the following properties:

– it shall be extruded;
– it may be used to fill the interstices;
– it shall be of a material listed in IEC 60092-360;
– it shall have a defined nominal thickness (value).

[SOURCE: IEC 60050-461:2008, 461-05-13, modified – The note to entry has been added.]

3.17
insulated cable
assembly consisting of

– one or more cores;
– their individual covering(s) (if any);
– assembly protection (if any);
– protective covering(s) (if any).

AVA Documents Document Sharing Hub

Full document details: IEC 60092-350 2020 RLV

Note 1 to entry: Additional un-insulated conductor(s) may be included in the cable.

Note 2 to entry: The assembly protection may consist of fillers, binders or inner coverings.

Note 3 to entry: The protective covering(s) consists of one or more "constituent elements" such as a metallic braid, wire or a metallic screen, thermosetting or thermoplastic sheaths, (impregnated) fibrous braid or woven tape, bedding for metal armour or paint for metal armour.

[SOURCE: IEC 60050-461:2008, 461-06-01, modified ~~(addition of~~ – Notes 2 and 3 to entry~~)~~ have been added.]

3.18
insulation screen
core screen
electrical screen of non-metallic semi-conducting layer in combination with a metallic layer

~~[SOURCE: IEC 60050-461:2008, 461-03-03, modified definition]~~

3.19
length of lay
axial length of one complete turn of the helix formed by one cable component in a twisted construction

[SOURCE: IEC 60050-461:2008, 461-04-01, modified ~~(addition of~~ – The words "in a twisted construction~~)~~" have been added.]

3.20
median value
middle value, when several results have been obtained and ordered in increasing (or decreasing) succession, if the number of available values is odd, and the mean of the two middle values if the number is even

~~[SOURCE: IEC 60502-2:2005, 3.1.3]~~

3.21
multi-unit cable
cable consisting of more than one pair, triple or quad unit either unscreened or with an individual electrostatic screen around each unit or having an electrostatic screen applied around the assembly of units (a collective screen) in a twisted construction

3.22
nominal value
value by which quantity is designated, and which is often used in tables

Note 1 to entry: Usually, in this document, nominal values refer to values which are to be checked by measurements, taking into account specified tolerances.

3.23
oversheath
outer sheath
protective overall jacket, US
protective jacket
non metallic sheath applied over a covering, generally metallic, ensuring the protection of the cable from the outside

Note 1 to entry: The outer sheath shall have the following properties:

– it shall be extruded;
– it may be used to fill the interstices;
– it shall be of a material listed in IEC 60092-360;
– it shall have a defined nominal thickness (value).

AVA Documents Document Sharing Hub

Full document details: IEC 60092-350 2020 RLV

Note 2 to entry: In North-America, the term sheath is generally used for metallic coverings, whereas the term jacket is used only for non-metallic coverings.

[SOURCE: IEC 60050-461:2008, 461-05-04, modified – Note 2 to entry has been replaced by a new note.]

3.24
pair unit
two cores laid up with or without interstitial fillers or binder tape(s)

3.25
quad unit
four cores laid up with or without interstitial fillers or binder tape(s)

3.26
separator
thin layer used as a barrier to prevent mutually detrimental effects between different components of a cable, such as between the conductor and insulation or between insulation and sheath

[SOURCE: IEC 60050-461:2008, 461-05-01]

3.27
single unit cable
cable consisting of either one pair, triple or quad unit, either unscreened or with an individual electrostatic screen

3.28
stranded conductor
conductor consisting of a number of individual wires all or some of which generally have a helical form

Note 1 to entry: The cross section of a stranded conductor may be circular or otherwise shaped.

Note 2 to entry: The term "strand" is also used to designate a single wire.

[SOURCE: IEC 60050-461:2008, 461-01-07, modified – The words "or strands" have been deleted from the definition.]

3.29
SZ cabling
method of cabling in which the direction of lay of the cable components is periodically reversed

[SOURCE: IEC 60050-461:2008, 461-04-07]

3.30
triple unit
three cores laid up with or without interstitial fillers or binder(s)

3.31 tests

3.31.1
routine test
test made by the manufacturer on each manufactured length of cable to check that each length meets the specified requirements

~~[SOURCE: IEC 60502-2, definition 3.2.1]~~

AVA Documents
Document Sharing Hub

Full document details: IEC 60092-350 2020 RLV

3.31.2
sample test
test made by the manufacturer on samples of completed cable or components taken from a completed cable, at a specified frequency, so as to verify that the finished product meets the specified requirements

~~[SOURCE: IEC 60502-2, definition 3.2.2]~~

3.31.3
type test
test made before supplying, on a general commercial basis, a type of cable covered by this document, in order to demonstrate satisfactory performance characteristics to meet the intended application

Note 1 to entry: These tests are of such a nature that, after they have been made, they need not be repeated unless changes are made in the cable materials or design or manufacturing process which might change the performance characteristics.

~~[SOURCE: IEC 60502-2, definition 3.2.3]~~

4 Constructional requirements

4.1 General requirements

4.1.1 General

The construction of the cable is given in the applicable product standard.

4.1.2 Voltage designation

The standard method of designating the rated voltages of cables covered by this document shall take the form

$$U_0/U\ (U_m)$$

where

U_0 is the rated power-frequency voltage between phase conductor and earth or metallic screen, for which the cable is designed;

U is the rated power-frequency voltage between phase conductors for which the cable is designed;

U_m is the maximum value of the "highest system voltage" for which the equipment may be used.

All voltages are given as RMS values.

4.1.3 Cable marking

4.1.3.1 Indication of origin

Cables shall be provided with a continuous indication of origin (manufacturer's name and/or trade mark) by one or more of the following methods:

a) printing, indenting or embossing on the outer sheath;

b) a printed tape within the cable;

c) the inclusion of identification threads within the cable;

d) printing on the insulation of at least one core.

Documents
Document Sharing Hub
Full document details: IEC 60092-350 2020 RLV

The marking shall be legible.

Spacing and dimensions of the indication of origin shall be as given in the applicable product standard.

Conformity shall be checked by visual examination, and the durability of the print, where applicable, shall be in accordance with the test given in 8.20.

NOTE National or regulatory authorities or approval bodies might request the method of marking according to their applicable rules.

4.1.3.2 Rated voltage and cable construction

When specified in the applicable product standard, the rated voltage (U_0/U) and the construction (number of cores and cross-sectional area of the conductors) shall be printed, indented or embossed on the outer sheath.

The marking shall be legible.

Spacing and dimensions shall be as given in the applicable product standard.

Conformity shall be checked by visual examination, and the durability of the print where applicable shall be in accordance with the test as given in 8.20.

4.1.3.3 Optional cable designation/external markings

When agreed between the manufacturer and purchaser, cables may, in addition, be marked with a code designation that signifies the type of insulation/screening/armouring and sheathing materials used in their construction.

The marking shall be by embossing, indenting or printing on the outer sheath.

The marking shall be legible.

Spacing and dimensions shall be as given in the applicable product standard.

Conformity shall be checked by visual examination, and the durability of the print where applicable shall be in accordance with the test as given in 8.20.

4.1.4 Core identification

All cores shall be clearly identified.

The cores of multi-core cables or cores within pair, triple or quad unit(s) shall be identified by colour or numbering as given in the applicable product standard.

The colour or numbering shall be clearly identifiable and durable.

Spacing and dimensions of any numbering shall be as given in the applicable product standard.

Conformity shall be checked by visual examination, and the durability of the print where applicable shall be in accordance with the test as given in 8.20.

AVA Documents
Document Sharing Hub

Full document details: IEC 60092-350 2020 RLV

4.1.5 Halogen-free cables

For halogen-free cables, the non-metallic components shall meet the requirements given in Table 7.

4.2 Conductors

4.2.1 Material

The conductors shall consist of plain or metal-coated annealed copper.

4.2.2 Metal coating and separator

The component copper wires shall be metal-coated when used for conductors having a cross-linked insulation, unless a separator between the conductor and the insulation is provided, or suitable compatibility type tests are carried out to demonstrate that no harmful effects occur with uncoated copper wires. The metal coating shall be considered as satisfactory if, on visual inspection, the wire surface appears smooth, uniform and bright, and the insulation does not adhere to the conductor.

If a compatibility test is required, it shall be carried out using the method and requirements specified in 8.6.

4.2.3 Class and form

The conductors considered in this document are intended only for fixed installations and shall comply with class 2 or class 5 of IEC 60228. The minimum nominal conductor size depends on the voltage rating of the cable and shall be in accordance with Table 1.

Stranded copper class 2 conductors are recommended for general fixed-installation systems.

To aid installation, a conductor of class 5 may be used. Cables using class 5 conductors should not be regarded as suitable for repeated flexing in service.

Stranded circular non-compacted or compacted conductors are permitted for all cross-sections. Sector-shaped conductors are permitted for cross-sections of 10 mm^2 and above.

Table 1 – Minimum size of conductors

U	Nominal cross-sectional area (minimum) mm^2
250 V	0,5
1 000 V	1,0
3 kV	10
6 kV	10
10 kV	16
15 kV	25
20 kV	35
30 kV	50

The nominal size of the conductors shall be limited to 630 mm^2 in accordance with the values specified in IEC 60228.

AVA Documents
Document Sharing Hub
Full document details: IEC 60092-350 2020 RLV

All conductors shall have a regular shape and shall be free from sharp projections and other defects liable to damage the insulation.

4.2.4 Resistance

Unless specified in the applicable standard, the DC resistance of the conductors shall not exceed the applicable maximum value given in IEC 60228.

The DC resistance of conductors used in multi-unit (pairs, triples or quads) cables shall not exceed the maximum value given in the applicable product standard.

The DC resistance of drain wires shall not exceed the maximum value given in the applicable product standard.

Braids, including an optional earth lead underneath and in continuous contact with the braid, and armours, when used as earthing conductors, should have a value of conductance at least equal to that of the value for phase conductors for cross-sections up to and including 16 mm^2 and 50 % of the value for phase conductors with cross-sections greater than 16 mm^2.

The use of braids or armours as earthing conductors may not be permitted in some countries or by some approval authorities.

4.3 Insulation system

4.3.1 Material

The insulation system shall consist of at least one of the following:

a) one of the insulation compounds listed in IEC 60092-360;

b) a combination of two or more layer(s) of the insulation compounds listed in IEC 60092-360 that complies with the full requirements of one type;

c) a combination of one or more layers of inorganic tape(s), and one or more layer(s) of the insulation compounds listed in IEC 60092-360 that complies with the full requirements of one type.

4.3.2 Application

The insulation shall be extruded in one or more closely adherent layers. The insulation system shall form a compact and homogeneous body and shall be so applied that it fits closely onto the conductor or tape(s), if any.

It shall be possible to remove the insulation without damaging the conductor or the metal coating, if any.

Compliance shall be checked by visual inspection.

4.3.3 Insulation thickness

The thickness of insulation is specified for each size and type of cable in the applicable product standard.

For single core or multi-core cables, the thickness at any point may be less than the specified value, provided the difference does not exceed 0,1 mm + 10 % of the specified value.

For single-unit or multi-unit cables, the thickness at any point may be less than the specified value, provided the difference does not exceed 0,1 mm + 20 % of the specified value.

AVA Documents
Document Sharing Hub
Full document details: IEC 60092-350 2020 RLV

The thickness of any separator, screen or inorganic tape(s) applied over the conductor or over the insulation shall not be included in the thickness of insulation.

4.4 Screens

4.4.1 Conductor and insulation screens for high-voltage cables

4.4.1.1 Conductor screen

The conductor screen shall consist of an extruded semi-conducting compound which may be applied over a semi-conducting tape.

The extruded semi-conducting compound shall be firmly bonded to the insulation.

4.4.1.2 Insulation screen

The insulation screen shall consist of a non-metallic semi-conducting layer in combination with a metallic layer. The non-metallic layer shall be extruded directly upon the insulation of each core and consist of either a bonded or strippable semi-conducting compound.

A layer of semi-conducting tape or compound may then be applied over the individual cores or core assembly.

The metallic layer shall be applied over the individual cores.

The metallic layer shall consist of one or more tapes, or a braid, or a concentric layer of wires, or a combination of tape(s) and wires.

The dimensional, physical and electrical requirements of the metallic layer shall be determined taking into account any other requirements (for example, national or approval authority regulations and standards), including the value of current to be carried in the case of fault.

4.4.2 Screens (shields) for low voltage cables

4.4.2.1 Construction

The screen shall consist of one of the following:

a) a metal/polyester laminated electrostatic screening tape applied with the metallic side in contact with a drain wire or a metallic screening tape with an appropriate overlap;

   The metal/polyester tape shall be either aluminium-bonded to polyester or copper-bonded to polyester. The thickness of the tape is specified in the applicable product standard. The metal/polyester tape shall be in contact with a drain wire which shall be composed of metal-coated annealed copper wires in the case of aluminium laminate tape and either plain or tinned annealed copper wires in the case of copper laminate tape. The maximum resistance of the drain wire is specified in the applicable product standard.

b) the metallic screening tape shall be a plain or metal-coated tape (the thickness of the tape is specified in the applicable product standard); or

c) a plain copper or metal-coated copper braid with a drain wire if necessary applied in accordance with the formula given in 4.8.2; or

d) a combination of a) and c) or b) and c) above. Using this option, the drain wire may be omitted.

4.4.2.2 Application

The screen may be applied either over a single unit as an individual screen or over a formation of multi-cores or multi-units as a collective screen.

Documents
Document Sharing Hub
Full document details: IEC 60092-350 2020 RLV

~~NOTE~~ The electrostatic screens may also serve as an electromagnetic screen, in which case the requirements need to be verified with the customer.

In multi-unit cables, the individual electrostatic screens shall be electrically isolated both from each other and the collective screen, if any.

4.5 Cabling

4.5.1 Multi-core cables

The individual cores shall be twisted together in concentric layers with either a right- or left-hand lay. The use of reversed lay (SZ formations) is permitted. When necessary, filler(s) or extruded layers as detailed in 4.6 may be used to obtain a circular cable.

A non-hygroscopic binder tape or tapes may be applied over each layer.

4.5.2 Multi-unit cables

The formation of the individual units and then the assembly of the units shall be in accordance with the applicable product standard.

4.6 Inner coverings, fillers and binders

The inner covering, if any, may be extruded or lapped, as specified in the relevant standard of the cable. The inner covering shall be extruded in case of a braid armour of galvanized steel wires.

It shall be possible to remove the inner covering without damaging the underlying components.

Taped inner coverings shall be applied in one or more overlapping layers.

An open helix of suitable tape is permitted as a binder before application of an extruded inner covering. The thickness of the binder tape is optional.

The inner covering, fillers and binders, if any, shall be of non-hygroscopic material. The material selected shall be compatible with cable components with which it is in contact and compatible with the operating temperature of the cable.

NOTE In hazardous locations, inner coverings used instead of an inner sheath will not prevent the migration of combustible gas or dust particles through the cable. This is normally prevented by hazardous location rated cable glands dependent upon an impervious inner sheath on which to effect a seal.

4.7 Inner sheath

4.7.1 Material

The inner sheath material shall be selected from one of those listed in IEC 60092-360. The sheathing compound selected shall be compatible with the cable components with which it is in contact and compatible with the operating temperature of the cable.

4.7.2 Application

The inner sheath shall be extruded in one or more closely adherent layers. The inner sheath shall form a compact and homogeneous body and shall be so applied that it fits closely onto the underlying components.

It shall be possible to remove the inner sheath without damaging the underlying insulation and/or screen(s).

Documents
Document Sharing Hub
Full document details: IEC 60092-350 2020 RLV

4.7.3 Thickness of inner sheath

The thickness of the inner sheath for each size and type of cable shall be as specified in the applicable product standard.

Unless specified in the applicable product standard, the thickness at any point may be less than the specified value, providing the difference does not exceed 0,1 mm + 15 % of the specified value for sheaths applied on a smooth cylindrical surface, or 0,2 mm + 20 % of the specified value for sheaths applied on an irregular cylindrical surface.

The thickness of any tape(s) under or over the inner sheath shall not be included in the measurement of the thickness of the inner sheath.

4.8 Metal braid armour

4.8.1 Material

The metal braid armour shall be made of zinc-coated (galvanized) steel wires complying with the galvanizing test specified in 8.12 and ISO 7989-2, or copper, metal-coated copper or copper-alloy wires.

~~For high voltage cables described in IEC 60092-354, the use of double steel tape armour and round or flat steel wire armour are permitted. For further guidance on construction, see IEC 60502-2.~~

4.8.2 Application

The "coverage density" of the braid shall be such that the weight of the braid is at least 90 % of the weight of a tube of the same metal, having an internal diameter equal to the calculated internal diameter under the braid and a thickness equal to the nominal diameter of the wires forming the braid.

The diameter under the braid is calculated with the fictitious method given in Annex A.

NOTE An alternative method for evaluating the "coverage density" of symmetrical braids is given by the following formula giving the "filling factor", F:

$$F = \frac{NPd}{\sin\alpha}, \text{ or}$$

$$(mnd/2\pi D)\ (1 + \pi^2 D^2/L^2)^{1/2}$$

where

α is the slope angle between the cable axis and the braid wires;

d is the diameter of braid wire;

N is the number of wires per carrier;

P is the number of picks per millimetre;

m is the total number of spindles;

n is the total number of ends per spindle;

D is the mean diameter of the braid;

L is the lay length of the braiding wire.

The corresponding "coverage density", expressed as a percentage, is given by the formula:

$$G = \frac{\pi}{2} \times F \times 100$$

Documents
Document Sharing Hub
Full document details: IEC 60092-350 2020 RLV

The coverage density G of 90 % is reached for a value of filling factor F of 0,573.

4.9 Outer sheath

4.9.1 Material

The sheath shall be selected from one of those listed in IEC 60092-360. The sheathing compound selected shall be compatible with the cable components with which it is in contact and compatible with the operating temperature of the cable.

4.9.2 Application

The outer sheath shall be extruded in one or more closely adherent layers. The outer sheath shall form a compact and homogeneous body and shall be so applied that it fits closely onto the underlying components.

It shall be possible to remove the outer sheath without damaging the underlying insulation and/or screen(s).

4.9.3 Thickness of outer sheath

The thickness of sheath for each size and type of cable shall be as specified in the applicable product standard.

Unless specified in the applicable product standard, the thickness at any point may be less than the specified value, if any, providing the difference does not exceed 0,1 mm + 15 % of the specified value for sheaths applied on a smooth cylindrical surface, or 0,2 mm + 20 % of the specified value for sheaths applied on an irregular cylindrical surface.

4.9.4 Calculation of lower and upper limits for the outer dimensions of cables

The calculation of lower and upper limits for the outer dimensions of cables with circular copper conductors are given in Annex D.

5 Test methods

5.1 Test conditions

5.1.1 Ambient temperature

Unless otherwise specified in the details for the particular test, tests shall be made at an ambient temperature of (20 ± 15) °C.

5.1.2 Frequency, waveform and magnitude of power-frequency test voltages

The frequency of the alternating test voltages shall be in the range 49 Hz to 61 Hz. The waveform shall be substantially sinusoidal. The power-frequency test voltages given in this document are RMS values.

5.2 Routine tests

5.2.1 General

The routine tests required by this document are:

a) measurement of the electrical resistance of conductors (see 5.2.2);

b) voltage test (see 5.2.3);

c) partial discharge test for rated voltages 6 kV up to 30 kV (see 5.2.4).

Documents
Document Sharing Hub
Full document details: IEC 60092-350 2020 RLV

The routine tests are normally carried out on each manufactured cable length and may be carried out, at the manufacturer's option, either on delivery lengths or on manufactured lengths before they are cut into delivery lengths.

5.2.2 Measurement of the electrical resistance of the conductors

Resistance measurements shall be made on all conductors of each cable length submitted to the routine test.

The completed cable length, or a sample from it, shall be placed in the test room, which shall be maintained at a reasonably constant temperature for at least 12 h before the test. In the case of doubt as to whether the conductor temperature is the same as the room temperature, the resistance shall be measured after the cable has been in the test room for 24 h. As an alternative, the resistance shall be measured on a sample of conductor conditioned for at least 1 h in a temperature-controlled liquid bath.

The measured value of resistance shall be corrected to a temperature of 20 °C and a length of 1 km in accordance with the formulae and factors given in IEC 60228.

Unless otherwise stated in the applicable product standard, the DC resistance of each conductor at 20 °C shall not exceed the appropriate maximum value specified for the applicable class of conductor in IEC 60228.

5.2.3 Voltage test

5.2.3.1 General

The voltage test shall be made at ambient temperature using, at the manufacturer's option, alternating voltage at power frequency, direct voltage or, where applicable, spark testing (high-frequency or other forms of voltage).

5.2.3.2 Single-core cable without metallic layer

If the single-core cable has no metallic layer, the cable as delivered shall be immersed in water at ambient temperature for a minimum period of 1 h.

A voltage shall be applied between the conductor and the water.

The voltage and the duration of its application shall be as given in Table 2.

Alternatively, the whole length of the completed cable as delivered shall be spark-tested (see 5.2.3.7).

5.2.3.3 Multi-core cable and cables with one or more metallic layers

A voltage shall be applied in turn between each conductor and each of the other conductors and the metallic layer, if any. The conductors may be suitably connected for successive applications of the test voltage to limit the total testing time, provided that the sequence of connections ensures that the voltage is applied for at least 5 min without interruption between each conductor and each other conductor and between each conductor and the metallic layer, if any.

In radial field cables, the voltage shall be applied between the conductor and the core screen.

The voltage and the duration of its application shall be as given in Table 2.

AVA Documents
Document Sharing Hub

Full document details: IEC 60092-350 2020 RLV

5.2.3.4 Voltage test on sheath

The test shall be made on sheathed cable where there is a metallic layer under the sheath.

The whole length of the completed cable as delivered shall be spark-tested (see 5.2.3.7).

5.2.3.5 Test voltage

Unless otherwise stated in the applicable product standard for the cable, the values of the test voltage for the standard rated voltages ~~are~~ shall be those given in Table 2.

Table 2 – Routine test voltage

Rated voltage of cable	Test voltage for 5 min	
U_0/U	Alternating current (AC)	Direct current (DC) [a]
kV	kV	kV
0,15/0,25	1,5	3,6
0,6/1	3,5	8,4
1,8/3	6,5	15,6
3,6/6	12,5	–
6/10	21	–
8,7/15	30,5	–
12/20	42	–
18/30	63	–

NOTE The values for enhanced insulation thickness are given in the product standard.

[a] DC testing is not recommended for cables with rated voltages > 1,8/3 kV.

5.2.3.6 Requirement

The test voltage shall be increased gradually to the specified value and no breakdown of the insulation shall occur.

5.2.3.7 Spark test

When specified, this test shall be carried out in the final stage of manufacture.

The cable shall withstand the test voltage specified without failure of the insulation or sheath as appropriate. The spark test equipment used shall detect a puncture in the insulation or sheath having a diameter equal to, or greater than, half the specified insulation or sheath thickness. The recovery time of the spark tester shall be not greater than 1 s.

The magnitude and presence of the voltage shall be such that, with the electrode system used and at the speed used for the passage of the cable through the spark tester, the test requirements are met.

Unless otherwise stated in the applicable product standard for the cable, the values of the test voltage for insulation shall be:

– AC (50 Hz) 3,0 kV + (5× tabulated insulation thickness in mm) kV
– DC V AC × 1,5
– H.F. V AC + 1,0 kV

Unless otherwise stated in the applicable product standard for the cable, the values of the test voltage for sheath shall be:

AVA Documents Document Sharing Hub

Full document details: IEC 60092-350 2020 RLV

– AC (50 Hz) 3,0 kV

– DC V AC × 1,5

NOTE ~~The adoption of IEC 62230 is under consideration (~~ For recommended minimum spark test voltage levels, see Annex B~~)~~.

5.2.4 Partial discharge test

The partial discharge test shall be carried out in accordance with ~~IEC 60885-2~~ IEC 60885-3.

The magnitude of the discharge at 1,73 U_0 shall not exceed 5 pC.

6 Sample tests

6.1 General

The sample tests required by this document are:

a) conductor examination (see 6.4);

b) check of dimensions (see 6.5 to 6.7);

c) hot-set test for insulations and sheaths (see 6.8);

d) insulation resistance test (volume resistivity determination, see 6.9).

6.2 Frequency of sample tests

a) Conductor examination and check of dimensions

Conductor examination, measurement of the thickness of insulation and sheath and measurement of the overall diameter, if required by the purchaser, shall be made on one length from each manufactured series of the same type and size of cable, but shall be limited to not more than 10 % of the number of lengths in any one contract.

b) Physical tests

By agreement between the purchaser and manufacturer, the test specified shall be made on samples taken from cables manufactured for the contract, provided that the total length in the contract exceeds 2 km of multi-core cables or 4 km of single-core cables. The number of samples to be tested is given in Table 3.

Documents
Document Sharing Hub
Full document details: IEC 60092-350 2020 RLV

Table 3 – Number of samples according to cable length

Cable length				Number of samples
Multi-core cables		Single-core cables		
Above	Up to and including	Above	Up to and including	
km	km	km	km	
2	10	4	20	1
10	20	20	40	2
20	30	40	60	3
> 30	–	> 60	–	[a] [b]

~~NOTE~~

[a] For multicore cable lengths > 30 km, add one sample for each additional 10 km.

[b] For single core cable lengths > 60 km, add one sample for each additional 20 km.

6.3 Repetition of tests

If any sample fails any of the tests of 6.2, two further samples shall be taken from the same batch and submitted to the same test or tests in which the original sample failed. If both additional samples pass the tests, all the cables in the batch from which they were taken shall be regarded as complying with the requirements of this document. If either of the additional samples fails, the batch from which they were taken shall be regarded as failing to comply.

6.4 Conductor examination

Compliance with the requirements of IEC 60228 for conductor construction shall be checked by inspection and by measurement when applicable.

6.5 Measurement of thickness of insulation

6.5.1 General

Each cable length selected for the test shall be represented by two pieces of cable, one taken from each end, any portion which may have suffered damage being discarded.

For cables having more than three cores of equal nominal cross-section, the number of cores on which the measurements are to be made shall be limited to either three cores, or 10 % of the cores, whichever number is greater.

6.5.2 Procedure

The test procedure shall be in accordance with the IEC 60811-201.

6.5.3 Requirements

For each piece of core, the smallest value, rounded off to the nearest 0,01 mm (see Annex C) shall not be less than specified in the applicable product standard.

If the measured value on either of the two pieces fails to meet the requirements specified in 4.3.3, two further pieces shall be checked. If both of these further pieces meet the specified requirements, the cable is deemed to comply, but if one of them does not meet the requirements, the cable is deemed not to comply.

AVA Documents
Document Sharing Hub
Full document details: IEC 60092-350 2020 RLV

6.6 Measurements of thickness of non-metallic sheaths

6.6.1 General

Each cable length selected for the test shall be represented by two pieces of cable, one taken from each end, any portion which may have suffered damage having been discarded.

6.6.2 Procedure

The test procedure shall be in accordance with IEC 60811-202.

6.6.3 Requirements

For each piece of sheath, the smallest value, rounded off to the nearest 0,01 mm (see Annex C) shall not be less than specified in the applicable product standard.

If the measured value on either of the two pieces fails to meet the requirements specified in 4.7.3 or 4.9.3, two further pieces shall be checked. If both of these further pieces meet the specified requirements, the cable is deemed to comply, but if one of them does not meet the requirements, the cable is deemed not to comply.

6.7 Measurement of external diameter

If the measurement of the external diameter of the cable is required as a sample test, it shall be carried out in accordance with IEC 60811-203.

6.8 Hot-set test for insulations and sheaths

6.8.1 General procedure

The sampling and test procedure shall be carried out in accordance with IEC 60811-507 employing the conditions given in IEC 60092-360 for the insulation and for the sheath.

6.8.2 Requirements

The test results shall comply with the requirements given in IEC 60092-360 for the insulation and for the sheath.

6.9 Insulation resistance test (volume resistivity determination)

The insulation resistance shall be measured at ambient temperature using a DC voltage of 80 V to 500 V, after any AC high-voltage test has been carried out, but before any DC high-voltage test is carried out.

The measurement shall in general be effected 1 min after application of the voltage. In certain cases, however, in order to reach a substantial steady-state condition, the time of application may be prolonged up to a maximum of 5 min.

The connection procedure in carrying out the test on different types of cables shall be as follows.

– For single-core cables with a metallic layer, the insulation resistance measurement shall be performed between the conductor and the metallic covering.
– For single-core cables without a metallic layer, the insulation resistance measurement shall be performed between the conductor and the water in which the cable shall be immersed at least 1 h before the test.
– For cables having two to five conductors, with or without metallic layer, the insulation resistance measurement shall be performed in turn between each conductor and all other conductors connected together and to the metallic covering, if any.

AVA Documents
Document Sharing Hub
Full document details: IEC 60092-350 2020 RLV

– For cables having more than five conductors, the insulation resistance measurement test shall be performed: first, between all conductors of uneven number in all layers and all conductors of even number in all layers; second, between all conductors of even layers and all conductors of uneven layers; third, if necessary, between the first and the last conductor of each layer having an uneven number of conductors.
– For cables with individually screened units, an additional insulation resistance test shall be performed in turn between each screen and all other screens connected together and to the metallic armour, if any.

The measurement values of the insulation resistance shall be corrected to the reference temperature of 20 °C by using an appropriate temperature correction factor based on experimental results obtained on the insulation material concerned.

Volume resistivity (ρ) shall be calculated from the measured insulation resistance by the formula:

$$\rho = 2\,\pi\,LR \,/\, \ln(\,D/d)$$

where
ρ is the volume resistivity in ohms centimetre;
R is the measured insulation resistance, corrected to 20 °C, in ohms;
L is the length of the cable, in centimetres;
D is the outer diameter of the insulation, in millimetres;
d is the inner diameter of the insulation, in millimetres.

The calculated value of volume resistivity (ρ) shall be not less than the value specified for the applicable insulating material in IEC 60092-360.

NOTE 1 In some instances, the value for the volume resistivity is given in the form of the "insulation resistance constant K_i" value (expressed in MΩ·km) which is equivalent to $0{,}367 \times 10^{-11}\,\rho$ (ρ expressed in Ω·cm).

NOTE 2 For the core of shaped conductors, the ratio D/d is the ratio of the perimeter over the insulation to the perimeter over the conductors.

7 Type tests, electrical

7.1 General

The type tests defined by this document, and to be applied on samples of completed cable, 10 m to 15 m long unless otherwise specified, are the following:

a) insulation resistance measurement at ambient temperature (see 7.2.1);
b) insulation resistance measurement at the maximum rated temperature (see 7.2.2);
c) increase of the AC capacitance after immersion in water when required (see 7.3);
d) high-voltage test for 4 h (see 7.4);
e) mutual capacitance (see 7.5);
f) inductance (see 7.6).

7.2 Insulation resistance measurement

7.2.1 Measurement at ambient temperature

7.2.1.1 General

This test shall be made on the sample length before any other electrical test. All outer coverings shall be removed and the cores shall be immersed in deionised water at ambient

AVA Documents Document Sharing Hub
Full document details: IEC 60092-350 2020 RLV

temperature at least 1 h before the test. The measurement shall be made between the conductor and the water (see 7.4).

The DC test voltage shall be in the range 80 V to 500 V and shall be applied for not less than 1 min and not more than 5 min. If requested, the measurement may be confirmed at (20 ± 2) °C.

7.2.1.2 Calculations

Volume resistivity (ρ) shall be calculated by the method given in 6.9.

NOTE In some instances, the value for the volume resistivity is given in the form of the "insulation resistance constant K_i" value (expressed in MΩ·km) which is equivalent to $0{,}367 \cdot 10^{-11}\ \rho$ (ρ expressed in Ω·cm).

7.2.1.3 Requirements

The calculated value of volume resistivity (ρ) shall be not less than the value specified for the applicable insulating material in IEC 60092-360.

7.2.2 Measurement at maximum rated temperature

7.2.2.1 General

The cores of the cable sample with all outer coverings removed shall be immersed in water, which shall be heated at the specified temperature for at least 1 h before test.

The DC test voltage shall be in the range 80 V to 500 V and shall be applied for not less than 1 min and not more than 5 min.

7.2.2.2 Calculations

Volume resistivity (ρ) shall be calculated by the method given in 6.9.

NOTE In some instances, the value for the volume resistivity is given in the form of the "insulation resistance constant K_i" value (expressed in MΩ·km) which is equivalent to $0{,}367 \cdot 10^{-11}\ \rho$ (ρ expressed in Ω cm).

7.2.2.3 Requirements

The calculated value of volume resistivity (ρ) shall be not less than the value specified for the applicable insulating material in IEC 60092-360.

7.3 Increase in AC capacitance after immersion in water

7.3.1 General

The increase in AC capacitance test shall be carried out in accordance with the following method.

7.3.2 Preparation of test specimens

Every test specimen shall consist of a core sample 4,5 m long in which any covering of the insulation (including vulcanization tape, if any) has been removed.

7.3.3 Apparatus

A water tank shall be used so that the central portion of the test specimen is immersed over a length of 3 m whilst a length of 0,7 m is maintained above the water level at each end.

The water shall be thermostatically maintained at a temperature of (50 ± 2) °C.

Documents
Document Sharing Hub
Full document details: IEC 60092-350 2020 RLV

The water level shall be maintained constant.

7.3.4 Procedure

The test specimen shall first be dried for 24 h in an oven, the air of which is maintained between 70 °C and 75 °C.

As soon as the test specimen is removed from the oven, the specimen shall be immersed, as indicated above, in tap water which has been previously heated to 50 °C.

The immersion shall be maintained at this temperature for 14 days.

The capacitance between the conductor and the water shall be measured with low-voltage AC at a frequency of 900 Hz ± 100 Hz. Three measurements shall be carried out:

– at the end of the first day: C1;
– at the end of the seventh day: C7;
– at the end of the fourteenth day: C14.

Precaution ~~must~~ shall be taken to ensure that the temperature and the water level are the same for all measurements.

The increase in AC capacitance shall be calculated and expressed in a percentage:

a) between the end of the first day and the end of the fourteenth day: (C14 – C1)/C1;
b) between the end of the seventh day and the end of the fourteenth day: (C14 – C7)/C7.

7.3.5 Requirements

The values calculated from the measurements shall be not more than those specified in IEC 60092-360.

7.4 High-voltage test for 4 h for cables rated up to 1,8/3 kV

7.4.1 General

The cores of the cable sample with all outer coverings removed shall be immersed in deionised water at room temperature for at least 1 h.

A power-frequency voltage equal to three times the rated voltage U_0 shall be gradually applied and maintained continuously for 4 h between the conductor and the water.

7.4.2 Requirement

No breakdown of the insulation shall occur.

7.5 Mutual capacitance (control and instrumentation cables only)

The mutual capacitance shall be measured at 1 kHz on a total of at least two pairs, triples or quads that have been selected at random from the inner and outer layers. The values obtained shall be recorded in the cable type-test report.

7.6 Inductance to resistance ratio (control and instrumentation cables only)

The inductance-to-resistance ratio (L/R ratio) shall be calculated from measurements of inductance (L) made at 1 kHz on a total of at least two pairs, triples or quads that have been selected at random from the inner and outer layers and the DC resistance measured at 20 °C. The values obtained shall be recorded in the cable type-test report.

AVA Documents
Document Sharing Hub
Full document details: IEC 60092-350 2020 RLV