IEC 60317-0-4

Edition 3.0 2015-10

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Withdrawn

Specifications for particular types of winding wires – Part 0-4: General requirements – Glass-fibre wound, resin or varnish impregnated, bare or enamelled rectangular copper wire

Spécifications pour types particuliers de fils de bobinage – Partie 0-4: Exigences générales – Fil de section rectangulaire en cuivre nu ou émaillé, guipé de fibres de verre imprégnées de vernis ou de résine

IEC 60317-0-4:2015-10(en-fr)

Documents
Document Sharing Hub

Full document details: IEC 60317-0-4 2015

THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2015 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office
3, rue de Varembé
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC
The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications
The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue
The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - www.iec.ch/searchpub
The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,…). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished
Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org
The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in 15 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary
More than 60 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc
If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

A propos de l'IEC
La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC
Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Catalogue IEC - webstore.iec.ch/catalogue
Application autonome pour consulter tous les renseignements bibliographiques sur les Normes internationales, Spécifications techniques, Rapports techniques et autres documents de l'IEC. Disponible pour PC, Mac OS, tablettes Android et iPad.

Recherche de publications IEC - www.iec.ch/searchpub

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études,…). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

Electropedia - www.electropedia.org

Le premier dictionnaire en ligne de termes électroniques et électriques. Il contient plus de 30 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans 15 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

Glossaire IEC - std.iec.ch/glossary
Plus de 60 000 entrées terminologiques électrotechniques, en anglais et en français, extraites des articles Termes et Définitions des publications IEC parues depuis 2002. Plus certaines entrées antérieures extraites des publications des CE 37, 77, 86 et CISPR de l'IEC.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: csc@iec.ch.

Withdrawn

Documents
Document Sharing Hub

Full document details: IEC 60317-0-4 2015

IEC 60317-0-4

Edition 3.0 2015-10

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Withdrawn

Specifications for particular types of winding wires – Part 0-4: General requirements – Glass-fibre wound, resin or varnish impregnated, bare or enamelled rectangular copper wire

Spécifications pour types particuliers de fils de bobinage – Partie 0-4: Exigences générales – Fil de section rectangulaire en cuivre nu ou émaillé, guipé de fibres de verre imprégnées de vernis ou de résine

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 29.060.10

ISBN 978-2-8322-2975-0

Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

AVA Documents
Document Sharing Hub

® Registered trademark of the International Electrotechnical Commission
Marque déposée de la Commission Electrotechnique Internationale

Full document details: IEC 60317-0-4 2015

CONTENTS

FOREWORD 4
INTRODUCTION 6
1 Scope 7
2 Normative references 7
3 Terms, definitions and general notes on tests and appearance 7
3.1 Terms and definitions 7
3.2 General notes 8
3.2.1 Methods of test 8
3.2.2 Winding wire 8
3.3 Appearance 9
4 Dimensions 9
4.1 Conductor dimensions 9
4.2 Tolerance on conductor dimensions 11
4.3 Rounding of corners 11
4.4 Increase in dimensions due to the insulation 11
4.5 Overall dimensions 13
4.5.1 Nominal overall dimensions 13
4.5.2 Minimum overall dimensions 13
4.5.3 Maximum overall dimensions 13
5 Electrical resistance 13
6 Elongation 13
7 Springiness 13
8 Flexibility and adherence 14
8.1 Mandrel winding test 14
8.2 Adherence test 14
8.2.1 Glass-fibre covered bare wires 14
8.2.2 Glass-fibre covered enamelled wires 14
9 Heat shock 14
10 Cut-through 14
11 Resistance to abrasion 14
12 Resistance to solvents 14
13 Breakdown voltage 14
14 Continuity of insulation 15
15 Temperature index 15
16 Resistance to refrigerants 15
17 Solderability 15
18 Heat or solvent bonding 15
19 Dielectric dissipation factor 15
20 Resistance to transformer oil 15
21 Loss of mass 15
23 Pin hole test 16
30 Packaging 16

Withdrawn

Documents
Document Sharing Hub

Full document details: IEC 60317-0-4 2015

Annex A (informative) Nominal cross-sectional areas for preferred and intermediate sizes 17
Bibliography 24

Table 1 – Nominal cross-sectional areas of preferred sizes 10
Table 2 – Conductor tolerances 11
Table 3 – Corner radii 11
Table 4 – Increase in dimensions 12
Table 5 – Elongation 13
Table 6 – Mandrel winding 14
Table 7 – Breakdown voltage 15
Table A.1 – Nominal cross-sectional areas *(1 of 7)* 17

Withdrawn

Documents
Document Sharing Hub

Full document details: IEC 60317-0-4 2015

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –

Part 0-4: General requirements – Glass-fibre wound, resin or varnish impregnated, bare or enamelled rectangular copper wire

FOREWORD

1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
6) All users should ensure that they have the latest edition of this publication.
7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60317-0-4 has been prepared by IEC technical committee 55: Winding wires.

This third edition cancels and replaces the second edition published in 1997, Amendment 1:1999 and Amendment 2:2005. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

a) addition of dimensional requirements for grade 1 enamelled wire in Table 4;

b) addition of dielectric breakdown requirements for grade 1 enamelled wire in Table 7.

Withdrawn

AVA Documents Document Sharing Hub

Full document details: IEC 60317-0-4 2015

The text of this standard is based on the following documents:

FDIS	Report on voting
55/1550/FDIS	55/1565/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all the parts in the IEC 60317 series, published under the general title *Specifications for particular types of winding wires*, can be found on the IEC website.

This standard is to be read in conjunction with the IEC 60851 series. The clause numbers used in this standard are identical with the respective test numbers of the IEC 60851 series.

In case of inconsistencies between IEC 60851 and this standard, the latter prevails.

The numbering of clauses in this standard is not continuous from Clauses 21 through 30 in order to reserve space for possible future wire requirements prior to those for wire packaging.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC website under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

Withdrawn

Documents
Document Sharing Hub

INTRODUCTION

This part of IEC 60317 is one of a series which deals with insulated wires used for windings in electrical equipment. The series has three groups describing:

1) Winding wires – Test methods (IEC 60851);
2) Specifications for particular types of winding wires (IEC 60317);
3) Packaging of winding wires (IEC 60264).

withdrawn

Documents
Document Sharing Hub

Full document details: IEC 60317-0-4 2015

SPECIFICATIONS FOR PARTICULAR TYPES OF WINDING WIRES –

Part 0-4: General requirements – Glass-fibre wound, resin or varnish impregnated, bare or enamelled rectangular copper wire

Withdrawn

1 Scope

This part of IEC 60317 specifies general requirements of glass-fibre wound, resin or varnish impregnated, bare or enamelled rectangular copper wire.

The range of nominal conductor dimensions is given in the relevant specification sheet.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60851 (all parts), *Winding wires – Test methods*

3 Terms, definitions and general notes on tests and appearance

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1.1
coating
material which is deposited on a conductor or wire by a suitable means and then dried and/or cured

3.1.2
conductor
bare metal after removal of the insulation

3.1.3
covering
material which is wound, wrapped or braided around a bare or insulated conductor

3.1.4
crack
opening in the insulation which exposes the conductor to view at the stated magnification

3.1.5
enamelled wire
wire coated with an insulation of cured resin

3.1.6
grade
range of thickness of the insulation of a wire

AVA Documents
Document Sharing Hub

Full document details: IEC 60317-0-4 2015

3.1.7
insulation
coating or covering on the conductor with the specific function of withstanding voltage

3.1.8
nominal conductor dimension
designation of the conductor size in accordance with IEC 60317

3.1.9
normal vision
20/20 vision, with corrective lenses if necessary

3.1.10
winding wire
wire used for winding a coil to provide a magnetic field

3.1.11
wire
conductor coated or covered with an insulation

3.2 General notes

3.2.1 Methods of test

All methods of test to be used for this part of IEC 60317 are given in the IEC 60851 series of standards.

The clause numbers used in this part of IEC 60317 are identical with the respective test numbers in the IEC 60851 series of standards.

In case of inconsistencies between the publication on test methods and this part of IEC 60317, the latter shall prevail.

Where no specific range of nominal conductor dimensions is given for a test, the test applies to all nominal conductor dimensions covered by the specification sheet.

Unless otherwise specified, all tests shall be carried out at a temperature from 15 °C to 40 °C and a relative humidity from 45 % to 75 %. Before measurements are made, the specimens shall be preconditioned under these atmospheric conditions for a time sufficient to allow the specimens to reach stability.

The wire to be tested shall be removed from the packaging in such a way that it is not subjected to tension or unnecessary bends. Before each test, sufficient wire should be discarded to ensure that any damaged wire is not included in the test specimens.

3.2.2 Winding wire

When reference is made to a winding wire according to a standard of the IEC 60317 series, the following information is given in the description:

– reference of the IEC specification;
– nominal conductor dimensions in millimetres (width × thickness);
– grade.

EXAMPLE IEC 60317-31 – 4,00 × 1,00 Grade 2GL1

Withdrawn

AVA Documents Document Sharing Hub

Full document details: IEC 60317-0-4 2015

3.3 Appearance

The fibrous covering shall be essentially smooth and continuous, and free from physical damage and foreign material when examined with normal vision, as wound on the original spool or reel.

NOTE Evidence of physical damage includes gashes, broken fibre strands, and the like.

4 Dimensions

4.1 Conductor dimensions

The dimensions for widths and thickness of conductors of winding wires with rectangular cross-section recommended in this part of IEC 60317 shall be in accordance with Table 1, and are taken from the R 20 series according to ISO 3.

Preferred and intermediate sizes are combinations of width and thickness both according to the R 20 series.

This part of IEC 60317 covers:

– widths from 2,00 mm up to and including 16,00 mm;
– thicknesses from 0,80 mm up to and including 5,60 mm.

For thickness over 5,60 mm up to and including 10 mm and for widths over 16 mm up to and including 25 mm where, for technical reasons, additional sizes may be needed, the R 40 series shall be used. The ratio width/thickness shall be within the specified limits and combinations of R 40 and R 40 are not allowed in the case of additional sizes.

The ratio width/thickness shall be greater than or equal to 1,4:1 and shall not exceed 8:1.

The actual values of dimensions are given in Table 1.

The nominal cross-sectional areas for preferred sizes are given in Table 1 and the nominal cross-sectional areas for intermediate sizes are given in Annex A.

Withdrawn

Documents
Document Sharing Hub

Full document details: IEC 60317-0-4 2015

Table 1 – Nominal cross-sectional areas of preferred sizes

Width	Thickness →																	
mm	0,80	0,90	1,00	1,12	1,25	1,40	1,60	1,80	2,00	2,24	2,50	2,80	3,15	3,55	4,00	4,50	5,00	5,60
	Corner radius (0,5 mm[a])			Corner radius (0,5 mm[a])				Corner radius (0,65 mm[a])			Corner radius (0,80 mm[a])				Corner radius (1,0 mm[a])			
2,00	1,463	1,626	1,785	2,025	2,285	2,585												
2,24	1,655	1,842	2,205	2,294	2,582	2,921	3,369											
2,50	1,863	2,076	2,285	2,585	2,910	3,285	3,785	4,137										
2,80	2,103	2,346	2,585	2,921	3,285	3,705	4,265	4,677	5,237									
3,15	2,383	2,661	2,935	3,313	3,723	4,195	4,825	5,307	5,937	6,693								
3,55	2,703	3,021	3,335	3,761	4,223	4,755	5,465	6,027	6,737	7,589	8,326							
4,00	3,063	3,426	3,785	4,265	4,785	5,385	6,185	6,831	7,637	8,597	9,451	10,65						
4,50	3,463	3,876	4,285	4,825	5,410	6,085	6,85	7,737	8,631	9,717	10,70	12,05	13,63					
5,00	3,863	4,326	4,785	5,385	6,035	6,785	7,785	8,637	9,637	10,84	12,18	13,45	15,20	17,20				
5,60	4,363	4,866	5,385	6,057	6,785	7,625	8,745	9,717	10,84	12,18	13,45	15,13	17,09	19,33	21,54			
6,30	4,903	5,496	6,085	6,841	7,660	8,605	9,865	10,98	12,24	13,75	15,20	17,09	19,30	21,82	24,34	27,49		
7,10		6,216	6,885	7,737	8,660	9,725	11,15	12,42	13,84	15,54	17,20	19,33	21,82	24,66	27,54	31,09	34,64	
8,00			7,785	8,745	9,785	10,99	12,59	14,04	15,64	17,56	19,45	21,85	24,65	27,85	31,14	35,14	39,14	43,94
9,00				9,865	11,04	12,39	14,19	15,84	17,64	19,80	21,95	24,65	27,80	31,40	35,14	39,64	44,14	49,54
10,0					12,29	13,79	15,79	17,64	19,64	22,04	24,45	27,45	30,95	34,95	39,14	44,14	49,14	55,14
11,2						15,47	17,71	19,80	22,04	24,79	27,46	30,81	34,73	39,21	43,94	49,54	55,14	61,86
12,5							19,79	22,14	24,64	27,64	30,70	34,45	38,83	43,83	49,14	55,39	61,64	69,14
14,0								24,84	27,64	31,00	34,45	38,65	43,55	49,15	55,14	62,14	69,14	77,54
16,0									31,64	35,48	39,45	44,25	49,85	56,25	63,14	71,14	79,14	88,74

Not recommended
Ratio width/thickness smaller than 1,4:1

Not recommended
Ratio width/thickness over 8:1

[a] Nominal thickness

Withdrawn

Documents
Document Sharing Hub

Full document details: IEC 60317-0-4 2015

4.2 Tolerance on conductor dimensions

The conductor dimensions shall not differ from the nominal values by more than the tolerance given in Table 2.

Table 2 – Conductor tolerances

Nominal width or thickness of the conductor mm		Tolerance mm
Over	**Up to and including**	
–	3,15	± 0,030
3,15	6,30	± 0,050
6,30	12,50	± 0,070
12,50	16,00	± 0,100

4.3 Rounding of corners

The arc shall merge smoothly into the flat surfaces of the conductor and the strip shall be free from sharp, rough and projecting edges. The conductor shall have corner radii complying with Table 3. The specified radii shall be maintained within ± 25 %.

Table 3 – Corner radii

Nominal thickness of the conductor mm		Corner radius mm
Over	**Up to and including**	
–	1,00	0,5 nominal thickness
1,00	1,60	0,50[a]
1,60	2,24	0,65[b]
2,24	3,55	0,80
3,55	5,60	1,00
If agreed between purchaser and supplier, the corner radii for wires with a width greater than 4,8 mm may be: [a] 0,5 mm nominal thickness; [b] 0,8 mm.		

4.4 Increase in dimensions due to the insulation

The increase in width or thickness due to the insulation shall be as specified in Table 4.

Withdrawn

Documents
Document Sharing Hub

Full document details: IEC 60317-0-4 2015

Table 4 – Increase in dimensions

Nominal width of the conductor mm		Increase in dimensions mm																	
		Glass-fibre covering over bare conductor						Glass-fibre covering over grade 1 enamelled wire						Glass-fibre covering over grade 2 enamelled wire					
		Single covering (GL1)			Double covering (GL2)			Single covering (grade 1 GL1)			Double covering (grade 1 GL2)			Single covering (grade 2 GL1)			Double covering (grade 2 GL2)		
Over	Up to and incl.	Min.	Nom.	Max.	Min.	Nom.	Max.	Min.	Nom.	Max.	Min.	Nom.	Max.	Min.	Nom.	Max.	Min.	Nom.	Max.
–	3,15	0,10	0,14	0,18	0,21	0,27	0,33	0,16	0,23	0,30	0,27	0,36	0,45	0,23	0,29	0,35	0,35	0,42	0,49
3,15	6,30	0,12	0,16	0,20	0,23	0,30	0,37	0,18	0,25	0,32	0,29	0,39	0,49	0,25	0,31	0,37	0,38	0,45	0,52
6,30	12,50	0,14	0,19	0,24	0,27	0,35	0,43	0,20	0,28	0,36	0,33	0,44	0,55	0,27	0,34	0,41	0,43	0,50	0,57
12,50	16,00	0,17	0,23	0,29	0,31	0,39	0,47	0,23	0,32	0,41	0,37	0,48	0,59	0,30	0,38	0,46	0,46	0,54	0,62

The maximum increase in thickness or width due to the insulation may be exceeded, provided the overall thickness or width of the insulated wire does not exceed the sum of the maximum thickness or width of the bare wire plus the maximum increase in dimension.

NOTE The minimum increases in dimensions apply only to the increase in thickness.

Withdrawn

AVA Documents
Document Sharing Hub

Full document details: IEC 60317-0-4 2015

4.5 Overall dimensions

4.5.1 Nominal overall dimensions

The nominal overall dimensions shall be calculated as the sum of the nominal bare conductor dimension and the nominal increase in dimension due to the insulation.

4.5.2 Minimum overall dimensions

The minimum overall dimensions shall be calculated as the sum of the minimum bare conductor dimension and the minimum increase in dimension due to the insulation.

4.5.3 Maximum overall dimensions

The maximum overall dimensions shall be calculated as the sum of the maximum bare conductor dimension and the maximum increase in dimension due to the insulation.

5 Electrical resistance

The resistance of the wire shall be expressed as the d.c. resistance at 20 °C. The method used shall provide an accuracy of 0,5 %.

The maximum value of resistance shall be not greater than the value calculated for the minimum tolerated cross-sectional area of the conductor resulting from the minimum dimensions in thickness and width and the maximum for the corner radius, and with a maximum resistivity of 1/58,5 Ω mm^2 m^{-1}.

One measurement shall be made.

6 Elongation

The elongation at fracture shall be in accordance with Table 5.

Table 5 – Elongation

Nominal thickness of the conductor mm		Minimum elongation %
Over	**Up to and including**	
–	2,50	30
2,50	5,60	32

7 Springiness

The wire shall not exceed the maximum springback of:

– 5,0 degrees for glass-fibre covered bare wires;

– 5,5 degrees for glass-fibre covered enamelled wires.

Withdrawn

Documents
Document Sharing Hub

8 Flexibility and adherence

8.1 Mandrel winding test

The covering shall show no crack after the wire has been bent flatwise and edgewise on a mandrel with a diameter as specified in Table 6.

Table 6 – Mandrel winding

Wire bent on		Mandrel diameter
Width	Sizes up to and including 8 mm	10 × width
	Sizes over 8 mm	15 × width
Thickness	All sizes	10 × thickness

Specimens showing no crack or opening shall meet the requirements of Clause 13.

8.2 Adherence test

8.2.1 Glass-fibre covered bare wires

The specimen shall be elongated by 10 %. There shall be no loss of adhesion of the glass-fibre covering.

8.2.2 Glass-fibre covered enamelled wires

The specimen shall be elongated by 10 %. There shall be no loss of adhesion either of the glass-fibre covering or the enamel.

9 Heat shock

Test inappropriate.

10 Cut-through

Test inappropriate.

11 Resistance to abrasion

Test inappropriate.

12 Resistance to solvents

Test inappropriate.

13 Breakdown voltage

The wire shall meet the requirements of Table 7.

withdrawn

AVA Documents Document Sharing Hub

Full document details: IEC 60317-0-4 2015