IEC 60384-20

Edition 3.0 2015-07

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Fixed capacitors for use in electronic equipment – Part 20: Sectional specification – Fixed metallized polyphenylene sulfide film dielectric surface mount d.c. capacitors

Condensateurs fixes utilisés dans les équipements électroniques – Partie 20: Spécification intermédiaire – Condensateurs fixes pour montage en surface pour courant continu à diélectrique en film de sulfure de polyphénylène métallisé

IEC 60384-20:2015-07(en-fr)

Documents
Document Sharing Hub
Full document details: IEC 60384-20 2015

THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2015 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office
3, rue de Varembé
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC
The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications
The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue
The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - www.iec.ch/searchpub
The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,…). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished
Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org
The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in 15 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary
More than 60 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc
If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

A propos de l'IEC
La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC
Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Catalogue IEC - webstore.iec.ch/catalogue
Application autonome pour consulter tous les renseignements bibliographiques sur les Normes internationales, Spécifications techniques, Rapports techniques et autres documents de l'IEC. Disponible pour PC, Mac OS, tablettes Android et iPad.

Recherche de publications IEC - www.iec.ch/searchpub

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études,…). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

Electropedia - www.electropedia.org

Le premier dictionnaire en ligne de termes électroniques et électriques. Il contient plus de 30 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans 15 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

Glossaire IEC - std.iec.ch/glossary
Plus de 60 000 entrées terminologiques électrotechniques, en anglais et en français, extraites des articles Termes et Définitions des publications IEC parues depuis 2002. Plus certaines entrées antérieures extraites des publications des CE 37, 77, 86 et CISPR de l'IEC.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: csc@iec.ch.

Documents
Document Sharing Hub

Full document details: IEC 60384-20 2015

IEC 60384-20

Edition 3.0 2015-07

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Fixed capacitors for use in electronic equipment – Part 20: Sectional specification – Fixed metallized polyphenylene sulfide film dielectric surface mount d.c. capacitors

Condensateurs fixes utilisés dans les équipements électroniques – Partie 20: Spécification intermédiaire – Condensateurs fixes pour montage en surface pour courant continu à diélectrique en film de sulfure de polyphénylène métallisé

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 31.060.10

ISBN 978-2-8322-2792-3

Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

® Registered trademark of the International Electrotechnical Commission
Marque déposée de la Commission Electrotechnique Internationale

AVA Documents
Document Sharing Hub

Full document details: IEC 60384-20 2015

CONTENTS

FOREWORD 5
1 General 7
1.1 Scope 7
1.2 Object 7
1.3 Normative references 7
1.4 Information to be given in a detail specification 8
1.4.1 General 8
1.4.2 Outline drawing and dimensions 8
1.4.3 Mounting 8
1.4.4 Ratings and characteristics 8
1.4.5 Marking 9
1.5 Terms and definitions 9
1.6 Marking 9
1.6.1 General 9
1.6.2 Information for marking 9
1.6.3 Marking on capacitors 9
1.6.4 Marking on packaging 10
2 Preferred ratings and characteristics 10
2.1 Preferred characteristics 10
2.2 Preferred values of ratings 10
2.2.1 Nominal capacitance (C_N) 10
2.2.2 Tolerance on nominal capacitance 10
2.2.3 Rated voltage (U_R) 10
2.2.4 Category voltage (U_C) 11
2.2.5 Rated temperature 11
3 Quality assessment procedures 11
3.1 Primary stage of manufacture 11
3.2 Structurally similar components 11
3.3 Certified test records of released lots 11
3.4 Qualification approval procedures 12
3.4.1 General 12
3.4.2 Qualification approval on the basis of the fixed sample size procedure 12
3.4.3 Tests 12
3.5 Quality conformance inspections 18
3.5.1 Formation of inspection lots 18
3.5.2 Test schedule 19
3.5.3 Delayed delivery 19
3.5.4 Assessment levels 19
4 Test and measurement procedures 20
4.1 Mounting 20
4.2 Visual examination and check of dimensions 20
4.2.1 General 20
4.2.2 Visual examination and check of dimensions 20
4.2.3 Requirements 20
4.3 Electrical tests 20
4.3.1 Voltage proof 20

AVA Documents
Document Sharing Hub
Full document details: IEC 60384-20 2015

4.3.2 Capacitance 21
4.3.3 Tangent of loss angle (tan δ) 21
4.3.4 Insulation resistance 22
4.4 Shear test 23
4.4.1 General 23
4.5 Substrate bending test 23
4.5.1 General 23
4.5.2 Initial inspections 23
4.5.3 Final inspections and requirements 23
4.6 Resistance to soldering heat 24
4.6.1 General 24
4.6.2 Initial inspections 24
4.6.3 Test conditions 24
4.6.4 Recovery 24
4.6.5 Final inspections and requirements 24
4.7 Solderability 24
4.7.1 General 24
4.7.2 Test conditions 24
4.7.3 Final inspections and requirements 24
4.8 Rapid change of temperature 24
4.8.1 General 24
4.8.2 Initial inspections 24
4.8.3 Test conditions 24
4.8.4 Final inspections and requirements 25
4.9 Climatic sequence 25
4.9.1 General 25
4.9.2 Initial inspections 25
4.9.3 Dry heat 25
4.9.4 Damp heat, cyclic, test Db, first cycle 25
4.9.5 Cold 25
4.9.6 Damp heat, cyclic, test Db, remaining cycles 25
4.9.7 Recovery 25
4.9.8 Final inspections and requirements 25
4.10 Damp heat, steady state 25
4.10.1 General 25
4.10.2 Initial inspections 25
4.10.3 Test conditions 26
4.10.4 Recovery 26
4.10.5 Final inspections and requirements 26
4.11 Endurance 26
4.11.1 General 26
4.11.2 Initial inspections 26
4.11.3 Test conditions 26
4.11.4 Final inspections and requirements 26
4.12 Charge and discharge 27
4.12.1 General 27
4.12.2 Initial inspections 27
4.12.3 Test conditions 27
4.12.4 Recovery 27

AVA Documents
Document Sharing Hub
Full document details: IEC 60384-20 2015

4.12.5 Final inspections and requirements 27
4.13 Component solvent resistance (if required) 27
4.13.1 General 27
4.14 Solvent resistance of the marking (if required) 27
4.14.1 General 27
Bibliography 28

Table 1 – Percentage limit of the rated voltage at a.c. voltage frequency 11
Table 2 – Category voltages for upper category temperature 125 °C 11
Table 3 – Category voltages for upper category temperature 155 °C 11
Table 4 – Sampling plan for qualification approval – Assessment level EZ 13
Table 5 – Test schedule for qualification approval *(1 of 5)* 14
Table 6 – Lot-by-lot inspection 19
Table 7 – Periodic tests 20
Table 8 – Test voltages 21
Table 9 – Tangent of loss angle limits 22
Table 10 – Requirements insulation resistance 23
Table 11 – Correction factor dependent on test temperature 23
Table 12 – Endurance test for Grade 1, 2 and 3 capacitors 26

Documents
Document Sharing Hub
Full document details: IEC 60384-20 2015

INTERNATIONAL ELECTROTECHNICAL COMMISSION

FIXED CAPACITORS FOR USE IN ELECTRONIC EQUIPMENT –

Part 20: Sectional specification – Fixed metallized polyphenylene sulfide film dielectric surface mount d.c. capacitors

FOREWORD

1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
6) All users should ensure that they have the latest edition of this publication.
7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60384-20 has been prepared by IEC technical committee 40: Capacitors and resistors for electronic equipment.

This third edition cancels and replaces the second edition, published in 2008, and constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

a) Revision of the structure in accordance with ISO/IEC Directives, Part 2:2011 (sixth edition) to the extent practicable, and harmonization between other similar kinds of documents.
b) In addition, Clause 4 and all the tables have been reviewed in order to prevent duplications and contradictions.

Documents
Document Sharing Hub

Full document details: IEC 60384-20 2015

The text of this standard is based on the following documents:

FDIS	Report on voting
40/2381/FDIS	40/2394/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60384 series, published under the general title *Fixed capacitors for use in electronic equipment*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC website under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

Documents
Document Sharing Hub

Full document details: IEC 60384-20 2015

FIXED CAPACITORS FOR USE IN ELECTRONIC EQUIPMENT –

Part 20: Sectional specification – Fixed metallized polyphenylene sulfide film dielectric surface mount d.c. capacitors

1 General

1.1 Scope

This part of IEC 60384 applies to fixed surface mount capacitors for direct current, with metallized electrodes and polyphenylene sulfide dielectric for use in electronic equipment. These capacitors have metallized connecting pads or soldering strips and are intended to be mounted directly onto substrates for hybrid circuits or onto printed boards. They may have "self-healing properties" depending on conditions of use and are primarily intended for applications where the a.c. component is small with respect to the rated voltage.

These capacitors are divided to 3 grades. Performance grade 1 for long life, performance grade 2 for general purpose and performance grade 3 for miniature type.

Capacitors for radio interference suppression are not included, but are covered by IEC 60384-14.

Capacitors used for motor or fluorescent lamp are outside the scope of this standard.

1.2 Object

The object of this standard is to prescribe preferred ratings and characteristics and to select from IEC 60384-1, the appropriate quality assessment procedures, tests and measuring methods and to give general performance requirements for this type of capacitor. Test severities and requirements prescribed in detail specifications referring to this standard shall be of equal or higher performance level, lower performance levels are not permitted.

1.3 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60062:2004, *Marking codes for resistors and capacitors*

IEC 60063, *Preferred number series for resistors and capacitors*

IEC 60068-1:2013, *Environmental testing – Part 1: General and guidance*

IEC 60384-1:2008, *Fixed capacitors for use in electronic equipment – Part 1: Generic specification*

IEC 61193-2:2007, *Quality assessment systems – Part 2: Selection and use of sampling plans for inspection of electronic components and packages*

ISO 3, *Preferred numbers – Series of preferred numbers*

Documents
Document Sharing Hub

Full document details: IEC 60384-20 2015

1.4 Information to be given in a detail specification

1.4.1 General

Detail specifications shall be derived from the blank detail specification.

Detail specifications shall not specify requirements inferior to those of the generic, sectional or blank detail specification. When more severe requirements are included, they shall be listed in 1.9 of the detail specification and indicated in the test schedules, for example by an asterisk.

The information given in 1.4.2 may, for convenience, be presented in tabular form.

The following information shall be given in each detail specification and the values quoted shall preferably be selected from those given in the appropriate clause of this standard.

1.4.2 Outline drawing and dimensions

There shall be an illustration of the capacitor as an aid to easy recognition and for comparison of the capacitor with others. Dimensions and their associated tolerances, which affect interchangeability and mounting, shall be given in the detail specification. All dimensions shall preferably be stated in millimetres, however, when the original dimensions are given in inches, the converted metric dimensions in millimetres shall be added.

The numerical values of the body shall be given as follows:

– for general: the width, length and height.

The numerical values of the terminals shall be given as follows:

– for terminals: the width, length and spacing.

When the configuration is other than described above, the detail specification shall state such dimensional information as will adequately describe the capacitors.

1.4.3 Mounting

The method of mounting for tests and measurements are given in 4.1. The detail specification shall specify the methods of mounting for normal use.

1.4.4 Ratings and characteristics

1.4.4.1 General

The ratings and characteristics shall be given in accordance with the relevant clauses of this standard, together with the following.

1.4.4.2 Nominal capacitance range

See 2.2.1.

When products approved to the detail specification have different nominal capacitance ranges, the following statement should be added: "The nominal capacitance range available in each voltage range is given in the register of approvals, available for example on the IECQ on-line certificate system website www.iecq.org".

1.4.4.3 Particular characteristics

Additional characteristics may be listed, when they are considered necessary to specify adequately the component for design and application purposes.

AVA Documents
Document Sharing Hub

Full document details: IEC 60384-20 2015

1.4.4.4 Soldering

The detail specification shall prescribe the test methods, severities and requirements applicable for the solderability and the resistance to soldering heat tests.

1.4.5 Marking

The detail specification shall specify the content of the marking on the capacitor and on the packaging. When there are deviations from 1.6, these shall be given in the detail specification.

1.5 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60384-1:2008, as well as the following apply.

1.5.1
performance grade 1 capacitors
<long life> capacitors for long-life applications with stringent requirements for the electrical parameters

1.5.2
performance grade 2 capacitors
<general purpose> capacitors for general application where the stringent requirements for grade 1 capacitors are not necessary

1.5.3
performance grade 3 capacitors
<low power, miniature type> miniature type capacitors having a rated voltage of less than 63 V and for which less stringent requirements than for grade 2 capacitors are acceptable

1.6 Marking

1.6.1 General

See IEC 60384-1:2008, 2.4, with the following details.

1.6.2 Information for marking

The information given in the marking is normally selected from the following list. The relative importance of each item is indicated by its position in the list:

a) nominal capacitance (in clear or code according to IEC 60062:2004);
b) rated voltage (d.c. voltage may be indicated by the symbol ⎓ or ⎯);
c) tolerance on nominal capacitance;
d) category voltage;
e) year and month (or, year and week) of manufacture;
f) manufacturer's name and/or trademark;
g) manufacturer's type designation;
h) reference to the detail specification.

1.6.3 Marking on capacitors

Marking on capacitors are marked as necessary.

Any marking shall be legible and not easily smeared or removed by rubbing with the finger.

Documents
Document Sharing Hub
Full document details: IEC 60384-20 2015

1.6.4 Marking on packaging

The packaging containing the capacitors should be clearly marked with all the information listed in 1.6.2 as necessary.

2 Preferred ratings and characteristics

2.1 Preferred characteristics

Preferred climatic categories shall be given in the preferred characteristics only.

The capacitors covered by this standard are classified into climatic categories according to the general rules given in IEC 60068-1:2013, Annex A.

The lower and upper category temperature shall be taken from the following:

lower category temperature: –55 °C, –40 °C and –25 °C;

upper category temperature: +100 °C, +105 °C, +125 °C and +155 °C.

With continuous operation at 155 °C in excess of the endurance test time, accelerated aging has to be considered (see detail specification).

The severities for the cold and dry heat tests are the lower and upper category temperatures respectively.

2.2 Preferred values of ratings

2.2.1 Nominal capacitance (C_N)

Preferred values of nominal capacitance shall be taken from the E 6 series of IEC 60063 are:

1 – 1,5 – 2,2 – 3,3 – 4,7 and 6,8;

and their decimal multiples ($\times 10^n$, n: integer).

If other values are required they shall preferably be chosen from the E 12 series.

2.2.2 Tolerance on nominal capacitance

The preferred values of tolerance on nominal capacitance are: ±5 %, ±10 % and ±20 %.

2.2.3 Rated voltage (U_R)

Preferred values of rated direct voltage taken from R 10 series of ISO 3 are:

1,0 – 1,6 – 2,5 – 4,0 – 5,0 – 6,3;

and their decimal multiples ($\times 10^n$, n: integer).

The sum of the d.c. voltage and the peak a.c. voltage applied to the capacitor should not exceed the rated voltage.

The value of the peak a.c. voltage should not exceed the following percentages of the rated voltage at the frequencies stated in Table 1 and should not be greater than 280 V, unless otherwise specified in the detail specification.

AVA Documents
Document Sharing Hub

Full document details: IEC 60384-20 2015

Table 1 – Percentage limit of the rated voltage at a.c. voltage frequency

AC voltage frequency Hz	Percentage limit of the rated voltage %
50	20
100	15
1 000	3
10 000	1

2.2.4 Category voltage (U_C)

The category voltage for capacitors is given in Table 2 and Table 3.

2.2.5 Rated temperature

The standard value of rated temperature is 100 °C or 105 °C.

Table 2 – Category voltages for upper category temperature 125 °C

Dimensions in volt

	Upper category temperature 125 °C / rated temperature 100 °C, or 105 °C									
U_R	10	16	25	40	50	63	100	160	250	400
$U_C = 0{,}80\ U_R$	8,0	13	20	32	40	50	80	130	200	320

Table 3 – Category voltages for upper category temperature 155 °C

Dimensions in volt

	Upper category temperature 155 °C / rated temperature 100 °C, or 105 °C									
U_R	10	16	25	40	50	63	100	160	250	400
$U_C = 0{,}50\ U_R$	5,0	8,0	13	20	25	32	50	80	130	200

3 Quality assessment procedures

3.1 Primary stage of manufacture

The primary stage of manufacture is the winding of the capacitor element or the equivalent operation.

3.2 Structurally similar components

Capacitors, considered as being structurally similar, are capacitors produced with similar processes and materials, though they may be of different case sizes and values.

3.3 Certified test records of released lots

The information required in IEC 60384-1:2008, Q.9 shall be made available when prescribed in the detail specification and when requested by a purchaser. After the endurance test the required parameters are the capacitance, tangent of loss angle and the insulation resistance.

Documents
Document Sharing Hub
Full document details: IEC 60384-20 2015

3.4 Qualification approval procedures

3.4.1 General

The procedures for qualification approval testing are given in IEC 60384-1:2008, Q.5.

The schedule to be used for qualification approval testing on the basis of lot-by-lot and periodic tests is given in 3.5. The procedure using a fixed sample size schedule is given in 3.4.2 and 3.4.3.

3.4.2 Qualification approval on the basis of the fixed sample size procedure

The fixed sample size procedure is described in IEC 60384-1:2008, Clause Q.5.3, list item b). The sample shall be representative of the range of capacitors for which approval is sought. The sample may be the whole or part of the range given in the detail specification.

The sample shall consist of four specimens having the maximum and minimum rated voltages, and, for these voltages, the maximum and minimum capacitances. When there are more than four rated voltages an intermediate voltage shall also be tested. Thus, for the approval of a range, testing is required of either four or six values (capacitance/voltage combinations). When the range consists of less than four values, the number of specimens to be tested shall be that required for four values.

Two (for six values) or three (for four values) per value may be used as replacements for specimens which are non-conforming because of incidents not attributable to the manufacturer.

The numbers given in Group 0 assume that all groups are applicable. If this is not so the numbers may be reduced accordingly.

When additional groups are introduced into the qualification approval test schedule, the number of specimens required for Group 0 shall be increased by the same number as that required for the additional groups.

Table 4 gives the number of samples to be tested in each group or subgroup together with the permissible number of non-conforming items for qualification approval tests.

3.4.3 Tests

The complete series of tests specified in Table 4 and Table 5 are required for the approval of capacitors covered by one detail specification. The tests of each group shall be carried out in the order given.

The whole sample shall be subjected to the tests of Group 0 and then divided for the other groups.

Non-conforming specimens found during the tests of Group 0 shall not be used for the other groups.

Approval is granted when the number of non-conforming samples is zero.

Table 4 and Table 5 together form the fixed sample size test schedule for the qualification approval on the basis of the fixed sample size procedure.

Table 4 gives the number of the samples or permissible non-conforming items for each tests or test groups.

Documents
Document Sharing Hub

Full document details: IEC 60384-20 2015

Table 5 gives a summary of the test conditions and performance requirements, and choices of the test conditions and performance requirements in the detail specification.

The test conditions and performance requirements for the qualification approval on the basis of the fixed sample size procedure should be identical to those for quality conformance inspections given in the detail specification.

Table 4 – Sampling plan for qualification approval – Assessment level EZ

Group no.	Test	Subclause	Number of specimens n[a]	Permissible number of non-conforming items c
0	Visual examination	4.2	144+12[d]	0
	Dimensions	4.2		
	Capacitance	4.3.2		
	Tangent of loss angle	4.3.3		
	Voltage proof	4.3.1		
	Insulation resistance	4.3.4		
	Spare specimens		12	
1A	Resistance to soldering heat	4.6	12	0
	Component solvent resistance [b]	4.13		
1B	Solderability	4.7	12	0
	Solvent resistance of the marking [b]	4.14		
2	Substrate bending test	4.5	12	0
3	Mounting	4.1	108	0[c]
	Visual examination	4.2.1		
	Capacitance	4.3.2		
	Tangent of loss angle	4.3.3		
	Insulation resistance	4.3.4		
3.1	Shear test	4.4	24	0
	Rapid change of temperature	4.8		
	Climatic sequence	4.9		
3.2	Damp heat, steady state	4.10	24	0
3.3	Endurance	4.11	36	0
3.4	Charge and discharge	4.12	24	0

[a] Capacitance/voltage combinations, see 3.4.2.

[b] If required.

[c] Specimens found defective after mounting shall not be taken into account when calculating the permissible non-conforming items for the following tests. They shall be replaced by spare parts.

[d] Spare specimens.

Documents
Document Sharing Hub

Full document details: IEC 60384-20 2015

Table 5 – Test schedule for qualification approval *(1 of 5)*

Subclause number and test [a], inspection items	D or ND [b]	Conditions of test [a] and measurements	Number of specimens (n) and number of permissible non-conformances (c)	Performance requirements [a]
Group 0	ND		See Table 4	
4.2.1 Visual examination		As in 4.2.2		See detail specification
4.2 Dimensions (detail)				See detail specification
4.3.2 Capacitance		As in 4.3.2.2		Within specified tolerance
4.3.3 Tangent of loss angle		As in 4.3.3.2		See Table 9
4.3.1 Voltage proof		As in 4.3.1.2 and 4.3.1.3		No breakdown or flashover. Self-healing breakdowns allowed
4.3.4 Insulation resistance		As in 4.3.4.2		See Table 10
Group 1A	D		See Table 4	
4.6 Resistance to soldering heat		As in 4.6.3		
4.6.2 Initial inspections Capacitance		As in 4.3.2.2		
4.6.4 Recovery		As in 4.6.4		
4.6.5 Final inspections Visual examination		As in 4.2.2		No signs of damage such as cracks
Capacitance		As in 4.3.2.2		$\lvert \Delta C/C \rvert \leq 2$ % of value measured in 4.6.2, however, ≤3 % for Grade 3
4.13 Component solvent resistance [c,e]		As in 4.13 Method 2		See detail specification
Group 1B	D		See Table 4	
4.7 Solderability		As in 4.7.2		
4.7.3 Final inspections Visual examination		As in 4.2.2		Areas to be soldered shall be covered with a new solder coating with no more than a small amount of scattered imperfections such as pinholes or un-wetted or de-wetted areas. These imperfections shall not be concentrated in one area.
4.14 Solvent resistance of the marking [c,e]		As in 4.14 Method 1		Legible marking

Documents
Document Sharing Hub
Full document details: IEC 60384-20 2015

Table 5 *(2 of 5)*

Subclause number and test [a], inspection items	D or ND[b]	Conditions of test [a] and measurements	Number of specimens (n) and number of permissible non-conformances (c)	Performance requirements [a]
Group 2	D		See Table 4	
4.5 Substrate bending test		See IEC 60384-1:2008, 4.35		
4.5.2 Initial inspections Capacitance		As in 4.3.2.2		
4.5.3 Final inspections Visual examination		As in 4.2.2		No visible damage
Capacitance		As in 4.3.2.2 (under board bending position)		$\lvert \Delta C/C \rvert$ for Grade 1 and Grade 2: ≤2 %, Grade 3: ≤5 % of value measured in 4.5.2.
Group 3	D		See Table 4	
4.1 Mounting		As in 4.1 Substrate material: … [d]		
Visual examination		As in 4.2.2		See detail specification
Capacitance		As in 4.3.2.2		$\lvert \Delta C/C \rvert$ for Grade 1 and Grade 2: ≤2 %, Grade 3: ≤3 % of value measured in 4.3.2
Tangent of loss angle		As in 4.3.3.2		See detail specification
Insulation resistance		As in 4.3.4.2		See detail specification
Subgroup 3.1	D		See Table 4	
4.4 Shear test		As in 4.4		
4.8 Rapid change of temperature		As in 4.8.3 T_A = Lower category temperature T_B = Upper category temperature		
4.8.2 Initial inspections				
Capacitance		As in 4.3.2.2		
Tangent of loss angle		As in 4.3.3.2		
4.8.4 Final inspections				
Visual examination		As in 4.2.2		No visible damage
Capacitance		As in 4.3.2.2		See detail specification
Tangent of loss angle		As in 4.3.3.2		See detail specification

Documents
Document Sharing Hub
Full document details: IEC 60384-20 2015

Table 5 *(3 of 5)*

Subclause number and test [a], inspection items	D or ND[b]	Conditions of test [a] and measurements	Number of specimens (n) and number of permissible non-conformances (c)	Performance requirements [a]
4.9 Climatic sequence				
4.9.2 Initial inspections				
Capacitance				
Tangent of loss		As in 4.3.2.2		
Angle				
at 10 kHz for $C_N \leq 1$ µF		As in 4.3.3.4		
at 1 kHz for $C_N > 1$ µF		As in 4.3.3.2		
4.9.3 Dry heat		As in 4.9.3 Temperature: upper category temperature Duration: 16 h		
4.9.4 Damp heat, cyclic, test Db, first cycle		As in 4.9.4		
4.9.5 Cold		As in 4.9.5 Temperature: lower category temperature Duration: 2 h		
4.9.6 Damp heat, cyclic, test Db, remaining cycles		As in 4.9.6	See Table 4	
4.9.7 Recovery		As in 4.9.7		
4.9.8 Final inspections				
Visual examination		As in 4.2.2		No visible damage Legible marking
Capacitance		As in 4.3.2.2		$\lvert \Delta C/C \rvert$ for Grade 1 and Grade 2: ≤3 %, Grade 3: ≤5 % of value measured in 4.9.2.
Tangent of loss angle:				
at 10 kHz for $C_N \leq 1$ µF		As in 4.3.3.4		Increase of tan δ: ≤0,002 5 for Grade 1 ≤0,004 for Grade 2 ≤0,005 for Grade 3 compared to values measured in 4.9.2
at 1 kHz for $C_N > 1$ µF		As in 4.3.3.2		Increase of tan δ: ≤0,001 5 for Grade 1 ≤0,002 5 for Grade 2 ≤0,003 for Grade 3 compared to values measured in 4.9.2
Insulation resistance		As in 4.3.4.2		≥50 % of values in 4.3.4.3 however, ≥25 % for Grade 3

Documents
Document Sharing Hub
Full document details: IEC 60384-20 2015

Table 5 *(4 of 5)*

Subclause number and test [a], inspection items	D or ND [b]	Conditions of test [a] and measurements	Number of specimens (n) and number of permissible non-conformances (c)	Performance requirements [a]
Subgroup 3.2	D		See Table 4	
4.10 Damp heat, steady state		As in 4.10.3		
4.10.2 Initial inspections				
Capacitance		As in 4.3.2.2		
Tangent of loss angle		As in 4.3.3.2		
4.10.4 Recovery		As in 4.10.4		
4.10.5 Final inspections				
Visual examination		As in 4.2.2		No visible damage
Capacitance		As in 4.3.2.2		$\lvert \Delta C/C \rvert$ for Grade 1 and Grade 2: ≤3 %, Grade 3: ≤5 % of value measured in 4.10.2.
Tangent of loss angle		As in 4.3.3.2		Increase of tan δ: ≤0,002 5 compared to values measured in 4.10.2.
Insulation resistance		As in 4.3.4.2		≥50 % of values in 4.3.4.3, however, ≥25 % for Grade 3
Subgroup 3.3	D		See Table 4	
4.11 Endurance		As in 4.11.3		
4.11.2 Initial inspections		As in 4.3.2.2		
Capacitance				
Tangent of loss angle				
at 10 kHz for $C_N \leq 1$ µF		As in 4.3.3.4		
at 1 kHz for $C_N > 1$ µF		As in 4.3.3.2		
4.11.4 Final inspections				No visible damage
Visual examination		As in 4.2.2		Legible marking
Capacitance		As in 4.3.2.2		$\lvert \Delta C/C \rvert \leq 5$ % for Grade 1 $\lvert \Delta C/C \rvert \leq 8$ % for Grade 2 and Grade 3 compared to measurements in 4.11.2
Tangent of loss angle:				Increase of tan δ:
at 10 kHz for $C_N \leq 1$ µF		As in 4.3.3.4		≤0,003 for Grade 1 ≤0,005 for Grade 2 and Grade 3 compared to values measured in 4.11.2
at 1 kHz for $C_N > 1$ µF		As in 4.3.3.2		Increase of tan δ: ≤0,002 for Grade 1 ≤0,003 for Grade 2 and Grade 3 compared to values measured in 4.11.2
Insulation resistance		As in 4.3.4.2		≥50 % of values in 4.3.4.3, however ≥30 % for Grade 3

Documents
Document Sharing Hub
Full document details: IEC 60384-20 2015