

INTERNATIONAL STANDARD



**Flexible insulating sleeving –
Part 3: Specifications for individual types of sleeving –
Sheet 247: Heat-shrinkable, polyolefin sleeving, dual wall, not flame retarded,
thick and medium wall**



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2019 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.



IEC 60684-3-247

Edition 2.0 2019-08
REDLINE VERSION

INTERNATIONAL STANDARD



**Flexible insulating sleeving –
Part 3: Specifications for individual types of sleeving –
Sheet 247: Heat-shrinkable, polyolefin sleeving, dual wall, not flame retarded,
thick and medium wall**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 29.035.20

ISBN 978-2-8322-7285-5

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD	3
INTRODUCTION	2
1 Scope	6
2 Normative references	6
3 Terms and definitions	7
4 Designation	7
5 Conditions of test	7
6 Requirements	7
7 Sleeving conformance	7
Annex A (informative) Guide to the available sizes and wall thicknesses	15
Bibliography	17
Table 1 – Property requirements (1 of 3)	8
Table 2 – Requirements for breakdown voltage	14
Table 3 – Resistance to selected fluids	14
Table 4 – Additional property requirements	15
Table A.1 – Type A medium wall	15
Table A.2 – Type B thick wall	16

INTERNATIONAL ELECTROTECHNICAL COMMISSION

FLEXIBLE INSULATING SLEEVING –

Part 3: Specifications for individual types of sleeving – Sheet 247: Heat-shrinkable, polyolefin sleeving, dual wall, not flame retarded, thick and medium wall

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.

International Standard IEC 60684-3-247 has been prepared by IEC technical committee 15: Solid electrical insulating materials.

This second edition cancels and replaces the first edition published in 2011 and Amendment 1:2016. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous editions:

- a) removal of the colour fastness to light test, as this is covered by the test for carbon black content;
- b) change of low temperature flexibility test to -20 °C to align with sheet 214;
- c) change of final conditioning temperature of peel strength samples to 200 °C to align with the temperature in Clause 5;
- d) removal of the fungus resistance test as there is no evidence that fungus growth is an issue either by testing or in use.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
15/890/FDIS	15/900/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all the parts in the IEC 60684 series, under the general title *Flexible insulating sleeving*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

This document is one of a series of standards which deals with flexible insulating sleeving for electrical purposes.

The series consists of three parts:

Part 1: Definitions and general requirements (IEC 60684-1)

Part 2: Methods of test (IEC 60684-2)

Part 3: Specifications for individual types of sleeving (IEC 60684-3)

This document comprises one of the sheets of Part 3 as follows:

Sheet 247: Heat-shrinkable, polyolefin sleeving, dual wall, not flame retarded, thick and medium wall

FLEXIBLE INSULATING SLEEVING –

Part 3: Specifications for individual types of sleeving – Sheet 247: Heat-shrinkable, polyolefin sleeving, dual wall, not flame retarded, thick and medium wall

1 Scope

This part of IEC 60684 gives the requirements for two types of heat-shrinkable, polyolefin sleeving, dual wall, not flame retarded with a nominal shrink ratio of 3:1.

This sleeving has been found suitable for use at temperatures of up to 100 °C.

- Type A: Medium wall, internal diameter up to 200,0 mm typically.
- Type B: Thick wall, internal diameter up to 200,0 mm typically.

These sleeveings are normally supplied in colour black.

Since these types of ~~sleeving~~ **sleeving** cover a significantly large range of sizes and wall thicknesses, **Annex A** (Tables A.1 and A.2) provides a guide to the range of sizes available. The actual size ~~shall~~ **will** be agreed between the user and supplier.

Materials which conform to this specification meet established levels of performance. However, the selection of a material by a user for a specific application ~~should~~ **will** be based on the actual requirements necessary for adequate performance in that application and not based on this specification alone.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60296:20032012, *Fluids for electrotechnical applications – Unused mineral insulating oils for transformers and switchgear*

~~IEC 60502-1:2004, Power cables with extruded insulation and their accessories for rated voltages from 1 kV ($U_m = 1,2$ kV) up to 30 kV ($U_m = 36$ kV) – Part 1: Cables for rated voltages of 1 kV ($U_m = 1,2$ kV) and 3 kV ($U_m = 3,6$ kV)~~

IEC 60684-1:2003, *Flexible insulating sleeving – Part 1: Definitions and general requirements*

IEC 60684-2:19972011, *Flexible insulating sleeving – Part 2: Methods of test*
~~Amendment 2 (2005)~~

IEC 60757:1983, *Code for designation of colours*

~~ISO 846:1997, Plastics – Evaluation of the action of micro-organisms~~

ISO 868:2003, *Plastics and ebonite – Determination of indentation hardness by means of a durometer (Shore hardness)*

ISO 11357-3:~~1999~~2018, *Plastics – Differential scanning calorimetry (DSC) – Part 3: Determination of temperature and enthalpy of melting and crystallization*

ISO 11358-1:~~1997~~2014, *Plastics – Thermogravimetry (TG) of polymers – Part 1: General principles*

3 Terms and definitions

No terms and definitions are listed this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Designation

The sleeving shall be identified by the following designation:

Description	IEC publication number	IEC part number	IEC sheet number	Type	Size (expanded and recovered internal diameter in mm)	Colour	Table 4* code
↓	↓	↓	↓	↓	↓	↓	↓
Sleeving	IEC 60684	- 3	- 247	- B	- 85,0/25,0	- BK	X

Any colour abbreviation shall comply with IEC 60757, where applicable. Non-standard colours shall be written out in full.

NOTE This information is for package labelling only, in accordance with IEC 60684-1.

~~* The addition of "X" at the end of the designation indicates that the properties contained in Table 4 have been agreed upon between the user and supplier.~~

5 Conditions of test

Unless otherwise specified, the sleeving shall be shrunk in a forced air circulation oven for (10 ± 1) min at $200 \text{ }^{\circ}\text{C} \pm 3 \text{ K}$ prior to testing.

6 Requirements

In addition to the general requirements given in IEC 60684-1, the sleeving shall comply with the requirements of Tables 1, 2, and 3 ~~and 4~~ where applicable.

7 Sleeving conformance

Conformance to the requirements of this specification shall normally be based on the results from typical sizes:

- Type A: Recovered ~~4D~~ internal diameter 25 mm to 30 mm

- Type B: Recovered ~~ID~~ internal diameter 25 mm to 30 mm

For the peel strength test, select a size to comply with the dimensions as detailed under the remarks in Table 1.

Table 1 – Property requirements (1 of 3)

Property	IEC 60684-2 clause or subclause	Units	Max. or Min.	Requirements	Remarks
Dimensions	3				
Internal diameter	3.1.2	mm			
Wall thickness	3.3.2	mm			
Concentricity	3.3.3	%			
expanded			Min.	50	
recovered			Min.	85	
Heat shock	6	-	-		Heat at 200 °C ± 5 K
Tensile strength	19.1 and 19.2	MPa	Min.	10	Jacket only, ignore flowing adhesive
Elongation at break	19.1 and 19.2	%	Min.	200	
Longitudinal change	9	%	Max.	-10 +5	
Bending at low temperature	14	-	-	No cracking shall be visible.	Test at -40 °C. For strips, the mandrel shall be between 20 and 22 times the wall thickness. Full section sleeving is tested unfilled and the mandrel shall be between 20 and 22 times the outer diameter.
Dimensional stability on storage	16	-	-	The dimensions shall remain as agreed.	See Clause 1 Scope.
Tensile strength	19.1 and 19.2	MPa	Min.	13	Jacket only.
Elongation at break	19.1 and 19.2	%	Min.	350	Use a jaw separation rate of 100 mm/min. Below 6,5mm Ø as sleeving. At 6,5 mm Ø and above as dumbbells.
Secant modulus at 2% elongation	19.4	MPa MPa	Min. Max.	80 160	Calculate cross-section area without adhesive.
Breakdown voltage	21	kV	Min.	Table 2	
Volume resistivity at room temperature after damp heat	23 23.4.2 23.4.4	Ω·m Ω·m	Min. Min.	10 ¹² 10 ¹¹	

Property	IEC 60684-2 clause or subclause	Units	Max. or Min.	Requirements	Remarks
Colour fastness to light	34			The colour standard contrast between the exposed and unexposed parts of the specimen shall be equal to or less than that of the fastness standard.	Fastness standard 5
Standard identification number			Min.		
Resistance to selected fluids	36				Use the fluids and test temperatures specified in Table 3.
Tensile strength	19.1 and 19.2	MPa	Min.	10	Immersion time (24 ± 1)h
Elongation at break	19.1 and 19.2	%	Min.	250	
Heat ageing	39				Heat at 150 °C ± 3 K.
Tensile strength	19.1 and 19.2	MPa	Min.	10	Jacket only.
Elongation at break	19.1 and 19.2	%	Min.	200	
Long term ageing	50				The ageing temperature shall be 100 °C ± 3 K.
Elongation at break	19.2	%	Min.	175	
Carbon black content	ISO 11358	%	Min.	2,5	
Hardness	ISO 868	Shore D	Min.	40	
Water absorption	40	%	Max.	0,5	

Property	IEC 60684-2 clause or subclause	Units	Max. or Min.	Requirements	Remarks
Peel strength	54	N/25 mm	Min.	<p>Cu—50</p> <p>Al—75</p> <p>Pb—40</p> <p>PE—100</p> <p>PVC—40</p> <p>EPR—50</p>	<p>Condition at 150 °C ± 3 K for (10 ± 1) min.</p> <p>For tests in addition to aluminium replace the mandrel with cable jacket material of PE, PVC and/or EPR that conforms to IEC 60502-1.</p> <p>See note 2</p>
Melting temperature	ISO 11357-3	°C	Min.	100	Adhesive only

NOTE 1—Where jacket only is indicated, the tensile strength calculation for cross-sectional area is based on the thickness of the jacket.

NOTE 2—Use a substrate diameter that is a minimum of 25 mm and is at least 20% above the recovered internal diameter of the sleeving.

Property	IEC 60684-2:2011 clause or subclause	Units	Max. or min.	Requirements	Remarks
Dimensions	3				
Internal diameter	3.1.2	mm			
Wall thickness	3.3.2	mm		To be agreed between purchaser and supplier	
Concentricity	3.3.3	%			
expanded			Min.	50	
recovered			Min.	85	
Heat shock	6	-	-		Heat at 200 °C ± 5 K
Tensile strength	19.2 and 19.3	MPa	Min.	10	Jacket only, ignore flowing adhesive
Elongation at break	19.2 and 19.3	%	Min.	200	Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb-bell samples cut from the sleeving
Longitudinal change	9	%	Max.	-10 + 5	
Bending at low temperature	14	-	-	No cracking shall be visible	Test at -20 °C For strips, the mandrel shall be between 20 times and 22 times the wall thickness. Full section sleeving is tested unfilled and the mandrel shall be between 20 times and 22 times the outer diameter.
Dimensional stability on storage	16	-	-	The dimensions shall remain as agreed	See Clause 1
Tensile strength	19.2 and 19.3	MPa	Min.	13	Jacket only
Elongation at break	19.2 and 19.3	%	Min.	350	Use a jaw separation rate of 100 mm/min. For internal diameters <6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb-bell samples cut from the sleeving.
Secant modulus at 2 % elongation	19.5	MPa	Min.	80	Calculate cross- section area without adhesive.
		MPa	Max.	160	
Breakdown voltage	21.2	kV	Min.	Table 2	
Volume resistivity at room temperature after damp heat	23				
	23.5.2	Ω·m	Min.	10 ¹²	
	23.5.4	Ω·m	Min.	10 ¹¹	

Table 1 (2 of 3)

Property	IEC 60684-2:2011 clause or subclause	Units	Max. or min.	Requirements	Remarks
Resistance to selected fluids	36				Use the fluids and test temperatures specified in Table 3
Tensile strength	19.2 and 19.3	MPa	Min.	10	Immersion time (24 ± 1) h
Elongation at break	19.2 and 19.3	%	Min.	250	Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb-bell samples cut from the sleeving
Heat ageing	39				Heat at 150 °C ± 3 K
Tensile strength	19.2 and 19.3	MPa	Min.	10	Jacket only
Elongation at break	19.2 and 19.3	%	Min.	200	Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb-bell samples cut from the sleeving
Long term ageing	50				The ageing temperature shall be 100 °C ± 3 K
Elongation at break	19.2 and 19.3	%	Min.	175	Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb-bell samples cut from the sleeving
Carbon black content	ISO 11358-1	%	Min.	2,5	Identify carbon black peak and report weight loss %
Hardness	ISO 868	Shore D	Min.	40	
Water absorption	40	%	Max.	0,5	

Table 1 (3 of 3)

Property	IEC 60684-2:2011 clause or subclause	Units	Max. or min.	Requirements	Remarks
Peel strength	54	N/25 mm	Min.	Cu – 50 Al – 75 PO-X – 100	<p>Use a Cu or Al tube with a minimum outer diameter of 25 mm and at least 20 % above the fully recovered internal diameter of the sleeving. The sleeving under test shall have a thickness of $2,0 \text{ mm} \pm 0,5 \text{ mm}$ when recovered on the tube. Other substrate materials and methods are subject to agreement between the supplier and the user.</p> <p>Prepare the Cu and Al tubes in the manner defined in IEC 60684-2:2011, 54.3. Precondition the prepared Cu and Al tubes in an oven at $100 \text{ }^{\circ}\text{C}$ for at least 30 min. Immediately place the sleeving on the prepared Cu or Al tubes and condition at $200 \text{ }^{\circ}\text{C} \pm 3 \text{ K}$ for $(10 \pm 1) \text{ min}$.</p> <p>To make the cross-linked polyolefin (PO-X) specimens shrink the sleeving onto the Cu or Al tubes by conditioning at $200 \text{ }^{\circ}\text{C} \pm 3 \text{ K}$ for $(10 \pm 1) \text{ min}$. Allow to cool, then abrade and clean the outer surface as detailed in IEC 60684-2:2011, 54.3. Finally, fix the narrow strip of adhesive masking tape longitudinally on the sleeving, then place the same sleeving on top and condition at $200 \text{ }^{\circ}\text{C} \pm 3 \text{ K}$ for $(10 \pm 1) \text{ min}$.</p>
Melting temperature	ISO 11357-3	$^{\circ}\text{C}$	Min.	100	<p>Adhesive only</p> <p>Value to be recorded is peak melting temperature (T_{pm})</p>