

INTERNATIONAL STANDARD



Semiconductor devices – Mechanical and climatic test methods – Part 15: Resistance to soldering temperature for through-hole mounted devices



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2020 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.



IEC 60749-15

Edition 3.0 2020-07
REDLINE VERSION

INTERNATIONAL STANDARD



**Semiconductor devices – Mechanical and climatic test methods –
Part 15: Resistance to soldering temperature for through-hole mounted devices**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 31.080.01

ISBN 978-2-8322-8686-9

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD	3
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Test apparatus	6
4.1 Solder pot	6
4.2 Dipping device	7
4.3 Heatsinks or shielding	7
5 Materials	7
5.1 Solder	7
5.2 Flux	8
6 Procedure	8
6.1 Test method	8
6.2 Ageing and pre-conditioning of specimens	8
6.3 Preparation of the solder bath	8
6.4 Use of flux	8
6.5 Solder dip	8
6.6 Precautions	8
6.7 Measurements	9
6.8 Failure criteria	9
7 Summary	9
Bibliography	10
Table 1 – Parameters for solder dipping	7

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**SEMICONDUCTOR DEVICES –
MECHANICAL AND CLIMATIC TEST METHODS –****Part 15: Resistance to soldering temperature
for through-hole mounted devices**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.

International Standard IEC 60749-15 has been prepared by IEC technical committee 47: Semiconductor devices.

This third edition cancels and replaces the second edition published in 2010. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) inclusion of new Clause 3, Terms and definitions;
- b) clarification of the use of a soldering iron for producing the heating effect;
- c) inclusion an option to use accelerated ageing.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
47/2630/FDIS	47/2639/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60749 series, published under the general title *Semiconductor devices – Mechanical and climatic test methods*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

SEMICONDUCTOR DEVICES – MECHANICAL AND CLIMATIC TEST METHODS –

Part 15: Resistance to soldering temperature for through-hole mounted devices

1 Scope

This part of IEC 60749 describes a test used to determine whether encapsulated solid state devices used for through-hole mounting can withstand the effects of the temperature to which they are subjected during soldering of their leads by using wave soldering ~~or a soldering iron~~.

In order to establish a standard test procedure for the most reproducible methods, the solder dip method is used because of its more controllable conditions. This procedure determines whether devices are capable of withstanding the soldering temperature encountered in printed wiring board assembly operations, without degrading their electrical characteristics or internal connections.

This test is destructive and may be used for qualification, lot acceptance and as a product monitor.

~~This test is, in general, in conformity with IEC 60068-2-20 but, due to specific requirements of semiconductors, the clauses of this standard apply.~~

~~2 General~~

The heat is conducted through the leads into the device package from solder heat at the reverse side of the board. This procedure does not simulate wave soldering or reflow heat exposure on the same side of the board as the package body.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60068-2-20, *Environmental testing – Part 2-20: Tests – Test T: Test methods for solderability and resistance to soldering heat of devices with leads*

IEC 60749-3, *Semiconductor devices – Mechanical and climatic test methods – Part 3: External visual examination*

IEC 60749-8, *Semiconductor devices – Mechanical and climatic test methods – Part 8: Sealing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

colophony

DEPRECATED: rosin

natural resin obtained as the residue after removal of turpentine from the oleo-resin of the pine tree, consisting mainly of abietic acid and related resin acids, the remainder being resin acid esters

Note 1 to entry: "Rosin" is a synonym for colophony, and is deprecated because of the common confusion with the generic term "resin".

3.2

lead-free solder

alloy that does not contain more than 0,1 % lead (Pb) by weight as its constituent and is used for joining components to substrates or for coating surfaces

[SOURCE: IEC 60194:2015, 75.1904, modified – The words "as its constituent" have been added to the definition.]

3.3

resistance to soldering heat

ability of device to withstand the highest temperature of the termination or lead in soldering process, within applicable temperature range of solder alloy

4 Test apparatus

4.1 Solder pot

A solder pot of sufficient size to contain at least 1 kg of solder shall be used. The solder pot dimensions shall allow full immersion of the leads without touching the bottom. The apparatus shall be capable of maintaining the solder at the temperature specified in Table 1.

Table 1 – Parameters for solder dipping

Parameter	Condition A (for wave solder)	Condition B (for soldering iron)
Temperature of molten solder °C	260 ± 5	350 ± 5
Number of immersions	≤ 2	≤ 2
Immersion rate mm s^{-1}	25 ± 5	25 ± 5
Dwell time s	10 ± 5	10 ± 5
Emersion rate mm s^{-1}	25 ± 5	25 ± 5
Distance between solder bath and device body mm	$1,5 \pm 0,5$	$1,5 \pm 0,5$

Parameter	SnPb solder	Pb-free solder
Temperature of molten solder °C	260 ± 5	270 ± 5
Number of immersions	≤ 2	≤ 2
Immersion rate mm s^{-1}	25 ± 6	25 ± 6
Dwell time s	10^{+2}_{-0}	7^{+2}_{-0}
Emersion rate mm s^{-1}	25 ± 6	25 ± 6

4.2 Dipping device

A mechanical dipping device shall be used that is capable of controlling the rates of immersion and emersion of the leads and providing the dwell time as specified in Table 1.

4.3 Heatsinks or shielding

If applicable, heatsinks or shielding shall be attached to the devices prior to the test and shall be as specified in the relevant specification.

5 Materials

5.1 Solder

The solder specification shall be as follows.

Chemical composition:

- for SnPb solder, the composition in percentage by weight shall be as follows:

~~Tin: 59 % to 65 %;~~

~~Lead: the remainder.~~

Sn60Pb40 or Sn63Pb37 (Sn ± 1 %) chemical composition

- for Pb-free solder, the composition in percentage by weight shall be as follows:

Silver: 3 % to 4 %;

Copper: 0,5 % to 1 %;

Tin: the remainder.

The solder shall not contain impurities which will adversely affect its properties.

Other solders and their applicable bath temperatures may be used as ~~specified~~ detailed in the relevant specification.

5.2 Flux

If flux is applied prior to solder dipping, the flux shall consist of 25 % by weight of colophony in 75 % by weight of isopropyl alcohol, unless otherwise detailed in the relevant specification.

6 Procedure

6.1 Test method

The method used in this procedure requires the specimen to be dipped into a solder bath under specified conditions. The solder bath method is the one which simulates most closely the soldering procedures of flow soldering and similar soldering processes. In circumstances where the solder dip method is considered to impracticable the specimen can be tested by the application of a heated soldering iron under controlled conditions. This is described in IEC 60068-2-20.

6.2 Ageing and pre-conditioning of specimens

If required by the relevant specification, the test conditioning shall be preceded by accelerated ageing such as steam ageing, damp heat conditioning, dry heat conditioning or unsaturated pressurized vapour conditioning. Accelerated ageing shall be performed in accordance with IEC 60068-2-20.

Any other special pre-conditioning of the specimens prior to testing shall be as ~~specified~~ detailed in the relevant specification. This preparation may include operations such as bending or other relocation of leads, and the attachment of heat sinks or protective shielding prior to solder dipping.

6.3 Preparation of the solder bath

The molten solder shall be stirred to assure that the temperature is uniform. The dross shall be skimmed from the surface of the molten solder just prior to dipping the part.

6.4 Use of flux

Where detailed in the relevant specification, all leads of the specimen shall be dipped in flux prior to solder dip; excess flux shall be removed by draining for a suitable time.

6.5 Solder dip

The part shall be attached to the dipping device (see 4.2) and the leads immersed in the molten solder ~~until to within 1 mm of the body of the device under test reaches the dimensions specified in Table 1.~~ The parameters for solder temperature, dwell time, number of immersions and rates of immersion and emersion are defined in Table 1. ~~Unless otherwise detailed in the procurement specification, Condition A shall be used.~~ After the dipping process, the part shall be allowed to cool in air and, if flux has been used, residues shall be removed with isopropanol or ethanol.

6.6 Precautions

Prior to and after the solder immersion, precautionary measures shall be taken to prevent undue exposure of the part to the heat radiated by the solder bath.