

INTERNATIONAL STANDARD



Optical fibres – Part 1-54: Measurement methods and test procedures – Gamma irradiation



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2018 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing 21 000 terms and definitions in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.



IEC 60793-1-54

Edition 3.0 2018-01
REDLINE VERSION

INTERNATIONAL STANDARD



**Optical fibres –
Part 1-54: Measurement methods and test procedures – Gamma irradiation**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 33.180.10

ISBN 978-2-8322-5277-2

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD	4
1 Scope	6
2 Normative references	6
3 Terms and definitions	7
4 Apparatus	7
4.1 General	7
4.2 Radiation source	7
4.2.1 Testing of environmental background radiation	7
4.2.2 Testing of adverse nuclear environments	7
4.3 Optical source	7
4.4 Optical filters/monochromators	7
4.5 Cladding mode stripper	7
4.6 Fibre support and positioning apparatus	7
4.7 Optical splitter	7
4.8 Input launch conditions	8
4.8.1 Class A, Category A1 fibres (graded index multimode fibres)	8
4.8.2 Class A, Category A2 fibres (quasi-step and step index fibres)	8
4.8.3 Class B fibres (single-mode fibres)	8
4.9 Detector – Signal detection electronics	8
4.10 Optical power meter	8
4.11 Radiation dosimeter	8
4.12 Temperature-controlled container	8
4.13 Test reel	8
5 Sampling and specimens	8
5.1 Specimens	8
5.1.1 Fibre specimen	8
5.1.2 Cable specimen	8
Specimen for environmental background radiation test	8
Specimen for testing adverse nuclear environments	8
5.2 Test sample length	9
5.3 Test reel	9
5.4 Ambient light shielding	9
6 Procedure	9
6.1 General	9
6.2 Calibration of radiation source	9
6.3 Preparation and pre-conditioning	9
6.4 Attenuation measurement for environmental background radiation	10
6.5 Attenuation measurement for adverse nuclear environment	10
7 Calculations	11
7.1 Change in optical attenuation Δa (environmental background radiation test)	11
7.2 Change in optical transmittance, a (adverse nuclear environmental radiation test)	11
7.3 Normalisation of the results	11
8 Results	11
8.1 Information to be provided with each measurement	11
8.2 Information available upon request	12

9	Specification information	12
	Bibliography	13

INTERNATIONAL ELECTROTECHNICAL COMMISSION

OPTICAL FIBRES –

**Part 1-54: Measurement methods and test procedures –
Gamma irradiation**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.

International Standard IEC 60793-1-54 has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

This third edition cancels and replaces the second edition published in 2012. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) test conditions related to photobleaching have been changed;
- b) the test length has been modified to yield a total induced attenuation in the test sample at the end of the irradiation between 3 dB and 10 dB.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
86A/1833/FDIS	86A/1848/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60793 series, published under the general title *Optical fibres*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The “colour inside” logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this publication using a colour printer.

OPTICAL FIBRES –

Part 1-54: Measurement methods and test procedures – Gamma irradiation

1 Scope

This document outlines a method for measuring the steady state response of optical fibres and optical cables exposed to gamma radiation. It can be employed to determine the level of radiation-induced attenuation produced in Class B single-mode or Class A, category A1 and A2 multimode optical fibres, in either cabled or uncabled form, due to exposure to gamma radiation.

The attenuation of cabled and uncabled optical fibres generally increases when exposed to gamma radiation. This is primarily due to the trapping of radiolytic electrons and holes at defect sites in the glass (i.e. the formation of "colour centres"). This test procedure focuses on two regimes of interest: the low dose rate regime suitable for estimating the effect of environmental background radiation, and the high dose rate regime suitable for estimating the effect of adverse nuclear environments. The testing of the effects of environmental background radiation is achieved with an attenuation measurement approach similar to IEC 60793-1-40 method A, cut-back. The effects of adverse nuclear environments are tested by monitoring the power before, during and after exposure of the test sample to gamma radiation. The depopulation of colour centres by light (photo bleaching) or by heat causes recovery (lessening of radiation induced attenuation). Recovery ~~may~~ can occur over a wide range of time which depends on the irradiation time and annealing temperature. This complicates the characterization of radiation induced attenuation since the attenuation depends on many variables including the temperature of the test environment, the configuration of the sample, the total dose and the dose rate applied to the sample and the light level used to measure it.

This test is not a material test for the non-optical material components of a fibre optic cable. If degradation of cable materials exposed to irradiation is ~~to be~~ studied, other test methods will be ~~required~~ used.

This test method is written to contain a clear, concise listing of instructions. The background knowledge that is necessary to perform correct, relevant and expressive irradiation tests as well as to limit measurement uncertainty is presented separately in IEC TR 62283.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60793-1-40, *Optical Fibres – Part 1-40: Measurement methods and test procedures – Attenuation*

IEC 60793-1-44, *Optical fibres – Part 1-44: Measurement methods and test procedures – Cut-off wavelength*

IEC 60793-1-46, *Optical fibres – Part 1-46: Measurement methods and test procedures – Monitoring of changes in optical transmittance*

IEC 61280-4-1, *Fibre-optic communication subsystem test procedures – Part 4-1: Installed cable plant – Multimode attenuation measurement*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Apparatus

4.1 General

Attention is drawn to the fact that strict regulations and suitable protective facilities are to be adopted in the laboratory for this test. Carefully selected trained personnel shall be used to perform this test. It can be extremely hazardous to test personnel if it is improperly performed or without qualified conditions.

4.2 Radiation source

4.2.1 Testing of environmental background radiation

A ^{60}Co or equivalent ionising source shall be used to deliver gamma radiation. This environment is characterised by relatively low total dose and dose rate.

4.2.2 Testing of adverse nuclear environments

A ^{60}Co or equivalent ionizing source(s) shall be used to deliver gamma radiation. This environment is characterised by higher total dose and dose rate.

4.3 Optical source

An optical source such as a ~~lamp~~ white light source, laser or light emitting diode emitting at wavelengths compatible with the optical fibres under test shall be used. The wavelength of the source shall be according to the detailed specification.

The optical source shall be stable in intensity over a time period sufficient to perform the measurement. The power coupled from the source into the test sample shall be ~~≤~~ -30 dBm (1,0 µW) with a tolerance of ± 2 dBm or as specified in the detail specification. The optical source ~~shall~~ may be modulated with a pulsed signal at a 50 % duty cycle, if a lock-in amplifier is used.

~~NOTE—If a source that couples more than 1,0 µW is used, photo-bleaching may occur.~~

4.4 Optical filters/monochromators

Unless otherwise specified, wavelength tolerances of ± 20 nm shall be obtained by filtering the optical source with a set of optical filters or a monochromator. The 3 dB optical bandwidth of the filters shall be less than or equal to 25 nm.

4.5 Cladding mode stripper

When necessary, a device that extracts cladding modes shall be employed at the input end and output end of the test sample. If the fibre coating materials are designed to strip cladding modes, a cladding mode stripper is not required.

4.6 Fibre support and positioning apparatus

A means of stable support for the input end of the test sample, such as a vacuum chuck, shall be arranged. This support shall be mounted on a positioning device so that the end of the test sample can be repeatedly positioned in the input beam.

4.7 Optical splitter

An optical splitter shall divert a small portion of the input light to a reference detector. The reference path shall be used to monitor system fluctuations for the duration of the test.

4.8 Input launch conditions

4.8.1 Class A, Category A1 fibres (graded index multimode fibres)

An equilibrium mode simulator shall be used to attenuate higher order propagation modes and to establish a steady-state mode condition near the input end of the fibre. The requirements for the launch conditions for sub-category A1a graded index multimode fibre measurements are defined in IEC 61280-4-1.

4.8.2 Class A, Category A2 fibres (quasi-step and step index fibres)

Launch conditions shall be created as specified in the detail specification.

4.8.3 Class B fibres (single-mode fibres)

An optical lens system or fibre pigtail may be employed to excite the test fibre. The power coupled into the test sample shall be stable for the duration of the test. If an optical lens system is used, a method of making the positioning of the fibre less sensitive is to overfill the fibre end spatially and angularly. If a pigtail is used, it may be necessary to use index matching material to eliminate interference effects. A high order mode filter shall be employed to remove high order propagating modes in the wavelength range greater than or equal to the cut-off wavelength of the test fibre. The test condition specified in IEC 60793-1-44, method C, satisfies this requirement.

4.9 Detector – Signal detection electronics

An optical detector that is linear and stable over the range of intensities that are encountered shall be used. A typical system might include a photovoltaic mode photodiode amplified by a current input preamplifier, with synchronous detection by a lock-up amplifier.

4.10 Optical power meter

A suitable optical power meter shall be used to determine that the power coupled from the optical source into the test sample is ~~less than or~~ equal to 1,0 µW or the level specified in the detail specification.

4.11 Radiation dosimeter

Thermo luminescent LiF or CaF crystal detectors (TLDs) or an ion chamber detector shall be used to measure the total radiation dose received by the specimen fibre.

4.12 Temperature-controlled container

Unless otherwise specified, the temperature-controlled container shall have the capability of maintaining the specified temperatures to within ± 2 °C.

4.13 Test reel

The test reel shall not act as a shield or sink for the radiation used in this test. Reels of wood, plastic or similar non-conducting materials would, in principle, act as transparent to the radiation. The additional absorption shall be taken into account for exact measurements.

An appropriate dose build-up layer of similar material shall be used.

5 Sampling and specimens

5.1 Specimens

5.1.1 Fibre specimen

The test specimen shall be a representative sample of the fibre specified in the detail specification.

5.1.2 Cable specimen

The test specimen shall be a representative sample of the cable described in the detail specification and shall contain at least one of the specified fibres.

~~4.2 Specimen for environmental background radiation test~~

~~Unless otherwise specified in the detail specification, the length of the test sample shall be $(3\,000 \pm 30)$ m. (Where reactor constraints dictate smaller lengths, the length of the test sample may be $(1\,100 \pm 20)$ m.) A minimum length at the ends of the test sample (typically 5 m) shall reside outside of the test chamber and be used to connect the optical source to the detector. The irradiated length of the test sample shall be reported.~~

~~4.3 Specimen for testing adverse nuclear environments~~

~~Unless otherwise specified in the detail specification, the length of the test sample shall be $(250 \pm 2,5)$ m. (When test conditions require a high total dose and dose rate a shorter test sample length may be necessary). A minimum length at the ends of the test sample (typically 5 m) shall remain outside of the test chamber and be used to connect the optical source to the detector. The irradiated length of the test sample shall be reported.~~

5.2 Test sample length

Unless otherwise specified in the detail specification, the length of the test sample shall be chosen according to the expected induced attenuation and depends on the fibre type to be tested. The length shall be selected to yield a total induced attenuation in the test sample at the end of the irradiation of between 3 dB and 10 dB. The influence of the fibre leads connecting the test sample shall be minimised below 10 % of the total induced attenuation by reducing their length, application of shielding, and selection of fibres with low radiation sensitivity. The irradiated length of the test sample shall be reported.

5.3 Test reel

The test sample shall be spooled onto a reel with a drum diameter of more than or equal to 10 cm, or that ~~is~~ as specified in the detail specification. Allowance shall be made for the unspooling of a measured length of the test sample from each end of the reel to allow for attachment to the optical measurement equipment. An alternative deployment method allows the fibre to be loosely wound in a coil of specified diameter. The minimum bending radius shall be considered.

5.4 Ambient light shielding

The test sample shall be shielded from ambient light to prevent external photobleaching.

6 Procedure

6.1 General

The radiation tests differ in exposure dose, dose rate, exposure time and temperature. The tests are an environmental background radiation test and an adverse nuclear radiation test.

6.2 Calibration of radiation source

Calibration of the radiation source for dose uniformity and level shall be made prior to the test sample being set up in the chamber. ~~Four TLDs shall be placed in the area of exposure and the centre of the TLDs shall be placed where the axis of the test reel will be placed. (Four TLDs are used to get a representative average value.) A dose equal to or greater than the actual test dose shall be used to calibrate the system. To maintain the highest possible accuracy in measuring the test dose, the TLDs shall not be used more than once.~~ Dose and dose rate measurements at four positions shall be made in the area of exposure where the test reel will be placed (four positions are used to get a representative average value).

6.3 Preparation and pre-conditioning

The test sample shall be preconditioned in the temperature chamber at (25 ± 5) °C for 1 h prior to testing, or at the test temperature for a preconditioned time as specified in the detail specification.

The input end of the short test length shall be placed in the positioning device and aligned in the test set to obtain maximum optical power as measured with a calibrated power meter.

The power at the input end of the test sample shall be measured with a calibrated power meter. If necessary, the source power level shall be adjusted so that the power at the input end of the fibre is ~~less than~~ 1,0 μ W or as specified in the detail specification.

~~NOTE—If a source that couples more than 1,0 μ W is used, photobleaching may occur.~~

With the radiation source off, the input end of the test sample shall be positioned to obtain maximum optical power at the detector. Once set, the input launch conditions shall not be changed during the gamma irradiation portion of the test.

~~A chart recorder or~~ suitable continuous measurement device shall be connected to the detection system so that a continuous power measurement can be made. The measurement equipment shall be set up such that the detection signal does not exceed the limits of the equipment.

Before starting the irradiation the stability of the measurement setup shall be obtained. The total fluctuation shall be below 10 % of the total induced attenuation at the end of irradiation.

A ^{60}Co or equivalent ionizing source(s) shall be used to deliver gamma radiation at a desired dose rate.

~~Dose rate levels are only approximate levels since the radiation source characteristics change. A variation in dose rate as high as ± 50 % can be expected between sources.~~ The time required to turn the radiation source on or off shall be < 10 % of the total exposure time.

It is important that the temperature is kept constant during the tests. If the test should be performed at different temperatures, then the attenuation prior to irradiation has to be measured for different temperatures for each specified wavelength.

6.4 Attenuation measurement for environmental background radiation

An attenuation measurement of the test sample shall be performed, at the specified test wavelengths, in accordance with IEC 60793-1-40, method A, cut-back. The attenuation a_1 of the fibre prior to exposure to the gamma radiation source shall be recorded. The environmental temperature shall be the same as during the up-coming irradiation tests when the initial attenuation measurement is performed.

Unless otherwise specified in the detailed specification, environmental background radiation effects, due to exposure to gamma radiation, shall be determined by subjecting the test sample to a nominal dose rate of 0,02 Gray/hour (Gy/h). The test sample shall be exposed to a total dose of 0,1 Gray (Gy). Different dose rates and total dose ~~values may~~ can be called for in the detail specification in order to simulate particular specific conditions.

Upon completion, and within 2 h of the irradiation process, an attenuation measurement of the test sample shall be performed in accordance with IEC 60793-1-40, method A, cut-back. The attenuation a_2 of the test sample after exposure to the gamma radiation source shall be recorded.

6.5 Attenuation measurement for adverse nuclear environment

The monitoring of the change of optical transmittance of the test sample shall be performed, at the specified test wavelengths, in accordance with method IEC 60793-1-46.

The output power P_B from the sample prior exposure to the gamma radiation source shall be recorded.

Unless otherwise specified in the detailed specification, adverse nuclear radiation effects, due to exposure to gamma radiation, shall be determined by subjecting the test sample to a nominal dose rate of 1 000 Gy/h. The test sample shall be exposed to a ~~total~~ dose of 1 000 Gy. Different dose rates and total dose ~~values may~~ can be called for in the detail specification in order to simulate particular specific conditions.

The output power from the sample shall be recorded for the duration of the gamma irradiation cycle. With help of the initial attenuation measurements, prior irradiation, one can determine the radiation induced attenuation in the fibre.

The power shall also be recorded for at least 15 min after completion of the irradiation process or as specified in the detail specification. The power level of the reference detector shall also be recorded during the recovery time after completion of the irradiation process.

7 Calculations

7.1 Change in optical attenuation Δa (environmental background radiation test)

$$\Delta a = a_2 - a_1 \text{ dB} \quad (1)$$

where

a_1 is the attenuation of the test sample prior to exposure to gamma radiation;

a_2 is the attenuation of the test sample after exposure to gamma radiation.

7.2 Change in optical transmittance, a (adverse nuclear environmental radiation test)

The change in optical transmittance a shall be calculated for each wavelength by using the following formula (testing of adverse nuclear environment):

$$a_0 = -10 \lg (P_0/P_B) \text{ dB} \quad (2)$$

$$a_{15} = -10 \lg (P_{15}/P_B) \text{ dB} \quad (3)$$

where

P_0 is the power output of the test sample within 1 s after irradiation is discontinued, unless otherwise specified;

P_{15} is the power output of the test sample 15 min after irradiation is discontinued, unless otherwise specified;

P_B is the power output of the test sample before irradiation begins;

a_0 is the change in optical transmittance of the test sample immediately after irradiation;

a_{15} is the change in optical transmittance of the test sample 15 min after irradiation.

7.3 Normalisation of the results

The results of the reference measurements should be used to normalize the test results if significant system instability is noted.

$$a_{\text{REF}} = -10 \lg (P_{E'}/P_{B'}) \text{ dB} \quad (4)$$

where

$P_{E'}$ is the power measured by the reference detector at the end of the measurement;

$P_{B'}$ is the power measured by the reference detector before irradiation begins.

Normalized test results that account for system instability are calculated with the following formulae:

$$a_{0\text{NOR}} = a_0 - a_{\text{REF}} \text{ dB} \quad (5)$$

$$a_{15\text{NOR}} = a_{15} - a_{\text{REF}} \text{ dB} \quad (6)$$

8 Results

8.1 Information to be provided with each measurement

Report the following information with each measurement:

- date and title of test;
- length of test sample exposed to radiation;
- test wavelengths;
- test temperatures;
- material-, dimensions- and design of the test reel;
- test dose and dose rate;
- change in attenuation Δa (environmental background radiation test);
- change in optical transmittances a_0 and a_{15} (adverse nuclear environment);
- characteristics of test sample such as fibre type, cable type, dimensions and composition;
- chart recording of test events.

8.2 Information available upon request

The following information shall be available upon request:

- description of radiation source;
- description of dosimeters used;
- type of optical source, model number and manufacturer;
- description of optical filters or monochromator;
- description of cladding mode stripper;
- description of input launch simulator and launch conditions used;
- type of optical splitter used;
- description of detection and recording apparatus;
- description of the characteristics of temperature chamber;
- date of latest calibration of test equipment;
- name or identification number of operator.

9 Specification information

The detail specification shall specify the following information:

- type of test sample to be tested;
- test reel diameter;
- test temperature(s);
- failure or acceptance criteria;
- number of samples;
- test wavelengths;
- total dose and dose rate;
- other test conditions.