

INTERNATIONAL STANDARD

NORME INTERNATIONALE



Optical fibres –

Part 2-10: Product specifications – Sectional specification for category A1 multimode fibres

Fibres optiques –

Partie 2-10: Spécifications de produits – Spécification intermédiaire pour les fibres multimodales de catégorie A1



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2022 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Secretariat
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Discover our powerful search engine and read freely all the publications previews. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 300 terminological entries in English and French, with equivalent terms in 19 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Recherche de publications IEC - webstore.iec.ch/advsearchform

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études, ...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et une fois par mois par email.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Découvrez notre puissant moteur de recherche et consultez gratuitement tous les aperçus des publications. Avec un abonnement, vous aurez toujours accès à un contenu à jour adapté à vos besoins.

Electropedia - www.electropedia.org

Le premier dictionnaire d'électrotechnologie en ligne au monde, avec plus de 22 300 articles terminologiques en anglais et en français, ainsi que les termes équivalents dans 19 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.



IEC 60793-2-10

Edition 7.1 2022-01
CONSOLIDATED VERSION

INTERNATIONAL STANDARD

NORME INTERNATIONALE



**Optical fibres –
Part 2-10: Product specifications – Sectional specification for category A1
multimode fibres**

**Fibres optiques –
Partie 2-10: Spécifications de produits – Spécification intermédiaire pour les
fibres multimodales de catégorie A1**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 33.180.10

ISBN 978-2-8322-1075-0

**Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

REDLINE VERSION

VERSION REDLINE



Optical fibres –

Part 2-10: Product specifications – Sectional specification for category A1 multimode fibres

Fibres optiques –

Partie 2-10: Spécifications de produits – Spécification intermédiaire pour les fibres multimodales de catégorie A1

CONTENTS

FOREWORD	5
1 Scope	7
2 Normative references	8
3 Terms and definitions	9
4 Abbreviated terms	10
5 Specifications	10
5.1 General.....	10
5.2 Dimensional requirements.....	10
5.3 Mechanical requirements	12
5.4 Transmission requirements	12
5.5 Environmental requirements	14
5.5.1 General	14
5.5.2 Mechanical environmental requirements (common to all fibres in category A1).....	15
5.5.3 Transmission environmental requirements	16
Annex A (normative) Specifications for sub-categories A1-OM2, A1-OM3, A1-OM4 and A1-OM5 multimode fibres.....	17
A.1 General.....	17
A.2 Dimensional requirements.....	17
A.3 Mechanical requirements	18
A.4 Transmission requirements	18
A.5 Environmental requirements	20
Annex B (normative) Specifications for sub-category A1-OM1 multimode fibres	21
B.1 General.....	21
B.2 Dimensional requirements.....	21
B.3 Mechanical requirements	21
B.4 Transmission requirements	22
B.5 Environmental requirements	22
Annex C (normative) Specifications for sub-category A1d multimode fibres	23
C.1 General.....	23
C.2 Dimensional requirements.....	23
C.3 Mechanical requirements	23
C.4 Transmission requirements	24
C.5 Environmental requirements	24
Annex D (normative) Fibre differential mode delay (DMD), calculated effective modal bandwidth (EMB _c) and calculated overfilled modal bandwidth (OMB _c) requirements	25
D.1 A1-OM3 fibre DMD requirements	25
D.1.1 General	25
D.1.2 DMD templates	25
D.1.3 DMD interval masks.....	26
D.2 A1-OM3 fibre EMB _c requirements	27
D.2.1 General	27
D.2.2 Calculated effective bandwidth	27
D.3 A1-OM4 DMD requirements	29
D.3.1 General	29

D.3.2	DMD templates	29
D.3.3	DMD interval masks	30
D.4	A1-OM4 fibre EMB _C requirements	30
D.4.1	General	30
D.4.2	Calculated effective bandwidth	30
D.5	A1-OM5 fibre modal bandwidth requirements	30
D.5.1	General	30
D.5.2	Calculated effective modal bandwidth	31
D.6	A1-OM2, A1-OM3, A1-OM4 and A1-OM5 calculated overfilled modal bandwidth	31
Annex E (informative)	System, modal bandwidth, and transmitter considerations	33
E.1	Background	33
E.2	System considerations	33
E.2.1	A1-OM3 and A1-OM4 fibres	33
E.2.2	A1-OM5 fibre	33
E.3	Effective modal bandwidth (EMB)	34
E.4	Transmitter encircled flux (EF) and centre wavelength requirements	37
E.4.1	Encircled flux	37
E.4.2	Centre wavelength for A1-OM3 and A1-OM4 fibres	38
E.4.3	Centre wavelength for A1-OM5 fibre	38
Annex F (informative)	Bandwidth nomenclature explanation	40
Annex G (informative)	Preliminary indications for items needing further study	41
G.1	Effective modal bandwidth (EMB) at 1 300 nm	41
G.2	Scaling of EMB with DMD	41
Annex H (informative)	Applications and cabling categories supported by A1 fibres	43
Annex I (informative)	1-Gigabit, 10-Gigabit, 25-Gigabit, 40-Gigabit and 100-Gigabit Ethernet applications	44
Bibliography		50
Figure 1	– Relation between bandwidths at 850 nm and 1 300 nm	14
Figure D.1	– DMD template requirements	26
Figure E.1	– Estimated minimum wide band EMB versus wavelength for A1-OM3	35
Figure E.2	– Estimated minimum wide band EMB versus wavelength for A1-OM4	36
Figure E.3	– Estimated minimum wide band EMB versus wavelength for A1-OM5	37
Figure E.4	– Approximate position of DMD weightings relative to the EF boundaries of Equations (E.10) and (E.11)	38
Table 1	– Cross reference IEC A1 multimode fibre designations to IEC 60793-2-10:2017	8
Table 2	– Dimensional attributes and measurement methods	11
Table 3	– Dimensional requirements common to category A1 fibres	11
Table 4	– Additional dimensional attributes required in sub-category specifications	11
Table 5	– Mechanical attributes and measurement methods	12
Table 6	– Mechanical requirements common to category A1 fibres	12
Table 7	– Transmission attributes and measurement methods	13
Table 8	– Additional transmission attributes required in sub-category specifications	13
Table 9	– Environmental exposure tests	15

Table 10 – Attributes measured for environmental tests	15
Table 11 – Strip force for environmental tests	15
Table 12 – Tensile strength for environmental tests	16
Table 13 – Stress corrosion susceptibility for environmental tests	16
Table 14 – Change in attenuation for environmental tests	16
Table A.1 – Dimensional requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres	18
Table A.2 – Mechanical requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres	18
Table A.3 – Transmission requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres	19
Table B.1 – Dimensional requirements specific to A1-OM1 fibres	21
Table B.2 – Mechanical requirements specific to A1-OM1 fibres	21
Table B.3 – Transmission requirements specific to A1-OM1 fibres	22
Table C.1 – Dimensional requirements specific to A1d fibres	23
Table C.2 – Mechanical requirements specific to A1d fibres	23
Table C.3 – Transmission requirements specific to A1d fibres	24
Table D.1 – DMD templates for A1-OM3 fibres	25
Table D.2 – DMD interval masks for A1-OM3 fibres	27
Table D.3 – DMD weightings	28
Table D.4 – DMD templates for A1-OM4 fibres	30
Table D.5 – DMD interval masks for A1-OM4 fibres	30
Table D.6 – DMD weighting for OMB _C	32
Table F.1 – Bandwidth nomenclature explanation	40
Table H.1 – Some standardised applications supported by A1-OM2, A1-OM3, A1-OM4, A1-OM5 fibres and in some cases A1-OM1 fibres	43
Table I.1 – Summary of 1 Gb/s, 10 Gb/s, 25 Gb/s, 40 Gb/s and 100 Gb/s Ethernet requirements and capabilities	45

INTERNATIONAL ELECTROTECHNICAL COMMISSION

OPTICAL FIBRES –

Part 2-10: Product specifications – Sectional specification for category A1 multimode fibres

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This consolidated version of the official IEC Standard and its amendment has been prepared for user convenience.

IEC 60793-2-10 edition 7.1 contains the seventh edition (2019-05) [documents 86A/1932/FDIS and 86A/1939/RVD] and its amendment 1 (2022-01) [documents 86A/2121/CDV and 86A/2140/RVC].

In this Redline version, a vertical line in the margin shows where the technical content is modified by amendment 1. Additions are in green text, deletions are in strikethrough red text. A separate Final version with all changes accepted is available in this publication.

International Standard IEC 60793-2-10 has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

This seventh edition constitutes a technical revision.

This edition includes the following significant change with respect to the previous edition: revision of the naming convention for A1 multimode fibres, which better matches with those found in ISO/IEC standards. These changes are outlined in the scope of this document along with a cross reference table for the new names.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60793 series, published under the general title *Optical fibres*, can be found on the IEC website.

The committee has decided that the contents of the base publication and its amendment will remain unchanged until the stability date indicated on the IEC web site under webstore.iec.ch in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

OPTICAL FIBRES –

Part 2-10: Product specifications – Sectional specification for category A1 multimode fibres

1 Scope

This part of IEC 60793 is applicable to optical fibre sub-categories A1-OM1, A1-OM2, A1-OM3, A1-OM4, A1-OM5, and A1d. These fibres are used or can be incorporated in information transmission equipment and optical fibre cables.

Sub-categories A1-OM2, A1-OM3, A1-OM4 and A1-OM5 apply to 50/125 μm graded index fibre in four bandwidth grades. Each of these bandwidth grades is defined for two levels of macrobend loss performance that are distinguished by "a" or "b" suffix. Those sub-categories with suffix "a" are specified to meet traditional macrobend loss performance levels. Those sub-categories with suffix "b" are specified to meet enhanced macrobend loss (i.e. lower loss) performance levels.

Sub-category A1-OM5 is specified to support single wavelength or multi-wavelength transmission systems in the vicinity of 850 nm to 950 nm. Although not normatively specified, bandwidth information covering this wavelength range is also included for A1-OM3 and A1-OM4.

Sub-category A1-OM1 applies to 62,5/125 μm graded index fibre and sub-category A1d applies to 100/140 μm graded index fibre.

Other applications include, but are not restricted to, the following: short reach, high bit-rate systems in telephony, distribution and local networks carrying data, voice and/or video services; on-premises intra-building and inter-building fibre installations including data centres, local area networks (LANs), storage area networks (SANs), private branch exchanges (PBXs), video, various multiplexing uses, outside telephone cable plant use, and miscellaneous related uses.

Three types of requirements apply to these fibres:

- general requirements, as defined in IEC 60793-2;
- specific requirements common to the category A1 multimode fibres covered in this document and which are given in Clause 5;
- particular requirements applicable to individual fibre sub-categories and models, or specific applications, which are defined in the normative specification Annexes A to D.

Table 1 shows the cross reference between the IEC A1 multimode optical fibre designations used in this document compared to those used in IEC 60793-2-10:2017. The table also refers to the normative annexes A, B and C for the A1 sub-category multimode fibres in this document that contains the detailed specification.

Table 1 – Cross reference IEC A1 multimode fibre designations to IEC 60793-2-10:2017

Annex	Sub-category	Sub-category/Model	Core diameter (nominal)	ISO/IEC 11801-1:2017
	This document designations	IEC 60793-2-10:2017 designations		Usage of cabled OMx fibres
A	A1-OM2	A1a.1	50 µm ^a	OM2 ^b
	A1-OM3	A1a.2	50 µm	OM3
	A1-OM4	A1a.3	50 µm	OM4
	A1-OM5	A1a.4	50 µm	OM5
B	A1-OM1	A1b	62,5 µm ^c	OM1 ^d
C	A1d	A1d	100 µm	-
^a Historically, ISO/IEC 11801:2002 also defined OM2 cables made with 62,5/125 µm fibres having a minimum overfilled launch bandwidth of 500 MHz·km at 850 nm and 500 MHz·km at 1 300 nm. This specific bandwidth combination of 62,5/125 µm fibre is not part of this document. ^b OM2 cables are not supported for new installations within ISO/IEC 11801-1:2017. ^c Historically, ISO/IEC 11801:2002 also defined OM1 cables made with 50/125 µm fibres having a minimum overfilled launch bandwidth of 200 MHz·km at 850 nm and 500 MHz·km at 1 300 nm. This specific bandwidth combination of 50/125 µm fibre is not part of this document. ^d OM1 cables are not supported for new installations within ISO/IEC 11801-1:2017.				

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60793-1-20, *Optical fibres – Part 1-20: Measurement methods and test procedures – Fibre geometry*

IEC 60793-1-21, *Optical fibres – Part 1-21: Measurement methods and test procedures – Coating geometry*

IEC 60793-1-22, *Optical fibres – Part 1-22: Measurement methods and test procedures – Length measurement*

IEC 60793-1-30, *Optical fibres – Part 1-30: Measurement methods and test procedures – Fibre proof test*

IEC 60793-1-31, *Optical fibres – Part 1-31: Measurement methods and test procedures – Tensile strength*

IEC 60793-1-32, *Optical fibres – Part 1-32: Measurement methods and test procedures – Coating strippability*

IEC 60793-1-33, *Optical fibres – Part 1-33: Measurement methods and test procedures – Stress corrosion susceptibility*

IEC 60793-1-40, *Optical fibres – Part 1-40: Measurement methods and test procedures – Attenuation*

IEC 60793-1-41, *Optical fibres – Part 1-41: Measurement methods and test procedures – Bandwidth*

IEC 60793-1-42, *Optical fibres – Part 1-42: Measurement methods and test procedures – Chromatic dispersion*

IEC 60793-1-43, *Optical fibres – Part 1-43: Measurement methods and test procedures – Numerical aperture measurement*

IEC 60793-1-46, *Optical fibres – Part 1-46: Measurement methods and test procedures – Monitoring of changes in optical transmittance*

IEC 60793-1-47, *Optical fibres – Part 1-47: Measurement methods and test procedures – Macrobending loss*

IEC 60793-1-49, *Optical fibres – Part 1-49: Measurement methods and test procedures – Differential mode delay*

IEC 60793-1-50, *Optical fibres – Part 1-50: Measurement methods and test procedures – Damp heat (steady state) tests*

IEC 60793-1-51, *Optical fibres – Part 1-51: Measurement methods and test procedures – Dry heat (steady state) tests*

IEC 60793-1-52, *Optical fibres – Part 1-52: Measurement methods and test procedures – Change of temperature tests*

IEC 60793-1-53, *Optical fibres – Part 1-53: Measurement methods and test procedures – Water immersion tests*

IEC 60793-2, *Optical fibres – Part 2: Product specifications – General*

IEC 61280-4-1:2009, *Fibre-optic communication subsystem test procedures – Part 4-1: Installed cable plant – Multimode attenuation measurement*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Abbreviated terms

CPR	coupled power ratio
DMD	differential mode delay
EF	encircled flux
EMB	effective modal bandwidth
EMB _c	calculated effective modal bandwidth
LAN	local area network
MMF	multimode fibre
NA	numerical aperture
OFL	overfilled launch
OMB _c	overfilled launch modal bandwidth calculated from differential mode delay (also known as OFL _c)
PBX	private branch exchange
PMD	physical medium dependent
ROFL	radial overfilled launch
SAN	storage area network

5 Specifications

5.1 General

The fibre consists of a glass core with a graded index profile and a glass cladding in accordance with IEC 60793-2.

The term "glass" usually refers to material consisting of non-metallic oxides.

5.2 Dimensional requirements

Dimensional attributes and measurement methods are given in Table 2.

Requirements common to all fibres in category A1 are indicated in Table 3.

Table 4 lists additional attributes that shall be specified by each sub-category specification.

Table 2 – Dimensional attributes and measurement methods

Attributes	Measurement methods
Cladding diameter	IEC 60793-1-20
Core diameter ^{a, b}	IEC 60793-1-20
Cladding non-circularity	IEC 60793-1-20
Core non-circularity	IEC 60793-1-20
Core-cladding concentricity error	IEC 60793-1-20
Primary coating diameter	IEC 60793-1-21
Primary coating non-circularity	IEC 60793-1-21
Primary coating-cladding concentricity error	IEC 60793-1-21
Fibre length	IEC 60793-1-22
^a Core diameter is specified at $850 \text{ nm} \pm 10 \text{ nm}$ with a test specimen length of $2,0 \text{ m} \pm 0,2 \text{ m}$ and a threshold value, k_{CORE} , of 0,025 for A1 fibres except A1-OM2b, A1-OM3b, A1-OM4b, A1-OM5b fibres. ^b Core diameter is specified at $850 \text{ nm} \pm 10 \text{ nm}$ with a test specimen length of $100 \text{ m} \pm 5 \%$ and a threshold value, k_{CORE} , of 0,025 for A1-OM2b, A1-OM3b, A1-OM4b, A1-OM5b fibres.	

Table 3 – Dimensional requirements common to category A1 fibres

Attributes	Unit	Limits
Core non-circularity	%	≤ 6
Primary coating diameter – uncoloured ^a	μm	245 ± 10
Primary coating diameter – coloured ^a	μm	250 ± 15
Primary coating-cladding concentricity error	μm	$\leq 12,5$
Fibre length	km	^b
^a The limits on primary coating diameter are most commonly used in telecommunications cables. There are other applications, which use other primary coating diameters, several of which are listed below. Alternative nominal primary coating diameters and tolerance (μm): 400 ± 40 500 ± 50 700 ± 100 900 ± 100		
^b Length requirements vary and should be agreed between supplier and customer.		

Table 4 – Additional dimensional attributes required in sub-category specifications

Attributes
Cladding diameter
Cladding non-circularity
Core diameter
Core-cladding concentricity error

5.3 Mechanical requirements

Mechanical attributes and measurement methods are given in Table 5.

Requirements common to all fibres in category A1 are in Table 6.

Table 5 – Mechanical attributes and measurement methods

Attributes	Test methods
Proof test	IEC 60793-1-30
Tensile strength	IEC 60793-1-31
Primary coating strippability	IEC 60793-1-32
Stress corrosion susceptibility	IEC 60793-1-33

Table 6 – Mechanical requirements common to category A1 fibres

Attributes	Unit	Limits
Proof stress level	GPa	$\geq 0,69^a$
Average strip force ^b	N	$1,0 \leq F_{\text{avg}} \leq 5,0$
Peak strip force ^b	N	$1,0 \leq F_{\text{peak}} \leq 8,9$
Tensile strength (median) for 0,5 m specimen length	GPa	$\geq 3,8$
Stress corrosion susceptibility constant, n_d	-	≥ 18
^a The proof test value of 0,69 GPa equals about 1 % strain or about 8,8 N force, for A1-OM1 to A1-OM5 fibres. For the relation between these different units, see IEC TR 62048:2014, 8.4. ^b Either average strip force or peak strip force, which are defined in the test procedure, may be specified by agreement between supplier and customer.		

5.4 Transmission requirements

Transmission attributes and measurement methods are given in Table 7.

Table 8 lists additional attributes that shall be specified by each sub-category specification.

Table 7 – Transmission attributes and measurement methods

Attributes	Measurement methods
Attenuation coefficient	IEC 60793-1-40
Modal bandwidth ^{a,b}	IEC 60793-1-41
Numerical aperture ^{c,d}	IEC 60793-1-43
Chromatic dispersion	IEC 60793-1-42
Change of optical transmission	IEC 60793-1-46
Macrobending loss	IEC 60793-1-47
Differential mode delay ^e	IEC 60793-1-49
^a For modal bandwidth, either overfilled launch (OFL) or overfilled launch modal bandwidth calculated from differential mode delay (OMB_c) can be used. OMB_c is the reference test method for A1-OM2, A1-OM3 and A1-OM4 fibres at 850 nm and is the required method for A1-OM5 fibres at 850 nm and 953 nm. ^b 850 nm modal bandwidth is specified with a test specimen length of 1 000 m ± 5 % for A1-OM3 to A1-OM5 fibres. For A1-OM3 fibres, the 850 nm modal bandwidth is measured at 850 nm ± 10 nm. For A1-OM4 and A1-OM5 fibres, the 850 nm modal bandwidth is measured at 850 nm ± 2 nm. For A1-OM5 fibre, the modal bandwidth is also measured at 953 nm ± 6 nm. ^c Numerical aperture is specified at 850 nm ± 10 nm with a test specimen length of 2 m ± 0,2 m and a threshold value, k_{NA}, of 0,05 for A1 fibres except A1-OM2b, A1-OM3b, A1-OM4b, A1-OM5b fibres. ^d Numerical aperture is specified at 850 nm ± 10 nm with a test specimen length of 100 m ± 5 % and a threshold value, k_{NA}, of 0,05 for A1-OM2b, A1-OM3b, A1-OM4b and A1-OM5b fibres. ^e Differential mode delay is specified with a test specimen length of 1 000 m ± 5 % for A1-OM3, A1-OM4 and A1-OM5 fibres. For A1-OM3 fibres, the DMD is measured at 850 nm ± 10 nm. For A1-OM4 and A1-OM5 fibres, the DMD is measured at 850 nm ± 2 nm. For A1-OM5 fibre, the DMD is also measured at 953 nm ± 6 nm.	

Specification compliance of chromatic dispersion can be assured by compliance to the numerical aperture (NA) specification for A1 fibre.

Table 8 – Additional transmission attributes required in sub-category specifications

Attributes
Attenuation coefficient
Modal bandwidth
Chromatic dispersion
Numerical aperture
Macrobending loss

For attenuation coefficient and modal bandwidth, the sub-category specifications may contain ranges of specifiable values instead of fixed limits. In this case, the actual values of the maximum attenuation coefficient and minimum modal bandwidth, at both 850 nm and 1 300 nm (or just at one of these wavelengths) shall be agreed between supplier and customer. For commercial purposes, the modal bandwidth is linearly normalized to 1 km.

For guidance purposes, Annex H shows a number of standardised applications supported by A1 fibres and Annex I shows transmission capabilities for these fibres.

The indicated maximum attenuation coefficients apply to uncabled optical fibres; for the maximum cabled attenuation coefficients, reference is made to IEC 60794-1-1, which can be used in conjunction with this document. Tighter specifications for the fibre may be requested to account for added attenuation in the cabling process.

Remarks on the specification of modal bandwidth:

Care should be taken in writing dual wavelength bandwidth specifications. It is understood that for category A1 fibres, the bandwidth at 850 nm may be related to the bandwidth at 1 300 nm in a way shown in Figure 1, depending on the refractive index parameter, g (see IEC 60793-2). See [1]¹, page 50, and [2], page 255, for similar figures. The shaded region under the curve of Figure 1 can be defined as the dual window area. In this area, regions X, Y, and Z are examples of where a fibre manufacturer may choose to optimise the process. That is, centre the production bandwidth peak at 850 nm, 1 300 nm, or between these two wavelengths.

Due to this optimisation of the manufacturing process, there will be combinations of bandwidth that are not possible (i.e., outside the shaded region).




Figure 1 – Relation between bandwidths at 850 nm and 1 300 nm

5.5 Environmental requirements

5.5.1 General

Environmental exposure tests and measurement methods are documented in two forms:

- relevant environmental attributes and test procedures are given in Table 9;
- measurements of a particular mechanical or transmission attribute that may change on the application of the environment are listed in Table 10.

¹ Numbers in square brackets refer to the Bibliography.

Table 9 – Environmental exposure tests

Environmental exposure	Test
Damp heat	IEC 60793-1-50
Dry heat	IEC 60793-1-51
Change of temperature	IEC 60793-1-52
Water immersion	IEC 60793-1-53

Table 10 – Attributes measured for environmental tests

Attribute	Measurement method
Change in optical transmission	IEC 60793-1-46
Attenuation	IEC 60793-1-40
Strip force	IEC 60793-1-32
Tensile strength	IEC 60793-1-31
Stress corrosion susceptibility	IEC 60793-1-33

These tests are normally conducted periodically as type-tests for a fibre and coating design. Unless otherwise indicated, the recovery period allowed between the completion of the environmental exposure and performing the attribute measurements shall be as stated in the particular environmental test method.

5.5.2 Mechanical environmental requirements (common to all fibres in category A1)

5.5.2.1 General

These tests are, in practice, the most severe requirements amongst the environments defined in Table 9.

Tables 11, 12, and 13 give the prescriptions for strip force, tensile strength and stress corrosion susceptibility respectively.

5.5.2.2 Strip force

The following attributes shall be verified following removal of the fibre from the particular environment.

Table 11 – Strip force for environmental tests

Environment	Average strip force N	Peak strip force N
Damp heat	$1,0 \leq F_{\text{avg}} \leq 5,0$	$1,0 \leq F_{\text{peak}} \leq 8,9$
Water immersion	$1,0 \leq F_{\text{avg}} \leq 5,0$	$1,0 \leq F_{\text{peak}} \leq 8,9$

5.5.2.3 Tensile strength

The following attribute shall be verified following removal of the fibre from the environment.

Table 12 – Tensile strength for environmental tests

Environment	Median tensile strength specimen length: 0,5 m GPa	15th percentile tensile strength specimen length: 0,5 m GPa
Damp heat	$\geq 3,03$	$\geq 2,76$
NOTE These requirements do not apply to hermetically coated fibre.		

5.5.2.4 Stress corrosion susceptibility

The following attribute shall be verified following removal of the fibre from the environment.

Table 13 – Stress corrosion susceptibility for environmental tests

Environment	Stress corrosion susceptibility constant, n_d
Damp heat	≥ 18
NOTE This requirement does not apply to hermetically coated fibre.	

5.5.3 Transmission environmental requirements

Change in attenuation from the initial value shall be less than the values in Table 14. Attenuation shall be measured periodically during the entire exposure to each environment and after removal.

Table 14 – Change in attenuation for environmental tests

Environment	Wavelength nm	Attenuation increase dB/km
Damp heat	850	$\leq 0,20$
	1 300	$\leq 0,20$
Dry heat	850	$\leq 0,20$
	1 300	$\leq 0,20$
Change of temperature	850	$\leq 0,20$
	1 300	$\leq 0,20$
Water immersion	850	$\leq 0,20$
	1 300	$\leq 0,20$

Annex A (normative)

Specifications for sub-categories A1-OM2, A1-OM3, A1-OM4 and A1-OM5 multimode fibres

A.1 General

Annex A contains particular requirements applicable to sub-categories A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres. Common requirements, repeated here for ease of reference from the main body of this document, are noted by a clause entry in the "Reference" column. The "Reference" column also refers to other annexes containing relevant information on the attribute. Relevant notes from the main body of this document are not repeated but indicated with a superscript "SS".

Sub-categories A1-OM2, A1-OM3, A1-OM4 and A1-OM5 are 50/125 μm graded index multimode fibres in four bandwidth grades. All are specified using overfilled bandwidth metrics, while sub-categories A1-OM3, A1-OM4 and A1-OM5 also apply differential mode delay measurements to deliver laser-optimised performance near 850 nm. Sub-category A1-OM5 also specifies both overfilled and differential mode delay bandwidth metrics at 953 nm to deliver laser-optimized performance over a wavelength range in the vicinity of 850 nm to 950 nm. A1-OM3 complies with A1-OM2 specifications. A1-OM4 complies with A1-OM3 specifications. A1-OM5 complies with A1-OM4 specifications.

Sub-category A1-OM2, A1-OM3, A1-OM4 and A1-OM5 are also specified for two levels of macrobend loss performance that are distinguished by "a" or "b" suffix. Those with suffix "a" (i.e. models A1-OM2a, A1-OM3a, A1-OM4a and A1-OM5a) are specified to meet traditional macrobend loss performance levels. Those with suffix "b" (i.e. models A1-OM2b, A1-OM3b, A1-OM4b and A1-OM5b) are specified to meet enhanced macrobend loss (i.e. lower loss) performance levels, and thereby also comply with traditional macrobend loss performance.

The nomenclature for the A1-OM2, A1-OM3, A1-OM4 and A1-OM5 sub-categories establishes a coding hierarchy that permits designation of fibres with increasing specificity. For example, purchase orders for A1-OM3 may be filled by A1-OM3a or A1-OM3b. As a result, where specifications and descriptions apply to all models at lower hierarchical levels, only the common portion of the name is stated.

The dimensional, mechanical and environmental requirements are common to all and specified in Tables A.1 and A.2. The common and distinguishing transmission requirements are specified in Table A.3.

A.2 Dimensional requirements

Table A.1 contains dimensional requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres.

Table A.1 – Dimensional requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres

Attributes	Unit	Limits	Reference
Cladding diameter	μm	125 ± 1	
Cladding non-circularity	%	≤ 1	
Core diameter ^{SS}	μm	$50 \pm 2,5$	
Core-cladding concentricity error	μm	≤ 2	
Core non-circularity	%	≤ 6	5.2
Primary coating diameter – uncoloured ^{SS}	μm	245 ± 10	5.2
Primary coating diameter – coloured ^{SS}	μm	250 ± 15	5.2
Primary coating-cladding concentricity error	μm	$\leq 12,5$	5.2
Length	km	(see 5.2)	5.2
^{SS} See notes in the main body of this document.			

A.3 Mechanical requirements

Table A.2 contains the mechanical requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres.

Table A.2 – Mechanical requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres

Attributes	Unit	Limits	Reference
Proof stress level ^{SS}	GPa	$\geq 0,69$	5.3
Average strip force ^{SS}	N	$1,0 \leq F_{\text{avg}} \leq 5,0$	5.3
Peak strip force ^{SS}	N	$1,0 \leq F_{\text{peak}} \leq 8,9$	5.3
^{SS} See notes in the main body of this document..			

A.4 Transmission requirements

Table A.3 contains transmission requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres.

Table A.3 – Transmission requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres

Attributes			Unit	Limits				Reference
Fibre sub-category				A1-OM2	A1-OM3	A1-OM4	A1-OM5	
Targeted operational wavelength(s) ^a			nm	850				Annex E
Maximum attenuation coefficient at 850 nm			dB/km	2,5				
Maximum attenuation coefficient at 953 nm			dB/km	Not specified				1,8
Maximum attenuation coefficient at 1 300 nm			dB/km	0,8				
Minimum modal bandwidth-length product for overfilled launch at 850 nm ^{ss}			MHz·km	500	1 500	3 500	3 500	Clause D.6
Minimum modal bandwidth-length product for overfilled launch at 953 nm ^{ss}			MHz·km	Not specified				Clause D.6
Minimum modal bandwidth-length product for overfilled launch at 1 300 nm			MHz·km	500				
Minimum effective modal bandwidth-length product at 850 nm ^{ss e}			MHz·km	Not specified	2 000 Meet Clause D.1 or Clause D.2	4 700 Meet Clause D.3 or Clause D.4	4 700 Meet Clause D.5	Annexes D, E, F, G
Minimum effective modal bandwidth-length product at 953 nm ^{ss e}			MHz·km	Not specified				Annexes D, E, F, G
Numerical aperture ^{ss}			Dimensionless	0,200 ± 0,015				
Fibre model				A1-OM2a	A1-OM3a	A1-OM4a	A1-OM5a	
Maximum macro-bending loss ^b	Bending radius	Number of turns	dB	Max at 850 nm / 1 300 nm				
		37,5 mm		0,5 / 0,5				
		15 mm		1,0 / 1,0				
Fibre model				A1-OM2b	A1-OM3b	A1-OM4b	A1-OM5b	
Maximum macro-bending loss ^b	Bending radius	Number of turns	dB	Max at 850 nm / 1 300 nm				
		37,5 mm		0,5 / 0,5				
		15 mm		0,1 / 0,3				
		7,5 mm		0,2 / 0,5				

Zero dispersion wavelength, λ_0	nm	$1\,295 \leq \lambda_0 \leq 1\,340$ ^c	$1\,297 \leq \lambda_0 \leq 1\,328$ ^d	
Zero dispersion slope, S_0 ^e	ps/(nm ² ·km)	$S_0 \leq 0,105$ from $1\,295 \text{ nm} \leq \lambda_0 \leq 1\,310 \text{ nm}$, and $\leq 0,000\,375 (1\,590 - \lambda_0)$ from $1\,310 \text{ nm} \leq \lambda_0 \leq 1\,340 \text{ nm}$ ^c	$S_0 \leq 4 (-103) / (840 (1 - (\lambda_0/840)^4))$ ^d	
^a Targeted operational wavelength(s) is informative. ^b The launch condition for the macrobending loss measurement shall fulfil that described in IEC 61280-4-1. ^c The worst case chromatic dispersion coefficient at 850 nm (e.g. $S_0 = 0,093\,75 \text{ ps}/(\text{nm}^2 \cdot \text{km})$ at $\lambda_0 = 1\,340 \text{ nm}$ or $S_0 = 0,101\,25 \text{ ps}/(\text{nm}^2 \cdot \text{km})$ at $\lambda_0 = 1\,320 \text{ nm}$) is $-104 \text{ ps}/(\text{nm} \cdot \text{km})$. ^d The coordinate that generates the worst-case dispersion for operating wavelengths from 840 nm to 1 000 nm is $\lambda_0 = 1\,328 \text{ nm}$, $S_0 = 0,093\,477 \text{ ps}/(\text{nm}^2 \cdot \text{km})$. The worst case chromatic dispersion coefficient at 850 nm is $-98,5 \text{ ps}/(\text{nm} \cdot \text{km})$. ^e When assessing system link performance at wavelengths from 840 nm to 953 nm, refer to the appropriate estimated minimum EMB equations found in Annex E in addition to the dispersion specifications for A1-OM3, A1-OM4, and A1-OM5 fibres. ^{ss} See notes in the main body of this document.				

A.5 Environmental requirements

The requirements of 5.5 shall be met.

Annex B (normative)

Specifications for sub-category A1-OM1 multimode fibres

B.1 General

Annex B contains particular requirements applicable to A1-OM1 fibres. Common requirements, repeated here for ease of reference from the main body of this document, are noted by a clause entry in the "Reference" column. Relevant notes from the main body of this document are not repeated but indicated with a superscript "SS".

Sub-category A1-OM1 fibre is a 62,5/125 µm graded index fibre.

B.2 Dimensional requirements

Table B.1 contains dimensional requirements specific to A1-OM1 fibres.

Table B.1 – Dimensional requirements specific to A1-OM1 fibres

Attributes	Unit	Limits	Reference
Cladding diameter	µm	125 ± 2	
Cladding non-circularity	%	≤ 2	
Core diameter ^{SS}	µm	$62,5 \pm 3$	
Core-cladding concentricity error	µm	≤ 3	
Core non-circularity	%	≤ 6	5.2
Primary coating diameter – uncoloured ^{SS}	µm	245 ± 10	5.2
Primary coating diameter – coloured ^{SS}	µm	250 ± 15	5.2
Primary coating-cladding concentricity error	µm	$\leq 12,5$	5.2
Length ^{SS}	km	(see 5.2)	5.2
^{SS} See notes in the main body of this document.			

B.3 Mechanical requirements

Table B.2 contains the mechanical requirements specific to A1-OM1 fibres.

Table B.2 – Mechanical requirements specific to A1-OM1 fibres

Attributes	Unit	Limits	Reference
Proof stress level ^{SS}	GPa	$\geq 0,69$	5.3
Average strip force ^{SS}	N	$1,0 \leq F_{avg} \leq 5,0$	5.3
Peak strip force ^{SS}	N	$1,0 \leq F_{peak} \leq 8,9$	5.3
^{SS} See notes in the main body of this document.			

B.4 Transmission requirements

Table B.3 contains transmission requirements specific to A1-OM1 fibres.

Table B.3 – Transmission requirements specific to A1-OM1 fibres

Attributes	Unit	Limits	Reference
Maximum attenuation coefficient at 850 nm	dB/km	3,0	
Maximum attenuation coefficient at 1 300 nm	dB/km	1,0	
Minimum modal bandwidth-length product at 850 nm	MHz·km	200	
Minimum modal bandwidth-length product at 1 300 nm	MHz·km	500	
Numerical aperture ^{SS}	Dimensionless	$0,275 \pm 0,015$	
Maximum macrobending loss 100 turns on bending radius of 37,5 mm at wavelengths 850 nm and 1 300 nm ^a	dB	0,5	
Zero dispersion wavelength, λ_0	nm	$1\,320 \leq \lambda_0 \leq 1\,365$ ^b	
Zero dispersion slope S_0 – from $1\,320 \text{ nm} \leq \lambda_0 \leq 1\,348 \text{ nm}$ – from $1\,348 \text{ nm} \leq \lambda_0 \leq 1\,365 \text{ nm}$	ps/(nm ² ·km)	$\leq 0,11$ ^b $\leq 0,001 (1\,458 - \lambda_0)$ ^b	
^a The launch condition for the macrobending loss measurement shall fulfil that described in IEC 61280-4-1. ^b The worst case chromatic dispersion coefficient at 850 nm ($S_0 = 0,11 \text{ ps}/(\text{nm}^2 \cdot \text{km})$ at $\lambda_0 = 1\,348 \text{ nm}$) is $-125 \text{ ps}/(\text{nm} \cdot \text{km})$. ^{SS} See notes in the main body of this document.			

B.5 Environmental requirements

The requirements of 5.5 shall be met.

Annex C (normative)

Specifications for sub-category A1d multimode fibres

C.1 General

Annex C contains particular requirements for A1d fibres. Common requirements, repeated here for ease of reference from this document, are noted by an entry in the "Reference" column. Relevant notes from the main body of this document are not repeated but indicated with a superscript "SS".

Sub-category A1d fibre is a 100/140 µm graded index fibre.

C.2 Dimensional requirements

Table C.1 contains dimensional requirements specific to A1d fibres.

Table C.1 – Dimensional requirements specific to A1d fibres

Attributes	Unit	Limits	Reference
Cladding diameter	µm	140 ± 4	
Cladding non-circularity	%	≤ 4	
Core diameter ^{SS}	µm	100 ± 5	
Core-cladding concentricity error	µm	≤ 6	
Core non-circularity	%	≤ 6	5.2
Primary coating diameter – uncoloured ^{SS}	µm	245 ± 10	5.2
Primary coating diameter – coloured ^{SS}	µm	250 ± 15	5.2
Primary coating-cladding concentricity error	µm	$\leq 12,5$	5.2
Length ^{SS}	km	(see 5.2)	5.2
^{SS} See notes in the main body of this document.			

C.3 Mechanical requirements

Table C.2 contains the mechanical requirements specific to A1d fibres.

Table C.2 – Mechanical requirements specific to A1d fibres

Attributes	Unit	Limits	Reference
Proof stress level ^{SS}	GPa	$\geq 0,69$	5.3
Average strip force ^{SS}	N	$1,0 \leq F_{\text{avg}} \leq 5,0$	5.3
Peak strip force ^{SS}	N	$1,0 \leq F_{\text{peak}} \leq 8,9$	5.3
^{SS} See notes in the main body of this document.			

C.4 Transmission requirements

Table C.3 contains transmission requirements specific to A1d fibres.

Table C.3 – Transmission requirements specific to A1d fibres

Attributes	Unit	Limits	Reference
Maximum attenuation coefficient at 850 nm ^a	dB/km	3,5 to 7,0	
Maximum attenuation coefficient at 1 300 nm ^a	dB/km	1,5 to 4,5	
Minimum modal bandwidth-length product at 850 nm ^a	MHz·km	10 to 200	
Minimum modal bandwidth-length product at 1 300 nm ^a	MHz·km	100 to 300	
Numerical aperture ^{SS}	Dimensionless	$0,26 \pm 0,03$ or $0,29 \pm 0,03$	
Maximum macrobending loss	dB	For further study	
Zero dispersion wavelength, λ_0	nm	$1\,330 \leq \lambda_0 \leq 1\,385$ ^b	
Zero dispersion slope S_0 – from $1\,330\text{ nm} \leq \lambda_0 \leq 1\,365\text{ nm}$ – from $1\,365\text{ nm} \leq \lambda_0 \leq 1\,385\text{ nm}$	ps/(nm ² ·km)	$\leq 0,105$ ^b $\leq 0,000\,5 (1\,575 - \lambda_0)$ ^b	
^a The limit column forms a range of values that may be specified. ^b The worst case chromatic dispersion coefficient at 850 nm ($S_0 = 0,105$ ps/(nm ² ·km) at $\lambda_0 = 1\,365$ nm) is –126 ps/(nm·km). ^{SS} See notes in the main body of this document.			

C.5 Environmental requirements

The requirements of 5.5 shall be met.

Annex D (normative)

Fibre differential mode delay (DMD), calculated effective modal bandwidth (EMB_c) and calculated overfilled modal bandwidth (OMB_c) requirements

D.1 A1-OM3 fibre DMD requirements

D.1.1 General

A1-OM3 fibres selected using the DMD mask method shall meet the requirements of D.1.2 and D.1.3. The radial limits, R_{INNER} and R_{OUTER} , were established for transmitters meeting the requirements of Clause E.4.

Refer to Annex E for information regarding effective modal bandwidth (EMB).

D.1.2 DMD templates

A1-OM3 fibres shall meet at least one of the six templates in Table D.1, each of which includes an inner and outer mask requirement, when measured according to IEC 60793-1-49.

Table D.1 – DMD templates for A1-OM3 fibres

Template number	Inner mask DMD (ps/m) for $R_{\text{INNER}} = 5 \mu\text{m}$ to $R_{\text{OUTER}} = 18 \mu\text{m}$	Outer mask DMD (ps/m) for $R_{\text{INNER}} = 0 \mu\text{m}$ to $R_{\text{OUTER}} = 23 \mu\text{m}$
1	$\leq 0,23$	$\leq 0,70$
2	$\leq 0,24$	$\leq 0,60$
3	$\leq 0,25$	$\leq 0,50$
4	$\leq 0,26$	$\leq 0,40$
5	$\leq 0,27$	$\leq 0,35$
6	$\leq 0,33$	$\leq 0,33$

The DMD requirements in Table D.1 are illustrated in Figure D.1. In this figure, the allowable DMD (as measured according to IEC 60793-1-49) is plotted versus the radial offset position of the single mode probe. There is a trade-off between the tightness of the inner mask and the outer mask to ensure a sufficient amount of the baud energy from a transmitter (meeting the launch specifications) arrives within the required time period (defined by the baud rate of the transmission system).




Figure D.1 – DMD template requirements

The "floating" characteristic of the inner mask is also illustrated in Figure D.1. In this figure, the inner mask (5 μm to 18 μm) may be positioned vertically (temporally) anywhere within the outer mask (0 μm to 23 μm). The DMD is more tightly constrained in the inner mask to allow for looser tolerances on the outer mask providing for improved ability to manufacture fibre conforming to this requirement. In the case of the 0,33 ps/m mask, the requirement is the same over the whole range from 0 μm to 23 μm creating a "flat" mask.

IEC 60793-1-49 can be used to ensure a minimum effective modal bandwidth-length product, when using sources meeting appropriate restrictions. When the launch condition requirements on the transmitters are coupled to the DMD requirements on the fibre, a balance can be achieved between fibre tolerance and transmitter tolerance. A careful study, using fibres contributed by several different fibre manufacturers and laser transmitters from several different source manufacturers, and including extensive and detailed simulations, shows that the above coupled specifications on fibre and sources will yield a minimum effective modal bandwidth-length product of 2 000 MHz·km [3] to [14].

The use of a template on the values of DMD achieves an effective trade-off between transmitter and fibre properties. The transmitter launch condition is bounded by encircled flux requirements at 4,5 μm and 19 μm as discussed in Clause E.4. The limitation on the transmitter encircled flux at the 4,5 μm radius assures that very little energy is carried by the lowest order modes of the fibre, allowing the relaxed tolerance on modal structure excited at small radii. The limitation on the transmitter encircled flux at the 19 μm radius assures that very little energy is carried by the highest order modes of the fibre, allowing the relaxed tolerance on modal structure excited at high radii.

D.1.3 DMD interval masks

The A1-OM3 fibre DMD shall not exceed 0,25 ps/m for any of the radial offset intervals given in Table D.2.

Table D.2 – DMD interval masks for A1-OM3 fibres

Interval number	R_{INNER} μm	R_{OUTER} μm
1	7	13
2	9	15
3	11	17
4	13	19

These interval masks screen out fibres having DMD that change too rapidly over short radial ranges. Fibres passing this screen have lower inter-symbol interference than those that do not.

D.2 A1-OM3 fibre EMB_c requirements

D.2.1 General

A1-OM3 fibres selected using the EMB_c method shall meet the requirements of D.2.2.

D.2.2 Calculated effective bandwidth

The DMD optical pulse shapes can be weighted by a set of launch distributions to determine a corresponding set of EMB_c values. The minimum EMB_c (minEMB_c) within this set shall meet the requirement of Equation (D.1):

$$\text{minEMB}_c \geq 1\,770 \text{ MHz}\cdot\text{km} \quad (\text{D.1})$$

where

minEMB_c is determined from the complex transfer function as described in IEC 60793-1-49 using the weights defined in Table D.3.

NOTE 1 Minimum EMB_c is a fibre parameter, and it is possible that its value is not optimal for use in system models. Refer to Annex E for information regarding the corresponding system parameter called the "effective modal bandwidth" (EMB) and its relationship to EMB_c .

NOTE 2 Refer to Annex F for additional explanation of bandwidth nomenclature.

Weightings within Table D.3 are provided for DMD measured at $1\,\mu\text{m}$ radial intervals starting from the centre of the core ($r = 0$) for ten simulated lasers with encircled flux (EF) metrics that correspond to those of ten actual lasers. The DMD weightings in Table D.3 are specific to sources meeting the specifications of Clause E.4.

Table D.3 – DMD weightings

Radial position	Laser ID				
r (μm)	1	2	3	4	5
0	0	0	0	0	0
1	0,033 023	0,023 504	0	0	0
2	0,262 463	0,188 044	0	0	0
3	0,884 923	0,634 634	0	0	0
4	2,009 102	1,447 235	0,007 414	0,005 637	0,003 034
5	3,231 216	2,376 616	0,072 928	0,055 488	0,029 856
6	3,961 956	3,052 908	0,262 906	0,200 05	0,107 634
7	3,694 686	3,150 634	0,637 117	0,483 667	0,258 329
8	2,644 369	2,732 324	1,197 628	0,896 95	0,458 494
9	1,397 552	2,060 241	1,916 841	1,402 833	0,661 247
10	0,511 827	1,388 339	2,755 231	1,957 805	0,826 035
11	0,110 549	0,834 722	3,514 797	2,433 247	1,000 204
12	0,004 097	0,419 715	3,883 317	2,639 299	1,294 439
13	0,000 048	0,160 282	3,561 955	2,397 238	1,813 982
14	0,001 111	0,047 143	2,617 093	1,816 953	2,506 95
15	0,005 094	0,044 691	1,480 325	1,296 977	3,164 213
16	0,013 918	0,116 152	0,593 724	1,240 553	3,572 113
17	0,026 32	0,219 802	0,153 006	1,700 02	3,618 037
18	0,036 799	0,307 088	0,012 051	2,240 664	3,329 662
19	0,039 465	0,329 314	0	2,394 077	2,745 395
20	0,032 152	0,268 541	0	1,952 429	1,953 241
21	0,019 992	0,166 97	0	1,213 833	1,137 762
22	0,008 832	0,073 514	0	0,534 474	0,494 404
23	0,002 612	0,021 793	0	0,158 314	0,146 517
24	0,000 282	0,002 679	0	0,019 738	0,018 328
25	0	0	0	0	0

Radial position	Laser ID				
r (μm)	6	7	8	9	10
0	0	0	0	0	0
1	0,015 199	0,016 253	0,022 057	0,010 43	0,015 681
2	0,120 91	0,129 011	0,176 39	0,083 496	0,124 978
3	0,407 702	0,434 844	0,595 248	0,281 802	0,421 548
4	0,925 664	0,987 184	1,351 845	0,650 28	0,957 203
5	1,488 762	1,587 6	2,174 399	1,130 599	1,539 535
6	1,825 448	1,94 661 4	2,666 278	1,627 046	1,887 747
7	1,702 306	1,815 285	2,486 564	2,044 326	1,762 955
8	1,218 378	1,299 241	1,780 897	2,291 72	1,292 184
9	0,643 911	0,686 635	0,945 412	2,280 813	0,790 844
10	0,238 557	0,255 85	0,360 494	1,937 545	0,559 38
11	0,098 956	0,131 429	0,163 923	1,383 006	0,673 655
12	0,204 274	0,327 091	0,318 712	0,878 798	1,047 689
13	0,529 982	0,848 323	0,778 983	0,679 756	1,589 037
14	1,024 948	1,567 513	1,383 174	0,812 36	2,138 626
15	1,611 695	2,224 027	1,853 992	1,074 702	2,470 827
16	2,210 689	2,555 06	1,914 123	1,257 323	2,361 764
17	2,707 415	2,464 566	1,511 827	1,255 967	1,798 213
18	2,938 8	2,087 879	0,908 33	1,112 456	1,059 264
19	2,739 32	1,577 111	0,386 991	0,879 309	0,444 481
20	2,090 874	1,056 343	0,111 76	0,608 183	0,123 304
21	1,261 564	0,595 102	0,014 829	0,348 921	0,012 552
22	0,552 14	0,256 718	0,001 818	0,151 12	0
23	0,163 627	0,076 096	0,000 54	0,044 757	0
24	0,020 443	0,009 446	0	0,005 639	0
25	0	0	0	0	0

D.3 A1-OM4 DMD requirements

D.3.1 General

A1-OM4 fibres selected using the DMD mask method shall meet the requirements of D.3.2 and D.3.3. See Clause D.1 for supporting information. The radial limits, R_{INNER} and R_{OUTER} , were established for transmitters meeting the requirements of Clause E.4.

Refer to Annex E for information regarding effective modal bandwidth (EMB).

D.3.2 DMD templates

A1-OM4 fibres shall meet at least one of the three templates in Table D.4, each of which includes an inner and outer mask requirement, when measured according to IEC 60793-1-49.

Table D.4 – DMD templates for A1-OM4 fibres

Template number	Inner mask DMD (ps/m) for $R_{\text{INNER}} = 5 \mu\text{m}$ to $R_{\text{OUTER}} = 18 \mu\text{m}$	Outer mask DMD (ps/m) for $R_{\text{INNER}} = 0 \mu\text{m}$ to $R_{\text{OUTER}} = 23 \mu\text{m}$
1	$\leq 0,10$	$\leq 0,30$
2	$\leq 0,11$	$\leq 0,17$
3	$\leq 0,14$	$\leq 0,14$

D.3.3 DMD interval masks

The A1-OM4 fibre DMD shall not exceed 0,11 ps/m for any of the radial offset intervals given in Table D.5 when measured according to IEC 60793-1-49.

Table D.5 – DMD interval masks for A1-OM4 fibres

Interval number	R_{INNER} μm	R_{OUTER} μm
1	7	13
2	9	15
3	11	17
4	13	19

D.4 A1-OM4 fibre EMB_c requirements

D.4.1 General

A1-OM4 fibres selected using the EMB_c method shall meet the requirements of D.4.2. See the introductory text for Table D.3 in D.2.2 for supporting information.

D.4.2 Calculated effective bandwidth

The DMD optical pulse shapes can be weighted by a set of launch distributions to determine a corresponding set of EMB_c values. The minimum EMB_c (minEMB_c) within this set shall meet the requirement of Equation (D.2):

$$\text{minEMB}_c \geq 4 \, 160 \, \text{MHz} \cdot \text{km} \quad (\text{D.2})$$

where

minEMB_c is determined from the complex transfer function as described in IEC 60793-1-49 using the weights defined in Table D.3.

D.5 A1-OM5 fibre modal bandwidth requirements

D.5.1 General

A1-OM5 fibres shall meet the requirements of D.5.2 and D.6. See the introductory text for Table D.3 in D.2.2 for supporting information.

D.5.2 Calculated effective modal bandwidth

The DMD optical pulse shapes shall be weighted by a set of launch distributions to determine a corresponding set of EMB_c values. The minimum EMB_c ($minEMB_c$) within this set shall meet the requirement of Equations (D.3) and (D.4):

$$minEMB_c \geq 4\,160 \text{ MHz}\cdot\text{km at } 850 \text{ nm} \quad (D.3)$$

$$minEMB_c \geq 2\,190 \text{ MHz}\cdot\text{km at } 953 \text{ nm} \quad (D.4)$$

where

$minEMB_c$ is determined from the complex transfer function as described in IEC 60793-1-49 using the weights defined in Table D.3.

D.6 A1-OM2, A1-OM3, A1-OM4 and A1-OM5 calculated overfilled modal bandwidth

The DMD optical pulse shapes shall be weighted for A1-OM2, A1-OM3 and A1-OM4 fibres by the launch distribution of Table D.6 to determine a corresponding OMB_c value at 850 nm. For A1-OM5 fibres, the launch distribution of Table D.6 shall be used to determine a corresponding value at 850 nm and 953 nm. The weights of Table D.6 are the same as those in IEC 60793-1-41 for method C.

Table D.6 – DMD weighting for OMB_c

Radial position, r μm	OFL weighting
0	0
1	0,000 73
2	0,001 57
3	0,002 53
4	0,003 62
5	0,004 87
6	0,006 31
7	0,007 95
8	0,009 83
9	0,011 98
10	0,014 43
11	0,017 25
12	0,020 46
13	0,024 14
14	0,028 36
15	0,033 17
16	0,038 69
17	0,045 00
18	0,052 21
19	0,060 47
20	0,069 92
21	0,080 73
22	0,093 10
23	0,107 25
24	0,123 45
25	0,141 97

Annex E (informative)

System, modal bandwidth, and transmitter considerations

E.1 Background

When a multimode fibre is used with laser transmitters, the bandwidth of the combination may vary widely, depending on the details of the modal structure of the lasers, the modal delay structure of the fibre, and the coupling between the laser and the fibre modes. More precisely, modal bandwidth is the –3 dB bandwidth of the impulse response produced from the modal delays of a particular fibre weighted by the mode power distribution excited by a particular laser. To generate a robust bandwidth estimate when the impulse response is non-Gaussian, the 3 dB bandwidth is replaced by an extrapolation of the 1,5 dB bandwidth.

Knowledge of the modal structure of a fibre, as determined by IEC 60793-1-49, allows a lower limit to be placed on the range of bandwidths which will be experienced when using a given fibre with various laser transmitters. The minEMB_c technique reviewed in Clause E.3 screens the fibre with 10 simulated lasers that explore the observed mode power distribution; the set of 10 simulated lasers is believed to be conservative compared to commercially available lasers but narrower than the set of theoretical lasers in the original TIA model shown in Figure E.2 [13]. The chosen lasers exhibit a variety of coupled mode power distribution characteristics: some with power more concentrated in lower order modes, some with power more concentrated in higher order modes, and some with both low order and high order mode power concentrations.

By using lasers which couple primarily into modes with well bounded delays, minimum modal bandwidth can be ensured. IEC 61280-1-4 can be used to measure the launch condition of laser transmitters into multimode fibre [15]. Appropriately selected launch condition specifications can restrict the modes of the fibre used by the transmitters primarily to those with appropriately limited differential mode delays.

A minimum modal bandwidth-length product can be ensured by combining a transmitter meeting the specifications in Clause E.4 below with a 50 µm fibre meeting the specifications in Annex D.

E.2 System considerations

E.2.1 A1-OM3 and A1-OM4 fibres

Refer to Clause E.3.

E.2.2 A1-OM5 fibre

Fibre specifications for high data systems have been developed using link models [16]. The 10 Gb/s and 25 Gb/s models build on the 1 Gb/s link model [16] which includes both a requirement that the power penalty or margin be positive and that the inter-symbol interference (ISI) be less than 3,6 dB.

The A1-OM5 fibre specifications were developed using the Excel link models for IEEE 100GBASE-SR4 (Example MMF Link Model.xls [17]) and Fibre Channel 32GFC (T11-12-376v0.xlsx [18]). The link models were used to determine the bandwidth requirements over the wavelength range from 840 nm to 953 nm. The wavelengths were varied within this range in the models. In the link models, the dispersion parameters U_0 (zero dispersion wavelength) and S_0 (zero dispersion slope) were adjusted to new values of 1 328 nm and 0,093 477 ps/(nm²·km) based on round-robin results, and the cabled fibre attenuation was decreased from 3,5 dB/km to 3,0 dB/km. Both link models are margin-limited over the 840 nm to 953 nm wavelength range (unlike the IEEE P802.3ae 10GBASE-S mode [19] used for OM3,

which is inter-symbol interference limited to less than or equal to 3,6 dB), and the EMB in the link model was adjusted to achieve a margin of 0,000 dB. For setting the EMB specification, it was agreed to use the 32GFC link model with zero margin because the EMB requirements are higher than for the 100GBASE-SR4 model (that is, bandwidth requirements were chosen that met requirements of both system link models). The normative EMB specifications are 4 700 MHz·km at 850 nm and 2 470 MHz·km at 953 nm. These are marked with circles in Figure E.1. With these requirements fulfilled, the expected worst-case EMB lies on or above the system requirements, as explained in Clause E.3.

E.3 Effective modal bandwidth (EMB)

During the development of fibre sub-category A1-OM3, a detailed time-domain Monte-Carlo simulation was used to assess the performance-screening ability of various DMD mask and DMD weighting proposals for transmitters meeting the specifications of Clause E.4 [3] to [14]. The proposals were judged based on their ability to pass fibres that did not cause inter-symbol interference (ISI) to exceed a specific value more often than a 0,5 % rate [13]. The specific ISI value was established via the IEEE 802.3ae link budget spreadsheet [19] for a channel that included the effects of transmitter rise time, receiver bandwidth, and a fibre with 2 000 MHz·km modal bandwidth. Thus, through the use of the Monte-Carlo simulation, fibres meeting the requirements of sub-category A1-OM3 provide a minimum EMB of 2 000 MHz·km.

The minimum EMB value is aligned with the assumptions of the IEEE 802.3ae link budget spreadsheet. Of particular relevance is the fact that, in the spreadsheet, the ISI impairment is modelled under Gaussian waveform assumptions for the transmitter and fibre outputs. According to the results of the Monte-Carlo simulation for fibres passing the requirements, the spreadsheet relationship between ISI and minimum fibre modal bandwidth is pessimistic. Therefore, the calculation of EMB from weighted DMD included a factor of 1,13 to align the fibre requirements developed with the time-domain Monte-Carlo simulation with the spreadsheet model as shown in Equation (E.1).

$$\text{EMB} = 1,13 \times \min\text{EMB}_c \quad (\text{E.1})$$

The EMB derived by Equation (E.1) also applies to the Fibre Channel link models. If other models are used, then a different EMB may be appropriate.

Fibres passing the requirements of Clauses D.3 and D.4 (i.e. A1-OM4 fibres) provide a minimum modal bandwidth at 850 nm that is 2,35 times higher than the minimum modal bandwidth of those passing the requirements of Clauses D.1 and D.2 (i.e. A1-OM3 fibres). As such, their minimum EMB is also 2,35 times higher under the same link budget spreadsheet assumptions as stated by Equation (E.2).

$$\text{EMB} \geq 2,35 \times 2\,000 \text{ MHz}\cdot\text{km} \geq 4\,700 \text{ MHz}\cdot\text{km} \quad (\text{E.2})$$

System performance studies with actual fibres and laser sources support this relationship [20] to [22]. Applications have emerged which will utilize multiple wavelengths in the vicinity of 850 nm to 950 nm. To support these applications, guidance which characterizes the minimum EMB for A1-OM3, A1-OM4, and A1-OM5 is provided in the form of Equations (E.3) through (E.9) and Figures E.1 through E.3. These equations should not be extrapolated without due consideration.

The population of A1-OM3 subcategory fibres generally exhibit estimated minimum EMB meeting Equations (E.3) and (E.4) which are depicted as two curves from (a) 840 nm to 850 nm and (b) 850 nm to 953 nm as depicted in Figure E.1. The unit of EMB in the two equations is MHz·km.

For $840 \text{ nm} \leq \lambda_c \leq 850 \text{ nm}$:


$$\text{EMB} \geq 1\,826 + (2\,000 - 1\,826) \times (\lambda_c - 840) / (850 - 840) \quad (\text{E.3})$$

For $850 \text{ nm} \leq \lambda_c \leq 953 \text{ nm}$:

$$\text{EMB} \geq 2\,000 \times (1,001\,0 - 0,980\,9x + 0,807\,3x^2 - 0,430\,4x^3 + 0,119\,4x^4) \quad (\text{E.4})$$

where

$$x = (\lambda_c - 850) / (953 - 850)$$



IEC

Figure E.1 – Estimated minimum wide band EMB versus wavelength for A1-OM3

The population of A1-OM4 subcategory fibres generally exhibit estimated minimum EMB meeting Equations (E.5) and (E.6) which are depicted as two curves from (a) 840 nm to 850 nm and (b) 850 nm to 953 nm in Figure E.2. The unit of EMB in the two equations is MHz.km.

For $840 \text{ nm} \leq \lambda_c \leq 850 \text{ nm}$:


$$\text{EMB} \geq 3\,840 + (4\,700 - 3\,840) \times (\lambda_c - 840) / (850 - 840) \quad (\text{E.5})$$

For $850 \text{ nm} \leq \lambda_c \leq 953 \text{ nm}$:

$$\text{EMB} \geq 4\,700 \times (1,000\,2 - 2,154\,9x + 3,270\,0x^2 - 2,732\,8x^3 + 0,928\,0x^4) \quad (\text{E.6})$$

where

$$x = (\lambda_c - 850) / (953 - 850)$$



IEC

Figure E.2 – Estimated minimum wide band EMB versus wavelength for A1-OM4

Fibres passing the requirements of Clause D.5 (i.e. A1-OM5 fibres) generally exhibit estimated EMB meeting Equations (E.7), (E.8) and (E.9), which are depicted as three straight-line segments from (a) 840 nm to 850 nm, (b) 850 nm to 930 nm, and (c) 930 nm to 953 nm in Figure E.3. The unit of EMB in all three equations is MHz.km.

For $840 \text{ nm} \leq \lambda_c \leq 850 \text{ nm}$:

$$\text{EMB} \geq 3\,840 + (4\,700 - 3\,840) \times (\lambda_c - 840) / (850 - 840) \quad (\text{E.7})$$

For $850 \text{ nm} \leq \lambda_c \leq 930 \text{ nm}$:


$$\text{EMB} \geq 4\,700 + (2\,565 - 4\,700) \times (\lambda_c - 850) / (930 - 850) \quad (\text{E.8})$$

For $930 \text{ nm} \leq \lambda_c \leq 953 \text{ nm}$:

$$\text{EMB} \geq 2\,565 + (2\,470 - 2\,565) \times (\lambda_c - 930) / (953 - 930) \quad (\text{E.9})$$

Equations (E.7), (E.8), and (E.9) describe three straight line segments between the minimum EMB indicated by the 32GFC link model at 840 nm and the two minimum EMBs at the nominal measurement wavelengths of 850 nm and 953 nm. Equations (E.7), (E.8) and (E.9) are plotted in Figure E.3 along with values of EMB that close the 32GFC link model. The straight line segments from 840 nm to 953 nm were carefully established as providing a minimum EMB

guidance over the wavelength range while not intentionally introducing special fibre design dependence.



IEC

Figure E.3 – Estimated minimum wide band EMB versus wavelength for A1-OM5

E.4 Transmitter encircled flux (EF) and centre wavelength requirements

E.4.1 Encircled flux


The DMD radial limits of the inner, outer and interval masks specified in Clauses D.1 and D.3, and the DMD weightings specified in Clauses D.2, D.4 and D.5, were established in conjunction with the particular bounded range of laser launch conditions specified in Equations (E.10) and (E.11). The minimum modal bandwidth for launch conditions outside of this range has not been determined, but will be lower than for launch conditions within this range.

The transmitter launch condition power distribution should meet the requirements of Equations (E.10) and (E.11) when measured according to IEC 61280-1-4 [15] with the transmitter coupled into a 50- μm fibre meeting the specifications of this document.

$$\text{EF at radius } 4,5 \mu\text{m} \leq 30 \% \quad (\text{E.10})$$

$$\text{EF at radius } 19 \mu\text{m} \geq 86 \% \quad (\text{E.11})$$

The approximate positions of the DMD weightings specified in Table D.3 are depicted in the Figure E.4 below, relative to the boundaries given in Equations (E.10) and (E.11) [2].



IEC

Figure E.4 – Approximate position of DMD weightings relative to the EF boundaries of Equations (E.10) and (E.11)

Several published application standards meet the requirements of E.4.1 and E.4.2 [23] to [26].

E.4.2 Centre wavelength for A1-OM3 and A1-OM4 fibres

Because the fibre's modal delays change with wavelength, the transmitter centre wavelength should be kept close to the nominal DMD measurement wavelength of 850 nm to achieve the highest modal bandwidth performance over the population of passing fibres. It may be appropriate to de-rate the modal bandwidth when the transmitter is not operating at 850 nm [8]. See [27] for an illustration of bandwidth roll-off for fibres with bandwidth similar to fibre model A1-OM4.

The laser transmitter centre wavelength (λ_c) should meet the requirements of Equation (E.12) when tested according to IEC 61280-1-3 [28].

$$840 \text{ nm} \leq \lambda_c \leq 860 \text{ nm} \quad (\text{E.12})$$

E.4.3 Centre wavelength for A1-OM5 fibre

Because the fibre's modal delays change with wavelength, the highest modal bandwidth performance is attained when the laser transmitter centre wavelength is between the DMD measurement wavelengths. When the laser transmitter's centre wavelength is outside this range, the modal bandwidth may degrade. See Equation (E.7), (E.8) and (E.9) for advice on bandwidth values between the DMD measurement wavelengths.

The laser transmitter centre wavelength (λ_c) should meet the requirements of Equation (E.13) when tested according to IEC 61280-1-3 [28].

$$840 \text{ nm} \leq \lambda_c \leq 953 \text{ nm} \quad (\text{E.13})$$

Annex F (informative)

Bandwidth nomenclature explanation

Table F.1 provides explanations of bandwidth parameters that have similar names and abbreviations.

Table F.1 – Bandwidth nomenclature explanation

Parameter name and abbreviation	Parameter description
Calculated effective modal bandwidth (EMB_c)	The calculated modal bandwidth resulting from a particular weighting of a particular DMD.
Minimum calculated effective modal bandwidth (minimum EMB_c or $minEMB_c$)	The minimum calculated modal bandwidth resulting from a particular set of weightings of a particular DMD.
Effective modal bandwidth (EMB)	The modal bandwidth that results from multiplying the minimum calculated effective modal bandwidth by 1,13 to arrive at a value aligned with the assumptions of the IEEE 802.3ae link model for transmitters compliant to Clause E.2.
Calculated overfilled modal bandwidth (OMB_c)	The calculated modal bandwidth resulting from weighting a particular DMD to simulate an overfilled launch condition.

Annex G (informative)

Preliminary indications for items needing further study

G.1 Effective modal bandwidth (EMB) at 1 300 nm

Chromatic dispersion properties allow DMD measured at one wavelength to be transformed to DMD at another wavelength. Thus, 850 nm DMD may be used to predict minimum effective modal bandwidth-length product at 1 300 nm. Preliminary engineering analysis indicates that fibres meeting the requirements of Annex D for $\geq 2\,000$ MHz·km EMB at 850 nm will also provide ≥ 500 MHz·km EMB at 1 300 nm.

Some 1 300 nm laser-based transmitters are defined to operate into both multimode fibre and single mode fibre. In order to provide better assurance that multimode fibres, with bandwidth performance specified only on the basis of overfilled launch conditions, deliver at least their minimum overfilled bandwidth-length product for 1 300 nm transmitters designed to launch into single mode fibre (e.g. 1000BASE-LX), IEEE Std 802.3™ specifies the use of offset-launch mode-conditioning patch cords when connecting such transmitters to this type of multimode fibre.

The offset-launch is implemented by joining a single mode fibre to a multimode fibre within the patch cord using a specified range of single mode-to-multimode radial offset. By launching significantly off-centre from the single mode fibre into the multimode fibre, many modes are excited that produce a mode power distribution closer to that of an overfilled launch than that of the native launch, which typically strongly excites only low-order modes.

Because overfilled-launch bandwidth measurements are heavily dominated by high-order mode behaviour, they are insensitive to the behaviour of low-order modes. Therefore, by avoiding strong excitation of the low-order modes, the offset-launch patch cord eliminates dependence on the behaviour of these poorly-characterized modes, and improves the correlation between minimum system bandwidth and the overfilled launch bandwidth-length measurement.

However, because the DMD test procedure does measure low-order mode behaviour, it is capable of bounding the lower limit of bandwidth-distance product for the native launches of these 1 300 nm transmitters. Fibres meeting A1-OM3 and A1-OM4 specifications are optimised for peak bandwidth at 850 nm, and have specifically limited low-order mode DMD.

Operating at wavelengths different from the peak wavelength introduces a systematic increase in DMD. The largest increase in DMD occurs for the highest order modes. Thus the overfilled bandwidth, which is dominated by high-order mode DMD, is a conservative indicator of lowest effective modal bandwidth for native 1 300 nm launches that concentrate power in the low order modes. Therefore, A1-OM3 and A1-OM4 fibres are expected to provide EMB at least as high as their 500 MHz·km minimum overfilled bandwidth-length product at 1 300 nm without the use of mode conditioning patch cords.

G.2 Scaling of EMB with DMD

Different effective modal bandwidth-length products can be derived from the templates and interval masks defined in Clauses D.1 and D.3 simply by scaling EMB in inverse proportion to DMD temporal width, provided the following three conditions are met:

- 1) the fibre is used with transmitters meeting the specifications in E.4.1;
- 2) the radial offset limits of the templates are not changed; and
- 3) the overfilled modal bandwidth-length product requirements are scaled in direct proportion to the EMB.

This scaling ability is substantiated by the following relationships. From the waveguide theory, the mode power distribution of the transmitter relates directly to the radial extents of the inner and outer DMD masks. The operating wavelength range constrains operation in close proximity to the nominal DMD measurement wavelength to minimise modal bandwidth changes due to wavelength. With the mode power distribution and the radial extent of the DMD masks fixed, and the operating wavelength range unchanged, scaling is supported by the inverse proportionality between RMS pulse width and bandwidth [29] [30]. In this case, the RMS pulse width equates to the DMD temporal width. Scaling the overfilled bandwidth in direct proportion to the desired EMB maintains the established proportionality between the DMD and overfilled bandwidth.

For example, an effective modal bandwidth-length product at 850 nm of $\geq 1\,000$ MHz·km (one-half of 2 000 MHz·km) can be provided with fibre meeting any of the six DMD templates given in Clause D.1, with each template having double the DMD temporal width in both the inner and outer masks, and an overfilled bandwidth-length product of ≥ 750 MHz·km.

Annex H (informative)

Applications and cabling categories supported by A1 fibres

Table H.1 shows various internationally standardised applications, as well as other recommended applications, which are supported by A1 fibres. It is not an exhaustive list, and many other applications not specifically listed may also be supported.

**Table H.1 – Some standardised applications supported by
A1-OM2, A1-OM3, A1-OM4, A1-OM5 fibres and in some cases A1-OM1 fibres**

Application	Source	Name
1GFC	ISO/IEC 14165-115	1-Gigabit Fibre Channel
2GFC	ISO/IEC 14165-115	2-Gigabit Fibre Channel
4GFC	ANSI/INCITS 479	4-Gigabit Fibre Channel
8GFC	ANSI/INCITS 479	8-Gigabit Fibre Channel
10GFC	ISO/IEC 14165-116	10-Gigabit Fibre Channel
16GFC	ANSI/INCITS 479	16-Gigabit Fibre Channel
32GFC	ANSI/INCITS 512	32-Gigabit Fibre Channel
1000BASE-SX	ISO/IEC/IEEE 8802-3	Gigabit Ethernet
1000BASE-LX	ISO/IEC/IEEE 8802-3	Gigabit Ethernet
10GBASE-S	ISO/IEC/IEEE 8802-3	10-Gigabit Ethernet
25GBASE-SR	ISO/IEC/IEEE 8802-3	25-Gigabit Ethernet
40GBASE-SR4	ISO/IEC/IEEE 8802-3	40-Gigabit Ethernet
100GBASE-SR10	ISO/IEC/IEEE 8802-3	100-Gigabit Ethernet
100GBASE-SR4	ISO/IEC/IEEE 8802-3	100-Gigabit Ethernet

Annex I (informative)

1-Gigabit, 10-Gigabit, 25-Gigabit, 40-Gigabit and 100-Gigabit Ethernet applications

Annex I is intended to outline a summary of category A1-OM2, A1-OM3, A1-OM4, A1-OM5 and A1-OM1 fibre requirements and related transmission capabilities for the 1-Gigabit, 10-Gigabit, 25-Gigabit, 40-Gigabit, and 100-Gigabit Ethernet application standards developed within IEEE 802.3. All the Ethernet applications at 1 Gb/s or higher are considered as "laser launch" applications.

Table I.1 shows a summary of 1 Gb/s, 10 Gb/s, 25 Gb/s, 40 Gb/s and 100 Gb/s Ethernet requirements and capabilities. The rows of Table I.1 are grouped by fibre sub-category and model and listed by increasing data rate. For each line item, there is an indication of the application link length and the requirements on transmitter launch characteristics. The requirements of the transmitter launch characteristics are of three types.

- Offset-launch mode-conditioning patch cord for 1 300 nm operations, defined in IEEE 802.3.
- Coupled power ratio (CPR) > 9 dB and avoidance of radial overfilled launch (ROFL) for 1 Gb/s 850 nm operations on fibres characterised solely by overfilled launch (OFL) bandwidth. CPR is defined in IEC 61280-4-1:2009; ROFL is defined in IEEE 802.3.
- Encircled Flux (EF) requirements for 10 Gb/s, 25 Gb/s, 40 Gb/s and 100 Gb/s 850 nm operation on fibre models A1-OM3, A1-OM4 and A1-OM5 with effective modal bandwidth ensured by DMD measurement. The EF requirements are: EF at 4,5 μm radius $\leq 30\%$ and EF at 19,0 μm radius $\geq 86\%$. For EF measurements, see IEC 61280-1-4.

Table I.1 – Summary of 1 Gb/s, 10 Gb/s, 25 Gb/s, 40 Gb/s and 100 Gb/s Ethernet requirements and capabilities

Fibre sub-category or model	Bit rate Gb/s	Nominal wavelength									
		850 nm				1 300 nm					
		Minimum modal bandwidth for indicated measurement condition MHz·km	Minimum effective modal bandwidth for transmitters meeting launch requirement MHz·km	IEEE 802.3 PMD ^a	Transmitter launch requirement	Link length m	Minimum modal bandwidth for indicated measurement condition MHz·km	Minimum effective modal bandwidth for transmitters meeting launch requirement MHz·km	IEEE 802.3 PMD ^a	Transmitter launch requirement	Link length m
A1-OM1	1	160 for OFL	n.s.	1000BASE-SX	CPR > 9 dB, avoid ROFL	220	500 for OFL	n.s.	1000BASE-LX	Offset-launch patch cord	550
A1-OM1	1	200 for OFL	n.s.	1000BASE-SX	CPR > 9 dB, avoid ROFL	275	500 for OFL	n.s.	1000BASE-LX	Offset-launch patch cord	550
A1-OM1	10	160 for OFL	n.s.	10GBASE-S	EF at 4,5 µm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	26	500 for OFL	n.s.	10GBASE-LX4	Offset-launch patch cord	300
A1-OM1	10	200 for OFL	n.s.	10GBASE-S	EF at 4,5 mm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	33	500 for OFL	n.s.	10GBASE-LX4	Offset-launch patch cord	300
A1-OM1	10	160 for OFL	n.s.	n.s.	n.s.	n.s.	500 for OFL	n.s.	10GBASE-LRM	Offset-launch patch cord or EF at 5 µm radius ≥ 30 %, EF at 11 µm radius ≥ 81 %	220

Fibre sub-category or model	Bit rate Gb/s	Nominal wavelength									
		850 nm					1 300 nm				
		Minimum modal bandwidth for indicated measurement launch condition MHz·km	Minimum effective modal bandwidth for transmitters meeting launch requirement MHz·km	IEEE 802.3 PMD ^a	Transmitter launch requirement	Link length m	Minimum modal bandwidth for indicated measurement launch condition MHz·km	Minimum effective modal bandwidth for transmitters meeting launch requirement MHz·km	IEEE 802.3 PMD ^a	Transmitter launch requirement	Link length m
A1-OM1	10	200 for OFL	n.s.	n.s.	n.s.	n.s.	500 for OFL	n.s.	10GBASE-LRM	Offset-launch patch cord or EF at 5 µm radius ≥ 30 %, EF at 11 µm radius ≥ 81 %	220
A1-OM2	1	400 for OFL	n.s.		CPR > 9 dB, avoid ROFL	500	400 for OFL	n.s.	1000BASE-LX	Offset-launch patch cord	550
A1-OM2	1	500 for OFL	n.s.		CPR > 9 dB, avoid ROFL	550	500 for OFL	n.s.	1000BASE-LX	Offset-launch patch cord	550
A1-OM2	10	400 for OFL	n.s.		EF at 4,5 mm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	66	400 for OFL	n.s.	10GBASE-LX4	Offset-launch patch cord	240
A1-OM2	10	500 for OFL	n.s.		EF at 4,5 µm radius ≤ 30 %, EF at 19,0 µm radius ≥ 86 %	82	500 for OFL	n.s.	10GBASE-LX4	Offset-launch patch cord	300