

INTERNATIONAL STANDARD



**Optical fibres –
Part 2-50: Product specifications – Sectional specification for class B single-
mode fibres**



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2018 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing 21 000 terms and definitions in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.



IEC 60793-2-50

Edition 6.0 2018-12
REDLINE VERSION

INTERNATIONAL STANDARD



**Optical fibres –
Part 2-50: Product specifications – Sectional specification for class B single-
mode fibres**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 33.180.10

ISBN 978-2-8322-6361-7

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	5
1 Scope.....	7
2 Normative references	8
3 Terms and definitions	10
4 Abbreviated terms and symbols	10
5 Specifications	10
5.1 General.....	10
5.2 Dimensional requirements.....	10
5.3 Mechanical requirements	11
5.4 Transmission requirements	12
5.5 Environmental requirements	14
5.5.1 General	14
5.5.2 Optical environmental requirements – Attenuation	14
5.5.3 Mechanical environmental requirements	15
Annex A (normative) Family specification for category ~~B1.1~~ B-652 Dispersion unshifted single-mode fibres.....	16
A.1 General.....	16
A.2 Dimensional requirements.....	16
A.3 Mechanical requirements	17
A.4 Transmission requirements	17
A.5 Hydrogen ageing for sub-category B-652.D.....	19
A.6 Environmental requirements	19
~~Annex (normative) Family specification for category B1.3 single-mode fibres.....~~	
Annex B (normative) Family specification for category ~~B.2~~ B-653 Dispersion shifted single-mode fibres	23
B.1 General.....	23
B.2 Dimensional requirements.....	23
B.3 Transmission requirements	24
B.3.1 General	24
B.3.2 Chromatic dispersion coefficient requirement for sub-category ~~B2_a~~ B- 653.A fibres	24
B.3.3 Chromatic dispersion coefficient requirement for sub-category ~~B2_b~~ B- 653.B fibres	25
B.4 Environmental requirements	25
Annex C (normative) Family specification for category ~~B1.2~~ B-654 cut-off shifted single-mode fibres	26
C.1 General.....	26
C.2 Dimensional requirements.....	26
C.3 Mechanical requirements	26
C.4 Chromatic dispersion parameters for B-654.E fibres	28
C.5 Environmental requirements	28
Annex D (normative) Family specification for category ~~B.4~~ B-655 non-zero dispersion shifted single-mode fibres	29
D.1 General.....	29
D.2 Dimensional requirements.....	29
D.3 Mechanical requirements	29

D.4	Transmission requirements	30
D.4.1	General	30
D.4.2	Chromatic dispersion coefficient limits for sub-category ~~B4_c~~ B-655.C fibres	30
D.4.3	Chromatic dispersion coefficient limits for sub-category ~~B4_d~~ B-655.D fibres	31
D.4.4	Chromatic dispersion coefficient limits for sub-category ~~B4_e~~ B-655.E fibres	31
D.5	Environmental requirements	31
Annex E (normative)	Family specification for category ~~B5~~ B-656 Wideband non-zero dispersion shifted single-mode fibres	32
E.1	General.....	32
E.2	Dimensional requirements.....	32
E.3	Mechanical requirements	32
E.4	Transmission requirements	33
E.4.1	General	33
E.4.2	Chromatic dispersion coefficient for category ~~B5~~ B-656 fibres.....	33
E.5	Environmental requirements	34
Annex F (normative)	Family specification for category ~~B6~~ B-657 Bending loss insensitive single-mode fibres.....	35
F.1	General.....	35
F.2	Dimensional requirements.....	35
F.3	Mechanical requirements	36
F.4	Transmission requirements	36
F.5	Environmental requirements	39
Annex G (informative)	System design information for category ~~B4~~ B-655 non-zero disperion shifted single-mode fibres	40
G.1	General.....	40
G.2	One standard deviation limits for sub-category ~~B4_d~~ B-655.D fibres.....	40
G.3	One standard deviation limits for sub-category ~~B4_e~~ B-655.E fibres	41
~~Annex (informative) Map from IEC nomenclature to ITU-T recommendations~~		~~44~~
Bibliography.....		44
Figure G.1 – Sub- category ~~B4_d~~ B-655.D chromatic dispersion coefficient limits		41
Figure G.2 – Sub-category ~~B4_e~~ B-655.E chromatic dispersion coefficient limits		42
Table 1 – Map of IEC designation to ITU-T Recommendations and IEC 60793-2-50:2015 designation.....		8
Table 2 – Dimensional attributes and measurement methods.....		11
Table 3 – Dimensional requirements common to all category B fibres		11
Table 4 – Mechanical attributes and test methods.....		12
Table 5 – Mechanical requirements common to all class B fibres		12
Table 6 – Transmission attributes and measurement methods		13
Table 7 – Transmission, requirements common to all class B fibres		13
Table 8 – Additional transmission attributes required in the family specifications		13
Table 9 – Environmental exposure tests		14
Table 10 – Attributes measured in environmental exposure tests		14
Table 11 – Change in attenuation for environmental tests		14

Table 12 – Coating strip force for environmental tests.....	15
Table 13 – Tensile strength for environmental tests	15
Table 14 – Stress corrosion susceptibility for environmental tests.....	15
Table A.1 – Dimensional requirements specific to category ~~B1.1~~ B-652.B fibres	16
Table A.2 – Dimensional requirements specific to category B-652.D fibres	17
Table A.3 – Mechanical requirements specific to category ~~B1.1~~ B-652 fibres	17
Table A.4 – Transmission requirements specific to sub-category ~~B1.1~~ B-652.B fibres	18
Table A.5 – Transmission requirements specific to sub-category B-652.D Fibres	18
Table A.6 – Chromatic dispersion properties for sub-category B-652.D fibres	19
Table B.1 – Dimensional requirements specific to category ~~B.2~~ B-653 fibres.....	23
Table B.2 – Mechanical requirements specific to category ~~B.2~~ B-653 fibres	24
Table B.3 – Transmission requirements specific to category ~~B.2~~ B-653 fibres	24
Table C.1 – Dimensional requirements specific to category ~~B1.2~~ B-654 fibres	26
Table C.2 – Mechanical requirements specific to category ~~B1.2~~ B-654 fibres	27
Table C.3 – Transmission requirements specific to category ~~B1.2~~ B-654 fibres	27
Table D.1 – Dimensional requirements specific to category ~~B.4~~ B-655 fibres	29
Table D.2 – Mechanical requirements specific to category ~~B.4~~ B-655 fibres	30
Table D.3 – Transmission requirements specific to category ~~B.4~~ B-655 fibres	30
Table E.1 – Dimensional requirements specific to category ~~B5~~ B-656 fibres.....	32
Table E.2 – Mechanical requirements specific to category ~~B5~~ B-656 fibres	33
Table E.3 – Transmission requirements specific to category ~~B5~~ B-656 fibres	33
Table F.1 – Dimensional requirements specific to category ~~B6~~ B-657 fibres.....	36
Table F.2 – Mechanical requirements specific to category ~~B6~~ B-657 fibres	36
Table F.3 – Transmission requirements specific to category ~~B6~~ B-657 fibres	36
Table G.1 – Examples for $\lambda_{\min} = 1\,530\text{ nm}$ and $\lambda_{\max} = 1\,565\text{ nm}$	40

INTERNATIONAL ELECTROTECHNICAL COMMISSION

OPTICAL FIBRES –

Part 2-50: Product specifications – Sectional specification for class B single-mode fibres

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.

International Standard IEC 60793-2-50 has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

The sixth edition cancels and replaces the fifth edition published in 2015. This edition constitutes a technical revision. This edition includes the following significant technical changes with respect to the previous edition:

- a) Introduction of a revised naming convention which better matches with those found in ITU-T Recommendations G.652, G.653, G.654, G.655, G.656, and G.657. These changes are outlined in the scope of this document along with a cross reference table for the new names. Annexes have been rearranged to improve clarity based on the new naming;
- b) Further details on the requirements for 200 micron coated single-mode fibre;
- c) Harmonization with the following ITU-T Recommendations published in November 2016: G.652, G.654, G.657 including revised chromatic dispersion specifications, new categories and new application spaces for these fibre categories;
- d) Descriptions of fibre types have been added to the titles of Annexes A to F.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
86A/1884/FDIS	86A/1898/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60793 series, published under the general title *Optical fibres*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

OPTICAL FIBRES –

Part 2-50: Product specifications – Sectional specification for class B single-mode fibres

1 Scope

This part of IEC 60793 is applicable to optical fibre categories ~~B1.1, B1.2, B1.3, B2, B4, B5 and B6~~ B-652, B-653, B-654, B-655, B-656 and B-657. A map illustrating the connection of IEC designations to ITU-T designations is shown in ~~Annex I~~ Table 1. These fibres are used or can be incorporated in information transmission equipment and optical fibre cables.

Three types of requirements apply to these fibres:

- general requirements, as defined in IEC 60793-2;
- specific requirements common to the class B single-mode fibres covered in this document and which are given in Clause 5;
- particular requirements applicable to individual fibre categories or specific applications, which are defined in Annexes A to ~~G~~ F.

For some fibre categories (shown in the relevant family specifications), there are sub-categories that are distinguished on the basis of difference in transmission attribute specifications. The designations for these sub-categories are documented in the individual family specifications.

Table 1 shows a map from the IEC designations to the ITU-T recommendations. The table also provides the normative annex in this document that contains the detailed specification as well as the name used to describe this fibre type in IEC 60793-2-50:2015. The ITU-T recommendations as well as the IEC categories/sub-categories within each recommendation are given. In some cases, as for Recommendation G.652, a given IEC designation maps to multiple categories in the ITU-T because the ITU-T categories are distinguished by cabled fibre attribute (PMD_Q) performance which are not distinguished in the IEC fibre specifications.

Table 1 – Map of IEC designation to ITU-T Recommendations and IEC 60793-2-50:2015 designation

Annex	Category	Sub Category	Description	IEC 60793-2-50:2015	ITU-T Rec
	B-652		Dispersion unshifted fibre		G.652
A		B-652.B		B1.1	G.652.B
A		B-652.D		B1.3	G.652.D
	B-653		Dispersion shifted fibre		G.653
B		B-653.A		B2_a	G.653.A
B		B-653.B		B2_b	G.653.B
	B-654		Cut-off shifted fibre		G.654
C		B-654.A		B1.2_a	G.654.A
C		B-654.B		B1.2_b	G.654.B
C		B-654.C		B1.2_c	G.654.C
C		B-654.D		N/A	G.654.D
C		B-654.E		N/A	G.654.E
C	B-655		Non-zero dispersion shifted fibre	B4	G.655
D		B-655.C		B4_c	G.655.C
D		B-655.D		B4_d	G.655.D
D		B-655.E		B4_e	G.655.E
E	B-656		Wideband non-zero dispersion shifted fibre	B5	G.656
F	B-657		Bending loss insensitive fibre	B6	G.657
F		B-657.A1		B6_a1	G.657.A1
F		B-657.A2		B6_a2	G.657.A2
F		B-657.B2		B6_b2	G.657.B2
F		B-657.B3		B6_b3	G.657.B3

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60793-1 (all parts), *Optical fibres* — ~~Measurement methods and test procedures~~

~~IEC 60793-1-1, Optical fibres — Measurement methods and test procedures — Part 1-1: General and guidance~~

IEC 60793-1-20, *Optical fibres – Part 1-20: Measurement methods and test procedures – Fibre geometry*

IEC 60793-1-21, *Optical fibres – Part 1-21: Measurement methods and test procedures – Coating geometry*

IEC 60793-1-22, *Optical fibres – Part 1-22: Measurement methods and test procedures – Length measurement*

IEC 60793-1-30, *Optical fibres – Part 1-30: Measurement methods and test procedures – Fibre proof test*

IEC 60793-1-31, *Optical fibres – Part 1-31: Measurement methods and test procedures – Tensile strength*

IEC 60793-1-32, *Optical fibres – Part 1-32: Measurement methods and test procedures – Coating strippability*

IEC 60793-1-33, *Optical fibres – Part 1-33: Measurement methods and test procedures – Stress corrosion susceptibility*

IEC 60793-1-34, *Optical fibres – Part 1-34: Measurement methods and test procedures – Fibre curl*

IEC 60793-1-40:~~2001~~, *Optical fibres – Part 1-40: Measurement methods and test procedures – Attenuation*

IEC 60793-1-42, *Optical fibres – Part 1-42: Measurement methods and test procedures – Chromatic dispersion*

IEC 60793-1-44, *Optical fibres – Part 1-44: Measurement methods and test procedures – Cut-off wavelength*

IEC 60793-1-45, *Optical fibres – Part 1-45: Measurement methods and test procedures – Mode field diameter*

IEC 60793-1-46, *Optical fibres – Part 1-46: Measurement methods and test procedures – Monitoring of changes in optical transmittance*

IEC 60793-1-47, *Optical fibres – Part 1-47: Measurement methods and test procedures – Macrobending loss*

IEC 60793-1-48, *Optical fibres – Part 1-48: Measurement methods and test procedures – Polarization mode dispersion*

IEC 60793-1-50, *Optical fibres – Part 1-50: Measurement methods and test procedures – Damp heat (steady state) tests*

IEC 60793-1-51, *Optical fibres – Part 1-51: Measurement methods and test procedures – Dry heat (steady state) tests*

IEC 60793-1-52, *Optical fibres – Part 1-52: Measurement methods and test procedures – Change of temperature tests*

IEC 60793-1-53, *Optical fibres – Part 1-53: Measurement methods and test procedures – Water immersion tests*

IEC 60793-2, *Optical fibres – Part 2: Product specifications – General*

IEC 60794-2, *Optical fibre cables – Part 2: Indoor cables – Sectional specification*

~~IEC 60794-3, Optical fibre cables – Part 3: Outdoor cables – Sectional specification~~

~~IEC TR 62316, Guidance for the interpretation of OTDR backscattering traces~~



3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60793-2 and the IEC 60793-1 series apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

NOTE General definitions for fibres are provided in IEC 60793-2. The definitions of the specified attributes are contained in the relevant test methods standard of the IEC 60793-1 series, while general definitions for testing are provided in IEC 60793-1-1.

4 Abbreviated terms and symbols

For the purposes of this document, the following abbreviated terms and symbols apply:

F_{avg}	Average strip force
F_{peak}	Peak strip force
λ_0	Zero dispersion wavelength
λ_c	Fibre cut-off wavelength
λ_{cc}	Cable cut-off wavelength
MFD	Mode field diameter
n_d	Stress corrosion parameter – dynamic
PMD	Polarization mode dispersion
PMD_Q	PMD link design value

5 Specifications

5.1 General

The fibre shall consist of a glass core and glass cladding in accordance with the construction of optical fibre class B – single-mode fibre – as given in IEC 60793-2.

The term “glass” usually refers to material consisting of non-metallic oxides. The composition of some fibres may be all glass, or glass and glass/hard polymeric composites.

5.2 Dimensional requirements

Relevant dimensional attributes and measurement methods are given in Table 2.

Requirements common to all categories of class B single-mode fibres are given in Table 3.

Cladding diameter, cladding non-circularity, and core – cladding concentricity error shall be specified in the family specifications

Table 2 – Dimensional attributes and measurement methods

Attribute	Measurement method
Cladding diameter	IEC 60793-1-20
Cladding non-circularity	IEC 60793-1-20
Core – cladding concentricity error	IEC 60793-1-20
Primary coating diameter	IEC 60793-1-21
Primary coating non-circularity	IEC 60793-1-21
Primary coating-cladding concentricity error	IEC 60793-1-21
Fibre length	IEC 60793-1-22

Table 3 – Dimensional requirements common to all category B fibres

Attribute	Unit	Limit
Primary coating diameter – uncoloured	µm	235 to 255 ^a
Primary coating diameter – coloured	µm	235 to 265 ^a
Primary coating-cladding concentricity error	µm	≤ 12,5
Fibre length	km	^b
^a The above limits on primary coating diameter are most commonly used in telecommunications cables. There are other applications, such as fibre for use within optical sub-systems, pigtails, or specialty applications such as for submarines cables or for compact FTTH cables, which use other primary coating diameters, several of which are listed below. ~~Alternative nominal primary coating diameters and ranges:~~ ~~200 µm ± 10 µm (uncoloured; 190 µm to 220 µm coloured)~~ ~~400 µm ± 40 µm~~ ~~500 µm ± 30 µm~~ ~~700 µm ± 100 µm~~ ~~900 µm ± 100 µm~~ ~~The primary coating-cladding concentricity error should be limited to a maximum 10 µm for 200 µm.~~ 180 µm to 210 µm uncoloured; 180 µm to 220 µm coloured 400 µm ± 40 µm 500 µm ± 50 µm 700 µm ± 70 µm 900 µm ± 90 µm Alternative coating diameters may impact fibre connectivity such as ribbons, multi-fibre connectors, mechanical splices, and fusion splice protectors; they may also need adjustments to connectivity tools and/or tighter coating tolerances.		
^b Length requirements vary and should be agreed between supplier and customer.		

5.3 Mechanical requirements

Relevant mechanical attributes and test methods are given in Table 4. The relationship between some of these attributes and mechanical reliability are described in IEC TR 62048 and ITU-T G.Sup.59.

Requirements common to all categories of class B single-mode fibres are given in Table 5.

Table 4 – Mechanical attributes and test methods

Attribute	Test method
Proof test	IEC 60793-1-30
Tensile strength	IEC 60793-1-31
Coating strippability	IEC 60793-1-32
Stress corrosion susceptibility	IEC 60793-1-33
Fibre curl	IEC 60793-1-34

Table 5 – Mechanical requirements common to all class B fibres

Attribute	Unit	Limit
Proof stress level	GPa	$\geq 0,69^a$
Coating strip force (average) ^{b, c}	N	$1,0 \leq F_{ave} \leq 5,0$
Coating strip force (peak) ^{b, c}	N	$1,0 \leq F_{peak} \leq 8,9$
Fibre curl radius	m	$\geq 2^d$
Tensile strength (median) for 0,5 m specimen length	GPa	$\geq 3,8$
Stress corrosion susceptibility parameter, n_d	–	≥ 18

^a The proof test value of 0,69 GPa equals about 1 % strain or about 8,8 N force. For the relation between these different units, see IEC TR 62048:2014, [7.4 clause 8.4](#).

^b Either average strip force or peak strip force, which are defined in the test procedure, may be specified with agreement between supplier and customer.

^c In case of alternative nominal primary coating diameters (see Table 2), associated alternative coating strip force values need to be agreed between supplier and customer [or provided in the detailed specifications provided in Annexes of this document](#).

^d Depending on splicing methods, a minimum of 4 m may be specified for fibre intended to be used in some cable constructions – such as ribbon cable.

5.4 Transmission requirements

Relevant transmission attributes and measurement methods are given in Table 6.

Requirements common to all categories of class B single-mode fibres are shown in Table 7.

Requirements that shall be specified in the family specifications are listed in Table 8.

Table 6 – Transmission attributes and measurement methods

Attribute	Measurement method
Attenuation coefficient	IEC 60793-1-40 ^a
Chromatic dispersion	IEC 60793-1-42
Cut-off wavelength ^b	IEC 60793-1-44
Mode field diameter	IEC 60793-1-45
Change of optical transmission	IEC 60793-1-46
Macrobending loss	IEC 60793-1-47
Polarization mode dispersion	IEC 60793-1-48
NOTE The indicated maximum attenuation values apply to cabled and uncabled optical fibres. Tighter specifications for the fibre may be requested to account for added attenuation in the cabling process; for the maximum cabled attenuation values, reference is made to IEC 60794-2, which can be used in conjunction with this document.	
^a The attenuation coefficient at various wavelengths can be calculated using the measured values at a few wavelengths using a spectral model such as that given in IEC 60793-1-40. For example, the attenuation at 1 480 nm can be calculated and used for design of systems that employ remote pumping of optical amplifiers. When using Method C, OTDR, additional guidance information in IEC TR 62316 shall be taken into account. As reported in IEC 60793-1-40:20xx, the spectral attenuation model, ~~to date~~, has ~~only~~ been demonstrated on ~~B1 and B2~~ all class B fibres.	
^b There are two ways to measure cut-off wavelength, leading to: fibre cut-off wavelength λ_c and to cable cut-off wavelength λ_{cc}, respectively. The correlation of the measured values of λ_c and λ_{cc} depends on the specific fibre and cable design and the test conditions. While in general $\lambda_{cc} < \lambda_c$ a general quantitative relationship cannot be easily established, the importance of ensuring single-mode transmission in the minimum cable length between joints at the minimum operating wavelength is paramount. This may be performed by recommending the maximum cable cut-off wavelength λ_{cc} of a cabled single-mode fibre to be 1 260 nm or for worst case length and bends by recommending a maximum fibre cut-off wavelength λ_c to be ~~1 250~~ 1 260 nm.	

Table 7 – Transmission, requirements common to all class B fibres

Attribute	Unit	Limit
Polarization mode dispersion (PMD) coefficient link design value (PMD_Q)	$ps/\sqrt{km}$	^a
^a A maximum value of PMD_Q on uncabled fibre shall be agreed between supplier and customer to satisfy the primary requirement of cable PMD, given in IEC 60794-3.		

Table 8 – Additional transmission attributes required in the family specifications

Attribute
Attenuation coefficient and wavelengths
Chromatic dispersion characteristics
Nominal mode field diameter (MFD) range and wavelength
Mode field diameter tolerance
Cable cut-off wavelength, λ_{cc}
Macrobending loss including: wavelength, mandrel size, and number of turns
Cladding diameter
Cladding non-circularity
Core – cladding concentricity error

For category ~~B4~~ B-655 fibre, information for system design is given in Annex G.

5.5 Environmental requirements

5.5.1 General

Environmental exposure tests and measurement methods are documented in two forms:

- relevant environmental attributes and test methods are given in Table 9;
- measurements of a particular mechanical or transmission attributes that may change on the application of the environment are listed in Table 10.

Table 9 – Environmental exposure tests

Attribute	Test method
Damp heat tests	IEC 60793-1-50
Dry heat tests	IEC 60793-1-51
Change of temperature tests	IEC 60793-1-52
Water immersion tests	IEC 60793-1-53

Table 10 – Attributes measured in environmental exposure tests

Attribute	Test method
Change in optical transmission	IEC 60793-1-46
Attenuation	IEC 60793-1-40
Coating strip force	IEC 60793-1-32
Tensile strength	IEC 60793-1-31
Stress corrosion susceptibility	IEC 60793-1-33

These tests are normally conducted periodically as type-tests for a fibre and coating design. Unless otherwise indicated, the recovery period allowed between the completion of the environmental exposure and performing the attribute measurements shall be as stated in the particular environmental test method.

5.5.2 Optical environmental requirements – Attenuation

Change in attenuation from the initial value shall be less than the values in Table 11. Attenuation shall be measured periodically during the entire exposure to each environment and after removal.

Table 11 – Change in attenuation for environmental tests

Environment	Wavelength nm	Maximum attenuation increase dB/km
Damp heat	1 550, 1 625	≤ 0,05
Dry heat	1 550, 1 625	≤ 0,05
Change of temperature	1 550, 1 625	≤ 0,05
Water immersion	1 550, 1 625	≤ 0,05
NOTE Attenuation changes at wavelengths lower than the test wavelength are smaller than the attenuation change at the test wavelength.		

5.5.3 Mechanical environmental requirements

5.5.3.1 General

These tests are, in practice, the most severe requirements amongst the environments defined in Table 9.

5.5.3.2 Coating strip force

The attributes given in Table 12 shall be verified following removal of the fibre from the particular environment.

Table 12 – Coating strip force for environmental tests

Environment	Average strip force N	Peak strip force N
Damp heat	$1,0 \leq F_{\text{avg}} \leq 5,0$	$1,0 \leq F_{\text{peak}} \leq 8,9$
Water immersion	$1,0 \leq F_{\text{avg}} \leq 5,0$	$1,0 \leq F_{\text{peak}} \leq 8,9$
NOTE In case of alternative nominal primary coating diameters (see Table 2), associated alternative coating strip force values need to be agreed between supplier and customer <i>unless specified in the detailed product specifications or provided in the annexes of this document.</i>		

5.5.3.3 Tensile strength

The attributes given in Table 13 shall be verified following removal of the fibre from the environment indicated.

Table 13 – Tensile strength for environmental tests

Environment	Median tensile strength (GPa), specimen length: 0,5 m	15 percentile of the tensile strength distribution (GPa), specimen length: 0,5 m
Damp heat	$\geq 3,03$	$\geq 2,76$
NOTE These requirements do not apply to hermetically coated fibre. (A hermetic coating is a protective layer that completely segregates the glass fibre from moisture, thereby ensuring a high level of stress corrosion resistance. Typical hermetic coating is a carbon layer of several microns thickness applied on the glass surface.)		

5.5.3.4 Stress corrosion susceptibility

The attribute given in Table 14 shall be verified following removal of the fibre from the environment indicated.

Table 14 – Stress corrosion susceptibility for environmental tests

Environment	Stress corrosion susceptibility parameter, n_d
Damp heat	≥ 18
NOTE This requirement does not apply to hermetically coated fibre (see definition for hermetic coating in Table 13).	

Annex A (normative)

Family specification for category ~~B1.1~~ B-652 Dispersion unshifted single-mode fibres

A.1 General

This dispersion unshifted single-mode fibre is optimized for use in the 1 310 nm region but can be used in the 1 550 nm and 1 625 nm regions. Depending on link length and bit rates, dispersion may need accommodation in the 1 550 nm and 1 625 nm regions.

The clauses and tables in Annex A contain particular requirements applicable to category ~~B1.1~~ B-652 fibres. Common requirements, repeated here for ease of reference from the sectional specification, are noted by an entry in the “Reference” column. Relevant notes from the sectional specification are not repeated but indicated with a superscript “SS”.

A.2 Dimensional requirements

Table A.1 contains dimensional requirements specific to category ~~B1.1~~ B-652.B fibres.

Table A.1 – Dimensional requirements specific to category ~~B1.1~~ B-652.B fibres

Attribute	Unit	Limit (250 µm coating)	Limit (200 µm coating)	Reference
Cladding diameter	µm	125 ± 1	125 ± 1	5.2
Cladding non-circularity	%	≤ 1,0	≤ 1,0	5.2
Core – cladding concentricity error	µm	≤ 0,6	≤ 0,6	5.2
Primary coating diameter – uncoloured ^a	µm	235 to 255	180 to 210	5.2
Primary coating diameter – coloured ^a	µm	235 to 265	180 to 220	5.2
Primary coating-cladding concentricity error	µm	≤ 12,5	≤ 10,0	5.2
Fibre length	km	See ~~5.1~~ 5.2	See 5.2	5.2
^a Alternative nominal primary coating diameters may be used (see Table 2), to be agreed between supplier and customer.				

Table A.2 contains dimensional requirements specific to category B-652.D fibres.

Table A.2 – Dimensional requirements specific to category B-652.D fibres

Attribute	Unit	Limit (250 µm coating)	Limit (200 µm coating)	Reference
Cladding diameter	µm	125 ± 0,7	125 ± 0,7	5.2
Cladding non-circularity	%	≤ 1,0	≤ 1,0	5.2
Core – cladding concentricity error	µm	≤ 0,6	≤ 0,6	5.2
Primary coating diameter – uncoloured ^a	µm	235 to 255	180 to 210	5.2
Primary coating diameter – coloured ^a	µm	235 to 265	180 to 220	5.2
Primary coating-cladding concentricity error	µm	≤ 12,5	≤ 10,0	5.2
Fibre length	km	See 5.2	See 5.2	5.2
^a Alternative nominal primary coating diameters may be used (see Table 2), to be agreed between supplier and customer.				

A.3 Mechanical requirements

Table A.3 contains mechanical requirements specific to category ~~B1.1~~ B-652 fibres.

Table A.3 – Mechanical requirements specific to category ~~B1.1~~ B-652 fibres

Attribute	Unit	Limit (250 μm coating)	Limit (200 μm coating)	Reference
Proof stress level	GPa	≥ 0,69 SS		5.3
Coating strip force (average) SS	N	$1,0 \leq F_{ave} \leq 5,0$	$0.4 \leq F_{ave} \leq 5,0$	5.3
Coating strip force (peak) SS	N	$1,0 \leq F_{peak} \leq 8,9$	$0.4 \leq F_{peak} \leq 8,9$	5.3
Fibre curl radius	m	≥ 2 a		5.3
Tensile strength (median) for 0,5 m specimen length	GPa	≥ 3,8		5.3
Stress corrosion susceptibility parameter, n_d	–	≥ 18		5.3
a Depending on splicing methods, a minimum of 4 m may be specified for fibre intended to be used in some cable constructions – such as ribbon cable.				

A.4 Transmission requirements

Table A.4 contains transmission requirements specific to sub-category ~~B1.1~~ B-652.B fibres and Table A.5 contains transmission requirements specific to sub-category B-652.D fibres. Table A.6 provides chromatic dispersion values for sub-category B-652.D fibres.

Table A.4 – Transmission requirements specific to sub-category ~~B1.1~~ B-652.B fibres

Attribute	Unit	Limit	Reference
Attenuation coefficient at 1 310 nm	dB/km	$\leq 0,40$	5.4
Attenuation coefficient at 1 550 nm	dB/km	$\leq 0,30$ 35	5.4
Attenuation coefficient at 1 625 nm	dB/km	$\leq 0,40$	5.4
Zero dispersion wavelength, λ_0	nm	$1\,300 \leq \lambda_0 \leq 1\,324$	5.4
Zero dispersion slope	ps/(nm ² x km)	$\leq 0,092$	5.4
Nominal MFD range at 1 310 nm ^a	μm	8,6 to 9,5	5.4
MFD tolerance	μm	$\pm 0,6$	5.4
Cable cut-off wavelength, λ_{cc}	nm	$\leq 1\,260$	5.4
Macrobending loss at 1 625 nm, 100 turns on a 30 mm radius mandrel	dB	$\leq 0,1$	5.4
Polarization mode dispersion (PMD) coefficient	ps/√km	See 5.4	5.4
NOTE In the 1 550 nm region, the chromatic dispersion can be approximated as a linear function with wavelength. A typical value for the chromatic dispersion at 1 550 nm is 17 ps/(nm x km) with a typical slope at 1 550 nm of 0,056 ps/(nm ² x km).			
^a The value of the nominal MFD shall be agreed between supplier and customer from within the range given. The tolerance shown is then applied around that nominal value.			

Table A.5 – Transmission requirements specific to sub-category B-652.D Fibres

Attribute	Unit	Limit	Reference
Attenuation coefficient from 1 310 nm to 1 625 nm ^a	dB/km	$\leq 0,40$	5.4
Attenuation coefficient at 1 383 nm ± 3 nm	dB/km	$\leq 0,40$	5.4
Attenuation coefficient 1 530 nm – 1 565 nm	dB/km	$\leq 0,30$	5.4
Chromatic dispersion	See Table A.6		5.4
Nominal MFD range at 1 310 nm ^b	μm	8,6 to 9,2	5.4
MFD tolerance	μm	$\pm 0,4$	5.4
Cable cut-off wavelength, λ_{cc}	nm	$\leq 1\,260$	5.4
Macrobending loss at 1 625 nm, 100 turns on a 30 mm radius mandrel	dB	$\leq 0,1$	5.4
Polarization mode dispersion (PMD) coefficient	ps/√km	See 5.4	5.4
^a This wavelength region can be extended to 1 260 nm by adding 0.07 dB/km induced Rayleigh scattering loss to the attenuation value at 1 310 nm.			
^b The value of the nominal MFD shall be agreed between supplier and customer from within the range given. The tolerance shown is then applied around that nominal value.			

Table A.6 – Chromatic dispersion properties for sub-category B-652.D fibres

Attribute ^a	Detail	Limit	Unit
3-term Sellmeier fitting (1260 nm to 1460 nm)	λ_{0min}	1 300	nm
	λ_{0max}	1 324	nm
	S_{0min}	0,073	ps/(nm ² × km)
	S_{0max}	0,092	ps/(nm ² × km)
Linear fitting (1460 nm to 1625 nm)	Minimum at 1 550 nm	13,3	ps/(nm × km)
	Maximum at 1 550 nm	18,6	ps/(nm × km)
	Minimum at 1 625 nm	17,2	ps/(nm × km)
	Maximum at 1 625 nm	23,7	ps/(nm × km)
^a Details of the equations used that define these attributes are provided in section 6.10 of ITU-T G.652.			

A.5 Hydrogen ageing for sub-category B-652.D

Select a fibre specimen at least 1 km long. After spooling the fibre to a test configuration that minimizes the effect of winding on attenuation at 1 310 nm, measure the attenuation coefficient of the specimen at 1 240 nm and at 1 383 nm. This measurement gives the baseline attenuation for the specimen. Expose the fibre to 0,01 atmospheres of hydrogen at room temperature (reference test). For practical considerations, such as the availability of equipment and testing time, higher H₂ concentrations (e.g. 1 atm) can be used with proper care as mentioned in Note 4. During this exposure, monitor the attenuation coefficient of the specimen at 1 240 nm. This wavelength is indicative of the molecular hydrogen present in the specimen. Constructing the change in attenuation as the monitored results minus the baseline value, continue exposure until the 1 240 nm attenuation changes by $\geq 0,03$ dB/km. At this time, the attenuation increase at 1 383 nm may be considered fully saturated, and the specimen may be removed from the hydrogen atmosphere. After at least 14 days in the normal laboratory environment, measure the attenuation coefficient of the fibre at 1 383 nm using methods A, B or C of IEC 60793-1-40.

NOTE 1 This is a type test performed periodically to ensure that the manufacturing process reliably yields fibre with acceptable ageing characteristics. For example, 10 fibre samples can be tested every 6 months.

NOTE 2 This test is not appropriate for hermetically coated fibre (see definition for hermetic coating in Table 12).

NOTE 3 For non-hermetic fibres, typical hydrogen exposure is from 4 days to 6 days (see definition for hermetic coating in Table 12).

NOTE 4 Hydrogen ageing should be performed in H₂ concentrations that produce results representative of the actual field conditions. Although increased H₂ concentration reduces testing time, it tends to produce slightly higher values of added loss at equivalent exposure time (see threshold for increases at 1 240 nm). The 0,01 atmosphere test is a compromise between impractically long testing times and unrealistically high added loss. When testing with higher H₂ concentration, the reduced testing time can require increased safety measures.

A.6 Environmental requirements

The requirements of 5.5 shall be met.

Annex C (normative)

Family specification for category B1.3 single-mode fibres

C.1 — General

This dispersion unshifted single-mode fibre can be used from 1 260 nm up to 1 625 nm. Chromatic dispersion in this band may impose requirements either on the maximum link length or on the need for accommodation.

The clauses and tables in Annex C contain particular requirements applicable to category B1.3 fibres. Common requirements, repeated here for ease of reference from the sectional specification, are noted by an entry in the “Reference” column. Relevant notes from the sectional specification are not repeated but indicated with a superscript “SS”.

C.2 — Dimensional requirements

Table C.1 contains dimensional requirements specific to category B1.3 fibres.

Table C.1 — Dimensional requirements specific to category B1.3 fibres

Attribute	Unit	Limit	Reference
Cladding diameter	µm	125 ± 1	5.2
Cladding non-circularity	%	$\leq 1,0$	5.2
Core concentricity error	µm	$\leq 0,6$	5.2
Primary coating diameter — uncoloured ^a	µm	235 to 255	5.2
Primary coating diameter — coloured ^a	µm	235 to 265	5.2
Primary coating-cladding concentricity error	µm	$\leq 12,5$	5.2
Fibre length	km	See 5.2	5.2
^a —Alternative nominal primary coating diameters may be used, (see Table 2), to be agreed between supplier and customer.			

C.3 — Mechanical requirements

Table C.2 contains mechanical requirements specific to category B1.3 fibres.

Table C.2 — Mechanical requirements specific to category B1.3 fibres

Attribute	Unit	Limit	Reference
Proof stress level	GPa	$\geq 0,69_{SS}$	5.3
Coating strip force (average) ^{SS}	N	$1,0 \leq F_{ave} \leq 5,0$	5.3
Coating strip force (peak) ^{SS}	N	$1,0 \leq F_{peak} \leq 8,9$	5.3
Fibre curl radius	m	$\geq 2^a$	5.3
Tensile strength (median) for 0,5 m specimen length	GPa	$\geq 3,8$	5.3
Stress corrosion susceptibility parameter, n_d	—	≥ 18	5.3
^a —Depending on splicing methods, a minimum of 4 m may be specified for fibre intended to be used in some cable constructions — such as ribbon cable.			

C.4 Transmission requirements

Table C.3 contains transmission requirements specific to category B1.3 fibres.

Table C.3—Transmission requirements specific to category B1.3 fibres

Attribute	Unit	Limit	Reference
Attenuation coefficient from 1 310 nm ^a to 1 625 nm	dB/km	$\leq 0,40$	
Attenuation coefficient at 1 383 nm $\pm$ 3 nm	dB/km	$\leq 0,40^b$	
Attenuation coefficient at 1 550 nm	dB/km	$\leq 0,30$	
Zero-dispersion wavelength, λ_0	nm	$1\,300 \leq \lambda_0 \leq 1\,324$	
Zero-dispersion slope	ps/nm ² ·km	$\leq 0,092$	
Nominal MFD range at 1 310 nm ^c	μm	8,6 to 9,5	
MFD tolerance	μm	$\pm 0,6$	
Cable cut-off wavelength	nm	$\leq 1\,260$	
Macrobending loss at 1 625 nm, 100 turns on a 30 mm radius mandrel	dB	$\leq 0,1$	
Polarization mode dispersion (PMD) coefficient	ps/√km	See 5.4	
NOTE—In the 1 550 nm region, the chromatic dispersion can be approximated as a linear function with wavelength. A typical value for the chromatic dispersion at 1 550 nm is 17 ps/nm ² ·km with a typical slope at 1 550 nm of 0,056 ps/nm ² ·km.			
^a —This wavelength region can be extended to 1 260 nm by adding 0,07 dB/km induced Rayleigh scattering loss to the attenuation value at 1 310 nm.			
^b —The average attenuation coefficient after ageing according to the test outlined in the following paragraph shall be less than the value specified for the range of 1 310 nm to 1 625 nm.			
^c —The value of the nominal MFD shall be agreed between supplier and customer from within the range given. The tolerance shown is then applied around that nominal value.			

C.5 Hydrogen ageing for category B1.3

Select a fibre specimen at least 1 km long. After spooling the fibre to a test configuration that minimizes the effect of winding on attenuation at 1 310 nm, measure the attenuation coefficient of the specimen at 1 240 nm and at 1 383 nm. This measurement gives the baseline attenuation for the specimen. Expose the fibre to 0,01 atmospheres of hydrogen at room temperature (reference test). For practical considerations, such as the availability of equipment and testing time, higher H₂ concentrations (e.g. 1 atm) can be used with proper care as mentioned in Note 4. During this exposure, monitor the attenuation coefficient of the specimen at 1 240 nm. This wavelength is indicative of the molecular hydrogen present in the specimen. Constructing the change in attenuation as the monitored results minus the baseline value, continue exposure until the 1 240 nm attenuation changes by $\geq 0,03$ dB/km. At this time, the attenuation increase at 1 383 nm may be considered fully saturated, and the specimen may be removed from the hydrogen atmosphere. After at least 14 days in the normal laboratory environment, measure the attenuation coefficient of the fibre at 1 383 nm using methods A, B or C of IEC 60793-1-40:2001.

NOTE 1—This is a type test performed periodically to ensure that the manufacturing process reliably yields fibre with acceptable ageing characteristics. For example, 10 fibre samples can be tested every 6 months.

NOTE 2—This test is not appropriate for hermetically coated fibre (see definition for hermetic coating in Table 12).

NOTE 3—For non-hermetic fibres, typical hydrogen exposure is from 4 days to 6 days (see definition for hermetic coating in Table 12).

NOTE 4—To be useful, hydrogen ageing is performed in H₂ concentrations that produce results representative of the actual field conditions. Although increased H₂ concentration reduces testing time, it tends to produce slightly

~~higher values of added loss at equivalent exposure time (see threshold for increases at 1 240 nm). The 0,01 atmosphere test is a compromise between impractically long testing times and unrealistically high added loss. When testing with higher H₂ concentration, the reduced testing time can require increased safety measures.~~

~~C.6 Environmental requirements~~

~~The requirements of 5.5 shall be met.~~

Annex B (normative)

Family specification for category ~~B2~~ B-653 Dispersion shifted single-mode fibres

B.1 General

This dispersion-shifted single-mode fibre is optimized for single-channel transmission in the 1 550 nm region. Multiple channels can only be transmitted if care is taken to avoid the effects of four-wave mixing by, for example, moderating the power levels or appropriate spacing or placement of the channels.

The clauses and tables in Annex B contain particular requirements applicable to category ~~B2~~ B-653 fibres. Common requirements, repeated here for ease of reference from the sectional specification, are noted by an entry in the “Reference” column. Relevant notes from the sectional specification are not repeated but indicated with a superscript “SS”.

There are two sub-categories which are designated as with suffixes, “~~a~~” and “~~b~~” “.A” and “.B”. These sub-categories are distinguished by the glass geometry tolerances, mode field diameter tolerance, and chromatic dispersion coefficient and mode field diameter attribute specifications.

B.2 Dimensional requirements

Table B.1 contains dimensional requirements specific to category ~~B2~~ B-653 fibres.

Table B.1 – Dimensional requirements specific to category ~~B2~~ B-653 fibres

Attribute	Unit	B-653.A Limit	B-653.B Limit	Reference
Cladding diameter	µm	125 ± 1	125 ± 1	5.2
Cladding non-circularity	%	≤ 2,0	≤ 1,0	5.2
Core – cladding concentricity error	µm	≤ 0,8	≤ 0,6	5.2
Primary coating diameter – uncoloured ^a	µm	235 to 255	235 to 255	5.2
Primary coating diameter – coloured ^a	µm	235 to 265	235 to 265	5.2
Primary coating-cladding concentricity error	µm	≤ 12,5	≤ 12,5	5.2
Fibre length	km	See 5.2	See 5.2	5.2
^a Alternative nominal primary coating diameters may be used, (see Table 2), to be agreed between supplier and customer.				

~~D.3 Mechanical requirements~~

Table B.2 contains mechanical requirements specific to category ~~B2~~ B-653 fibres.

Table B.2 – Mechanical requirements specific to category ~~B2~~ B-653 fibres

Attribute	Unit	Limit	Reference
Proof stress level	GPa	$\geq 0,69$ ^{SS}	5.3
Coating strip force (average) ^{SS}	N	$1,0 \leq F_{ave} \leq 5,0$	5.3
Coating strip force (peak) ^{SS}	N	$1,0 \leq F_{peak} \leq 8,9$	5.3
Fibre curl radius	M	≥ 2 ^a	5.3
Tensile strength (median) for 0,5 m specimen length	GPa	$\geq 3,8$	5.3
Stress corrosion susceptibility parameter, n_d	–	≥ 18	5.3
^a Depending on splicing methods, a minimum of 4 m may be specified for fibre intended to be used in some cable constructions – such as ribbon cable.			

B.3 Transmission requirements

B.3.1 General

Table B.3 contains transmission requirements specific to category ~~B2~~ B-653 fibres.

Table B.3 – Transmission requirements specific to category ~~B2~~ B-653 fibres

Attribute	Unit	B-653.A Limit	B-653.B Limit	Reference
Attenuation coefficient at 1 310 nm ^a	dB/km	$\leq 0,50$	$\leq 0,50$	5.4
Attenuation coefficient at 1 550 nm	dB/km	$\leq 0,30$ ³⁵	$\leq 0,30$ ³⁵	5.4
Attenuation coefficient at 1 625 nm ^a	dB/km	$\leq 0,40$	$\leq 0,40$	5.4
Chromatic dispersion coefficient	ps/(nm × km)	See B.3.2	See B.3.3	5.4
Nominal MFD range at 1 550 nm ^b	μm	7,8 to 8,5	7,8 to 8,5	5.4
MFD tolerance	μm	$\pm 0,8$	$\pm 0,6$	5.4
Cable cut-off wavelength, λ_{cc}	nm	$\leq 1\,270$	$\leq 1\,270$	5.4
Macrobending loss at 1 550 nm, 100 turns on a 30 mm radius mandrel	dB	$\leq 0,5$	$\leq 0,1$	5.4
Polarization mode dispersion (PMD) coefficient	ps/ $\sqrt{\text{km}}$	See 5.4	See 5.4	5.4
^a This attenuation coefficient is not specified in ITU-T G.653 at this time. If ITU-T specifies this parameter the value in the ITU-T document takes precedent.				
^b The value of the nominal MFD shall be agreed between supplier and customer from within the range given. The tolerance shown is then applied around that nominal value.				

B.3.2 Chromatic dispersion coefficient requirement for sub-category ~~B2-a~~ B-653.A fibres

The requirement is given as a combined requirement on the absolute value of the chromatic dispersion coefficient for a range of wavelength and a limit on the zero-dispersion wavelength, λ_0 , and slope at λ_0 , S_0 .

$$|D(\lambda)| \leq 3,5 \text{ ps}/(\text{nm} \times \text{km}) \text{ for } 1\,525 \text{ nm} \leq \lambda \leq 1\,575 \text{ nm} \quad (\text{B.1})$$

and

$$1\,500\text{ nm} \leq \lambda_0 \leq 1\,600\text{ nm} \quad (\text{B.2})$$

and

$$S_0 \leq 0,085\text{ ps}/(\text{nm}^2 \times \text{km}). \quad (\text{B.3})$$

B.3.3 Chromatic dispersion coefficient requirement for sub-category ~~B2_b~~ B-653. B fibres

The requirement is given as a series of bounding line segments versus wavelength. These line segment boundaries are equivalent to the requirements stated in D.4.2. The units of chromatic dispersion coefficient, $D(\lambda)$, are ps/(nm × km) and the units of wavelength, λ , are nm.

$$0,085 (\lambda - 1\,525) - 3,5 \leq D(\lambda) \text{ for } 1\,460\text{ nm} \leq \lambda \leq 1\,525\text{ nm} \quad (\text{B.4})$$

$$\frac{3,5}{75} (\lambda - 1\,600) \leq D(\lambda) \text{ for } 1\,525\text{ nm} \leq \lambda \leq 1\,625\text{ nm} \quad (\text{B.5})$$

$$D(\lambda) \leq \frac{3,5}{75} (\lambda - 1\,500) \text{ for } 1\,460\text{ nm} \leq \lambda \leq 1\,575\text{ nm} \quad (\text{B.6})$$

$$D(\lambda) \leq 0,85 (\lambda - 1\,575) + 3,5 \text{ for } 1\,575\text{ nm} \leq \lambda \leq 1\,625\text{ nm} \quad (\text{B.7})$$

B.4 Environmental requirements

The requirements of 5.5 shall be met.

Annex C (normative)

Family specification for category ~~B1.2~~ B-654 cut-off shifted single-mode fibres

C.1 General

This dispersion unshifted single-mode fibre is optimized for low loss in the 1 550 nm region, with the cutoff wavelength shifted above the 1 310 nm region.

The clauses and tables in Annex C contain particular requirements applicable to category ~~B1.2~~ B-654 fibres. Common requirements, repeated here for ease of reference from the sectional specification, are noted by an entry in the "Reference" column. Relevant notes from the sectional specification are not repeated but indicated with a superscript "SS".

There are ~~three~~ five sub-categories which are designated as with suffixes, "~~_b~~", "~~_c~~" and "~~_d~~" ".A", ".B", ".C", ".D" and ".E". These sub-categories are distinguished by the chromatic dispersion coefficient and mode field diameter attribute specifications.

C.2 Dimensional requirements

Table C.1 contains dimensional requirements specific to category ~~B1.2~~ B-654 fibres.

Table C.1 – Dimensional requirements specific to category ~~B1.2~~ B-654 fibres

Attribute	Unit	Limit	Reference
Cladding diameter	µm	125 ± 1	5.2
Cladding non-circularity	%	≤ 2,0	5.2
Core – cladding concentricity error	µm	≤ 0,8	5.2
Primary coating diameter – uncoloured ^a	µm	235 to 255	5.2
Primary coating diameter – coloured ^a	µm	235 to 265	5.2
Primary coating-cladding concentricity error	µm	≤ 12,5	5.2
Fibre length	km	See 5.2	5.2
^a Alternative nominal primary coating diameters may be used, (see Table 2), to be agreed between supplier and customer.			

C.3 Mechanical requirements

Table C.2 contains mechanical requirements specific to category ~~B1.2~~ B-654 fibres.

Table C.2 – Mechanical requirements specific to category ~~B1.2~~ B-654 fibres

Attribute	Unit	Limit	Reference
Proof stress level	GPa	$\geq 0,69$ ^{SS}	5.3
Coating strip force (average) ^{SS}	N	$1,0 \leq F_{ave} \leq 5,0$	5.3
Coating strip force (peak) ^{SS}	N	$1,0 \leq F_{peak} \leq 8,9$	5.3
Fibre curl radius	M	≥ 2 ^a	5.3
Tensile strength (median) for 0.5 m specimen length	GPa	≥ 3.8	5.3
Stress corrosion-susceptibility parameter, n_d	-	≥ 18	5.3
^a Depending on splicing methods, a minimum of 4 m may be specified for fibre intended to be used in some cable constructions – such as ribbon cable.			

~~B.4~~ Transmission requirements

Table C.3 contains transmission requirements specific to category ~~B1.2~~ B-654 fibres. There are ~~three~~ five sub-categories designated as "~~b~~", "~~c~~" and "~~d~~" ".A", ".B", ".C", ".D", and ".E".

Table C.3 – Transmission requirements specific to category ~~B1.2~~ B-654 fibres

Attribute	Unit	.A Limit	~~b~~ .B Limit	~~c~~ .C Limit	~~d~~ .D Limit	.E Limit	Ref
Attenuation coefficient at 1 550 nm	dB/km	$\leq 0,22$	$\leq 0,22$	$\leq 0,22$	$\leq 0,20$	$\leq 0,23$	5.4
Attenuation coefficient at 1 625 nm ^a	dB/km	NA	$\leq 0,40$	$\leq 0,40$	$\leq 0,40$	NA	5.4
Chromatic dispersion slope at 1 550 nm	ps/(nm ² x km)	$\leq 0,070$	$\leq 0,070$	$\leq 0,070$	$\leq 0,070$	$\leq 0,070$ ≥ 0.050	5.4
Chromatic dispersion coefficient at 1 550 nm	ps/(nm x km)	≤ 20	≤ 22	≤ 20	≤ 23	≤ 23 ≥ 17	5.4
Nominal MFD range at 1 550 nm ^b	μm	9,5 to 10,5	9,5 to 13,0	9,5 to 10,5	11,5 to 15,0	11,5 to 12,5	5.4
MFD tolerance	μm	$\pm 0,7$	$\pm 0,7$	$\pm 0,7$	$\pm 0,7$	$\pm 0,7$	5.4
Cable cut-off wavelength, λ_{cc}	nm	$\leq 1\,530$	$\leq 1\,530$	$\leq 1\,530$	$\leq 1\,530$	$\leq 1\,530$	5.4
Macrobending loss at 1 625 nm, 100 turns on a 30 mm radius mandrel	dB	$\leq 0,50$	$\leq 0,50$	$\leq 0,50$	$\leq 2,0$ ^c	$\leq 0,1$	5.4
Polarization mode dispersion (PMD) coefficient	ps/ $\sqrt{\text{km}}$	See 5.4	See 5.4	See 5.4	See 5.4	See 5.4	5.4
^a This attenuation coefficient is not specified in ITU-T G.654 at this time. If ITU-T specifies this parameter the value in the ITU-T document takes precedent.							
^b The value of the nominal MFD shall be agreed between supplier and customer from within the range given. The tolerance shown is then applied around that nominal value.							
^c Other application specific test conditions and requirements (bending radius and number of turns) at 1 550 nm are under study.							

C.4 Chromatic dispersion parameters for B-654.E fibres

For B-654.E fibre, the chromatic dispersion parameters indicated in Table C.3 are specified in order to bind the minimum/maximum chromatic dispersion coefficient $D(\lambda)$ at wavelength λ from 1 530 nm to 1 625 nm. This allows more accurate system design, in which dispersion-compensating schemes are incorporated. The quadratic fitting for the group delay found in Table D.1 of IEC 60793-1-42:2013 is applied, and the $D(\lambda)$ is bound by the following inequality:

$$D_{1\,550\min} + S_{1\,550\min}(\lambda - 1\,550) \leq D(\lambda) \leq D_{1\,550\max} + S_{1\,550\max}(\lambda - 1\,550) \quad (\text{C.1})$$

where $D_{1\,550\min}$, $D_{1\,550\max}$, $S_{1\,550\min}$, and $S_{1\,550\max}$ are listed in Table C.3 and below:

$$D_{1550\min} = 17 \text{ ps}/(\text{nm} \times \text{km})$$

$$D_{1550\max} = 23 \text{ ps}/(\text{nm} \times \text{km})$$

$$S_{1550\min} = 0,050 \text{ ps}/(\text{nm}^2 \times \text{km})$$

$$S_{1550\max} = 0,070 \text{ ps}/(\text{nm}^2 \times \text{km}).$$

C.5 Environmental requirements

The requirements of 5.5 shall be met.

Annex D (normative)

Family specification for category ~~B4~~ B-655 non-zero dispersion shifted single-mode fibres

D.1 General

This non-zero dispersion-shifted single-mode fibre is optimized for multiple channel transmission in the 1 550 nm region with a cut-off wavelength that may be shifted above the 1 310 nm region. The **chromatic** dispersion coefficient is required to be non-zero throughout the band from 1 530 nm to 1 565 nm, but may be either positive or negative. Depending on the **chromatic** dispersion characteristics, multiple channel transmission may be possible at bands either above or below the normal 1 550 nm region.

The clauses and tables in Annex D contain particular requirements applicable to category ~~B4~~ B-655 fibres. Common requirements, repeated here for ease of reference from the sectional specification, are noted by an entry in the "reference" column. Relevant notes from the sectional specification are not repeated but indicated with a superscript "SS".

There are three sub-categories which are designated as with suffixes, "~~_e~~", "~~_d~~", and "~~_e~~" ".C", ".D", and ".E". These sub-categories are distinguished by the chromatic dispersion coefficient attribute specifications. For sub-category ~~B4_e~~ B-655.C, the traditional "box specification" is maintained. For sub-categories ~~B4_d~~ and ~~B4_e~~ B-655.D and B-655.E fibres, the chromatic dispersion limits are in the form of a pair of curves versus wavelength. See Annex G for more information on these curves.

D.2 Dimensional requirements

Table D.1 contains dimensional requirements specific to category ~~B4~~ B-655 fibres.

Table D.1 – Dimensional requirements specific to category ~~B4~~ B-655 fibres

Attribute	Unit	B-655.C Limit	B-655.D Limit	B-655.E Limit	Reference
Cladding diameter	µm	125 ± 1			5.2
Cladding non-circularity	%	≤ 2,0	≤ 1,0	≤ 1,0	5.2
Core – cladding concentricity error	µm	≤ 0,8	≤ 0,6	≤ 0,6	5.2
Primary coating diameter – uncoloured ^a	µm	235 to 255			5.2
Primary coating diameter – coloured ^a	µm	235 to 265			5.2
Primary coating-cladding concentricity error	µm	≤ 12,5			5.2
Fibre length	km	See 5.2			5.2
^a Alternative nominal primary coating diameters may be used, (see Table 2), to be agreed between supplier and customer.					

D.3 Mechanical requirements

Table D.2 contains mechanical requirements specific to category ~~B4~~ B-655 fibres.

Table D.2 – Mechanical requirements specific to category ~~B4~~ B-655 fibres

Attribute	Unit	Limit	Reference
Proof stress level	GPa	$\geq 0,69$ ^{SS}	5.3
Coating strip force (average) ^{SS}	N	$1,0 \leq F_{ave} \leq 5,0$	5.3
Coating strip force (peak) ^{SS}	N	$1,0 \leq F_{peak} \leq 8,9$	5.3
Fibre curl radius	M	≥ 2 ^a	5.3
Tensile strength (median) for 0,5 m specimen length	GPa	$\geq 3,8$	5.3
Stress corrosion susceptibility parameter, n_d	–	≥ 18	5.3
^a Depending on splicing methods, a minimum of 4 m may be specified for fibre intended to be used in some cable constructions – such as ribbon cable.			

D.4 Transmission requirements

D.4.1 General

Table D.3 contains transmission requirements specific to category ~~B4~~ B-655 fibres.

Table D.3 – Transmission requirements specific to category ~~B4~~ B-655 fibres

Attribute	Unit	Limit		Reference
		B-655.C	B-655.D,E	
Attenuation coefficient at 1 550 nm	dB/km	$\leq 0,30$	35	5.4
Attenuation coefficient at 1 625 nm	dB/km	$\leq 0,40$		5.4
Chromatic dispersion coefficient	ps/(nm x km)	See D.4.2, D.4.3, and D.4.4		5.4
Nominal MFD range at 1 550 nm ^a	μm	8,0 to 11,0		5.4
MFD tolerance	μm	$\pm 0,7$	$\pm 0,6$	5.4
Cable cut-off wavelength, λ_{cc}	nm	$\leq 1\,450$		5.4
Macrobending loss at 1 625 nm, 100 turns on a 30 mm radius mandrel	dB	$\leq 0,50$	$\leq 0,1$	5.4
Polarization mode dispersion (PMD) coefficient	ps/ $\sqrt{\text{km}}$		See 5.4	5.4
^a The value of the nominal MFD shall be agreed between supplier and customer from within the range given. The tolerance shown is then applied around that nominal value.				

NOTE Annex G includes implementation examples that do not preclude any other possible implementations.

D.4.2 Chromatic dispersion coefficient limits for sub-category ~~B4-e~~ B-655.C fibres

The chromatic dispersion coefficient, $D(\lambda)$, is given in ps/(nm x km) and varies with wavelength, λ . The following inequalities shall be met:

$$1,0 \text{ ps/nm} \cdot \text{km} \leq D_{\min} \leq |D(\lambda)| \leq D_{\max} \leq 10,0 \text{ ps/nm} \cdot \text{km} \quad (\text{D.1})$$

for $1\,530 \text{ nm} \leq \lambda \leq 1\,565 \text{ nm}$

and
$$D_{\max} - D_{\min} \leq 5,0 \text{ ps/nm} \cdot \text{km} \quad (\text{D.2})$$

The sign of the chromatic dispersion coefficient may be positive or negative, but $D(\lambda)$ shall not cross zero in the range of wavelengths from 1 530 nm to 1 565 nm.

The values of $D_{\min}$ and $D_{\max}$ as well as the sign shall be agreed between customer and supplier.

D.4.3 Chromatic dispersion coefficient limits for sub-category ~~B4_d~~ B-655.D fibres

The chromatic dispersion coefficient, $D(\lambda)$, is given in ps/(nm × km) and varies with wavelength, λ . The following inequalities shall be met:

$$\frac{7,00}{90}(\lambda - 1460) - 4,20 \leq D(\lambda) \leq \frac{2,91}{90}(\lambda - 1460) + 3,29 \quad (\text{D.3})$$

for 1 460 nm ≤ λ ≤ 1 550 nm

and

$$\frac{2,97}{75}(\lambda - 1 550) + 2,80 \leq D(\lambda) \leq \frac{5,06}{75}(\lambda - 1 550) + 6,20 \quad (\text{D.4})$$

for 1 550 nm ≤ λ ≤ 1 625 nm

D.4.4 Chromatic dispersion coefficient limits for sub-category ~~B4_e~~ B-655.E fibres

The chromatic dispersion coefficient, $D(\lambda)$, is given in ps/(nm × km) and varies with wavelength, λ . The following inequalities shall be met.

$$\frac{5,42}{90}(\lambda - 1460) + 0,64 \leq D(\lambda) \leq \frac{4,65}{90}(\lambda - 1460) + 4,66 \quad (\text{D.5})$$

for 1 460 nm ≤ λ ≤ 1 550 nm

and

$$\frac{3,30}{75}(\lambda - 1 550) + 6,06 \leq D(\lambda) \leq \frac{4,12}{75}(\lambda - 1 550) + 9,31 \quad (\text{D.6})$$

for 1 550 nm ≤ λ ≤ 1 625 nm

D.5 Environmental requirements

The requirements of 5.5 shall be met.

Annex E (normative)

Family specification for category ~~B5~~ B-656 Wideband non-zero dispersion shifted single-mode fibres

E.1 General

This non-zero dispersion-shifted single-mode fibre is optimized for multiple channel transmission in the wavelength range of 1 460 nm to 1 625 nm with the positive value of the chromatic dispersion coefficient that is greater than some non-zero value. This fibre can be used for both CWDM and DWDM systems throughout the wavelength region between 1 460 nm and 1 625 nm.

The clauses and tables in Annex E contain particular requirements applicable to category ~~B5~~ B-656 fibres. Common requirements, repeated here for ease of reference from the sectional specification, are noted by an entry in the “reference” column. Relevant notes from the sectional specification are not repeated but indicated with a superscript ^{“SS”}.

E.2 Dimensional requirements

Table E.1 contains dimensional requirements specific to category ~~B5~~ B-656 fibres.

Table E.1 – Dimensional requirements specific to category ~~B5~~ B-656 fibres

Attribute	Unit	Limit	Reference
Cladding diameter	µm	125 ± 1	5.2
Cladding non-circularity	%	≤ 2,0	5.2
Core – cladding concentricity error	µm	≤ 0,8	5.2
Primary coating diameter – uncoloured ^a	µm	235 to 255	5.2
Primary coating diameter – coloured ^a	µm	235 to 265	5.2
Primary coating-cladding concentricity error	µm	≤ 12,5	5.2
Fibre length	km	See 5.2	5.2
^a Alternative nominal primary coating diameters may be used, (see Table 2), to be agreed between supplier and customer.			

E.3 Mechanical requirements

Tableau E.2 contains mechanical requirements specific to category ~~B5~~ B-656 fibres.

Table E.2 – Mechanical requirements specific to category ~~B5~~ B-656 fibres

Attribute	Unit	Limit	Reference
Proof stress level	GPa	$\geq 0,69$ ^{SS}	5.3
Coating strip force (average) ^{SS}	N	$1,0 \leq F_{ave} \leq 5,0$	5.3
Coating strip force (peak) ^{SS}	N	$1,0 \leq F_{peak} \leq 8,9$	5.3
Fibre curl radius	M	≥ 2 ^a	5.3
Tensile strength (median) for 0,5 m specimen length	GPa	$\geq 3,8$	5.3
Stress corrosion susceptibility parameter, n_d	–	≥ 18	5.3
^a Depending on splicing methods, a minimum of 4 m may be specified for fibre intended to be used in some cable constructions, such as ribbon cable.			

E.4 Transmission requirements

E.4.1 General

Table E.3 contains transmission requirements specific to category ~~B5~~ B-656 fibres.

Table E.3 – Transmission requirements specific to category ~~B5~~ B-656 fibres

Attribute	Unit	Limit	Reference
Attenuation coefficient at 1 460 nm	dB/km	$\leq 0,40$	5.4
Attenuation coefficient at 1 550 nm	dB/km	$\leq 0,30$ ³⁵	5.4
Attenuation coefficient at 1 625 nm	dB/km	$\leq 0,40$	5.4
Chromatic dispersion coefficient ^a	ps/(nm x km)	See E.4.2	5.4
Nominal MFD range at 1 550 nm ^b	μm	7,0 to 11,0	5.4
MFD tolerance	μm	$\pm 0,7$	5.4
Cable cut-off wavelength, λ_{cc}	nm	$\leq 1\,450$	5.4
Macrobending loss at 1 625 nm, 100 turns on a 30 mm radius mandrel	dB	$\leq 0,50$	5.4
Polarization mode dispersion (PMD) coefficient	ps/ $\sqrt{\text{km}}$	See 5.4	5.4
^a If a Raman pump is used outside the wavelength region from 1 460 nm to 1 625 nm, fibre properties have to be suitable for accommodating this pump, for example λ_0 may need to be less than the pump wavelength.			
^b The value of nominal MFD shall be agreed between supplier and customer from within the range given. The tolerance shown is then applied around that nominal value.			

E.4.2 Chromatic dispersion coefficient for category ~~B5~~ B-656 fibres

The chromatic dispersion coefficient, $D(\lambda)$, is given in ps/(nm x km) and varies with wavelength, λ . The following inequalities shall be met:

$$\frac{2,60}{90}(\lambda - 1460) + 1,00 \leq D(\lambda) \leq \frac{4,68}{90}(\lambda - 1460) + 4,60 \quad (\text{E.1})$$

for $1\,460 \text{ nm} \leq \lambda \leq 1\,550 \text{ nm}$

and

$$\frac{0,98}{75}(\lambda - 1550) + 3,60 \leq D(\lambda) \leq \frac{4,72}{75}(\lambda - 1550) + 9,28 \quad (\text{E.2})$$

for $1\,550\text{ nm} \leq \lambda \leq 1\,625\text{ nm}$

E.5 Environmental requirements

The requirements of 5.5 shall be met.

Annex F (normative)

Family specification for category ~~B6~~ B-657 Bending loss insensitive single-mode fibres

F.1 General

~~This specification describes two main sub-category groups of bending loss insensitive single-mode optical fibre which are suitable for use in the access networks, including inside buildings at the end of these networks.~~

This document describes two categories of single-mode optical fibre A and B with improved bending loss performance compared with that of the B-652 category. Both categories A and B contain two subcategories which differ in macrobending loss.

The clauses and tables in Annex F contain particular requirements applicable to category ~~B6~~ B-657 fibres. Common requirements, repeated here for ease of reference from the sectional specification, are noted by an entry in the "reference" column. Relevant notes from the sectional specification are not repeated but indicated with a superscript "SS".

There are four sub-categories which are designated with suffixes ~~"_a1", "_a2", "_b2" and "_b3"~~ ".A1", ".A2", ".B2" and ".B3". The fibres are suitable to be used in the O, E, S, C and L-band (i.e. throughout the 1 260 nm to 1 625 nm range). They have improved bending loss and tighter dimensional specifications compared to ~~B1.3~~ B-652.D fibres for improved connectivity.

Sub-categories ~~B6_a1 and B6_a2~~ B-657.A1 and B-657.A2 fibres are a subset of category ~~B1.3~~ B-652.D fibres and therefore are compliant with ~~B1.3~~ B-652.D fibres and have the same transmission properties.

NOTE 1 Compliance here means adherence to the referenced fibre category (~~B1.3~~ B-652.D) meeting or exceeding the values of the specified attributes.

Sub-category ~~B6_a1~~ B-657.A1 fibres are appropriate for a minimum bend radius of 10 mm; sub-category ~~B6_a2~~ B-657.A2 fibres for a minimum bend radius of 7,5 mm.

Sub-categories ~~B6_b2 and B6_b3~~ B-657.B2 and B-657.B3 fibres are intended to be used for restricted distances (less than 1 000 m) at the end of access networks, in particular inside buildings or near buildings (e.g. outside building riser cabling). Application length of ~~B6_b~~ B-657.B fibre, however, depends on the deployment strategy of each network operator.

Sub-category ~~B6_b~~ B-657.B fibres are not necessarily compliant with category ~~B1.3~~ B-652 fibres in terms of chromatic dispersion coefficient specifications. These fibres, however, are system compatible with ~~B6_a~~ B-657.A (and ~~B1.3~~ B-652.D) fibres in Access networks.

NOTE 2 Compatibility here means that the product in this sub-category will introduce negligible system impairment or deployment issues but may not be compliant with the referenced fibre category (~~B1.3~~ B-652.D).

Sub-category ~~B6_b2~~ B-652.B2 fibres are appropriate for a minimum bend radius of 7,5 mm; sub-category ~~B6_b3~~ B-652.B3 fibres for a minimum bend radius of 5 mm.

NOTE 3 Most category ~~B1.1 and B1.3~~ B-652 fibres deployed have macrobending losses of several dBs over ten turns at 1 625 nm with 15 mm bend radius.

F.2 Dimensional requirements

Table F.1 contains dimensional requirements specific to category ~~B6~~ B-657 fibres.

Table F.1 – Dimensional requirements specific to category ~~B6~~ B-657 fibres

Attribute	Unit	Limit	Limit	Reference
		(250µm coating)	(200µm coating)	
Cladding diameter	µm	125 ± 0,7		5.2
Cladding non-circularity	%	≤ 1,0		5.2
Core – cladding concentricity error	µm	≤ 0,5		5.2
Primary coating diameter – uncoloured ^a	µm	235 to 255	180 to 210	5.2
Primary coating diameter – coloured ^a	µm	235 to 265	180 to 220	5.2
Primary coating-cladding concentricity error	µm	≤ 12,5	≤ 10,0	5.2
Fibre length	Km	See 5.2		5.2
^a Alternative nominal primary coating diameters may be used (see Table 2), to be agreed between supplier and customer.				

F.3 Mechanical requirements

Table F.2 contains mechanical requirements specific to category ~~B6~~ B-657 fibres.

Table F.2 – Mechanical requirements specific to category ~~B6~~ B-657 fibres

Attribute	Unit	Limit		Reference
		(250 μm coating)	(200 μm coating)	
Proof stress level ^a	GPa	≥ 0,69 ^{SS}		5.3
Coating strip force (average) ^{SS}	N	1,0 ≤ F_{ave} ≤ 5,0	0,4 ≤ F_{ave} ≤ 5,0	5.3
Coating strip force (peak) ^{SS}	N	1,0 ≤ F_{peak} ≤ 8,9	0,4 ≤ F_{peak} ≤ 8,9	5.3
Fibre curl radius	m	≥ 2 ^b		5.3
Tensile strength (median) for 0,5 m specimen length	GPa	≥ 3,8		5.3
Stress corrosion susceptibility parameter, n_d	—	≥ 18		5.3

^a The failure probability for fibre under 30 mm of radius bend as described in category ~~B1.3~~ B-657 of this document, increases with decreasing bend radius. ~~The mechanical reliability of optical fibre in this application space is a function of the characteristics of the cable structure, the installation techniques and deployment conditions. Attention is drawn to the fact that, for some installations, additional constraints on installation, such as higher fibre proof test levels or other factors may be required to ensure the full expected life. It is recommended that the proof stress level applied to fibre and other factors along with the required reliability level during its lifetime are agreed between supplier and customer considering the environmental conditions imposed on the fibres during and after installation. See ITU-T G.Sup.59 for more guidance on cabled fibre reliability.~~

^b Depending on splicing methods, a minimum of 4 m may be specified for fibre intended to be used in some cable constructions, such as ribbon cable.

F.4 Transmission requirements

Table F.3 contains transmission requirements specific to category ~~B6~~ B-657 fibres.

~~NOTE – Some limits are not specified for sub-categories of B6 fibres. These are indicated by NS in Table G.3.~~

Table F.3 – Transmission requirements specific to category ~~B6~~ B-657 fibres

Attribute	Unit	~~B6_a1~~ Limit	~~B6_a2~~ Limit	~~B6_b2~~ Limit	~~B6_b3~~ Limit	Referen- ce
Attenuation coefficient from 1 310 nm to 1 625 nm ^a	dB/km	≤ 0,40	≤ 0,40	≤ 0,40	≤ 0,40	
Attenuation coefficient at 1 383 nm ± 3 nm ^b	dB/km	≤ 0,40	≤ 0,40	≤ 0,40	≤ 0,40	
Attenuation coefficient at 1 550 nm	dB/km	≤ 0,30	≤ 0,30	≤ 0,30	≤ 0,30	
Zero dispersion wavelength, λ_0	nm	1 300 ≤ λ_0 ≤ 1 324	1 300 ≤ λ_0 ≤ 1 324	1 250 ≤ λ_0 ≤ 1 350	1 250 ≤ λ_0 ≤ 1 350	
Zero dispersion slope	ps/nm ² ·km	≤ 0,092	≤ 0,092	≤ 0,11	≤ 0,11	
Nominal MFD range at 1 310 nm ^c	μm	8,6 to 9,5	8,6 to 9,5	8,6 to 9,5	8,6 to 9,5	
MFD tolerance	μm	± 0,4	± 0,4	± 0,4	± 0,4	
Cable cut-off wavelength	nm	≤ 1 260	≤ 1 260	≤ 1 260	≤ 1 260	
Macrobending loss at 1 550 nm, 10 turns on a 15 mm radius mandrel	dB	≤ 0,25	≤ 0,03	≤ 0,03	NS	
Macrobending loss at 1 550 nm, 1 turn on a 10 mm radius mandrel	dB	≤ 0,75	≤ 0,1	≤ 0,1	≤ 0,03	
Macrobending loss at 1 550 nm, 1 turn on a 7,5 mm radius mandrel	dB	NS	≤ 0,5	≤ 0,5	≤ 0,08	
Macrobending loss at 1 550 nm, 1 turn on a 5 mm radius mandrel	dB	NS	NS	NS	≤ 0,15	
Macrobending loss at 1 625 nm, 10 turns on a 15 mm radius mandrel	dB	≤ 1,0	≤ 0,1	≤ 0,1	NS	
Macrobending loss at 1 625 nm, 1 turn on a 10 mm radius mandrel	dB	≤ 1,5	≤ 0,2	≤ 0,2	≤ 0,1	
Macrobending loss at 1 625 nm, 1 turn on a 7,5 mm radius mandrel	dB ps/nm·km	NS	≤ 1,0	≤ 1,0	≤ 0,25	
Macrobending loss at 1 625 nm, 1 turn on a 5 mm radius mandrel	dB	NS	NS	NS	≤ 0,45	
Polarization mode dispersion (PMD) coefficient	ps/√km	See 5.4	See 5.4	See 5.4	See 5.4	