

INTERNATIONAL STANDARD



Optical fibre cables –

Part 2-30: Indoor cables – Family specification for optical fibre ribbon cables for use in terminated cable assemblies



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2019 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

INTERNATIONAL STANDARD



Optical fibre cables –
Part 2-30: Indoor cables – Family specification for optical fibre ribbon cables for
use in terminated cable assemblies

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 33.180.10

ISBN 978-2-8322-6684-7

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD	4
1 Scope	6
2 Normative references	6
3 Terms and definitions	7
4 Construction	7
4.1 General	7
4.2 Optical fibres and primary coating	8
4.3 Buffer	8
4.4 Ruggedized fibre	8
4.5 Slotted core	8
4.6 Tube	8
4.7 Stranded loose tube	8
4.8 Ribbon structure	8
4.9 Strength and anti-buckling members	8
4.10 Ripcord	8
4.11 Sheath	8
4.12 Sheath marking	9
4.13 Identification	9
4.14 Example of cable construction	9
5 Dimensions	9
5.1 Optical fibres and primary coating	9
5.2 Ribbon structural geometry	10
5.3 Optical fibre ribbon cable	10
6 Tests	10
6.1 General	10
6.2 Dimensions	10
6.3 Mechanical requirements	11
6.3.1 Cable tensile performance	11
6.3.2 Cable crush	11
6.3.3 Cable impact	11
6.3.4 Cable bending	11
6.3.5 Cable repeated bending	11
6.3.6 Cable bending under tension	12
6.3.7 Cable bending at low temperature	12
6.3.8 Cable flexing	12
6.3.9 Cable torsion	12
6.3.10 Cable kink	12
6.4 Environmental requirements – Temperature cycling	12
6.5 Transmission requirements	13
6.5.1 General	13
6.5.2 Single mode optical fibres	13
6.5.3 Single-mode dispersion unshifted optical fibre (B1.1)	13
6.5.4 Single-mode dispersion unshifted optical fibre (B1.2)	14
6.5.5 Single-mode dispersion unshifted optical fibre (B1.3)	14
6.5.6 Single-mode dispersion shifted optical fibre (B2)	14
6.5.7 Single-mode non-zero dispersion optical fibre (B4)	14

6.5.8	Single-mode wide band non-zero dispersion optical fibre (B5)	15
6.5.9	Single-mode bending loss insensitive optical fibre (B6).....	15
6.5.10	Multimode fibres	15
6.6	Fire performance	15
Annex A (informative)	Example of cable construction	17
Annex B (informative)	Family specification indoor cables – Optical fibre ribbon cables.....	18
B.1	Blank detail specification	18
B.1.1	Cable description.....	18
B.1.2	Cable element	19
B.1.3	Cable construction	19
B.1.4	Installation and operating conditions.....	20
B.1.5	Mechanical, environmental and fire performance tests.....	20
B.2	Additional requirements for Cables subject to the MICE environmental classification (ISO/IEC 24702 ISO 11801-3 and related standards)	21
Bibliography		24
Figure 1	– Example of identification by means of colour coding and positioning	9
Figure A.1	– Example of cross-section of a four-fibre ribbon cable	17

~~Table — Specifications for Industrial Premises installations as defined in ISO/IEC 24702~~.....

Table 1	– Dimensions of optical fibre ribbon cables	10
Table 2	– Temperature cycling conditions	13
Table 3	– Common single-mode fibre requirements	13
Table 4	– Cabled attenuation requirements for B1.1 optical fibre	13
Table 5	– Cabled attenuation requirements for B1.2 optical fibre	14
Table 6	– Cabled attenuation requirements for B1.3 optical fibre	14
Table 7	– Cabled attenuation requirements for B2 optical fibre	14
Table 8	– Cabled attenuation requirements for B4 optical fibre	14
Table 9	– Cabled attenuation requirements for B5 optical fibre	15
Table 10	– Cabled attenuation requirements for B6 optical fibre	15
Table 11	– Requirements for multimode optical fibre (A1a and A1b)	15
Table B.1	– Cable description	18
Table B.2	– Cable element.....	19
Table B.3	– Cable construction	19
Table B.4	– Installation and operating conditions	20
Table B.5	– Tests applicable	21

INTERNATIONAL ELECTROTECHNICAL COMMISSION

OPTICAL FIBRE CABLES –

**Part 2-30: Indoor cables –
Family specification for optical fibre ribbon
cables for use in terminated cable assemblies**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.

International Standard IEC 60794-2-30 has been prepared by sub-committee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

This third edition cancels and replaces the second edition published in 2008. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) removal of Annex C;
- b) reference to the most recent fibre standards;
- c) reference to IEC 60794-1-21, IEC 60794-1-22, IEC 60794-1-23 and IEC 60794-1-24.

This standard is to be used in conjunction with IEC 60794-1-1, IEC 60794-1-2 and IEC 60794-2.

The text of this International Standard is based on the following documents:

CDV	Report on voting
86A/1704/CDV	86A/1808/RVC

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60794 series, published under the general title *Optical fibre cables*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

OPTICAL FIBRE CABLES –

Part 2-30: Indoor cables – Family specification for optical fibre ribbon cables for use in terminated cable assemblies

1 Scope

This part of IEC 60794 is a family specification which covers indoor optical fibre ribbon cables for ~~indoor~~ use in terminated cable assemblies. The requirements of the sectional specification IEC 60794-2 are applicable to cables covered by this document.

The requirements of this document are written to define flat ribbon cables. This document can be applicable to other cable constructions. Parts of IEC 60794-3 which are applicable for ribbon tests are the subject of IEC 60794-1-31.

Annex B contains requirements that supersede the normal requirements in case the cables are intended to be used in installations governed by the MICE table of ISO ~~IEC 24702~~ 11801-3 [4]¹.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE These reference complete the normative references already listed in the generic specifications (IEC 60794-1-1, ~~Clause 2~~, and IEC 60794-1-2, ~~Clause 2~~) or in the sectional specification (IEC 60794-2, ~~Clause 2~~).

IEC 60304: ~~1982~~, *Standard colours for insulation for low-frequency cables and wires*

IEC 60793-1-20, *Optical fibres – Part 1-20: Measurement methods and test procedures – Fibre geometry*

IEC 60793-1-40, *Optical fibres – Part 1-40: Measurement methods and test procedures – Attenuation*

IEC 60793-1-44, *Optical fibres – Part 1-44: Measurement methods and test procedures – Cut-off wavelength*

IEC 60793-2, *Optical fibres – Part 2: Product specifications – General*

IEC 60793-2-10, *Optical fibres – Part 2-10: Product specifications – Sectional specification for category A1 multimode fibres*

IEC 60793-2-50, *Optical fibres – Part 2-50: Product specification – Sectional specification for class B single-mode fibres*

IEC 60794-1-1, *Optical fibre cables – Part 1-1: Generic specification – General* ~~86A/1054/NP~~

¹ Numbers in square brackets refer to the Bibliography.

IEC 60794-1-2, *Optical fibre cables – Part 1-2: Generic specification – Basic optical cable test procedures – General guidance*

IEC 60794-1-21, *Optical fibre cables – Part 1-21: Generic specification – Basic optical cable test procedures – Mechanical test methods*

IEC 60794-1-22, *Optical fibre cables – Part 1-22: Generic specification – Basic optical cable test procedures – Environmental test methods*

IEC 60794-1-23, *Optical fibre cables – Part 1-23: Generic specification – Basic optical cable test procedures – Cable element test methods*

IEC 60794-2:2017, *Optical fibre cables – Part 2: Indoor cables – Sectional specification*

IEC 60794-3, *Optical fibre cables – Part 3: Outdoor cables – Sectional specification*

~~IEC 60811-1-1:1993, Common test methods for insulating and sheathing materials of electric cables and optical cables – Part 1-1: Methods for general application – Measurement of thickness and overall dimensions – Tests for determining the mechanical properties~~

~~IEC 60811-1-4:1985, Common test methods for insulating and sheathing materials of electric cables – Part 1: Methods for general application – Section Four: Tests at low temperatures.~~

IEC 60811-202, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 202: General tests – Measurement of thickness of non-metallic sheath*

IEC 60811-203, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 203: General tests – Measurement of overall dimensions*

IEC 60811-504, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 504: Mechanical tests – Bending tests at low temperature for insulation and sheaths*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Construction

4.1 General

In addition to the constructional requirements in IEC 60794-2, the following considerations apply to ~~indoor~~ ribbon cables for use in terminated cable assemblies.

The cable shall be designed and manufactured for a predicted operating lifetime of at least 15 years. In this context, the attenuation of the installed cable at the operational wavelength(s) shall not exceed values agreed between the customer and the supplier. The materials in the cable shall not present a health hazard within its intended use.

There shall be no fibre splice in a delivery length unless otherwise agreed by the customer and the supplier.

It shall be possible to identify each individual fibre throughout the length of the cable.

4.2 Optical fibres and primary coating

~~Multimode or single-mode optical fibres meeting the requirements of IEC 60793-2 shall be used.~~

Category A1 multimode fibres which meet the requirements of IEC 60793-2-10 or categories B1.1, B1.2, B1.3, B2, B4, B5 and B6 single-mode optical fibres which meet the requirements of IEC 60793-2-50 shall be used. The linear coefficient of optical fibre attenuation and attenuation point discontinuity may be affected by the cable manufacturing process. Maximum values for these optical characteristics shall be agreed between the customer and the supplier.

4.3 Buffer

None.

4.4 Ruggedized fibre

None.

4.5 Slotted core

None.

4.6 Tube

None.

4.7 Stranded loose tube

None.

4.8 Ribbon structure

~~The ribbon structure shall conform to 6.5 and 8.2.3 of IEC 60794-3. Fibres shall be formed into units of typically two, four, six, eight, or twelve fibres each. The fibres within the units shall remain parallel and not cross over. An example of a ribbon construction is shown in Figure A.1~~

The ribbon structure shall be in accordance with IEC 60794-3.

4.9 Strength and anti-buckling members

The optical fibre ribbon cable may incorporate a tensile strength member. The strength member ~~can~~ may be a layer of suitable material, longitudinally or helically applied, and/or may be embedded in the overall sheath.

4.10 Ripcord

None.

4.11 Sheath

The optical fibre ribbon shall be uniformly covered with a protective sheath generally as shown in Figure A.1.


4.12 Sheath marking

If required, the cable shall be marked as agreed between the customer and the supplier.

4.13 Identification

The coated fibre shall be distinguishable by means of colour coding and positioning. For example (see Figure 1):

- a fibre ribbon has an identification coloured fibre on one side and a sub-identification coloured one on the other side;
- the identification and the sub-identification coloured fibres are the first and the last in the fibre ribbon, respectively;
- any colour of the identification colours group is different from that of the sub-identification colours group;
- the colour types and the order used for identification and sub-identification should be agreed between the customer and the supplier. The colours of the other fibres shall be agreed by the customer and/or the supplier;
- the colour range used is similar to the first 12 colours described in Table 1 of IEC 60794-2:2002, i.e., blue, yellow, red, white, green, violet, orange, grey, turquoise, black, brown and pink.



IEC

NOTE 1 The identification colour enables each fibre ribbon to be identified individually within a group of ribbons.

NOTE 2 The sub-identification colour shows the ribbon group.

NOTE 3 The identification and the sub-identification colour in a ribbon enables each fibre to be identified individually within the ribbon.

Figure 1 – Example of identification by means of colour coding and positioning

Other methods of identification are under consideration.

4.14 Example of cable construction

An example of a ribbon cable construction is shown in Figure A.1. Other configurations are not precluded if they meet the mechanical, environmental and transmission requirements given in this document.

5 Dimensions

5.1 Optical fibres and primary coating

The dimensions of the individual primary coated fibres in the finished product shall be in accordance with IEC 60793-2.

5.2 Ribbon structural geometry

The ribbon geometry shall ~~conform to 8.2.3 of~~ be in accordance with IEC 60794-3.

5.3 Optical fibre ribbon cable

The structural geometry of the optical fibre ribbon cables shall be designed so as to comply with the mechanical, environmental and transmission requirements as defined in this document. For instance, either rectangular or circular structure can be chosen.

~~Unless otherwise specified~~ In the case of a rectangular structure, the dimensions and the structural geometry of optical fibre ribbon cables shall be as shown in Table 1.

Other structures can be applied if agreed between the supplier and the customer.

Table 1 – Dimensions of optical fibre ribbon cables

Number of fibres	Optical fibre ribbon cables			
	Width mm		Height mm	
	Nominal	Maximum tolerance	Nominal	Maximum tolerance
2	3,0 to 3,5	± 0,4	2,3 to 2,7	± 0,3
4	3,0 to 3,5	± 0,4	2,3 to 2,7	± 0,3
6	3,5 to 4,0	± 0,4	2,3 to 2,7	± 0,3
8	2,5 to 4,5	± 0,4	0,9 to 3,0	± 0,3
12	3,5 to 5,5	± 0,4	0,9 to 3,0	± 0,3
NOTE These dimensions apply to the ribbon cable including the sheath and any strength members.				

6 Tests

6.1 General

Compliance with the relevant detail specification requirements shall be verified by carrying out tests selected from the following subclauses. It is not intended that all the tests shall be carried out; the tests which are to be performed and the frequency of testing shall be agreed between the customer and the supplier.

Some of the following tests can be performed on a short sample length of optical fibre ribbon cable which is still an integral part of a longer length. For testing, the force shall be applied on the flat sides of the cable. Thus, it becomes possible to detect permanent changes in attenuation. The wavelength and maximum increase in attenuation change can be agreed between the customer and the supplier.

6.2 Dimensions

The dimensions and structural geometry of optical fibre ribbon can be verified with a type test described in ~~8.2.3 of~~ IEC 60794-3 to establish and ~~assure~~ ensure proper control of the ribbon manufacturing process. Once the process is established, and in order to ensure functional performance, the dimensions of ribbons may be controlled and verified, for final inspection purposes, with a dial gauge as described in Method G4 of ~~IEC 60794-1-2~~ IEC 60794-1-23. The size of the optical fibre ribbon cable, width and height, shall be measured in accordance with the methods of ~~IEC 60811-1-1~~ IEC 60811-203.

6.3 Mechanical requirements

6.3.1 Cable tensile performance

Method:	IEC 60794-1-2-E1A IEC 60794-1-21, E1
Diameter of chuck drums and transfer devices:	not lower than the minimum dynamic bending diameter specified for the cable
Velocity of transfer device:	either 100 mm/min or 100 N/min
Load:	200 N applied for 5 min
Length of sample:	sufficient to achieve the desired accuracy of measurement of attenuation and shall be agreed between the customer and the supplier.
Requirement:	no change in attenuation after the test, and there shall be no damage to the cable elements.

6.3.2 Cable crush

Method:	IEC 60794-1-2 IEC 60794-1-21, E3
Force:	500 N
Duration:	1 min
Length between test locations:	500 mm
Requirement:	no change in attenuation after the test, and there shall be no damage to the cable elements.

NOTE The force is applied on the flat sides of the cable.

6.3.3 Cable impact

Method:	IEC 60794-1-2 IEC 60794-1-21, E4
Radius of striking surface:	12,5 mm
Impact energy:	1,0 J
Number of impacts:	at least 3, each separated by at least 500 mm
Requirement:	no fibre breakage

NOTE The force is applied on the flat sides of the cable.

6.3.4 Cable bending

Method:	IEC 60794-1-2 IEC 60794-1-21, E11A
Mandrel diameter:	50 mm
Number of turns per helix:	6
Number of cycles:	10
Requirements:	no fibre breakage

NOTE The bending is applied in the vertical direction to the flat sides of the cable.

6.3.5 Cable repeated bending

Method:	IEC 60794-1-2 IEC 60794-1-21, E6
Bending radius:	100 mm
Number of cycles:	300
Mass of weights:	2 kg
Requirement:	no fibre breakage

NOTE The bending is applied in the vertical direction to the flat sides of the cable.

6.3.6 Cable bending under tension

None.

6.3.7 Cable bending at low temperature

Method:	IEC 60794-1-2 IEC 60794-1-21, E11A (see also IEC 60811-1-4, Clause 8 IEC 60811-504)
Bending radius:	10 times cable diameter for flat cables; diameter is the minor minimum dimension. For cables with preferential bend, the diameter is perpendicular to the plane of bending.
Number of cycles:	2
Test temperature:	0 °C, –10 °C or –15 °C depending on application and customer requirements
Number of turns per helix:	according to Clause 8 of IEC 60811-1-4 IEC 60811-504
Requirements:	in addition to the requirement of Clause 8 of IEC 60811-1-4 IEC 60811-504, no fibre shall break during the test.

6.3.8 Cable flexing

Method:	IEC 60794-1-2 IEC 60794-1-21, E8
Number of cycles:	300
Pulley diameter:	100 mm
Mass of weight:	2 kg
Requirement:	no fibre breakage

NOTE The bending is applied in the vertical direction to the flat sides of the cable.

6.3.9 Cable torsion

Method:	IEC 60794-1-2 IEC 60794-1-21, E7
Number of cycles:	20
Distance between fixed and rotation clamp:	250 mm
Tension load:	20 N
Requirement:	no fibre breakage

6.3.10 Cable kink

None.

6.4 Environmental requirements – Temperature cycling

Method:	IEC 60794-1-2 IEC 60794-1-22, F1
Period t_1:	sufficient so that the cable has reached, and stabilised to, the specified temperature
Number of cycles:	2
Length of sample:	sufficient to achieve the desired accuracy of measurement of attenuation

Temperature:

see Table 2

Requirement:

the wavelength and maximum increase in attenuation shall be agreed between the customer and the supplier

Table 2 – Temperature cycling conditions

	Temperature T_A	Temperature T_B
a)	0 °C	50 °C
b)	–5 °C	50 °C
c)	–20 °C	60 °C
d)	–45 °C	60 °C

NOTE Condition a), b), c) or d) ~~should~~ shall be selected depending on application and customer requirements, for example, condition c) is ~~for~~ appropriate ~~for applications to~~ implementation of ISO/IEC 11801 [3].

6.5 Transmission requirements

6.5.1 General

The transmission requirements shall be verified in accordance with IEC 60793-2-10 or IEC 60793-2-50 and shall be agreed between the customer and the supplier. Maximum cable attenuation shall comply with IEC 60794-1-1. See Tables 3 to 11.

NOTE ~~1 625 nm performance is optional depending upon agreement between the customer and the supplier.~~

6.5.2 Single mode optical fibres

Table 3 – Common single-mode fibre requirements

Characteristics	IEC 60794-2:2017 subclause	Family requirements	Test methods	Remarks
Uncabled optical fibre	4.1	IEC 60793-2		
Cabled fibre cut-off wavelength	4.42	$\lambda_{cc} < \lambda$ operational	IEC 60793-1-44	
Fibre colouring	4.1	IEC 60304	Visual inspection	
Outer diameter including colouring	4.1	As IEC 60793-2	IEC 60793-1-20	
Attenuation discontinuities at 1 550 nm	4.42	$\leq 0,10$ dB	IEC 60793-1-40	

6.5.3 Single-mode dispersion unshifted optical fibre (B1.1)

Table 4 – Cabled attenuation requirements for B1.1 optical fibre

Characteristics (9)	IEC 60794-2:2017 subclause (10)	Family (11) requirements	Test methods (12)	Remarks (13)
Attenuation coefficient (cabled fibres)	4.42	According to detail specification	IEC 60793-1-40	
at 1 310 nm		$\leq 0,40$ dB/km		
at 1 550 nm		$\leq 0,30$ dB/km		
at 1 625 nm		$\leq 0,30$ dB/km		

6.5.4 Single-mode dispersion unshifted optical fibre (B1.2)

Table 5 – Cabled attenuation requirements for B1.2 optical fibre

Characteristics ⁽⁹⁾	IEC 60794-2:2017 subclause ⁽¹⁰⁾	Family ⁽¹¹⁾ requirements	Test methods ⁽¹²⁾	Remarks ⁽¹³⁾
Attenuation coefficient (cabled fibres)	4.42	According to detail specification	IEC 60793-1-40	
at 1 550 nm		≤ 0,25 dB/km		
at 1 625 nm		≤ 0,40 dB/km		

6.5.5 Single-mode dispersion unshifted optical fibre (B1.3)

Table 6 – Cabled attenuation requirements for B1.3 optical fibre

Characteristics ⁽⁹⁾	IEC 60794-2:2017 subclause ⁽¹⁰⁾	Family ⁽¹¹⁾ requirements	Test methods ⁽¹²⁾	Remarks ⁽¹³⁾
Attenuation coefficient (cabled fibres)	4.42	According to detail specification	IEC 60793-1-40	
at 1 310 nm to 1 625 nm		≤ 0,40 dB/km		
at 1 383 nm		≤ 0,40 dB/km		
at 1 550 nm		≤ 0,30 dB/km		

6.5.6 Single-mode dispersion shifted optical fibre (B2)

Table 7 – Cabled attenuation requirements for B2 optical fibre

Characteristics ⁽⁹⁾	IEC 60794-2:2017 subclause ⁽¹⁰⁾	Family ⁽¹¹⁾ requirements	Test methods ⁽¹²⁾	Remarks ⁽¹³⁾
Attenuation coefficient (cabled fibres)	4.42	According to detail specification	IEC 60793-1-40	
at 1 310 nm		≤ 0,50 dB/km		
at 1 550 nm		≤ 0,30 dB/km		
at 1 625 nm		≤ 0,40 dB/km		

6.5.7 Single-mode non-zero dispersion optical fibre (B4)

Table 8 – Cabled attenuation requirements for B4 optical fibre

Characteristics ⁽⁹⁾	IEC 60794-2:2017 subclause ⁽¹⁰⁾	Family ⁽¹¹⁾ requirements	Test methods ⁽¹²⁾	Remarks ⁽¹³⁾
Attenuation coefficient (cabled fibres)	4.42	According to detail specification	IEC 60793-1-40	
at 1 550 nm		≤ 0,30 dB/km		
at 1 625 nm		≤ 0,40 dB/km		

6.5.8 Single-mode wide band non-zero dispersion optical fibre (B5)**Table 9 – Cabled attenuation requirements for B5 optical fibre**

Characteristics (9)	IEC 60794-2:2017 subclause (10)	Family (11) requirements	Test methods (12)	Remarks (13)
Attenuation coefficient (cabled fibres)	4.42	According to detail specification	IEC 60793-1-40	
at 1 460 nm		≤ 0,40 dB/km		
at 1 550 nm		≤ 0,30 dB/km		
at 1 625 nm		≤ 0,40 dB/km		

6.5.9 Single-mode bending loss insensitive optical fibre (B6)**Table 10 – Cabled attenuation requirements for B6 optical fibre**

Characteristics	IEC 60794-2:2017 subclause	Family requirements	Test methods	Remarks
Attenuation coefficient (cabled fibres)	4.2	According to detail specification	IEC 60793-1-40	
at 1 310 nm to 1 625 nm		≤ 0,40 dB/km		
at 1 383 nm		≤ 0,40 dB/km		
at 1 550 nm		≤ 0,30 dB/km		

6.5.10 Multimode fibres**Table 11 – Requirements for multimode optical fibre (A1a and A1b)**

Characteristics (9)	IEC 60794-2:2017 subclause (10)	Family (11) requirements	Test methods (12)	Remarks (13)
Uncabled optical fibre	4.1	IEC 60793-2-10		
Attenuation coefficient (cabled fibres)	4.42	According to detail specification	IEC 60793-1-40	
at 850 nm		3,5 dB/km		
at 1 300 nm		1,5 dB/km		
Attenuation discontinuities at 850 nm and 1 300 nm	4.42	≤ 0,20 0,10 dB	IEC 60793-1-40	
Fibre colouring	4.1	IEC 60304	Visual inspection	
Outer diameter including colouring	4.1	As IEC 60793-2	IEC 60793-1-20	

6.6 Fire performance

~~IEC/TR 62222 provides guidance and recommendations for the requirements and test methods for the fire performance of communication cables when installed in buildings. The recommendations relate to typical applications and installation practices, and an assessment of the fire hazards presented. Applicable legislation and regulation are also taken into account.~~

~~IEC/TR 62222 references several IEC fire performance test methods and also other test methods that may be required by local or national legislation and regulation. The tests to be applied, and the requirements, shall be agreed between the customer and supplier taking into account the fire hazard presented by the end use application of the patchcord assembly in which the cable is intended to be used.~~

IEC TR 62222 [1] provides recommendations for the requirements and test methods for the fire performance of communication cables when installed in buildings.

The recommendations relate to typical applications and installation practices and also take into account legislation and regulation applicable to the fire performance of cables that govern the tests to be performed.

Tests to be performed shall be agreed between the customer and the supplier.

Annex A (informative)

Example of cable construction




Figure A.1 – Example of cross-section of a four-fibre ribbon cable

Annex B (informative)

Family specification indoor cables – Optical fibre ribbon cables

B.1 Blank detail specification

B.1.1 Cable description

See Table B.1.

Table B.1 – Cable description

(1) Prepared by		(2) Document No: Issue: Date:
(3) Available from:	(4) Generic specification: IEC 60794-1-1 Sectional specification: IEC 60794-2	
(5) Additional references: ISO/IEC 24702 if required		
(6) Cable description:		
(7) Cable construction:		
Optical fibres		
Range of fibre count		
Modularity		
Construction <ul style="list-style-type: none">– Optical fibres and primary coating– Ribbon– Strength and anti-buckling members Outer sheath <ul style="list-style-type: none">– Material– Minimum wall thickness Marking identification <ul style="list-style-type: none">– Customer requirement– Identification of manufacturer		Additional remarks
(8) Application information:		
Application (indoor) Maximum outer diameter (d) or width and height Rated maximum tensile load Minimum bending radius for operation Temperature range: <ul style="list-style-type: none">– Transport and storage– Installation– Operation Manufacturing cable length <ul style="list-style-type: none">– Typical– Nominal/tolerances:		Mm N mm or nxd °C °C °C M –0 +1 %

B.1.2 Cable element

See Table B.2.

Table B.2 – Cable element

Characteristics (9)	IEC 60794-2:2017 subclause (10)	Family (11) requirements	Test methods (12)	Remarks (13)
Optical fibres and primary coating	3.2	According to detail specification		
Buffer	3.3	According to detail specification	Visual inspection	
Ribbon	3.8	According to detail specification	IEC 60794-1-2 IEC 60794-1-23 G2, G3 or G4	
Strength and anti-buckling member	3.9	According to detail specification	Visual inspection	

B.1.3 Cable construction

See Table B.3.

Table B.3 – Cable construction

Characteristics (9)	IEC 60794-2:2017 subclause (10)	Family (11) requirements	Test methods (12)	Remarks (13)
Cable core		According to detail specification	Visual inspection	
Strength member	3.9	According to detail specification	Visual inspection	
– Longitudinal				
– Helical				
– Embedded in the sheath				
Sheath	3.11	According to detail specification		
– Material		According to detail specification	IEC 60811-1-1 IEC 60811-202	
– Minimum sheath thickness		According to detail specification	IEC 60811-1-1 IEC 60811-203	
– Width and height		According to detail specification		
– Optional protection		According to detail specification		
– Abrasion resistance		According to detail specification	IEC 60794-1-2 IEC 60794-1-21, Method E2A	
Sheath marking	3.12	According to detail specification	Visual inspection	
– Configuration, dimensions		According to detail specification	IEC 60794-1-2 IEC 60794-1-21, Method E2B	Steel needle diameter $d = 1,0$ mm
– Abrasion resistance				Load: 4 N
Cable length				

B.1.4 Installation and operating conditions

See Table B.4.

Table B.4 – Installation and operating conditions

Characteristics (9)	IEC 60794-2:2017 subclause (10)	Family (11) requirements	Test methods (12)	Remarks (13)
General requirements	3.8			
Bend of cable element		According to detail specification	IEC 60794-1-2 IEC 60794-1-23, Method G1	
Ribbons:				
– dimensions		According to detail specification	IEC 60794-3, 8.2.3.1	
– separability of individual fibres from ribbon		According to detail specification	IEC 60794-1-2 IEC 60794-1-23, Method G5 or according to detail specification	
– ribbon stripping		According to detail specification		
– torsion		According to detail specification	IEC 60794-1-2 IEC 60794-1-23, Method G6	

B.1.5 Mechanical, environmental and fire performance tests

See Table B.5.