

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Railway applications – Fixed installations – Electric traction – Specific requirements for composite insulators used for overhead contact line systems

Applications ferroviaires – Installations fixes – Traction électrique – Exigences particulières pour les isolateurs composites destinés aux réseaux de lignes aériennes de contact



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2011 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland
Email: inmail@iec.ch
Web: www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: www.iec.ch/searchpub

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: www.iec.ch/online_news/justpub

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

- Electropedia: www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: www.iec.ch/webstore/custserv

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: csc@iec.ch

Tel.: +41 22 919 02 11

Fax: +41 22 919 03 00

A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

- Catalogue des publications de la CEI: www.iec.ch/searchpub/cur_fut-f.htm

Le Catalogue en-ligne de la CEI vous permet d'effectuer des recherches en utilisant différents critères (numéro de référence, texte, comité d'études,...). Il donne aussi des informations sur les projets et les publications retirées ou remplacées.

- Just Published CEI: www.iec.ch/online_news/justpub

Restez informé sur les nouvelles publications de la CEI. Just Published détaille deux fois par mois les nouvelles publications parues. Disponible en-ligne et aussi par email.

- Electropedia: www.electropedia.org

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 20 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International en ligne.

- Service Clients: www.iec.ch/webstore/custserv/custserv_entry-f.htm

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions, visitez le FAQ du Service clients ou contactez-nous:

Email: csc@iec.ch

Tél.: +41 22 919 02 11

Fax: +41 22 919 03 00



IEC 62621

Edition 1.0 2011-06

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Railway applications – Fixed installations – Electric traction – Specific requirements for composite insulators used for overhead contact line systems

Applications ferroviaires – Installations fixes – Traction électrique – Exigences particulières pour les isolateurs composites destinés aux réseaux de lignes aériennes de contact

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX

U

ICS 45.060

ISBN 978-2-88912-569-2

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions	7
4 Characteristics of composite insulators for overhead contact line systems	8
4.1 General	8
4.2 Environmental conditions	8
4.3 System voltages and frequencies.....	9
4.4 Creepage distance.....	9
4.5 Mechanical requirements	10
4.6 Corrosion	11
4.7 Fire safety	11
4.8 Tracking and erosion	11
4.9 Arc protection	11
4.10 In-running insulators	12
5 Testing	12
5.1 General	12
5.2 Design tests	12
5.3 Type tests	14
5.3.1 General	14
5.3.2 Electrical tests	14
5.3.3 Mechanical tests	14
5.3.4 Verification of dimensions	14
5.4 Sample tests	15
5.5 Routine tests	15
6 Identification	15
7 Transport, storage, installation and maintenance	15
Annex A (informative) Purchaser requirements	16
Annex B (informative) Principles of the damage limit, load coordination and testing	17
Annex C (informative) Guidance on non-standard mechanical stresses and dynamic mechanical loading	21
Annex D (informative) Determination of the equivalent bending moment caused by combined loads.....	23
Bibliography	26
Figure B.1 – Load-time strength and damage limit of a core assembled with fittings.....	18
Figure B.2 – Graphical representation of the relationship of the damage limit to the mechanical characteristics and service loads of an insulator with a 16 mm diameter core	19
Figure B.3 – Test loads	20
Figure D.1 – Combined loads applied to unbraced insulators	24
Table 1 – Definition of relevant mechanical characteristics according to insulator type	10
Table 2 – Design tests	13

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**RAILWAY APPLICATIONS –
FIXED INSTALLATIONS –
ELECTRIC TRACTION –
SPECIFIC REQUIREMENTS FOR COMPOSITE INSULATORS
USED FOR OVERHEAD CONTACT LINE SYSTEMS**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 62621 has been prepared by IEC technical committee 9: Electrical equipment and systems for railways.

This standard is based on EN 50151:2003.

The text of this standard is based on the following documents:

FDIS	Report on voting
9/1539/FDIS	9/1560/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

INTRODUCTION

This standard specifies requirements for the design and testing of composite insulators used on railway electric traction overhead contact line systems. Such insulators, which are installed at relatively low heights in the harsh environment of railway infrastructures, require specific considerations during design to reduce the effects of vandalism and environmental pollution from railway operations, especially when combined with a lack of natural washing. Insulators may be included in arrangements in tunnels and over bridges or be in contact with traction unit pantographs where combined mechanical loading (tension, bending and torsion) may require special consideration.

The standard is intended to allow the manufacturer to comply with local working practices, to ensure compatibility with existing electric traction overhead contact line systems, and provide an insulator which will give reliable service over its target life span with minimum maintenance.

Insulators intended for overhead lines are predominately designed to resist tension and/or bending loads and are not designed to resist torsional loads. Mitigating measures to reduce torsional loading are generally introduced by the overhead contact lines design engineer. Some combined loading (tension, compression and torsion) can be experienced and this is represented in the testing procedure specified in this document.

The testing procedures given for railway applications in this standard are predominately referenced from IEC 61109, IEC 61952 and IEC 62217.

**RAILWAY APPLICATIONS –
FIXED INSTALLATIONS –
ELECTRIC TRACTION –
SPECIFIC REQUIREMENTS FOR COMPOSITE INSULATORS
USED FOR OVERHEAD CONTACT LINE SYSTEMS**

1 Scope

This International Standard specifies characteristics for composite insulators of electric traction overhead contact line systems for railways, as defined in IEC 60913. Insulators specified in this standard are applied for electric traction supply voltages with a nominal voltage greater than 1 000 V for a.c. or a nominal voltage greater than 1 500 V for d.c.. Specific applications where high torsional loads can occur are outside the scope of this standard and particular tests are agreed between the supplier and customer to represent the critical loading arrangements.

This International Standard applies to composite insulators as defined in 3.1 below and not to other polymeric insulators.

The provisions contained in this standard are intended for the design and construction of new electric traction overhead contact line systems using insulators, or when complete refurbishment of existing overhead contact line systems takes place.

This standard provides the purchaser and manufacturer with a range of tests which are used to evaluate the suitability of an insulator product for a given railway environment. Additional tests may be specified by the client to measure the compliance of the insulator under particular operating conditions.

The standard establishes the product characteristics, the test methods and acceptance criteria.

The object of this standard is to stipulate the provisions for the design and provision of the service indicated by the manufacturer to the customer or informed buyer for application on the railway infrastructure.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60587, *Electrical insulating materials used under severe ambient conditions – Test methods for evaluating resistance to tracking and erosion*

IEC 60815-1:2008, *Selection and dimensioning of high-voltage insulators intended for use in polluted conditions – Part 1: Definitions, information and general principles*

IEC 60815-3:2008, *Selection and dimensioning of high-voltage insulators intended for use in polluted conditions – Part 3: Polymer insulators for a.c. systems*

IEC 60826, *Design criteria of overhead transmission lines*

IEC 60850:2007, *Railway applications – Supply voltages of traction systems*

IEC 60913, *Electric traction overhead lines*

IEC 61109:2008, *Insulators for overhead lines – Composite suspension and tension insulators for a.c. systems with a nominal voltage greater than 1 000 V – Definitions, test methods and acceptance criteria*

IEC 61467:2008, *Insulators for overhead lines – Insulator strings and sets for lines with a nominal voltage greater than 1 000 V – AC power arc tests*

IEC 61952:2008, *Insulators for overhead lines – Composite line post insulators for A.C. systems with a nominal voltage greater than 1 000 V – Definitions, test methods and acceptance criteria*

IEC 62217:2005, *Polymeric insulators for indoor and outdoor use with a nominal voltage > 1 000 V – General definitions, test methods and acceptance criteria*

IEC 62497-1:2010, *Railway applications – Insulation coordination – Part 1: Basic requirements Clearances and creepage distances for all electrical and electronic equipment*

ISO 34-1, *Rubber, vulcanized or thermoplastic- determination of tear strength – Part 1: Trouser, angle and crescent test pieces*

ISO 37, *Rubber, vulcanized or thermoplastic – Determination of tensile stress-strain properties*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

NOTE Certain terms from IEC 62217:2005 are reproduced here for ease of reference. Additional definitions applicable to insulators can be found in IEC 60050-471[1]¹, IEC 61109:2008 and IEC 61952:2008.

3.1

composite insulator

insulator made of at least two insulating parts, namely a core and a housing equipped with end fittings

NOTE Composite insulator, for example, can consist either of individual sheds mounted on the core, with or without an intermediate sheath, or alternatively, of a housing directly moulded or cast in one or several pieces on to the core.

3.2

nominal design load

load, specified by the customer, corresponding to the normal everyday permanent and dynamic loads

¹ Figures in square brackets refer to the bibliography.

4 Characteristics of composite insulators for overhead contact line systems

4.1 General

Composite materials and polymers permit the manufacture of insulators for use on outdoor overhead contact line systems. The insulators consist of an insulating core which bears the mechanical load, a polymeric housing which protects the core, and end fittings by which the load is transmitted to the core. These materials allow special applications in overhead contact line systems (including in-running section insulation and flexible supports) and are also used for their advantages of lightness, resistance to vandalism and pollution performance. Despite many common features of design, the materials used and the construction details employed by different manufacturers may be quite different and may lead to different performance parameters.

Electric traction overhead contact line systems applied for railways have several characteristics not associated with power lines. They are of low height and run through urban areas, making them targets for vandalism. They are incorporated in bridges and tunnels, built for rolling stock only, and fit into small spaces. They suffer close proximity to railway generated pollution and, in tunnels and bridges are not washed by natural rainfall. They suffer movement and snatch loads due to normal pantograph contact with the wires. When used as in-running insulators, they suffer mechanical forces and abrasion by the pantograph passing at high speed where the polymeric housing may suffer deformation, tearing and parting from the core (see 4.10).

Some tests have been grouped together in this standard as “design tests”, to be performed only once on insulators which satisfy the same design conditions. As far as practical, the influence of time, circumstance and climate on electrical and mechanical properties of the components (core material, housing, interfaces etc.) and of the complete composite insulators has been considered in specifying the design tests so that a satisfactory life-time may be expected under normally known stress conditions of overhead contact line systems.

The high number of insulators installed in a restricted environment of an operational railway with limited access for maintenance or installed in harsh environmental conditions, requires a high level of reliability at the appropriate electrical insulation level for the system voltage, including temporary and transient overvoltages, and a high level of mechanical integrity. In this case, a reasonable safety factor for mechanical and electrical properties of the insulators shall be agreed between the manufacturer and customer.

4.2 Environmental conditions

Environmental conditions such as temperature, humidity, vibration, solar radiation, pollution, etc., can have serious effects on the electrical and mechanical properties of insulators. The aging of housing material and interfaces, exposure of the core to environment and the corrosion of end fittings shall be given special consideration. When used for lower temperature, the behaviour or brittle property of the housing material and interfaces shall be considered.

NOTE When temperature falls below the crystallisation or glass transition temperature of the housing, its elasticity becomes lost. This change is reversible if a temperature increase takes place.

The normal environmental conditions to which insulators are submitted in service are defined in IEC 62217:2005.

Since the insulators are intended for outdoor use and may be installed in harsh environmental conditions, pollution shall be considered. The pollution degrees are defined in Table A.4 of IEC 62497-1:2010.

4.3 System voltages and frequencies

System voltages and frequencies specified by IEC 60850:2007 are generally applied for this standard. Values of standard system voltages (phase to ground) and the correlation between nominal voltages of the railway power distribution system and the required insulation voltages for circuits of equipment which are intended to be connected to these systems are shown in Table 1 of IEC 60850:2007.

The purchaser shall provide information on the railway electrification system and operating requirements which may affect the design of insulators.

NOTE Purchaser requirements are given in Annex A.

The dry lightning impulse withstand voltage shall be at least equal to the rated impulse voltage defined in IEC 62497-1:2010. The wet power frequency withstand voltage shall be at least equal to the short duration power frequency test level defined in IEC 62497-1:2010.

The rated impulse voltage for circuits powered by electric traction contact lines are shown in Table A.2 of IEC 62497-1:2010. Overhead lines are considered a case of inherent control. The rated insulation level is based on statistical and risk considerations. Therefore the rated impulse voltage is chosen among the preferred values given in Table A.2 of IEC 62497-1:2010, but irrespective of the correspondence with the insulation voltages and of the overvoltage levels stated in said table.

Table A.2 of IEC 62497-1:2010 is based on the worst dielectric conditions of electrodes. In overhead lines, different conditions are present and by consequence different clearances given in established standards or regulations such as IEC 60913 are allowed.

4.4 Creepage distance

The dry arcing distance, creepage distance and geometrical shed profile electrically define an insulator. Creepage distances shall be dimensioned according to the highest permanent voltage of the system. Consideration shall also be given to the insulation material and its behaviour in polluted conditions. The manufacturer may recommend greater than the minimum creepage distance to give adequate life for that material.

The overall shape and size of the insulator is defined by the customer's spatial requirements, the mechanical and electrical performance requirements and its compatibility with existing equipment. The manufacturer can decide on shed profile.

Additional railway environmental pollution may be generated by traction braking systems, diesel and steam trains which run under electrified lines. The exhaust from steam trains is very hot ($> 200\text{ }^{\circ}\text{C}$) and should not be allowed to play on insulators. This can be prevented by careful positioning of insulators on the line or by a restriction on train movements and stopping positions. The exhaust from diesel trains is less severe, but contains oil and carbonaceous deposits, which can contaminate insulators. No additional creepage is necessary for diesel usage but it is important to ensure that the diesel exhaust does not dwell on the insulators by checking stopping positions etc.

Insulators positioned under bridges and in tunnels are not washed by natural rainfall which can lead to pollution accumulation. In these harsh environmental conditions and in order to minimise the degradation of the housing material, the creepage distance and the design need to cover the specific application. This will also be particularly applicable to insulators which are used in contact with the pantograph collector unit and which may require increased creepage distance to allow for the width of the pantograph (see 4.10).

Operating conditions and pollution level are specified in Table A.4 of IEC 62497-1:2010. Dimensioning of creepage distance versus rated insulation voltage, as given in IEC 62497-1:2010, is as follows:

- normal operating conditions: 24 mm/kV to 33 mm/kV;
- unfavourable operating conditions: 36 mm/kV to 40 mm/kV;
- extremely unfavourable operating conditions: > 48 mm/kV.

NOTE 1 Normal operating conditions exist when there is low industrial pollution, a low population density and no thermal engines.

NOTE 2 Unfavourable operating conditions exist when there is high industrial pollution and industrial gases, a high population density, mixed railway operation, road traffic and frequent fog.

NOTE 3 Extremely unfavourable operating conditions exist when large power plants, chemical industry, smelting works near the ocean with frequent fog are close by.

NOTE 4 Clearances and creepage distances may be reduced by agreement between customer and supplier or in product standards.

Composite insulators present certain advantages over ceramic and glass insulators due to their form and materials. These advantages include a generally improved pollution withstand behaviour when compared to similar ceramic or glass insulators of equal creepage distance; this improvement is even more enhanced by use of hydrophobicity transfer material (HTM). In principle and purely from a pollution withstand or flashover point of view, it can thus be concluded that a reduced creepage distance may be used for such insulators. However, compared to traditional insulating materials, polymer materials are more susceptible to degradation by the environment, electric fields and arc activity which may, in certain conditions, reduce insulator pollution performance or lifetime. Subclause 9.4 of IEC 60815-1:2008 gives the considerations and Subclause 5.2 of IEC 60815-3:2008 gives issues specific to reduction of creepage distance for polymeric housing materials.

For d.c. system voltages, some insulation may require a somewhat higher value of unified specific creepage distance compared to a.c. insulation under the same conditions.

NOTE 5 This effect will be dealt with in detail in a forthcoming part of IEC 60815 for d.c. systems.

4.5 Mechanical requirements

The withstand loads defined by the manufacturer shall take into account the characteristics shown in Table 1.

Table 1 – Definition of relevant mechanical characteristics according to insulator type

Type of insulator	Mechanical characteristics	Definitions
Stressed mainly in tension	SML (specified mechanical load) /RTL (routine test load)	According to IEC 61109:2008
Stressed mainly in bending	SCL (specified cantilever load) /MDCL (maximum design cantilever load) /STL (specified tensile load) /RTL (routine test load)	According to IEC 61952:2008

In all cases, the maximum working load (static and dynamic) shall be below the damage limit of the insulator. It is normal practice to adopt a safety factor of at least 2,5 between the SML and the maximum working load; this generally ensures that there is also a sufficient margin between the damage limit of the insulator and all service loads. IEC 60826 and IEC 60913 give guidance for calculation of loads and application of proper safety factors.

NOTE The MDCL may additionally be adjusted by any angular deflection criteria or bending deflection defined in the client requirements.

4.6 Corrosion

The end fittings shall be suitably protected from corrosion and be electrochemically compatible with interface connections. Particular attention shall be made to the protection of the end fittings and connecting zone sealing against moisture ingress, chemical activity or degradation under temperature variations or unidirectional current flow.

4.7 Fire safety

The composite insulators shall not exhibit sustained self ignition, such as when subjected to a power arc test. The location, maintenance, creepage distance and overvoltage protection shall be chosen to minimise the possibility of a power arc flashover.

When used in particular environments or applications, particularly in tunnels and station areas, composite insulators may be required to have safety behaviour in terms of flammability, smoke emission and toxicity.

Flammability tests are intended to verify the housing material for ignition, flame propagation and self-extinguishing properties. Flammability requirements are defined in the testing requirements (see Clause 5).

Smoke emission tests are intended to identify the opacity of the smoke emission when the insulator material burns.

Toxicity tests are intended to verify the toxicity of the smoke emission when the insulator material burns.

4.8 Tracking and erosion

Surface damage may arise in severe environmental conditions due to surface leakage currents and partial arcing.

Tracking and erosion tests are given in IEC 62217:2005. These tests are better described as screening tests, which can be used to reject materials, or designs, which are inadequate.

NOTE 1 For further information, refer to Annex C of IEC 62217:2005 and CIGRE Technical Brochure No. 142: “*Natural and artificial ageing and pollution testing of polymeric insulators*”, June 1999 [2].

NOTE 2 A review of the representativity, repeatability and reproducibility of ageing tests is under consideration and guidance will be given in the future in a new Technical Report prepared by IEC TC 36. In the meantime, it is recommended that particular care should be taken when specifying the type and parameters of such tests.

4.9 Arc protection

The heating effect of power arcs shall be considered in the design of metal fittings. Critical damage to the metal fittings resulting from the magnitude and duration of the short-circuit current can be avoided by properly designed arc-protection devices.

It has not been considered useful to specify a power arc test as a mandatory test for suspension/tension and post insulators. The test parameters are manifold and can have very different values depending on the configurations of the network and the supports and on the design of arc-protection devices. This standard, however, does not exclude the possibility of a power arc test by agreement between the manufacturer and customer.

IEC 61467:2008 gives details of a.c. power arc testing of insulator sets and tests for sustained ignition.

In-running insulator arrangements regularly receive power arcs and the full insulating assembly shall be power arc tested (see 4.10).

4.10 In-running insulators

In railway applications, it is essential to divide the overhead contact lines into discrete electrical sections. This requires breaks or insulators in the contact wire, on which the traction pantograph runs. Composite insulators can provide versatile section insulators with a small mass to minimise pantograph impacts and damage.

Insulators in the overhead contact lines which are designed to work in contact with the traction pantograph unit require additional creepage distances depending upon the pantograph width, system voltage and operating speed. The requirements for insulation length may exceed the values in this standard and shall be agreed separately between the supplier and purchaser.

If the insulator surface wears, it may not accumulate pollution and testing for pollution deposits may not be required. Alternatively if the surface does not wear, pollution can build up from the pantograph strips, which could lead to flashover or surface degradation. This shall be borne in mind when designing the insulators and drafting maintenance instructions or determining life cycle costs.

In-running insulator arrangements regularly receive power arcs and the full insulating assembly shall be power arc tested on the basis of Clause 8 of IEC 61467:2008 or by a field test according to IEC 60913. In order to remove power arcs from insulators, arc extinguishing horn gaps may be used.

Testing shall be in accordance with the requirements defined in Clause 5.

5 Testing

5.1 General

All tests, appropriate to the design requirements of the insulator, shall be undertaken in accordance with current recognised international standards, such as IEC 61109:2008 which applies for composite suspension/tension insulators, or IEC 61952:2008 which applies for composite line post insulators.

For use in special environments, test conditions shall be agreed between manufacturer and purchaser.

5.2 Design tests

These tests are intended to verify the suitability the design, materials and method of manufacture (technology). A manufacturer is likely to have a family of composite insulator designs which are defined by:

- materials of the core, housing and manufacturing method;
- material of the end fittings, their design and method of attachment;
- layer thickness of the housing over the core;
- diameter of the core.

The parameters of the design insulator shall be identified on the manufacturer's drawing giving all dimensional tolerances. Design tests shall be performed according to Table 2.

Table 2 – Design tests

Test contents	Test methods or standards
Tests on interfaces and connections of end fittings	IEC 62217:2005
Pre-stressing	IEC 61109:2008 or IEC 61952:2008
Water immersion pre-stressing	IEC 62217:2005
Verification tests – Visual examination – Steep-front impulse voltage test – Dry power-frequency voltage test	IEC 62217:2005
Tests on shed and housing material	IEC 62217:2005
Hardness test	IEC 62217:2005
Mechanical properties test ^a – Tension test (tension strength) – Tear test (tear strength, angle test pieces)	ISO 37 ISO 34-1
Accelerated weathering test	IEC 62217:2005
Housing tracking and erosion test	IEC 62217:2005
Fire test	IEC 62217:2005
Shed and housing material tracking and erosion test ^b	IEC 60587
Tests on the core material	IEC 62217:2005
Dye penetration test	IEC 62217:2005
Water diffusion test	IEC 62217:2005
Assembled core load-time test	IEC 61109:2008 or IEC 61952:2008
NOTE Test methods or standards are referred to IEC 62217:2005 for general parts, IEC 61109:2008 for composite suspension/tension insulators and IEC 61952:2008 for composite post insulators.	
^a The range of the tension strength and the tear strength can be agreed between customer and supplier.	
^b The test method, end-point criteria and classification of the material can be agreed between customer and supplier.	

When a composite insulator is submitted to the design tests, it becomes a parent insulator for a design class and the results shall be considered valid for the whole class. This tested parent insulator defines a design of insulators which have the following characteristics:

- A: same materials for the core and housing and same manufacturing method;
- B: same material for the end fittings, same design and same method of attachment;
- C: same or greater minimum layer thickness of the housing over the core (including an intermediate sheath where used) within a tolerance of 15 %;
- D: same or smaller stress under mechanical loads;
- E: same or greater diameter of the core;
- F: same housing profile parameters within a tolerance of 15 %. For equivalent housing profile parameters refer to footnote a) in Table 1 of IEC 61109:2008.

As far as practical, the influence of time on the electrical and mechanical properties of the components (core material, housing, interfaces etc.) and of the complete composite insulators has been considered in specifying the design tests to ensure a satisfactory life-time under normally known stress conditions of transmission lines. An explanation of the principles of the damage limit, load coordination and testing for composite suspension/tension insulators is presented in Annex B.

When changes in the design occur, re-qualification shall be performed according to Table 1 of IEC 61952:2008 or Table 1 of IEC 61109:2008. If the housing materials or manufacture process are changed, the mechanical properties test, shed and housing material tracking and erosion test (see IEC 60587) shall also be repeated.

5.3 Type tests

5.3.1 General

Type tests are intended to verify the characteristics of a composite insulator, which depend mainly on its shape and size. These tests shall be applied to composite insulators which have passed the design tests.

Type tests are defined in IEC 61109:2008 for composite suspension/tension insulators and in IEC 61952:2008 for composite line post insulators.

5.3.2 Electrical tests

An insulator type is defined for electrical testing purposes by the arcing distance, creepage distance, shed inclination, shed diameter and shed spacing. The electrical type tests shall be performed only once on insulators satisfying the above criteria for one type. The electrical type tests shall be repeated only when any of the above characteristics is changed.

5.3.3 Mechanical tests

An insulator type is defined for mechanical testing purposes, by the parameters in Table 1, core material, core diameter, the method of attachment and coupling design. The mechanical type tests shall be performed only once on insulators satisfying the above criteria for each type. The mechanical type tests shall be repeated only when any of the above characteristics are changed.

Where combined loading (tension, compression or torsion) is expected of the insulator, the customer shall define the loading conditions and expected duration of loading. The manufacturer shall calculate the limiting stress on the core defined in Table 1, and to verify this by type tests in accordance with IEC 61952:2008 "*Cantilever failing load test*" with the combined loads applied. Annex B gives the principles of the damage limit, load coordination and testing.

Where deflection of the insulator is a criteria set by the client, it shall be measured during the "cantilever failing load test" to confirm the deflection limits are within the customer specification.

5.3.4 Verification of dimensions

If not already routine tested, the insulators shall be examined visually and their conformity with the drawing shall be checked using the tolerances below.

Unless otherwise agreed, a tolerance of:

- $\pm(0,04 \times d + 1,5)$ mm when $d \leq 300$ mm,
- $\pm(0,025 \times d + 6)$ mm when $d > 300$ mm with a maximum tolerance of ± 50 mm,

shall be allowed on all dimensions for which specific tolerances are not requested (d being the dimension in millimetres).

The measurement of creepage distance shall be related to the design dimensions and tolerances as determined from the insulator drawing, even though this dimension may be greater than the value originally specified by the purchaser. When a minimum creepage distance is specified by the purchaser, the negative tolerance is also limited by this value.

5.4 Sample tests

Sample tests are used to verify characteristics of composite insulators other than those outlined in 5.2 and 5.3 and include characteristics which depend on the quality of manufacture and the materials used. Sample tests are performed on insulators taken at random from lots offered for acceptance.

Sample tests are defined in IEC 61109:2008 for composite suspension/tension insulators and in IEC 61952:2008 for composite line post insulators. Where deflection of the insulator is a criteria set by the client, it shall additionally be measured during the “cantilever failing load test”.

5.5 Routine tests

The aim of these tests is to eliminate composite insulators with manufacturing defects. They are carried out on every composite insulator to be supplied. Routine tests are defined in IEC 61109:2008 for composite suspension/tension insulators and in IEC 61952:2008 for composite line post insulators.

6 Identification

The manufacturer's drawing shall show the relevant dimensions and values necessary for identifying and testing the insulator in accordance with this standard. The drawing shall also show applicable manufacturing tolerances.

Each insulator shall be marked with the name or trade mark of the manufacturer and the year of manufacture. In addition, each insulator may be marked with the SML or MDCL. These markings shall be legible and indelible.

7 Transport, storage, installation and maintenance

The insulators shall be suitably prepared to be protected from damage, distortion or deterioration during the method of transport to site, and site storage. The insulators shall be protected, as necessary, against the weather and storage on site during the construction phase.

Manufacturers of insulators shall provide appropriate instructions and information covering general conditions during transport, storage, installation and maintenance of the insulators. In addition to the requirements of IEC 62217:2005, information on handling of composite insulators can be found in CIGRE Technical Brochure 184 [3].

During installation, or when used in non-standard configurations, composite insulators may be submitted to high torsion, compression or bending loads for which they are not designed.

NOTE Annex C gives guidance on non-standard mechanical stresses and dynamic mechanical loading of composite insulators. Annex D gives the information for determination of the equivalent bending moment caused by combined loads.

The manufacturer may specify any precaution or special instructions for the insulator to achieve the performance requirements including:

- cleaning,
- routine maintenance including any special precautions,
- handling,
- storage and transport,
- installation.

Annex A (informative)

Purchaser requirements

The purchaser shall provide information on the railway electrification system and operating requirements which may affect the design of insulators. This shall include, as appropriate, but not be limited to the following:

- electrical system – service parameters (see 4.3);
- outline spatial and dimensional parameters and inclination used in service;
- ambient temperature range (maximum and minimum) of the electrification system;
- system deflection and movement constraints;
- angular movement limitations;
- nominal working loads and possible maximum working load;
- pollution and environmental considerations;
- end fittings connection requirements;
- if possible, anti-corrosion measures, e.g. zinc coating thickness;
- any additional requirement for special tests;
- any special delivery, packaging or marking requirements;
- identification of inspection and tests to be witnessed by the customer;
- maintenance, cleaning or handling constraints;
- weight or dynamic constraints;
- vandalism frequency and impact levels;
- pantograph strip material and strip width;
- if possible, pantograph/ contact wire running load;
- number of pantograph passes;
- pantograph speed.