IEC 62788-1-4

Edition 1.0 2016-09

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Measurement procedures for materials used in photovoltaic modules – Part 1-4: Encapsulants – Measurement of optical transmittance and calculation of the solar-weighted photon transmittance, yellowness index, and UV cut-off wavelength

Procédures de mesure des matériaux utilisés dans les modules photovoltaïques – Partie 1-4: Encapsulants – Mesurage du facteur de transmission optique et calcul du facteur de transmission photonique à pondération solaire, de l'indice de jaunissement et de la fréquence de coupure des UV

IEC 62788-1-4:2016-09(en-fr)

Documents
Document Sharing Hub

Full document details: IEC 62788-1-4 2016

THIS PUBLICATION IS COPYRIGHT PROTECTED
Copyright © 2016 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office
3, rue de Varembé
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC
The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications
The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue
The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - www.iec.ch/searchpub
The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,…). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished
Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org
The world's leading online dictionary of electronic and electrical terms containing 20 000 terms and definitions in English and French, with equivalent terms in 15 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary
65 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc
If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

A propos de l'IEC
La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC
Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Catalogue IEC - webstore.iec.ch/catalogue
Application autonome pour consulter tous les renseignements bibliographiques sur les Normes internationales, Spécifications techniques, Rapports techniques et autres documents de l'IEC. Disponible pour PC, Mac OS, tablettes Android et iPad.

Recherche de publications IEC - www.iec.ch/searchpub
La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études,…). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished
Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

Electropedia - www.electropedia.org
Le premier dictionnaire en ligne de termes électroniques et électriques. Il contient 20 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans 15 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

Glossaire IEC - std.iec.ch/glossary
65 000 entrées terminologiques électrotechniques, en anglais et en français, extraites des articles Termes et Définitions des publications IEC parues depuis 2002. Plus certaines entrées antérieures extraites des publications des CE 37, 77, 86 et CISPR de l'IEC.

Service Clients - webstore.iec.ch/csc
Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: csc@iec.ch.

Documents
Document Sharing Hub

Full document details: IEC 62788-1-4 2016

IEC 62788-1-4

Edition 1.0 2016-09

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Measurement procedures for materials used in photovoltaic modules – Part 1-4: Encapsulants – Measurement of optical transmittance and calculation of the solar-weighted photon transmittance, yellowness index, and UV cut-off wavelength

Procédures de mesure des matériaux utilisés dans les modules photovoltaïques – Partie 1-4: Encapsulants – Mesurage du facteur de transmission optique et calcul du facteur de transmission photonique à pondération solaire, de l'indice de jaunissement et de la fréquence de coupure des UV

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 27.160

ISBN 978-2-8322-3634-5

Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

® Registered trademark of the International Electrotechnical Commission
Marque déposée de la Commission Electrotechnique Internationale

AVA Documents
Document Sharing Hub

Full document details: IEC 62788-1-4 2016

CONTENTS

FOREWORD 3
1 Scope 5
2 Normative references 5
3 Terms and definitions 6
4 Principle 7
5 Apparatus 7
6 Test specimens 7
6.1 Nominal (and unweathered) transmittance to the cell 7
6.2 Weathering studies 8
6.3 Glass for superstrates/substrates 9
6.4 Number of specimens 9
6.5 Preconditioning of specimens 9
7 Measurement procedure 9
7.1 General 9
7.2 Specimen preparation 9
7.3 Instrument calibration (baseline measurements) 9
7.4 Specimen measurements 10
7.5 Witness measurements 10
8 Calculation and expression of results 10
8.1 Post-processing of data 10
8.2 Calculation of weighted transmittance 10
8.3 Calculation of the Yellowness Index (YI) 11
8.4 Calculation of the UV cut-off wavelength 11
9 Uncertainty of measurements 11
10 Test report 12
Annex A (informative) Advanced analysis of transmittance (absorption coefficients) 14
Annex B (informative) Applying the quantum efficiency of a specific cell technology 16
Bibliography 18

Table 1 – Details of the solar weight transmittance parameters 11

Documents
Document Sharing Hub

Full document details: IEC 62788-1-4 2016

INTERNATIONAL ELECTROTECHNICAL COMMISSION

MEASUREMENT PROCEDURES FOR MATERIALS USED IN PHOTOVOLTAIC MODULES –

Part 1-4: Encapsulants – Measurement of optical transmittance and calculation of the solar-weighted photon transmittance, yellowness index, and UV cut-off wavelength

FOREWORD

1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
6) All users should ensure that they have the latest edition of this publication.
7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 62788-1-4 has been prepared by IEC technical committee 82: Solar photovoltaic energy systems.

The text of this standard is based on the following documents:

FDIS	Report on voting
82/1148/FDIS	82/1165/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

Documents
Document Sharing Hub

Full document details: IEC 62788-1-4 2016

A list of all parts in the IEC 62788 series, published under the general title *Measurement procedures for materials used in photovoltaic modules*, can be found on the IEC website.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC website under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

Documents
Document Sharing Hub

Full document details: IEC 62788-1-4 2016

MEASUREMENT PROCEDURES FOR MATERIALS USED IN PHOTOVOLTAIC MODULES –

Part 1-4: Encapsulants – Measurement of optical transmittance and calculation of the solar-weighted photon transmittance, yellowness index, and UV cut-off wavelength

1 Scope

This part of IEC 62788 provides a method for measurement of the optical transmittance of encapsulation materials used in photovoltaic (PV) modules. The standardized measurements in this procedure quantify the expected transmittance of the encapsulation to the PV cell. Subsequent calculation of solar-weighted transmittance allows for comparison between different materials. The results for unweathered material may be used in an encapsulation manufacturer's datasheets, in manufacturer's material or process development, in manufacturing quality control (material acceptance), or applied in the analysis of module performance.

This measurement method can also be used to monitor the performance of encapsulation materials after weathering, to help assess their durability. The standardized measurements are intended to examine an interior region within a PV module, e.g., without the effects of oxygen diffusion around the edges of the cells. Subsequent calculation of yellowness index allows for quantification of durability and consideration of appearance. The change in transmittance, yellowness index, and ultraviolet (UV) cut-off wavelength may be used by encapsulation or module manufacturers to compare the durability of different materials.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60904-3, *Photovoltaic devices – Part 3: Measurement principles for terrestrial photovoltaic (PV) solar devices with reference spectral irradiance data*

ISO 291:2008, *Plastics – Standard atmospheres for conditioning and testing*

ISO 11664-1:2007, *Colorimetry – Part 1: CIE standard colorimetric observers*

ISO 11664-2:2007, *Colorimetry – Part 2: CIE standard illuminants*

ISO 13468-2:1999, *Plastics – Determination of the total luminous transmittance of transparent materials – Part 2: Double-beam instrument*

ISO 17223:2014, *Plastics – Determination of yellowness index and change in yellowness index*

ASTM E424-71:2007, *Standard test methods for solar energy transmittance and reflectance (Terrestrial) of sheet material*

Documents
Document Sharing Hub

Full document details: IEC 62788-1-4 2016

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at http://www.electropedia.org/
- ISO Online browsing platform: available at http://www.iso.org/obp

NOTE In cases where definitions already exist, refer to IEC TS 61836. Calculations related to these definitions are given in Clause 8.

3.1
solar-weighted transmittance of photon irradiance
proportion of the solar spectral photon irradiance ($E_{p\lambda}$, $m^{-2}\cdot s^{-1}\cdot nm^{-1}$) optically transmitted through the specimen, throughout the range of the terrestrial solar spectrum (280 nm to 2 500 nm) (see Table 1)

Note 1 to entry: The photon irradiance ($E_{p\lambda}$, $m^{-2}\cdot s^{-1}\cdot nm^{-1}$) accounts for the wavelength-specific energy of the optical flux and should not be confused with spectral irradiance (E_{λ}, $W\cdot m^{-2}\cdot nm^{-1}$).

3.2
representative solar-weighted transmittance of photon irradiance
proportion of the solar spectral photon irradiance ($E_{p\lambda}$, $m^{-2}\cdot s^{-1}\cdot nm^{-1}$) optically transmitted through the specimen, throughout the range of the terrestrial solar spectrum (300 nm to 1 250 nm) (see Table 1)

Note 1 to entry: In the case of a PV device, the representative solar-weighted transmittance of photon irradiance is defined throughout the range of the spectrum utilized by a representative PV device (which may not include wavelengths as low as 280 nm or as great as 2 500 nm).

3.3
UV cut-off wavelength
λ_{cUV}
wavelength of light below which the encapsulation is considered optically absorbing and above which the encapsulation is considered transmitting

Note 1 to entry: In this procedure, the absolute transmittance of 10 % (corresponding to the optical absorbance of 1) is considered as the threshold of the UV cut-off wavelength. As described further in [9][1], the UV cut-off wavelength may also be used to quantify the effects of weathering.

3.4
weathering
process of subjecting specimens to environmental conditions that could include ultra-violet radiation, temperature, humidity, and ozone

Note 1 to entry: Weathering may occur in artificial or natural environments. Weathering could occur at the nominal (field) or an accelerated rate.

3.5
yellowness index
YI
calculated value identifying the yellowness of the test specimen perceived by a human observer (see ASTM E313-10)

Note 1 to entry: YI may be used to quantify the effects of weathering.

[1] Numbers in square brackets refer to the Bibliography.

Documents
Document Sharing Hub
Full document details: IEC 62788-1-4 2016

4 Principle

The total spectral transmittance of laminated specimens, containing encapsulation material, shall be measured using a spectrophotometer equipped with an integrating sphere. Solar-weighted transmittance, yellowness index, and UV cut-off wavelength will be subsequently calculated from the transmittance measurements.

The transmittance measured using this procedure may be used in a more advanced optical analysis to improve the accuracy of PV performance analysis or distinguish between different encapsulation materials, as described in Annex A. The transmittance measured using this procedure may be used to estimate module performance (current yield) if the quantum efficiency of the PV cell is known, as described in Annex B. The method does not attempt to account for variations in transmittance with the angle of incidence, which may vary with time of day, sky conditions, and geometry of the module, especially if concentration is used.

5 Apparatus

The test instrument shall consist of a double beam spectrophotometer equipped with an integrating sphere. A single beam spectrophotometer may be used if the port reflectance can be properly accounted for, as in Annex A and [2]. Details regarding the construction and configurations of the test instrument may be found in ISO 13468-2 or ASTM E424-71. A measurement range of at least 280 nm to 2 500 nm is required for calculation of the solar-weighted transmittance using the AM1.5 global spectrum as in IEC 60904-3. A wavelength increment no larger than 1 nm is preferred for the measurement, however increments up to 5 nm are permitted with linear interpolation to 1 nm.

An integrating sphere of at least 100 mm in diameter with a port area of < 5 %, as in [11], is recommended to reduce the error in the measurement. The port area as in [9] should not exceed 13 %.

6 Test specimens

6.1 Nominal (and unweathered) transmittance to the cell

Specimens shall be constructed using a laminate structure of glass/encapsulation, as described in Annex A and [12].

The solar-weighted transmittance and representative solar-weighted transmittance, as calculated in Clause 8, may be used for the purpose of reporting on an encapsulation manufacturer's datasheet.

The specimens shall contain an examination region free from visible flaws including: scratches, pits, sink marks, bubbles, or other imperfections. The examination region shall be at least 50 % larger in diameter than the measurement area of the test instrument.

NOTE 1 A spot size of 1 cm × 1 cm is common in many commercial spectrophotometer instruments. Use of specimens at least 2 to 3 times this size will improve uniformity (resulting from fabrication) and handling (during measurement).

The size (length and width) should be adequate to allow the specimen to fit inside the test instrument.

The nominal thickness of the encapsulation specimens shall be equal to the thickness intended for use in PV modules.

Specimens should be cured (if applicable) according to the manufacturer's specification and using a process as similar as possible to the method used in the intended manufacturing process.

AVA Documents
Document Sharing Hub

Full document details: IEC 62788-1-4 2016

The thickness of the encapsulation portion of the test specimen shall be measured after its preparation. The thickness shall be taken as the average of three measurements obtained at different locations on the test region of the specimen.

Glass plates shall be parallel with minimal edge pinch or edge flare. I.e. the encapsulation thickness at any of the corners shall not be more than 10 % different than that in the centre of the sample. In a typical bag laminator this will require the use of a frame around the samples during lamination, but any other means of accomplishing this specification is acceptable.

The back surface of the specimens (the exposed encapsulation intended to face to the integrating sphere) shall not be intentionally textured.

For additional resolution to more accurately distinguish between materials, subsequent studies may utilize a thicker encapsulation layer that may be analysed to determine the optical attenuation coefficient as described in Annex A.

If the encapsulation material is intended to be used with superstrates other than glass, the same procedure may be used in a subsequent study. Specimens using polymeric superstrates may be prone to optical polarization occurring within the instrument. As in [9] and [12], a depolarizer should be used with the instrument to minimize the effects of polarization.

NOTE 2 The effect of haze in specimens prone to optical haze can be mitigated through the use of a diffusing film, as described in [13].

6.2 Weathering studies

A glass/encapsulation/glass laminate specimen geometry is recommended.

The size (length and width) should be adequate to allow the specimen to fit inside the test instrument.

As described in [14], the minimum size of 5 cm × 5 cm is recommended for weathering specimens based on previous examinations of poly (ethylene-co-vinyl acetate).

Large specimens are preferred in weathering studies, because a test region may be distinguished, where the diffusion of oxygen or moisture is limited.

Other geometries may be used with this procedure to evaluate the effects of weathering. For example, a permeable polymeric backsheet facilitates the examination of moisture ingress. Some PV modules make use of an edge seal to reduce moisture permeation.

Separate “blank” pieces of superstrate or substrate may be weathered with the test specimens to quantify the degradation of those components.

The specimens shall contain an examination region free from visible flaws including: scratches, pits, sink marks, bubbles or other imperfections. The examination region shall be at least 50 % larger in diameter than the measurement area of the test instrument.

The nominal thickness of the encapsulation specimens shall be as intended for use in the PV module. Specimens should be cured (if applicable) according to the manufacturer’s specification and as similar as possible to the method used in the intended manufacturing procedure.

The thickness of the encapsulation in the laminate may be controlled by inserting a removable material around the specimen perimeter.

Documents
Document Sharing Hub

Full document details: IEC 62788-1-4 2016

6.3 Glass for superstrates/substrates

Measurements of the nominal (unweathered) transmittance to the cell for the purpose of encapsulation manufacturer's datasheets shall be performed using (3 ± 0,2) mm thick silica glass. The glass shall have smooth, defect-free surfaces that are sufficiently flat and parallel such that the diffuse component of transmitted light is less than 1 % between 280 nm and 2 500 nm.

The solar-weighted transmittance of photon irradiance of silica glass, which may be used to verify that the composition of the glass is appropriate, is approximately 93 %, because the reduction in transmittance comes from reflections at the surfaces. As in [1] and [12], the transmittance of the glass should be greater than 90 % at 280 nm.

The glass shall not be coated or contain antireflective layers. The glass shall not be intentionally textured.

Subsequent examination beyond that intended for the encapsulation material datasheet, including weathering, may be performed according to this procedure using other superstrate and/or substrate materials that can incorporate other optical features, e.g., antireflective coatings, surface texture, and untempered PV glass.

6.4 Number of specimens

A minimum of 3 replicates shall be used for the determination of the transmittance to the cell or in weathering studies. Optical characteristics, including transmittance, YI, and the UV cut-off wavelength shall be subsequently calculated using the average of the three separate specimens, with the range of the measurements indicated to identify their variability.

6.5 Preconditioning of specimens

Specimens used for the purpose of datasheet reporting shall be maintained at (23 ± 2) °C, (50 ± 5) % RH for at least 24 h, as recommended in ISO 291, prior to optical measurement.

The use of elevated temperature and humidity conditions in a weathering study may result in a supersaturated moisture condition within specimens, affecting their optical transmittance when they are returned to the laboratory ambient condition. In such cases, specimen conditioning, including a controlled environmental chamber, may be applied to prevent spurious effects, e.g., optical haze or moisture related absorptance. Specimen-condition effects may be verified using periodic measurements. Refer to the weathering test procedure for any specific details related to specimen conditioning and storage intermittent to weathering.

7 Measurement procedure

7.1 General

Transmittance measurements shall be performed in accordance with the procedure in ISO 13468-2.

7.2 Specimen preparation

Prior to measurement, specimens should be free of dust, grease or other contaminants. The specimens and instrument should be in thermal equilibrium prior to measurement.

7.3 Instrument calibration (baseline measurements)

Allow the instrument lamp to adequately equilibrate after it has been lighted, observing the typical warm-up period, e.g., 15 min or as recommended by the instrument manufacturer. Perform the correction scan(s) to compensate for the instrument baseline signal.

Documents
Document Sharing Hub
Full document details: IEC 62788-1-4 2016

The 100 % transmittance baseline measurement should be performed in air, with no superstrate, specimen, or substrate material present. The 0 % transmittance baseline measurement should also be performed, if possible.

Periodic measurement of the baseline is recommended to minimize instrument drift and ensure the measured values are accurate. The instrument drift occurring over an extended measurement session may be instrument specific.

It is recommended to maintain the instrument drift below 0,05 % to minimize the uncertainty of measurement (Clause 9). The instrument drift should be considered in the instrument bias when the uncertainty of measurements is determined.

7.4 Specimen measurements

Perform the transmittance measurements for the test specimens over the wavelength range of at least 280 nm to 2 500 nm using a 1 nm increment.

Linear interpolation to a 1 nm increment may be used when only a coarser measurement increment (maximum of 5 nm) is available. The error associated with a coarser increment may be more influential at shorter wavelengths (where YI and the UV cut-off wavelength are determined) than at longer wavelengths (where only the solar-weighted transmittance is affected). When applied, the use of linear interpolation should be noted in the test report.

Discontinuities associated with changes in the optical components (including detector, light source, and/or monochromator) may occur during the measurement. Such discontinuities can be minimized via the instrument settings.

It may be useful to extend the range of measurement in durability studies to provide insight into the results. For example, by measuring UV wavelengths as low as 200 nm, the integrity of UV absorbers and stabilizers can be confirmed from the UV cut-off wavelength.

The spectral bandwidth of the measurement should be less than or equal to the increment of the measurement, i.e., 1 nm or 5 nm.

7.5 Witness measurements

Perform the transmittance measurements on a witness specimen at the beginning of each measurement session to ensure proper operation of the instrument and minimize the measurement error. Perform the transmittance measurements of any witness specimens using the same procedure applied to the test specimen(s). The witness specimens may include a traceable standard specimen, laboratory working witness specimen, or the silica superstrate/substrate material.

8 Calculation and expression of results

8.1 Post-processing of data

The measurements obtained from three separate specimens shall be averaged at each wavelength increment. The range (difference of the maximum and minimum) shall also be determined at each wavelength increment.

8.2 Calculation of weighted transmittance

The solar-weighted transmittance may be calculated from formula (1):

Documents
Document Sharing Hub
Full document details: IEC 62788-1-4 2016

$$\tau_{sw} = \frac{\int \tau[\lambda] E_{p\lambda}[\lambda] d\lambda}{\int E_{p\lambda}[\lambda] d\lambda} \quad (1)$$

Where

τ_{sw} refers to the solar-weighted transmittance (%);

τ is the measured transmittance of the specimen (%);

λ is the wavelength of light (nm); and

$E_{p\lambda}$ is the reference global spectral photon irradiance (as given in IEC 60904-3).

The details for the calculation of the various solar-weighted transmittance parameters are identified in Table 1. The parameters include: the "solar-weighted" transmittance, which may be applied generally, based on a broad solar spectrum; and the "representative solar-weighted" transmittance, which may be applied for most commercially available single junction terrestrial PV cells (including silicon, cadmium telluride, copper indium gallium selenide, and gallium arsenide) based on their useable wavelength range. The solar-weighted transmittance (as well as YI) obtained from the spectrophotometer measurements (1 nm interval) shall be calculated using a discretized sum, by means of the modified trapezoidal integration technique, as in IEC 60904-3. The denominator for formula (1) is specified in Table 1 for the purpose of verification, based on IEC 60904-3.

Table 1 – Details of the solar weight transmittance parameters

Parameter	Symbol	Lower bound wavelength nm	Upper bound wavelength nm	$\int E_{p\lambda}[\lambda] d\lambda$ $m^{-2} \cdot s^{-1}$
"solar-weighted" transmittance	τ_{sw}	280	2 500	$4{,}15502132187479 \times 10^{21}$
"representative solar-weighted" transmittance	τ_{rsw}	300	1 250	$3{,}03000915425 \times 10^{21}$
NOTE The solar-weighted spectral transmittance may be more specifically applied to estimate module performance, i.e., current yield, if the quantum efficiency of the PV cell is known, as described in Annex B.				

8.3 Calculation of the Yellowness Index (YI)

YI shall be calculated according to the procedure in ISO 17223. The three tristimulus coefficients shall be determined using the CIE Standard D65 Illuminant spectrum (as in ISO 11664-2), and the CIE 1964 XYZ colour space (for a human observer with a 10° field of view, as in ISO 11664-1). YI shall be calculated for a wavelength increment, e.g., 1 nm, consistent with the measured transmittance data.

NOTE Additional details related to the YI may be found in ASTM E313-10 and ASTM E308-08.

8.4 Calculation of the UV cut-off wavelength

The UV cut-off wavelength, λ_{cUV}, shall be determined as the longest wavelength (to the nearest nm) in the UV range (where $\lambda \leq 400$ nm) where the transmittance equals 10 % or less.

In cases where the UV cut-off wavelength is known to be less than 280 nm, the range of measurement should be extended below 280 nm to quantify its specific value.

9 Uncertainty of measurements

The uncertainty associated with the randomness of measurement may be estimated from:

AVA Documents Document Sharing Hub

Full document details: IEC 62788-1-4 2016