IEC/TR 62797

Edition 1.0 2013-08

TECHNICAL REPORT

colour inside

International comparison of measurements of the magnetic moment using vibrating sample magnetometers (VSM) and superconducting quantum interference device (SQUID) magnetometers

IEC/TR 62797:2013(E)

Documents
Document Sharing Hub

Full document details: IEC TR 62797 2013

THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2013 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.
If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembé
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

Useful links:

IEC publications search - www.iec.ch/searchpub

The advanced search enables you to find IEC publications by a variety of criteria (reference number, text, technical committee,…).
It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available on-line and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary (IEV) on-line.

Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

Documents
Document Sharing Hub

Full document details: IEC TR 62797 2013

IEC/TR 62797

Edition 1.0 2013-08

TECHNICAL REPORT

colour inside

International comparison of measurements of the magnetic moment using vibrating sample magnetometers (VSM) and superconducting quantum interference device (SQUID) magnetometers

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

PRICE CODE V

ICS 29.030

ISBN 978-2-8322-1018-5

Warning! Make sure that you obtained this publication from an authorized distributor.

® Registered trademark of the International Electrotechnical Commission

Documents
Document Sharing Hub

Full document details: IEC TR 62797 2013

CONTENTS

FOREWORD 4
INTRODUCTION 6
1 Scope 7
2 Overview 7
3 Samples 8
3.1 Hard ferrites 8
3.2 Magnetic tapes 8
4 Measuring quantities and measuring conditions 8
4.1 General 8
4.2 Hard ferrite spheres 8
4.3 Magnetic tape samples 9
4.4 Role of the measuring temperature 9
5 Analysis of the measured quantities 10
Annex A (informative) International comparison of measurements of the magnetic moment using vibrating sample magnetometers and SQUID magnetometers 15
Annex B (informative) Participants 30
Bibliography 31

Figure 1 – Isotropic and anisotropic ferrites: standard deviations 12
Figure 2 – Magnetic tape samples: standard deviations 12
Figure 3 – Isotropic and anisotropic ferrites: weighted uncertainties 13
Figure 4 – Magnetic tape samples: weighted uncertainties 13
Figure 5 – Normalized best values $y_i / < y >$ of the coercive field strength H_{cJ} and maximum energy product $(BH)_{max}$ 14
Figure A.1 – Dispersion of the J_{800k} values measured by the participating laboratories on the isotropic ferrite sample HF-Iso1 16
Figure A.2 – Dispersion of the J_r values measured by the participating laboratories on the isotropic ferrite sample HF-Iso1 17
Figure A.3 – Dispersion of the H_{cJ} values measured by the participating laboratories on the isotropic ferrite sample HF-Iso1 18
Figure A.4 – Dispersion of the H_{cB} values measured by the participating laboratories on the isotropic ferrite sample HF-Iso1 19
Figure A.5 – Dispersion of the $(BH)_{max}$ values measured by the participating laboratories on the isotropic ferrite sample HF-Iso1 20
Figure A.6 – Dispersion of the J_{800k} values measured by the participating laboratories on the anisotropic ferrite sample HF-Aniso1 21
Figure A.7 – Dispersion of the J_r values measured by the participating laboratories on the anisotropic ferrite sample HF-Aniso1 22
Figure A.8 – Dispersion of the H_{cJ} values measured by the participating laboratories on the anisotropic ferrite sample HF-Aniso1 23
Figure A.9 – Dispersion of the H_{cB} values measured by the participating laboratories on the anisotropic ferrite sample HF-Aniso1 24
Figure A.10 – Dispersion of the $(BH)_{max}$ values measured by the participating laboratories on the anisotropic ferrite sample HF-Aniso1 25
Figure A.11 – Dispersion of the m_{400k} values measured by the participating laboratories on the magnetic tape sample A1 26

AVA Documents
Document Sharing Hub
Full document details: IEC TR 62797 2013

Figure A.12 – Dispersion of the m_r values measured by the participating laboratories on the magnetic tape sample A1 27

Figure A.13 – Dispersion of the $S = m_r/m_{400k}$ values measured by the participating laboratories on the magnetic tape sample A1 28

Figure A.14 – Dispersion of the H_{cJ} values measured by the participating laboratories on the magnetic tape sample A1 29

Table A.1 – Magnetic polarization value J_{800k} at $H_a = H_{peak}$ = 800 kA/m measured by the participating laboratories on the isotropic hard ferrite HF-Iso1 15

Table A.2 – Remanent magnetic polarization J_r measured by the participating laboratories on the isotropic hard ferrite HF-Iso1 17

Table A.3 – Coercive field H_{cJ} measured by the participating laboratories on the isotropic hard ferrite HF-Iso1 18

Table A.4 – Coercive field H_{cB} measured by the participating laboratories on the isotropic hard ferrite HF-Iso1 19

Table A.5 – Maximum energy product $(BH)_{max}$ measured by the participating laboratories on the isotropic hard ferrite HF- Iso1 20

Table A.6 – Magnetic polarization value J_{800k} at $H_a = H_{peak}$ = 800 kA/m measured by the participating laboratories on the anisotropic hard ferrite HF-Aniso1 21

Table A.7 – Remanent magnetic polarization J_r measured by the participating laboratories on the anisotropic hard ferrite HF-Aniso1 22

Table A.8 – Coercive field H_{cJ} measured by the participating laboratories on the anisotropic hard ferrite HF-Aniso1 23

Table A.9 – Coercive field H_{cB} measured by the participating laboratories on the anisotropic hard ferrite HF-Aniso1 24

Table A.10 – Maximum energy product $(BH)_{max}$ measured by the participating laboratories on the anisotropic hard ferrite HF- Aniso1 25

Table A.11 – Magnetic moment m_{400k} measured at at $H_a = H_{peak}$ = 400 kA/m by the participating laboratories on the magnetic tape sample 1A 26

Table A.12 – Remanent magnetic moment m_r measured by the participating laboratories on the magnetic tape sample 1A 27

Table A.13 – Squareness ratio $S = m_r/m_{400k}$ measured by the participating laboratories on the magnetic tape sample 1A 28

Table A.14 – Coercive field H_{cJ} measured by the participating laboratories on the magnetic tape sample 1A 29

Documents
Document Sharing Hub

Full document details: IEC TR 62797 2013

INTERNATIONAL ELECTROTECHNICAL COMMISSION

INTERNATIONAL COMPARISON OF MEASUREMENTS OF THE MAGNETIC MOMENT USING VIBRATING SAMPLE MAGNETOMETERS (VSM) AND SUPERCONDUCTING QUANTUM INTERFERENCE DEVICE (SQUID) MAGNETOMETERS

FOREWORD

1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
6) All users should ensure that they have the latest edition of this publication.
7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. However, a technical committee may propose the publication of a technical report when it has collected data of a different kind from that which is normally published as an International Standard, for example "state of the art".

IEC 62797, which is a technical report, has been prepared by IEC technical committee 68: Magnetic alloys and steels.

The text of this technical report is based on the following documents:

Enquiry draft	Report on voting
68/448/DTR	68/454/RVC

Full information on the voting for the approval of this technical report can be found in the report on voting indicated in the above table.

Documents
Document Sharing Hub

Full document details: IEC TR 62797 2013

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A bilingual version of this publication may be issued at a later date.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

Documents
Document Sharing Hub

Full document details: IEC TR 62797 2013

INTRODUCTION

Following a proposal made at the meeting of IEC TC 68 Working Group 2 (Magnetic alloys and steels – Measuring methods) in Braunschweig (PTB, 13-14 November 2006), an intercomparison exercise was started regarding the measurement of the magnetic moment by means of the vibrating sample magnetometer (VSM) method. The VSM finds widespread use in industrial and research laboratories, because of its sensitivity, ruggedness, and relative simplicity of use [1][1]. It is not an absolute method and requires calibration by means of a reference sample. This is typically represented by a very pure Ni sphere, calibrated by means of an independent method [2]. The VSM is generally applied for the characterization of hard magnetic materials, but, depending on the specific sensitivity of the apparatus, can also be used to test paramagnetic and diamagnetic materials. Its application to magnetically soft materials is generally restricted to the determination of the saturation magnetization. In fact, being an open circuit method, the VSM is not suited to the measurement of the magnetization curve of soft magnetic materials.

The basic aim of this comparison is to verify the degree of reproducibility of the method, a prerequisite for the prospective development of a related IEC measuring standard. The existing ASTM Standard A894/894M-00 [3] is devoted to the determination of the saturation magnetization of nonmetallic magnetic materials. Ten different research laboratories, listed in Annex B, agreed to participate in the comparison exercise. Each laboratory was assumed to have appropriate traceability of measurements and was required to determine the measurement uncertainty according to the ISO/IEC Guide to the expression of uncertainty in measurement [4]. Two laboratories used superconducting quantum interference device (SQUID) magnetometers.

The comparison was coordinated by INRIM (Istituto Nazionale di Ricerca Metrologica, Torino, Italy) and the Hannam University (Taejon, Korea). A summarizing paper on these experiments was presented at the International Workshop on One- and Two-Dimensional Measurement and Testing (Vienna, September 2012) and is to be published on the Int. J. Appl. Electromagnetics and Mechanics [8].

[1] Numbers in square brackets refer to the Bibliography.

Documents
Document Sharing Hub

Full document details: IEC TR 62797 2013

INTERNATIONAL COMPARISON OF MEASUREMENTS OF THE MAGNETIC MOMENT USING VIBRATING SAMPLE MAGNETOMETERS (VSM) AND SUPERCONDUCTING QUANTUM INTERFERENCE DEVICE (SQUID) MAGNETOMETERS

1 Scope

This Technical Report provides the results of an international comparison of measurements of the magnetic moment, using vibrating sample magnetometers (VSM) and superconducting quantum interference device (SQUID) magnetometers.

The basic object of this comparison is to verify the degree of reproducibility of the method employed as a prerequisite for the prospective development of a related IEC measuring standard.

2 Overview

In this report an intercomparison exercise on the measurement of the magnetic moment by means of the vibrating sample magnetometer (VSM) and superconducting quantum interference device (SQUID) magnetometer is presented. The VSM finds widespread use in industrial and research laboratories, because of its sensitivity, ruggedness, and relative simplicity of use. The basic aim of this comparison was to verify the degree of reproducibility of the VSM method, as a prerequisite for the prospective development of a related IEC measuring standard. At present time, the VSM method is invoked in the ASTM Standard A984, which is devoted, however, exclusively to the determination of the saturation magnetization of nonmetallic magnetic materials. An exercise was carried out by ten different laboratories regarding the measurement of the hysteresis loop parameters in hard ferrites and the magnetic moment in tape samples by means of the VSM (SI units). Each laboratory was assumed to have appropriate traceability of measurements and was required to determine the measurement uncertainty according to the ISO/IEC Guide to the expression of uncertainty in measurement. The comparison was coordinated by INRIM. The results were analyzed according to standard rules (e.g. ISO and EURAMET guidelines).

The following relative standard deviations of the laboratories best estimates around the unweighted mean were found:

a) Anisotropic hard ferrites: coercive field H_{cJ} ~ 1,0 %; coercive field H_{cB} ~ 0,9 %; polarization at applied field H_a ~ 800 kA/m J_{800k} ~ 0,80 %; remanent polarization J_r ~ 1,8 %; maximum energy product $(BH)_{max}$ ~ 1,2 %.

b) Isotropic hard ferrites: coercive field H_{cJ} ~ 1,0 %; coercive field H_{cB} ~ 3,5 %; polarization at applied field H_a = 800 kA/m J_{800k} ~ 1,2 %; remanent polarization J_r ~ 3,2 %; maximum energy product $(BH)_{max}$ ~ 6,2 %.

c) Magnetic tape samples: magnetic moment at H_a = 400 kA/m m_{400k} ~ 1,8 % - 2,8 %; remanent magnetic moment m_r ~ 1,3 % - 1,6 %; squareness S ~ 2,0 %; coercive field H_{cJ} ~ 1,1 % - 2,2 %.

Documents
Document Sharing Hub
Full document details: IEC TR 62797 2013

3 Samples

3.1 Hard ferrites

Two different types of hard ferrite spherical samples (isotropic and anisotropic) were prepared at INRIM by grinding commercial sintered ferrite specimens. Two samples for each type were circulated.

- Isotropic hard ferrite spherical sample. Label: HF_iso1. Mass m = 74,50 mg. Density δ = 4 950 kg/m^3. Volume V = 15,05 mm^3.
- Isotropic hard ferrite spherical sample. Label: HF_iso2. Mass m = 77,15 mg. Density δ = 4 950 kg/m^3. Volume V = 15,59 mm^3.
- Anisotropic hard ferrite spherical sample. Label: HF_anis1. Mass m = 73,33 mg. Density δ = 4 870 kg/m^3. Volume V = 15,06 mm^3.
- Anisotropic hard ferrite spherical sample. Label: HF_anis2. Mass m = 73,31 mg. Density δ = 4 870 kg/m^3. Volume V = 15,06 mm^3.

The circulation of the samples started with measurements made at INRIM. After completion of the measurements by all the other laboratories, INRIM measured the sample mass again and repeated the magnetic measurements. A slight decrease of the mass, which ranged from 0,2 % to 0,3% in all samples, was eventually found. No attempt was made, however, to correct for this loss of mass, which presumably took place gradually along the exercise. Its effect has been assumed to be incorporated in the overall measuring uncertainty.

3.2 Magnetic tapes

Disk samples were cut from two different types of magnetic tape at Hannam University and dispatched to INRIM before starting the circulation. Two samples for each type were tested.

- Tape 1A. Mass m = 1,258 mg. Diameter d = 3 mm.
- Tape 1B. Mass m = 1,248 mg. Diameter d = 3 mm.
- Tape 2A. Mass m = 1,246 mg. Diameter d = 3 mm.
- Tape 2B. Mass m = 1,205 mg. Diameter d = 3 mm.

Again, INRIM tested the samples at the beginning and at the end of the exercise. It was found that Tape 1B and Tape 2B samples were damaged. The measurements concerning Tape 1A and Tape 2A only were therefore retained for analysis.

4 Measuring quantities and measuring conditions

4.1 General

A demagnetization procedure before starting the measurements was recommended. The suggested maximum peak value of the magnetic field strength to be progressively and cyclically decreased, was $H_{a,peak,max} \geq 800$ kA/m.

4.2 Hard ferrite spheres

Before starting the measurement, the demagnetized spherical samples were oriented with their macroscopic easy axis aligned with the applied field direction. A simple way to achieve alignment is to let the sample free to orient itself in a weak field. Fine adjustments may possibly be done on site by looking for maximum VSM response. Notice that the nominally isotropic sample is endowed with slight macroscopic anisotropy. Previous experiments showed that a ± 5° misalignment in anisotropic samples can lead to a decrease of the measured remanence around 1 %. A similar decrease occurs in the typical isotropic ferrites for a misalignment as high as 30° - 40°. The measurement in this material is therefore negligibly affected by imperfect orientation of the easy axis along the applied field direction.

Documents
Document Sharing Hub

The applied field was then increased up to $H_{a,peak}$ = 800 kA/m and the return magnetization curve was recorded, after correction for the demagnetizing effect. The effective field was obtained as $H = H_a - \frac{N_d}{\mu_0} J$, with H_a the applied field, J the magnetic polarization, μ_0 = $4\pi \cdot 10^{-7}$ Vs/Am, and the demagnetizing coefficient, under the assumption of a perfectly spherical sample, N_d = 1/3. The following quantities were measured:

- Magnetic polarization J_{800k} at H_a = $H_{a,peak}$ = 800 kA/m;
- Remanent polarization J_r for H = 0;
- Coercive fields H_{cB} and H_{cJ};
- Maximum energy product $(BH)_{max}$.

4.3 Magnetic tape samples

Before starting the measurement, the demagnetized disk-shaped samples were oriented with their macroscopic easy axis aligned with the applied field direction. A faint mark on the disk surface indicated the easy axis. The applied field was increased up to $H_{a,peak}$ = 400 kA/m and subsequently decreased down to the symmetric value $-H_{a,peak}$ = -400 kA/m. No correction for the demagnetizing field was made.

The following quantities were determined:

- Magnetic moment m_{400k} for H_a = $H_{a,peak}$ = 400 kA/m;
- Remanent moment m_r for H_a = 0;
- Squareness $S = m_r / m_{400k}$;
- Coercive field H_{cJ}.

While the intercomparison was specifically directed at evaluating the reproducibility of the VSM method, two of the laboratories (PTB and NPL) performed their measurements by means of a SQUID magnetometer. SI units were used all along the experiments.

4.4 Role of the measuring temperature

The prescribed measuring temperature was 23 °C ± 1 °C. This temperature refers to the region occupied by the sample and the sensing coils, which, due to possible heating of the electromagnet, may be slightly different from the room temperature.

INRIM performed specific measurements by changing the sample temperature between 19 °C and 26 °C, in order to determine the temperature coefficient of the measured quantities. Laboratories making the measurements at temperatures different from 23 °C could correct their results according to value and sign of these coefficients.

1) Isotropic and anisotropic hard-ferrites (HF_iso1, HF_iso2, HF_anis1, HF_anis2).

   a) Coercive field H_{cJ} $\quad \alpha_{hcJ} = \frac{1}{H_{cJ}} \cdot \frac{dH_{cJ}}{dT} = +0{,}2\ \%/C^o$

   b) Coercive field H_{cB} $\quad \alpha_{hcB} = \frac{1}{H_{cB}} \cdot \frac{dH_{cB}}{dT} = +5 \cdot 10^{-2}\ \%/C^o$

   c) Remanence and peak polarization values J $\quad \alpha_J = \frac{1}{J} \cdot \frac{dJ}{dT} = -0{,}12\ \%/C^o$

2) Magnetic tapes (1A, 1B, 2A, 2B)

   a) Coercive field H_c $\quad \alpha_{hc} = \frac{1}{H_c} \cdot \frac{dH_c}{dT} = -8 \cdot 10^{-2}\ \%/C^o$

AVA Documents Document Sharing Hub

Full document details: IEC TR 62797 2013