

American National Standard

for zinc-coated ferrous single and double upset
spool insulator bolts for overhead line construction

Approved March 2, 1988

Secretariat: National Electrical Manufacturers Association

Page 1 of 4 pages

1 Scope

This standard covers both single and double upset spool insulator bolts used in overhead line construction.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this American National Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this American National Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below.

ANSI C135.1-1979, *Galvanized steel bolts and nuts for overhead line construction*

ANSI/NEMA PH10-1977, *Galvanized ferrous washers*¹⁾

ANSI/ASTM A153-82, *Specifications for zinc coating (hot-dip) on iron and steel hardware*¹⁾.

3 General

Single and double upset spool insulator bolts covered by this standard shall, in all respects, meet the basic dimensional and performance requirements hereinafter stated. The text, specifications or standard references, and figures supplement each other, and all shall be considered parts of this standard.

4 Material

4.1 Bolts

All single and double upset spool insulator bolts shall be made from hot-rolled steel which has been produced by the open-hearth, basic-oxygen, or electric-furnace process and which is of a grade and quality suitable to meet the requirements of this standard.

¹⁾ This standard has been administratively withdrawn. Contact the secretariat for more recent information.

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether he has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review and users are cautioned to obtain the latest editions.

The American National Standards Institute does not develop standards and will in no circumstances give an interpretation of any American National Standard. Moreover, no person shall have the right or authority to issue an interpretation of an American National Standard in the name of the American National Standards Institute.

CAUTION NOTICE: This American National Standard may be revised or withdrawn at any time. The procedures of the American National Standards Institute require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of approval. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute.

4.2 Nuts

All steel nuts shall be in accordance with ANSI C135.1-1979.

4.3 Locknuts

Locknuts shall be of the double concave type unless another type is specified.

4.4 Washers

Ferrous washers shall be in accordance with ANSI/NEMA PH 10-1977.

4.5 Self-locking cotters

Cotters for spool insulator bolts shall be self-locking type, made from corrosion-resistant material.

5 Dimensions

5.1 Length

That portion of spool insulator bolts used for mounting through a pole shall be considered the "length." This length shall be measured from the threaded end (semicone point not included) to the near face of the closed upset.

5.2 Semicone Points

Single and double upset spool insulator bolts shall have points on each end in accordance with ANSI C135.1-1979.

6 Threads

6.1 Single and double upset spool insulator bolts shall have threads in accordance with ANSI C135.1-1979.

6.2 The external threaded portion of all bolts shall, after galvanizing, be in such condition that nuts tapped in accordance with table 8 of ANSI C135.1-1979 will fit the galvanized bolt so that the nut can be run the entire length of the thread without the use of tools.

7 Galvanizing

After fabrication, single or double upset spool insulator bolts shall be hot-dip galvanized in accordance with ANSI/ASTM A153-82, except the cotter hole may be drilled after galvanizing.

8 Strength

8.1 Single and double upset spool insulator bolts and nuts shall, without deflecting more than 10 degrees under load, develop strengths shown in the table in figure 2 when tested by the method shown thereon.

8.2 The load shall be applied at a rate of approximately 0.4 inch per minute free running crosshead speed of the testing machine.

9 Finish

Single and double upset spool insulator bolts shall be reasonably smooth on all surfaces and shall be free of sharp projections. Cotters shall be cut squarely and shall be free of sharp projections.

10 Marking

All single and double upset spool insulator bolts shall bear the manufacturer's symbol or identification mark.

11 Marking of shipping packages

Each package of single or double upset spool insulator bolts shall be marked with the manufacturer's name and catalog number.