



ASSOCIATION CONNECTING
ELECTRONICS INDUSTRIES

IPC-4110

Specification and Characterization Methods for Nonwoven Cellulose Based Paper for Printed Boards

ANSI/IPC-4110

August 1998

A standard developed by IPC

2215 Sanders Road, Northbrook, IL 60062-6135

Tel. 847.509.9700 Fax 847.509.0700

www.ipc.org



Documents

Document Sharing Hub

The Principles of Standardization

In May 1995 the IPC's Technical Activities Executive Committee adopted Principles of Standardization as a guiding principle of IPC's standardization efforts.

Standards Should:

- Show relationship to Design for Manufacturability (DFM) and Design for Engineering (DFE)
- Minimize time to market
- Contain simple (simplified) language
- Just include spec information
- Focus on end product performance
- Include a feedback system on use and problems for future improvement

Standards Should Not:

- Inhibit innovation
- Increase time-to-market
- Keep people out
- Increase cycle time
- Tell you how to make something
- Contain anything that cannot be defended with data

Notice

IPC Standards and Publications are designed to serve the public interest through eliminating misunderstandings between manufacturers and purchasers, facilitating interchangeability and improvement of products, and assisting the purchaser in selecting and obtaining with minimum delay the proper product for his particular need. Existence of such Standards and Publications shall not in any respect preclude any member or nonmember of IPC from manufacturing or selling products not conforming to such Standards and Publication, nor shall the existence of such Standards and Publications preclude their voluntary use by those other than IPC members, whether the standard is to be used either domestically or internationally.

Recommended Standards and Publications are adopted by IPC without regard to whether their adoption may involve patents on articles, materials, or processes. By such action, IPC does not assume any liability to any patent owner, nor do they assume any obligation whatever to parties adopting the Recommended Standard or Publication. Users are also wholly responsible for protecting themselves against all claims of liabilities for patent infringement.

IPC Position Statement on Specification Revision Change

It is the position of IPC's Technical Activities Executive Committee (TAEC) that the use and implementation of IPC publications is voluntary and is part of a relationship entered into by customer and supplier. When an IPC standard/guideline is updated and a new revision is published, it is the opinion of the TAEC that the use of the new revision as part of an existing relationship is not automatic unless required by the contract. The TAEC recommends the use of the latest revision.

Adopted October 6, 1998

Why is there a charge for this standard?

Your purchase of this document contributes to the ongoing development of new and updated industry standards. Standards allow manufacturers, customers, and suppliers to understand one another better. Standards allow manufacturers greater efficiencies when they can set up their processes to meet industry standards, allowing them to offer their customers lower costs.

IPC spends hundreds of thousands of dollars annually to support IPC's volunteers in the standards development process. There are many rounds of drafts sent out for review and the committees spend hundreds of hours in review and development. IPC's staff attends and participates in committee activities, typesets and circulates document drafts, and follows all necessary procedures to qualify for ANSI approval.

IPC's membership dues have been kept low in order to allow as many companies as possible to participate. Therefore, the standards revenue is necessary to complement dues revenue. The price schedule offers a 50% discount to IPC members. If your company buys IPC standards, why not take advantage of this and the many other benefits of IPC membership as well? For more information on membership in IPC, please visit www.ipc.org or call 847/790-5372.

Thank you for your continued support.



ASSOCIATION CONNECTING
ELECTRONICS INDUSTRIES

ANSI/IPC-4110

Specification and Characterization Methods for Nonwoven Cellulose Based Paper for Printed Boards

Developed by the Nonwoven Cellulose Reinforcement Task Group
(3-12g) of the Strategic Components of Base Materials Subcommittee
(3-12) of the Base Materials Committee (3-10) of IPC

APPROVED OCTOBER 1, 1998 BY



AMERICAN NATIONAL STANDARDS INSTITUTE

Users of this standard are encouraged to participate in the
development of future revisions.

Contact:

IPC
2215 Sanders Road
Northbrook, Illinois
60062-6135
Tel 847 509.9700
Fax 847 509.9798



Acknowledgment

Any standard involving a complex technology draws material from a vast number of sources. While the principal members of the Nonwoven Cellulose Reinforcement Task Group are shown below, it is not possible to include all of those who assisted in the evolution of this standard. To each of them, the members of the IPC extend their gratitude.

Base Materials Committee	Nonwoven Cellulose Reinforcement Task Group	Technical Liaison of the IPC Board of Directors
Chairman D. Sober isolaUSA	Chairman U. Kempf Fibermark, Inc.	J. Donaghy Sheldahl
Nonwoven Cellulose Reinforcement Task Group		
Bruce Andrews, Crane & Company Inc.	Terry Fischer, Hitachi Chemical Co. America	Chris Malik, JPS Glass and Industrial Fabrics Corp.
Mike Bryant, BGF Industries, Inc.	Jeffrey Gleim, P.H. Glatfelter Company/	Thomas Nowak, Nowak & Associates
H. Landis Carter, JPS Glass and Industrial Fabrics Corp.	Florian Gunkle, AlliedSignal Lamine Systems	Paul Reichenbacher, AlliedSignal Lamine Systems
Yong Deng, Owens-Corning Fiberglass Corp.	Ulrich Kempf, FiberMark, Inc.	Tony Senese, Taconic
Nitin Desai, Motorola, Inc.	Rodney Komlenic, Ahlstrom Paper Group	William Shaw, FiberMark, Inc.
Joe Dickson, Sigma Circuits, Inc.	Robert Konsowicz, GIL Technologies	Lowell Sherman, Defense Supply Center Columbus DSCC
Howard Elliott, Polyclad Laminates, Inc.	Dennis Lockyer, Crane & Company, Inc.	Douglas Sober, isolaUSA
Werner Engelmaier, Engelmaier Associates, Inc.	P. Douglas Lyle, Owens-Corning Fiberglass Corp.	Xie Xiaoyan, Dongguan Shengyi Copper Clad Lamine Co. Ltd.
James Feeney, Morton Electronic Materials		

Table of Contents

1 SCOPE	1	3.4.1 Roll Length.....	2
1.1 Purpose	1	3.4.2 Roll Width	2
1.2 Classification.....	1	3.5 Chemical Requirements	2
2 APPLICABLE DOCUMENTS	1	3.5.1 Ash Content.....	2
2.1 IPC	1	3.5.2 pH	2
2.2 TAPPI	1	4 QUALITY ASSURANCE	2
3 REQUIREMENTS	1	4.1 Responsibility for Inspection	2
3.1 Terms and Definitions	1	4.1.1 Test Equipment and Inspection Facilities.....	3
3.1.1 Absorptivity	1	4.1.2 Standard Laboratory Conditions	3
3.1.2 Air Holes	1	4.2 Preparation of Samples	3
3.1.3 Bagginess	1	4.3 Inspection Procedure	3
3.1.4 Caliper Variation (MD and CD)	1	4.3.1 Classification of Major and Minor Visual Defects	3
3.1.5 Cellulose Fibers.....	1	4.3.2 Sampling Plans.....	3
3.1.6 Conducting Particles.....	1	4.4 Acceptability Quality Level	3
3.1.7 Dents	1	4.5 Statistical Process Control (SPC)	3
3.1.8 Dirt	1	5 PREPARATION FOR DELIVERY	3
3.1.9 Edge Tear	1	5.1 Roll Size	3
3.1.10 Folds	1	5.1.1 Roll Length.....	3
3.1.11 Holes	1	5.1.2 Roll Width	4
3.1.12 Poor Formation.....	1	5.2 Splices.....	4
3.1.13 Rough Surface	2	5.3 Preservation and Packaging	4
3.1.14 Shives.....	2	5.4 Packing	4
3.1.15 Soft Roll	2	5.5 Labeling	4
3.1.16 Weight Variation (MD and CD).....	2	6 NOTES	4
3.1.17 Wet Tensile	2	6.1 Purchase Orders.....	4
3.2 Physical Requirements	2	6.2 New Materials	4
3.2.1 Product.....	2		
3.3 Visual Requirements.....	2		
3.3.1 Visual/Appearance Procedures.....	2		
3.3.2 Visual/Appearance Defects	2		
3.3.3 TAPPI Test Methods and Procedures	2		
3.3.4 Density Calculation	2		
3.4 Dimensional Requirements	2		

Tables

Table 3-1	Major and Minor Visual Defects.....	2
Table 3-2	Test Methods and TAPPI Procedures.....	2
Table 4-1	General Inspection	3

This Page Intentionally Left Blank

Specification and Characterization Methods for Nonwoven Cellulose Based Paper for Printed Boards

1 SCOPE

This specification covers paper made from cellulosic fibers intended as a reinforcing material in laminated plastics for electrical and electronic use.

1.1 Purpose This specification determines the nomenclature, definitions, and general, chemical, and physical requirements for paper made from cellulosic fibers.

1.2 Classification This specification provides physical and chemical characteristics of the paper required to meet the design and performance requirements of PWBs.

2 APPLICABLE DOCUMENTS

2.1 IPC¹

IPC-T-50 Terms and Definitions for Interconnecting and Packaging Electronic Circuits

2.2 TAPPI²

T 400 sp-95 Sampling and Inspecting a Single Lot of Paper, Paperboard, Containerboard, or Related Product

T 402 om-93 Standard Conditioning and Testing Atmosphere for Paper, Board, Pulp Handsheets, and Related Products

T 404 om-92 Tensile Breaking Strength and Elongation of Paper and Paperboard (Using Pendulum-Type Tester)

T 410 om-93 Grammage of Paper and Paperboard (Weight per Unit Area)

T 411 om-89 Thickness (Caliper) of Paper, Paperboard, and Combined Board

T 412 om-94 Moisture in Paper and Paperboard

T 413 om-93 Ash in Paper and Paperboard

T 456 om-87 Wet Tensile Strength

T 460 om-96 Air Resistance of Paper (Gurley Method)

T 509 om-96 Hydrogen Ion Concentration (pH) of Paper Extracts (Cold Extraction Method)

3 REQUIREMENTS

3.1 Terms and Definitions Other than the terms listed in 3.1.1 through 3.1.17, the definition of terms **shall** be in accordance with IPC-T-50 and TAPPI documents.

3.1.1 Absorptivity The rate of resin saturant pick-up into the paper.

3.1.2 Air Holes Small circular areas containing less fibers, which are caused by air bubbles.

3.1.3 Bagginess Material that is distorted, stretched, or deformed in the middle or along the edges of the sheet.

3.1.4 Caliper Variation (MD and CD) A sheet that is of uneven thickness in the width and length.

3.1.5 Cellulose Fibers Fibers derived from trees by pulping processes, cotton linter fibers, and mixtures of the two fiber types. These fibers may be bleached to a high brightness.

3.1.6 Conducting Particles Small foreign particles capable of conducting current.

3.1.7 Dents Indentations in the surface of the paper or in the edge of the roll.

3.1.8 Dirt Small dark particles of foreign origin (i.e., bark pieces, floor dirt, seed particles, or any other visible contaminants).

3.1.9 Edge Tear Tears in the edge of the paper.

3.1.10 Folds A permanent fold or crease in the paper, generally in the machine direction, occurring during processing or rewinding.

3.1.11 Holes An area in the paper where few or no fibers are present.

3.1.12 Poor Formation Very uneven distribution of fibers in the sheet, resulting in a mottled appearance.

3.1.13 Rough Surface Extreme uneven caliper, generally caused by poor formation.

1. IPC, 2215 Sanders Road, Northbrook, IL 60062, 847-509-9700, <http://www.ipc.org>

2. TAPPI, 1-800-322-8686 (U.S.), 1-800-446-9431 (Canada), +1-770-209-7303 (International), or visit <http://www.tappi.org> for a list of TAPPI Publications.