

INTERNATIONAL STANDARD

ISO
10400

First edition
1993-12-15

Petroleum and natural gas industries — Formulae and calculation for casing, tubing, drill pipe and line pipe properties

*Industries du pétrole et du gaz naturel — Formules et calculs relatifs aux
propriétés des cuvelages, tubes de production, tiges de forage et tubes
de conduites*



Reference number
ISO 10400:1993(E)

AVA Documents
Document Sharing Hub

ISO 10400:1993(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 10400 was prepared by the American Petroleum Institute (API) (as Bul 5C3, 5th edition) and was adopted, under a special "fast-track procedure", by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum and natural gas industries*, in parallel with its approval by the ISO member bodies.

© ISO 1993

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization

Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Introduction

International Standard ISO 10400:1993 reproduces the content of API Bul 5C3, 5th edition, 1989. ISO, in endorsing this API document, recognizes that in certain respects the latter does not comply with all current ISO rules on the presentation and content of an International Standard. Therefore, the relevant technical body, within ISO/TC 67, will review ISO 10400:1993 and reissue it, when practicable, in a form complying with the ISO directives.

This standard is not intended to obviate the need for sound engineering judgement as to when and where this standard should be utilized and users of this standard should be aware that additional or differing requirements may be needed to meet the needs for the particular service intended.

Standards referenced herein may be replaced by other international or national standards that can be shown to meet or exceed the requirements of the referenced standards.

Petroleum and natural gas industries — Formulae and calculation for casing, tubing, drill pipe and line pipe properties

1 Scope

This International Standard establishes the formulae used in the calculation of the various casing, tubing, drill pipe and line pipe properties for the oil and natural gas industries.

2 Requirements

Requirements are specified in

"API BULLETIN 5C3 (Bul 5C3), Fifth Edition, July 1989 — *Bulletin on Formulas and Calculations for Casing, Tubing, Drill Pipe, and Line Pipe Properties*",

which is adopted as ISO 10400.

For the purposes of international standardization, however, modifications shall apply to specific clauses and paragraphs of publication API Bul 5C3. These modifications are outlined below.

Throughout publication API Bul 5C3, the conversion of English units shall be made in accordance with ISO 31. The content of section 11, **Metrication** shall read as given below.

Page 8

Information given in the POLICY is relevant to the API publication only.

METRICATION

METRIC CONVERSIONS AND CALCULATIONS

Metric units in API Bul 5C3 are shown in italic type and in the text and most tables in parentheses. Outside diameters and wall thicknesses are converted from inch dimensions. The converted values are rounded to the nearest 0,1 mm for diameters less than 18 in, and to the nearest 1,0 mm for diameters 18 in and larger. Wall thicknesses are rounded to the nearest 0,1 mm.

Metric inside diameters and drift diameters are calculated from the metric outside diameters and wall thicknesses and rounded to the nearest 0,1mm.

Metric plain-end masses are calculated from the metric outside diameters and wall thicknesses by the following formula and rounded to the nearest 0,01 kg/m.

$$W_{pe} = 0,024\ 66(D - t)t$$

Metric hydrostatic test pressures are calculated from the metric outside diameters and wall thicknesses and metric fiber stresses as shown in clause 8.

The factors used where conversions are appropriate are as follows:

1 inch (in)	= 25,4 mm exactly
1 square inch (in ²)	= 645,16 mm ² exactly
1 foot (ft)	= 0,3048 m exactly
1 pound (lb)	= 0,453 59 kg
1 pound per foot (lb/ft)	= 1,488 2 kg/m
1 pound per square inch (lb/in ²)	= 6,895 kPa for pressure = 0,006 895 MPa for stress
1 footpound-force (ft-bf)	= 1,355 8 J for impact energy = 1,355 8 N·m for torque

The following formula was used to convert degrees Fahrenheit (°F) to degrees Celsius (°C): °C = 5/9 (°F - 32).

ROUNDING OF METRIC UNITS

Metric units are converted or calculated in accordance with factors given above and the number of digits shown in the table.

Table — Number of decimals to be shown in metric units

1	2	3
PROPERTY	METRIC UNITS	NUMBER OF DECIMALS
Diameter	mm	1
Thickness and imperfections	mm	1
Upset and coupling length	mm	1
Length	m	2
Mass	kg	2
Mass per foot	kg/m	2
Stress and tensile strength	MPa	0
Pressure	kPa × 100	0
Guided bend A	mm	1
Thread elements		
Major diameter	mm	1
Pitch diameter	mm	3
Thread length	mm	2
Thread height	mm	3
Recess depth	mm	1
J (distance from end of pipe to centre of coupling)	mm	1

Bulletin on Formulas and Calculations for Casing, Tubing, Drill Pipe and Line Pipe Properties

API BULLETIN 5C3 (Bul 5C3)
FIFTH EDITION, JULY 1989

American Petroleum Institute
1220 L Street, Northwest
Washington, DC 20005



ISO 10400:1993(E)

Issued by
AMERICAN PETROLEUM INSTITUTE
Production Department

FOR INFORMATION CONCERNING THE TECHNICAL CONTENTS OF
THIS PUBLICATION CONTACT THE API PRODUCTION DEPARTMENT,
2535 ONE MAIN PLACE, DALLAS, TX 75202 — (214) 748-3841.
SEE BACK COVER FOR INFORMATION CONCERNING HOW TO OBTAIN
ADDITIONAL COPIES OF THIS PUBLICATION.

Users of this publication should become familiar with its scope and content.
This document is intended to supplement rather than
replace individual engineering judgment.

OFFICIAL PUBLICATION



REG. U.S. PATENT OFFICE

Copyright © 1989 American Petroleum Institute

TABLE OF CONTENTS

Section	Page
1 COLLAPSE PRESSURE	5
1.1 Collapse Pressure Formulas	5
1.1.1 Yield Strength Collapse Pressure Formula	5
1.1.2 Plastic Collapse Pressure Formula	6
1.1.3 Transition Collapse Pressure Formula	7
1.1.4 Elastic Collapse Pressure Formula	8
1.1.5 Collapse Pressure Under Axial Tension Stress	8
1.1.6 Effect of Internal Pressure on Collapse	9
1.1.7 Collapse Pressure Formula Symbols	9
1.2 Derivation of Collapse Pressure Formulas	9
1.2.1 Yield Strength Collapse Pressure Formula Derivation	10
1.2.2 Plastic Collapse Pressure Formula Derivation	10
1.2.3 Transition Collapse Pressure Formula Derivation	12
1.2.4 Elastic Collapse Pressure Formula Derivation	14
1.3 Collapse Testing Procedure	14
1.3.1 Test Specimen	14
1.3.2 Test Apparatus	14
1.3.3 Test Procedure	14
1.3.4 Data Reporting	14
2 PIPE BODY YIELD STRENGTH	16
3 INTERNAL PRESSURE RESISTANCE	16
3.1 Internal Yield Pressure	16
3.1.1 Internal Yield Pressure for Pipe	16
3.1.2 Internal Yield Pressure for Couplings	17
3.2 Internal Pressure Leak Resistance at E_1 or E_7 Plane	18
4 JOINT STRENGTH	19
4.1 Round Thread Casing Joint Strength	19
4.2 Buttress Thread Casing Joint Strength	20
4.3 Extreme-Line Casing Joint Strength	20
4.4 Tubing Joint Strength	21
4.5 Joint Strength of Round Thread Casing with Combined Bending and Internal Pressure	21
4.6 Line Pipe Joint Strength	22
5 WEIGHTS	23
5.1 Nominal Weight	23
5.2 Calculated Plain End Weight	23
5.3 Calculated Threaded and Coupled Weight	23
5.4 Calculated Upset and Threaded Weight for Integral Joint Tubing and Extreme-Line Casing	24
5.5 Calculated Upset Weight	24
5.6 Weight Gain Due to End Finishing	25
5.7 Calculated Coupling Weight	26
5.7.1 Calculated Coupling Weight for Line Pipe and Round Thread Casing and Tubing	26
5.7.2 Calculated Coupling Weight for Buttress Thread Casing	27
5.8 Calculated Weight Removed in Threading	28
5.8.1 Calculated Weight Removed in Threading Pipe or Pin Ends	28
5.8.2 Calculated Weight Removed in Threading Integral Joint Tubing Box Ends	30

5.9 Calculated Weight of External Upsets	31
5.10 Calculated Weight of Internal Upsets	31
5.11 Calculated Weight of External-Internal Upsets	31
5.12 Calculated Weight of Extreme-line Upsets	32
6 ELONGATION	33
7 FLATTENING TESTS	33
7.1 Flattening Tests for Casing and Tubing	33
7.2 Flattening Tests for Line Pipe	34
8 HYDROSTATIC TEST PRESSURES	34
8.1 Hydrostatic Test Pressure for Plain-End Pipe, Extreme-Line Casing and Integral Joint Tubing	34
8.2 Hydrostatic Test Pressure for Threaded and Coupled Pipe	35
8.2.1 Internal Yield Pressure for Couplings	35
8.2.2 Internal Pressure Leak Resistance at E_1 or E_7 Plane	37
9 MAKE-UP TORQUE	37
10 GUIDED BEND TESTS	38
11 METRICATION	39
11.1 Metric Conversions and Calculations	39
11.2 Rounding of Metric Units	40
12 CALCULATION ACCURACY AND ROUNDING	40
12.1 Accuracy	40
12.2 Intermediate Rounding	40
12.3 Final Rounding	40

FOREWORD

- a. This bulletin is under the jurisdiction of the Committee on Standardization of Tubular Goods.
- b. The purpose of this bulletin is to show the formulas used in the calculation of the various pipe properties given in API standards, including background information regarding their development and use.
- c. American Petroleum Institute (API) Bulletins are published to provide information for which there is a broad industry need but which does not constitute either Specifications or Recommended Practices.
- d. Any Bulletin may be used by anyone desiring to do so, and a diligent effort has been made by API to assure the accuracy and reliability of the data contained herein. However, the Institute makes no representation, warranty or guarantee in connection with the publication of any Bulletin and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use, for any violation of any federal, state, or municipal regulation with which an API recommendation may conflict, or for the infringement of any patent resulting from the use of this publication.
- e. This Standard (supplement) shall become effective on the date printed on the cover but may be used voluntarily from the date of distribution.

Attention Users: Portions of this publication have been changed from the previous edition. The locations of changes have been marked with a bar in the margin, as shown to the left of this paragraph. In some cases the changes are significant, while in other cases the changes reflect minor editorial adjustments. The bar notations in the margins are provided as an aid to users as to those parts of this publication that have been changed from the previous edition, but API makes no warranty as to the accuracy of such bar notations.

Note: This is the fifth edition of this bulletin. The first edition was authorized for publication at the 1970 Standardization Conference as detailed in Circ PS-1398 and issued in 1971. Subsequent editions were issued in 1974, 1980, and 1985.

Requests for permission to reproduce or translate all or any part of the material published herein should be addressed to the Director, American Petroleum Institute, Production Department, 2535 One Main Place, Dallas TX 75202.

POLICY

1. API PUBLICATIONS NECESSARILY ADDRESS PROBLEMS OF A GENERAL NATURE. WITH RESPECT TO PARTICULAR CIRCUMSTANCES, LOCAL, STATE, AND FEDERAL LAWS AND REGULATIONS SHOULD BE REVIEWED.

2. API IS NOT UNDERTAKING TO MEET THE DUTIES OF EMPLOYERS, MANUFACTURERS, OR SUPPLIERS TO WARN AND PROPERLY TRAIN AND EQUIP THEIR EMPLOYEES, AND OTHERS EXPOSED, CONCERNING HEALTH AND SAFETY RISKS AND PRECAUTIONS, NOR UNDERTAKING THEIR OBLIGATIONS UNDER LOCAL, STATE, OR FEDERAL LAWS.

3. INFORMATION CONCERNING SAFETY AND HEALTH RISKS AND PROPER PRECAUTIONS WITH RESPECT TO PARTICULAR MATERIALS AND CONDITIONS SHOULD BE OBTAINED FROM THE EMPLOYER, THE MANUFACTURER OR SUPPLIER OF THAT MATERIAL, OR THE MATERIAL SAFETY DATA SHEET.

4. NOTHING CONTAINED IN ANY API PUBLICATION IS TO BE CONSTRUED AS GRANTING ANY RIGHT, BY IMPLICATION OR OTHERWISE,

FOR THE MANUFACTURE, SALE, OR USE OF ANY METHOD, APPARATUS, OR PRODUCT COVERED BY LETTERS PATENT. NEITHER SHOULD ANYTHING CONTAINED IN THE PUBLICATION BE CONSTRUED AS INSURING ANYONE AGAINST LIABILITY FOR INFRINGEMENT OF LETTERS PATENT.

5. GENERALLY, API STANDARDS ARE REVIEWED AND REVISED, REAFFIRMED, OR WITHDRAWN AT LEAST EVERY FIVE YEARS. SOMETIMES A ONE-TIME EXTENSION OF UP TO TWO YEARS WILL BE ADDED TO THIS REVIEW CYCLE. THIS PUBLICATION WILL NO LONGER BE IN EFFECT FIVE YEARS AFTER ITS PUBLICATION DATE AS AN OPERATIVE API STANDARD OR, WHERE AN EXTENSION HAS BEEN GRANTED, UPON REPUBLICATION. STATUS OF THE PUBLICATION CAN BE ASCERTAINED FROM THE API AUTHORIZING DEPARTMENT [TELEPHONE (214) 748-3841]. A CATALOG OF API PUBLICATIONS AND MATERIALS IS PUBLISHED ANNUALLY AND UPDATED QUARTERLY BY API, 1220 L STREET, N.W., WASHINGTON, D.C. 20005.

SECTION 1 COLLAPSE PRESSURE

1.1 COLLAPSE PRESSURE FORMULAS

The minimum collapse pressures given in API Bul 5C2 are calculated by means of formulas 1.1.1.1, 1.1.2.1, 1.1.3.1 and 1.1.4.1, adopted at the 1968 Standardization Conference and reported in Circular PS-1360 dated September 1968.

Formulas 1.1.1.2, 1.1.2.2 and 1.1.3.2 for the intersections between the four collapse pressure formulas have been determined algebraically and used for calculating the applicable D/t range for each collapse pressure formula. Factors A, B, C, F and G have been calculated using formulas 1.2.2.12, 1.2.2.13, 1.2.2.14, 1.2.3.2 and 1.2.3.3. Grades with alphabetic prefixes are API grades. Those without alphabetic prefixes are non API grades. When determining the appropriate formula to be used for calculating collapse resistance for a particular D/t ratio and minimum yield strength, the D/t ranges determined by formulas 1.1.1.2, 1.1.2.2 and 1.1.3.2 govern, rather than the collapse formula that gives the lowest collapse pressure. The D/t ranges for API and some non API grades are given in Tables 1.1.1.1, 1.1.2.1, 1.1.3.1 and 1.1.4.1.

The collapse pressures for Bul 5C2 are calculated using the specified values for D and t rounding D/t to two decimals carrying eight digits in all intermediate calculations and rounding the collapse pressure to the nearest 10 psi.

1.1.1 YIELD STRENGTH COLLAPSE PRESSURE FORMULA

The yield strength collapse pressure is not a true collapse pressure, but rather the external pressure, P_{Y_p} , that generates minimum yield stress, Y_p , on the inside wall of a tube as calculated by formula 1.1.1.1

$$P_{Y_p} = 2Y_p \left[\frac{(D/t) - 1}{(D/t)^2} \right] \quad \dots\dots\dots 1.1.1.1$$

The formula for yield strength collapse pressure formula 1.1.1.1 is applicable for D/t values up to the value of D/t corresponding to the intersection with the plastic collapse formula 1.1.2.1. This intersection is calculated by formula 1.1.1.2 as follows:

$$(D/t)_{yp} = \frac{\sqrt{(A - 2)^2 + 8 (B + C/Y_p)} + (A - 2)}{2(B + C/Y_p)} \quad \dots\dots\dots 1.1.1.2$$

The applicable D/t ratios for yield strength collapse are shown in table 1.1.1.1.

**TABLE 1.1.1.1
YIELD COLLAPSE PRESSURE
FORMULA RANGE**

1	2
Grade†	D/t Range*
H-40	16.40 and less
-50	15.24 " "
J-K-55	14.81 " "
-60	14.44 " "
-70	13.85 " "
C-75 & E	13.60 " "
L-N-80	13.38 " "
C-90	13.01 " "
C-T-95 & X	12.85 " "
-100	12.70 " "
P-105 & G	12.57 " "
P-110	12.44 " "
-120	12.21 " "
Q-125	12.11 " "
-130	12.02 " "
S-135	11.92 " "
-140	11.84 " "
-150	11.67 " "
-155	11.59 " "
-160	11.52 " "
-170	11.37 " "
-180	11.23 " "

†Grades indicated without letter designation are not API grades but are grades in use or grades being considered for use and are shown for information purposes.

*The D/t range values were calculated from formulas 1.1.1.2, 1.2.2.12, 1.2.2.13 and 1.2.2.14 to eight or more digits.

1.1.2 PLASTIC COLLAPSE PRESSURE FORMULA

The minimum collapse pressure for the plastic range of collapse is calculated by formula 1.1.2.1.

$$P_p = Y_p \left[\frac{A}{D/t} - B \right] - C \quad \dots\dots\dots 1.1.2.1$$

The formula for minimum plastic collapse pressure is applicable for D/t values ranging from $(D/t)_{PT}$, formula 1.1.1.2 for yield point collapse pressure, to the intersection with the formula 1.1.3.1 for transition collapse pressure $(D/t)_{PT}$. Values for $(D/t)_{PT}$ are calculated by means of formula 1.1.2.2.

$$(D/t)_{PT} = \frac{Y_p (A - F)}{C + Y_p (B - G)} \quad \dots\dots\dots 1.1.2.2$$

The factors and applicable D/t range for the plastic collapse formula are shown in table 1.1.2.1.

TABLE 1.1.2.1
FORMULA FACTORS AND D/t RANGES
FOR PLASTIC COLLAPSE

1	2	3	4	5
Grade†	A	Formula Factor* B	C	D/t Range*
H-40	2.950	0.0465	754	16.40 to 27.01
-50	2.976	0.0515	1056	15.24 to 25.63
J-K-55	2.991	0.0541	1206	14.81 to 25.01
-60	3.005	0.0566	1356	14.44 to 24.42
-70	3.037	0.0617	1656	13.85 to 23.38
C-75 & E	3.054	0.0642	1806	13.60 to 22.91
L-N-80	3.071	0.0667	1955	13.38 to 22.47
C-90	3.106	0.0718	2254	13.01 to 21.69
C-T-95 & X	3.124	0.0743	2404	12.85 to 21.33
-100	3.143	0.0768	2553	12.70 to 21.00
P-105 & G	3.162	0.0794	2702	12.57 to 20.70
P-110	3.181	0.0819	2852	12.44 to 20.41
-120	3.219	0.0870	3151	12.21 to 19.88
Q-125	3.239	0.0895	3301	12.11 to 19.63
-130	3.258	0.0920	3451	12.02 to 19.40
S-135	3.278	0.0946	3601	11.92 to 19.18
-140	3.297	0.0971	3751	11.84 to 18.97
-150	3.336	0.1021	4053	11.67 to 18.57
-155	3.356	0.1047	4204	11.59 to 18.37
-160	3.375	0.1072	4356	11.52 to 18.19
-170	3.412	0.1123	4660	11.37 to 17.82
-180	3.449	0.1173	4966	11.23 to 17.47

†Grades indicated without letter designation are not API grades but are grades in use or grades being considered for use and are shown for information purposes.

*The D/t range values and formula factors were calculated from formulas 1.1.1.2, 1.1.2.2, 1.2.2.12, 1.2.2.13, 1.2.2.14, 1.2.3.2 and 1.2.3.3 to eight or more digits.

1.1.3 TRANSITION COLLAPSE PRESSURE FORMULA

The minimum collapse pressure for the plastic to elastic transition zone P_T is calculated by formula 1.1.3.1.

$$P_T = Y_p \left[\frac{F}{D/t} - G \right] \dots\dots\dots 1.1.3.1$$

The formula for P_T is applicable for D/t values from $(D/t)_{PT}$, formula 1.1.2.2 for plastic collapse pressure to the intersection $(D/t)_{TE}$ with the formula 1.1.4.1 for elastic collapse. Values for $(D/t)_{TE}$ are calculated by formula 1.1.3.2.

$$(D/t)_{TE} = \frac{2 + B/A}{3B/A} \dots\dots\dots 1.1.3.2$$

The factors and applicable D/t range for the transition collapse pressure formula are shown in table 1.1.3.1.

TABLE 1.1.3.1
FORMULA FACTORS AND D/t RANGE
FOR TRANSITION COLLAPSE

1	2	3	4
Grade†	Formula Factors*		D/t Range*
	F	G	
H-40	2.063	0.0325	27.01 to 42.64
-50	2.003	0.0347	25.63 to 38.83
J-K-55	1.989	0.0360	25.01 to 37.21
-60	1.983	0.0373	24.42 to 35.73
-70	1.984	0.0403	23.38 to 33.17
C-75 & E	1.990	0.0418	22.91 to 32.05
L-N-80	1.998	0.0434	22.47 to 31.02
C-90	2.017	0.0466	21.69 to 29.18
C-T-95 & X	2.029	0.0482	21.33 to 28.36
-100	2.040	0.0499	21.00 to 27.60
P-105 & G	2.053	0.0515	20.70 to 26.89
P-110	2.066	0.0532	20.41 to 26.22
-120	2.092	0.0565	19.88 to 25.01
Q-125	2.106	0.0582	19.63 to 24.46
-130	2.119	0.0599	19.40 to 23.94
S-135	2.133	0.0615	19.18 to 23.44
-140	2.146	0.0632	18.97 to 22.98
-150	2.174	0.0666	18.57 to 22.11
-155	2.188	0.0683	18.37 to 21.70
-160	2.202	0.0700	18.19 to 21.32
-170	2.231	0.0734	17.82 to 20.60
-180	2.261	0.0769	17.47 to 19.93

†Grades indicated without letter designation are not API grades but are grades in use or grades being considered for use and are shown for information purposes.

*The D/t range values and formula factors were calculated from formulas 1.1.2.2, 1.1.3.2, 1.2.2.12, 1.2.2.13, 1.2.2.14, 1.2.3.2 and 1.2.3.3 to eight or more digits.

1.1.4 ELASTIC COLLAPSE PRESSURE FORMULA

The minimum collapse pressure for the elastic range of collapse is calculated by formula 1.1.4.1

$$P_E = \frac{46.95 \times 10^6}{(D/t) ((D/t) - 1)^2} \dots\dots\dots 1.1.4.1$$

The applicable D/t range for elastic collapse is shown in table 1.1.4.1

TABLE 1.1.4.1
D/t RANGE FOR ELASTIC COLLAPSE

1	2
Grade†	D/t Range*
H-40	42.64 and greater
-50	38.83 " "
J-K-55	37.21 " "
-60	35.73 " "
-70	33.17 " "
C-75 & E	32.05 " "
L-N-80	31.02 " "
C-90	29.18 " "
C-T-95 & X	28.36 " "
-100	27.60 " "
P-105 & G	26.89 " "
P-110	26.22 " "
-120	25.01 " "
Q-125	24.46 " "
-130	23.94 " "
S-135	23.44 " "
-140	22.98 " "
-150	22.11 " "
-155	21.70 " "
-160	21.32 " "
-170	20.60 " "
-180	19.93 " "

†Grades indicated without letter designation are not API grades but are grades in use or grades being considered for use and are shown for information purposes.

*The D/t range values were calculated from formulas 1.1.3.2, 1.2.2.12, and 1.2.2.13 to eight or more digits.

1.1.5 COLLAPSE PRESSURE UNDER AXIAL TENSION STRESS

The collapse resistance of casing in the presence of an axial stress is calculated by modifying the yield stress to an axial stress equivalent grade according to Formula 1.1.5.1

$$Y_{pa} = [\sqrt{1 - 0.75(S_a/Y_p)^2} - 0.5 S_a/Y_p] Y_p \dots\dots\dots 1.1.5.1$$

Where:

S_a = Axial Stress, psi (tension is positive)

Y_p = Minimum yield strength of the pipe, psi

Y_{pa} = Yield strength of axial stress equivalent grade, psi

Collapse resistance formula factors and D/t ranges for the axial stress equivalent grade are then calculated by means of Formulas 1.2.2.12, 1.2.2.13, 1.2.2.14, 1.1.1.2, 1.1.2.2, 1.1.3.2, 1.2.3.2 and 1.2.3.3. Using formula factors for the axial stress equivalent grade, collapse resistance under axial stress is calculated by means of Formulas 1.1.1.1, 1.1.2.1, 1.1.3.1 and 1.1.4.1.

The reduced collapse pressures are calculated using D/t rounded to two decimals and carrying eight digits in all intermediate calculations and rounding the reduced collapse pressure to the nearest 10 psi.

API collapse resistance formulas are not valid for the yield strength of axial stress equivalent grade (Y_{pa}) less than 24,000 psi.