
International Standard



105/N

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Textiles — Tests for colour fastness — Part N: Colour fastness to bleaching agencies

Textiles — Essais de solidité des teintures — Partie N: Solidité des teintures aux agents de blanchiment

First edition — 1978-12-15

Updated and reprinted — 1982-09-01

UDC 677.016.47

Ref. No. ISO 105/N-1978 (E)

Descriptors : textiles, dyes, tests, colour fastness, visual inspection, bleaching tests, chemical tests, sodium hypochlorite, hydrogen peroxide, cellulose textiles, sodium chlorites, sulphur dioxide.



Documents

Document Sharing Hub

Price based on 10 pages

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 105/N was developed by Technical Committee ISO/TC 38, *Textiles*.

It was submitted directly to the ISO Council, in accordance with sub-clause 5.10.1 of part 1 of the Directives for the technical work of ISO.

This part of ISO 105 cancels and replaces group N of ISO 105-1978, originally published as parts 6, 7 and 20 of ISO Recommendation R 105/I-1959, and parts 7 and 8 of ISO Recommendation R 105/II-1963.

NOTE — International Standard ISO 105 is presented in the form of parts. Each of these parts corresponds to a group and is split up into its different component sections. This form facilitates the replacement of existing sections by successive editions as necessary.

Contents of ISO 105

- ISO 105/A Textiles — Tests for colour fastness —**
Part A : General principles
- A01** General principles of testing
 - A02** Grey scale for assessing change in colour
 - A03** Grey scale for assessing staining
- ISO 105/B Textiles — Tests for colour fastness —**
Part B : Colour fastness to light and weathering
- B01** Colour fastness to light : Daylight
 - B02** Colour fastness to light : Xenon arc
 - B03** Colour fastness to weathering : Outdoor exposure
 - B04** Colour fastness to weathering : Xenon arc
 - B05** Detection and assessment of photochromism
- ISO 105/C Textiles — Tests for colour fastness —**
Part C : Colour fastness to washing and laundering
- C01** Colour fastness to washing : Test 1
 - C02** Colour fastness to washing : Test 2
 - C03** Colour fastness to washing : Test 3
 - C04** Colour fastness to washing : Test 4
 - C05** Colour fastness to washing : Test 5
 - C06** Colour fastness to domestic and commercial laundering
- ISO 105/D Textiles — Tests for colour fastness —**
Part D : Colour fastness to dry cleaning
- D01** Colour fastness to dry cleaning
 - D02** Colour fastness to rubbing : Organic solvents
- ISO 105/E Textiles — Tests for colour fastness —**
Part E : Colour fastness to aqueous agencies
- E01** Colour fastness to water
 - E02** Colour fastness to sea water
 - E03** Colour fastness to chlorinated water (swimming-bath water)
 - E04** Colour fastness to perspiration
 - E05** Colour fastness to spotting : Acid
 - E06** Colour fastness to spotting : Alkali
 - E07** Colour fastness to spotting : Water
 - E08** Colour fastness to water : Hot water
 - E09** Colour fastness to potting
 - E10** Colour fastness to decatizing
 - E11** Colour fastness to steaming
 - E12** Colour fastness to milling : Alkaline milling
 - E13** Colour fastness to acid-felting : Severe
 - E14** Colour fastness to acid-felting : Mild
- ISO 105/F Textiles — Tests for colour fastness —**
Part F : Standard adjacent fabrics
- F01** Specification for standard adjacent fabric : Wool
 - F02** Specification for standard adjacent fabric : Cotton and viscose
 - F03** Specification for standard adjacent fabric : Polyamide
 - F04** Specification for standard adjacent fabric : Polyester
 - F05** Specification for standard adjacent fabric : Acrylic
 - F06** Specification for standard adjacent fabric : Silk
- ISO 105/G Textiles — Tests for colour fastness —**
Part G : Colour fastness to atmospheric contaminants
- G01** Colour fastness to nitrogen oxides
 - G02** Colour fastness to burnt gas fumes
 - G03** Colour fastness to ozone in the atmosphere

- ISO 105/J Textiles — Tests for colour fastness —**
Part J : Measurement of colour and colour differences
J01 Method for the measurement of colour and colour differences
- ISO 105/N Textiles — Tests for colour fastness —**
Part N : Colour fastness to bleaching agencies
N01 Colour fastness to bleaching : Hypochlorite
N02 Colour fastness to bleaching : Peroxide
N03 Colour fastness to bleaching : Sodium chlorite : Mild
N04 Colour fastness to bleaching : Sodium chlorite : Severe
N05 Colour fastness to stoving
- ISO 105/P Textiles — Tests for colour fastness —**
Part P : Colour fastness to heat treatments
P01 Colour fastness to dry heat (excluding pressing)
P02 Colour fastness to pleating : Steam pleating
- ISO 105/S Textiles — Tests for colour fastness —**
Part S : Colour fastness to vulcanizing
S01 Colour fastness to vulcanizing : Hot air
S02 Colour fastness to vulcanizing : Sulphur monochloride
S03 Colour fastness to vulcanizing : Open steam
- ISO 105/X Textiles — Tests for colour fastness —**
Part X : Tests not included in parts A to S or part Z
X01 Colour fastness to carbonizing : Aluminium chloride
X02 Colour fastness to carbonizing : Sulphuric acid
X03 Colour fastness to chlorination
X04 Colour fastness to mercerizing
X05 Colour fastness to organic solvents
X06 Colour fastness to soda boiling
X07 Colour fastness to cross-dyeing : Wool
X08 Colour fastness to degumming
X09 Colour fastness to formaldehyde
X10 Assessment of migration of textile colours into polyvinyl chloride coatings
X11 Colour fastness to hot pressing
X12 Colour fastness to rubbing
X13 Colour fastness of wool dyes to processes using chemical means for creasing, pleating and setting
- ISO 105/Z Textiles — Tests for colour fastness —**
Part Z : Colorant characteristics
Z01 Colour fastness to metals in the dye-bath : Chromium salts
Z02 Colour fastness to metals in the dye-bath : Iron and copper

Textiles — Tests for colour fastness

N01 Colour fastness to bleaching : Hypochlorite

1 SCOPE AND FIELD OF APPLICATION

This method is intended for determining the resistance of the colour of textiles of all kinds and in all forms to the action of bleaching baths containing sodium, calcium or lithium hypochlorite in concentrations normally used in commercial bleaching. It is applicable mainly to natural and regenerated cellulose materials.

2 PRINCIPLE

A specimen of the textile is agitated in a solution of sodium or lithium hypochlorite, rinsed in water, agitated in a hydrogen peroxide solution or sodium bisulphite solution, rinsed and dried. The change in colour is assessed with the grey scale.

3 REFERENCES

ISO 105 :

Section A01, *General principles of testing*.

Section A02, *Grey scale for assessing change in colour*.

Section C01, *Colour fastness to washing : Test 1*.

4 APPARATUS AND REAGENTS

4.1 Glass or glazed porcelain container which can be closed, for specimen and bleaching solution.

4.2 Either :

Sodium hypochlorite (NaOCl) solution containing 2,0 g of available chlorine per litre, buffered at $\text{pH } 11,0 \pm 0,2$ with 10 g of anhydrous sodium carbonate (Na_2CO_3) per litre, at the temperature $20 \pm 2^\circ\text{C}$.

To prepare this reagent, use sodium hypochlorite of the following composition :

- active chlorine : 140 to 160 g/l
- sodium chloride (NaCl) : 120 to 170 g/l
- sodium hydroxide (NaOH) : 20 g/l maximum

- sodium carbonate (Na_2CO_3) : 20 g/l maximum
- iron (Fe) : 0,01 g/l maximum

Or :

Lithium hypochlorite (LiOCl) solution containing 0,2 g of available chlorine per litre, buffered at $\text{pH } 11,0 \pm 0,2$ with 10 g of anhydrous sodium carbonate (Na_2CO_3) per litre, at the temperature $20 \pm 2^\circ\text{C}$.

To prepare this reagent, use solid lithium hypochlorite, which contains approximately 300 g of LiOCl per kilogram. About 10 g of solid lithium hypochlorite dissolved in 1 litre of distilled water yields a solution of the prescribed concentration of 2,0 g of available chlorine per litre.

4.3 Hydrogen peroxide solution containing 2,5 ml of hydrogen peroxide [30 % (*m/m*) H_2O_2] per litre, or a solution containing 5 g of **sodium bisulphite** (NaHSO_3) per litre.

4.4 Soap solution, containing 5 g of soap per litre (see sub-clause 4.3 of section C01) for wetting out water-repellent fabrics.

4.5 Grey scale for assessing change in colour (see clause 3).

5 TEST SPECIMEN

5.1 If the textile to be tested is fabric, use a specimen 10 cm $\times$ 4 cm.

5.2 If the textile to be tested is yarn, knit it into fabric and use a specimen 10 cm $\times$ 4 cm, or make a wick of parallel lengths 10 cm long and about 0,5 cm in diameter, tied near both ends.

5.3 If the textile to be tested is loose fibre, comb and compress enough of it to form a sheet 10 cm $\times$ 4 cm; in order to support the fibres, sew the sheet on a piece of cloth which will not affect the action of the hypochlorite on the specimen.

UDC 677.016.47

First edition — 1978-12-15

Descriptors : textiles, dyes, tests, colour fastness, visual inspection, bleaching tests, sodium hypochlorite.

Approved by member bodies of : Austria; Belgium; Bulgaria; Canada; Chile; Czechoslovakia; Denmark; France; Greece; Hungary; India; Ireland; Israel; Italy; Netherlands; New Zealand; Norway; Pakistan; Poland; Portugal; Spain; Sweden; Switzerland; United Kingdom; U.S.S.R.

© International Organization for Standardization, 1978 •

Printed in Switzerland



Documents

Document Sharing Hub

N01 page 1