

INTERNATIONAL STANDARD

ISO
10602

Second edition
1995-02-01

Photography — Processed silver-gelatin type black-and-white film — Specifications for stability

*Photographie — Film de type gélatino-argentique noir et blanc traité —
Spécifications relatives à la stabilité*



Reference number
ISO 10602:1995(E)
AVA Documents
Document Sharing Hub

Contents

	Page
1 Scope	1
2 Normative references	1
3 Definitions	2
4 Safety and hazards	2
4.1 Hazard warnings	2
4.2 Hazard information code system	3
4.3 Safety precautions	3
5 Requirements for film bases	3
6 Requirements for processed film	3
6.1 Safety film	3
6.2 Amount of free acid	3
6.3 Tensile properties and loss in tensile properties	3
7 Requirements for the emulsion and backing layers of processed film	4
7.1 Layer adhesion	4
7.2 Emulsion flow	4
7.3 Blocking	4
7.4 Thiosulfate concentration	4
7.5 Residual silver compounds	5
8 Requirements for image stability	5
8.1 Radiographic films	5
8.2 Microfilms	5
8.3 Other films	5
9 Test methods	5
9.1 Identification of film base	5

9.2	Accelerated ageing conditions	6
9.3	Determination of the amount of free acid	6
9.4	Tensile property test for processed film	7
9.5	Tape-stripping adhesion test	8
9.6	Humidity-cycling adhesion test	8
9.7	Emulsion flow test	9
9.8	Blocking test	9
9.9	Residual silver compound test	9
9.10	Image-stability test	9

Annexes

A	Preparation of standard solution of tetrabutylammonium hydroxide	11
B	Washing and the effect of residual thiosulfate on the developed silver image	12
C	Effect of residual silver compounds on the developed silver image	13
D	Accelerated image-stability test for radiographic films	14
E	Accelerated image-stability test for microfilms	15
F	Accelerated image-stability test for aerial films	16
G	Bibliography	17

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 10602 was prepared by Technical Committee ISO/TC 42, *Photography*.

This second edition cancels and replaces the first edition (ISO 10602:1993), which has been technically revised.

Annex A forms an integral part of this International Standard. Annexes B, C, D, E, F and G are for information only.

Introduction

Since 1930 great advances have been made in the use of photographic films for the preservation of records. The preservation of film records by governments, banks, insurance companies, industry and other enterprises has been stimulated by a recognition of the economies in storage space, organization, accessibility and ease of reproduction that result from the use of film records.

During the early development period of the art of copying documents, 35 mm nitrate motion-picture film was sometimes used. This material is highly flammable and is not a safety film as specified in ISO 543. **Nitrate film is not acceptable for any record film.** The manufacture of nitrate film declined after World War II and was discontinued in most countries in the 1950's.

For many years the only safety films in commercial use were made on some type of cellulose ester base, such as cellulose acetate, cellulose acetate propionate or cellulose acetate butyrate. The useful life of safety cellulose-ester-type films is somewhat conjectural, since actual experience with commercial material extends back only to about 1908. However, these materials show severe degradation when exposed to high temperatures and particularly to high humidities. Laboratory incubation studies predict a useful life of at least a century when stored under recommended conditions[1], [2], [3], [4].

A second type of polymer safety film base belonging to the polyester class, known chemically as poly(ethylene terephthalate), was introduced commercially in 1956. This material has a number of advantages over the cellulose ester base such as greater strength, stiffness, tear resistance, flexibility, dimensional stability and other characteristics, which make it superior for many photographic applications[5], [6]. Actual experience with polyester film is considerably less than with cellulose ester film although this material has been used for over 35 years.

Practical experience to date and accelerated ageing tests indicate that this film support is more stable than safety cellulose ester film base and is expected to have a useful life of 500 years[1], [4].

This second edition eliminates the film classifications of "archival", "long-term" and "medium-term" and replaces them with the LE (life expectancy) rating. In addition, residual hypo limits and image-stability tests are given for radiographic film, microfilm and all other films.

Studies on the stability of silver-gelatin-type films have investigated the effect of residual hypo on the image permanence of radiographic films[7], microfilms[8] and aerial films[9]. This work suggested modifications to the residual hypo limits and a more quantitative image-stability test was included in the first edition of ISO 10602. Residual hypo limits and image-stability tests are now included for all film categories.

Former annex D, "Microscopic spots and blemishes", and annex E, "Emulsion adhesion", have been eliminated; an annex F, "Accelerated image-stability test for aerial films", has been added.

This International Standard identifies certain hazards to permanence attributable to the chemical or physical characteristics of processed film and gives methods of evaluating them. Some of these characteristics are the responsibility of the film manufacturer, some of the film processor, and some are influenced by both. However, specifying the chemical and physical characteristics of the material does not, by itself, ensure satisfactory keeping behaviour. It is essential to provide proper storage temperature and humidity, and protection from the hazards of fire, water, fungus and certain atmospheric pollutants. It is important that films be stored under the conditions specified in ISO 5466 and ISO 10214.

Photography — Processed silver-gelatin type black-and-white film — Specifications for stability

1 Scope

1.1 This International Standard establishes the specifications for photographic films intended for the storage of records.

1.2 It applies specifically to films with a base of safety cellulose ester or polyester [poly(ethylene terephthalate)] having silver-gelatin emulsions, processed to produce a black-and-white silver image by negative or full-reversal processing. It applies to film processed by a monobath which includes thiosulfate as the fixing agent followed by a conventional wash. It also applies to silver films given a stabilizing treatment by partial or full conversion to silver sulfide, silver selenide or gold.

1.3 This International Standard does not apply to films with colour images of any type, nor to films with a magnetic recording track. It does not apply to films with silver images produced by dry or thermal processing or by diffusion-reversal processing. It does not apply to films that have been processed by a monobath using other than a thiosulfate-type fixing solution. It is not applicable to films where the silver salts are removed by means other than thiosulfate solutions^[10].

1.4 This International Standard does not apply to films to which lacquers have been applied.

1.5 This International Standard applies to films having ultrasonic or dielectric (induction heated) splices. It does not cover films with splices made by means of adhesive tape or solvent-type splices.¹⁾

1) Solvent-type splices are suspect since they may retain traces of residual solvents containing peroxide which can pose some risk of oxidative attack on the silver image.

2) To be published. (Revision of ISO 5-3:1984)

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 5-1:1984, *Photography — Density measurements — Part 1: Terms, symbols and notations.*

ISO 5-2:1991, *Photography — Density measurements — Part 2: Geometric conditions for transmission density.*

ISO 5-3:—²⁾, *Photography — Density measurements — Part 3: Spectral conditions.*

ISO 417:1993, *Photography — Determination of residual thiosulfate and other related chemicals in processed photographic materials — Methods using iodine-amylose, methylene blue and silver sulfide.*

ISO 543:1990, *Photography — Photographic films — Specifications for safety film.*

ISO 1184:1983, *Plastics — Determination of tensile properties of films.*

ISO 5466:1992, *Photography — Processed safety photographic films — Storage practices.*

ISO 10214:1991, *Photography — Processed photographic materials — Filing enclosures for storage*.

3 Definitions

For the purposes of this International Standard, the definitions given in ISO 5-1 and the following definitions apply.

3.1 archival medium: A recording material that can be expected to retain information forever so that it can be retrieved without significant loss when properly stored.

NOTE 1 There is, however, no such material and it is not a term to be used in International Standards or system specifications.

3.2 life expectancy (LE): The length of time that information is predicted to be retrievable in a system under extended-term storage conditions.

NOTE 2 However, the actual useful life of film is very dependent upon the existing storage conditions (see ISO 5466 and ISO 10214).

3.3 LE designation: A rating for the “life expectancy” of recording materials and associated retrieval systems. The number following the LE symbol is a prediction of the minimum life expectancy, in years, for which information can be retrieved without significant loss when stored under extended term storage conditions.

NOTE 3 For example, LE-100 indicates that information can be retrieved for at least 100 years' storage.

3.4 extended-term storage conditions: Storage conditions suitable for the preservation of recorded information having permanent value.

3.5 medium-term storage conditions: Storage conditions suitable for the preservation of recorded information for a minimum of 10 years.

3.6 film base: The plastic support for the emulsion and backing layers.

3.7 emulsion layer(s): The image or image-forming layer(s) of photographic films, papers and plates.

3.8 noncurl backing layer: A layer, usually made of gelatin, applied to the side of the film base opposite that of the emulsion layer, for the purpose of preventing curl. It is comparable to the emulsion layer in thickness and is not removed in processing.

NOTE 4 Antihalation or other layers removed in processing are excluded from this definition.

3.9 safety photographic film: Photographic film which passes the ignition time test and burning time test as specified in ISO 543.

3.10 safety cellulose-ester base: A film base composed mainly of the cellulose esters of acetic, propionic or butyric acids, or mixtures thereof.

3.11 safety poly(ethylene terephthalate) base: A polyester film base composed mainly of a polymer of ethylene glycol and terephthalic acid.

3.12 full-reversal processing: Processing that includes development, bleach, clear, re-exposure and second development, followed by fixing and washing.

4 Safety and hazards

4.1 Hazard warnings

Some of the chemicals specified in the test procedures are caustic, toxic or otherwise hazardous. Safe laboratory practice for the handling of chemicals requires the use of safety glasses or goggles, rubber gloves and other protective apparel such as face masks or aprons where appropriate. Specific danger notices are given in the text and footnotes for particularly dangerous materials, but normal precautions are required during the performance of any chemical procedures at all times. The first time that a hazardous material is noted in the test procedure section, the hazard will be indicated by the word “DANGER” followed by a symbol consisting of angle brackets “< >” containing a letter which designates the specific hazard. A double bracket “<< >>” will be used for particularly perilous situations. In subsequent statements involving handling of these hazardous materials, only the hazard symbol consisting of the brackets and letter(s) will be displayed. Furthermore, for a given material, the hazard symbol will be used only once in a single paragraph.

Detailed warnings for handling chemicals and their diluted solutions are beyond the scope of this International Standard.

Employers shall provide training and health and safety information in conformance with legal requirements.

The hazard symbol system used in this International Standard is intended to provide information to the users and is not meant for compliance with any legal requirements for labelling as these vary from country to country.

It is strongly recommended that anyone using these chemicals obtain from the manufacturer pertinent information about the hazards, handling, use and disposal of these chemicals.

4.2 Hazard information code system

- < B > Harmful if inhaled. Avoid breathing dust, vapour, mist or gas. Use only with adequate ventilation.
- < C > Harmful if contact occurs. Avoid contact with eyes, skin or clothing. Wash thoroughly after handling.
- < S > Harmful if swallowed. Wash thoroughly after handling. If swallowed, obtain medical attention immediately.
- << S >> May be fatal if swallowed. If swallowed, obtain medical attention immediately.
- < F > Will burn. Keep away from heat, sparks and open flame. Use with adequate ventilation³⁾.
- < O > Oxidizer. Contact with other material may cause fire. Do not store near combustible materials.

4.3 Safety precautions

All pipette operations shall be performed with a pipette bulb or plunger pipette.

Safety glasses shall be worn for all laboratory work.

5 Requirements for film bases

The base used for record films, as specified in this International Standard, shall be of a safety polyester [i.e. poly(ethylene terephthalate)] or a cellulose-ester type, and can be identified by the method described in 9.1.

Some films on a cellulose-ester-type base can have a maximum LE rating of 100. Some films on a polyester base can have a maximum LE rating of 500.

NOTE 5 These limitations are based on historical experiences as discussed in the introduction.

6 Requirements for processed film

Films shall be stored under the conditions specified in ISO 5466 and ISO 10214.

6.1 Safety film

The film shall meet the requirements specified in ISO 543.

6.2 Amount of free acid

Different specifications and test methods are given for polyester base and cellulose-ester base films. The polyester base shall not have an amount of free acid greater than the equivalent of 1,0 ml of 0,1 mol/l sodium hydroxide solution per gram of film, and the cellulose-ester base shall not have an amount of free acid greater than the equivalent of 0,5 ml of 0,1 mol/l sodium hydroxide solution per gram of film. The amount of free acidity shall be measured in accordance with 9.3.

The volume of 0,1 mol/l sodium hydroxide equivalent to the amount of free acid of the processed film shall not increase by more than 0,5 ml/l over its original value after the accelerated ageing described in 9.2.

6.3 Tensile properties and loss in tensile properties

The film samples shall be processed and dried under the conditions used for the film records. Processed films shall be tested for tensile properties as described in 9.4 and shall have a tensile stress and elongation at break as specified in table 1 (unheated film). The loss in tensile properties after accelerated ageing as described in 9.2 shall not exceed the percentage specified in table 1 (heated film).

3) The flammable warning symbol < F > will not be used for quantities of common solvents under 1 litre.