
**Space systems — Test procedure to
evaluate spacecraft material ejecta upon
hypervelocity impact**

*Systèmes spatiaux — Mode opératoire d'essai pour l'évaluation des
éjectats de matériaux des véhicules spatiaux résultant d'impacts à
hypervitesse*





COPYRIGHT PROTECTED DOCUMENT

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms, definitions, abbreviated terms and symbols	1
3.1 Terms and definitions	1
3.2 Abbreviated terms	3
3.3 Symbols	3
4 General requirements	3
5 Calibration	4
5.1 General	4
5.2 Impact parameters	4
5.3 General environment	4
5.4 Ejecta characterization	5
5.5 Report of calibration tests	5
6 Experimental procedure	5
6.1 General	5
6.2 Impact parameters	5
6.3 General environment	6
6.4 Ejecta characterization and evaluation	6
6.5 Additional tests	7
6.6 Analysis of test results	7
7 Reporting of test results	8
7.1 General	8
7.2 Report of testing of materials	8
7.3 Database	9
8 Quality assurance	9
8.1 General	9
8.2 Quality requirements	9
Annex A (informative) Characterization of material ejected upon impact (ejecta)	11
Annex B (informative) Example of an ejecta model	13
Annex C (informative) Ejecta measurement methods	16
Annex D (informative) Example of a data sheet	20
Annex E (informative) Technical data	22
Bibliography	23

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 11227 was prepared by Technical Committee ISO/TC 20, *Aircraft and space vehicles*, Subcommittee SC 14, *Space systems and operations*.

Introduction

Throughout its orbit lifetime, any spacecraft is exposed to the risk of collision with man-made space debris and natural micrometeoroids. Concentration of natural particles is nearly stable, but the amount of man-made debris is likely to increase over time. Details concerning this space environment can be found in the documents cited in the bibliography (see References [1] and [2]).

Damage caused by meteoroids or debris can result in total or partial mission failure and in a potential generation of small debris. Because of the large collision velocities (hypervelocity domain), even a small object produces upon impact a large amount of small particles, which are called ejecta. Ejecta can damage parts of the spacecraft itself and increase the population of space debris. The orbital lifetime of the ejecta depends on several factors such as size, initial velocity, and orbit altitude of the parent body. This population of space debris is already evaluated at a few percent of the total space debris population and it is likely to increase in the future^{[3][4][5]}. It is therefore necessary, for the mitigation of such particles, to assess the mechanism of their production.

As shown by previous experimental studies^{[6][7][8]}, the amount of ejecta depends primarily on the type of material exposed directly to the space environment. It is greater for brittle materials than for ductile materials; it depends also on the size and on the velocity of impacting particles. Consequently, the best approach for assessing the process is to perform laboratory impact simulation using hypervelocity launchers.

The purpose of this International Standard is to describe a standard approach for assessing the behaviour, under orbital debris or meteoroid hypervelocity impacts, of the materials that are used on the external surfaces of spacecraft^[9].

Results obtained from the standard tests carried out on as wide a range of materials as possible will be stored in a database created for this purpose, or incorporated into an existing one such as ECSS-Q70-71A (see Annex D and Reference [10]). This database will help designers choose spacecraft outer materials that mitigate the risk of space debris.

Space systems — Test procedure to evaluate spacecraft material ejecta upon hypervelocity impact

1 Scope

This International Standard describes an experimental procedure for assessing the behaviour, under orbital debris or meteoroid impacts, of materials that are intended to be used on the external surfaces of spacecraft and launch vehicle orbital stages. This International Standard provides a unified method by which to rank materials. The ejecta production characteristics of different materials are compared under standardized conditions in which test parameters are fixed to one number. Optional tests with different parameters are also useful for the proper selection of materials in other conditions, and they could be performed as research items.

This International Standard establishes the requirements to be satisfied for the test methods in order to characterize the amount of ejecta produced when a surface material is impacted by a hypervelocity projectile. Its purpose is to evaluate the ratio of ejecta total mass to projectile mass, and the size distribution of the fragments. These are the necessary inputs for modelling the amount of impact ejecta that a surface material might release during its orbital lifetime, thereby helping to assess its suitability for space use while mitigating the production of small space debris.

The purpose of this International Standard is to provide data that need to be taken into account in the selection of outer spacecraft materials, though the selection is not based on these criteria alone.

The experimental procedure defines

- the type of facility to be used,
- the size, velocity and type of projectile to be used,
- the evaluation of impact ejecta released,
- the reporting of test results, and
- the quality requirements to be used.

It is anticipated that this International Standard will be the first of several test procedure standards aimed at characterizing the release of small debris from the external surfaces of spacecraft and launch vehicle orbital stages as the result of interaction with the space environment. It is applicable to spacecraft and launch vehicles operating in all types of Earth orbits.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 24113, *Space systems — Space debris mitigation requirements*

3 Terms, definitions, abbreviated terms and symbols

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 24113 and the following apply.

3.1.1

brittle material

material that breaks due to a propagation defect under the action of a stress

3.1.2

ductile material

material that can be plastically deformed without breaking under the action of a stress

3.1.3

ejecta cone

shaped spray of fine particles, comprising fragments and spalls that are released during a high-velocity impact.

3.1.4

fragmentation

process by which an orbiting space object dissociates and produces debris, such as break-up, exposure to space environment, and ageing

3.1.5

hypervelocity impact

impact occurring with a velocity greater than the velocity of sound in any given material

3.1.6

impact crater

damage left on a material, generally hemispherical in shape, after a projectile has hit its surface without going throughout the material

3.1.7

light gas gun

LGG

experimental device consisting of a powder gun that compresses a low-density gas to accelerate a projectile up to hypervelocities

3.1.8

meteoroid

particles of natural origin, resulting from the disintegration and fragmentation of comets and asteroids, which orbit the sun

3.1.9

perforation

hole created by an impact on a thin material in which there is no formation of a crater

3.1.10

plasma gun

experimental device that produces an accelerated plasma flow, which is compressed in a coil and then drags a projectile up to hypervelocities

3.1.11

silica aerogel

low-density solid material, made with a porous, silica-based structure, used for the retrieval of ejecta fragments in impact experiments

3.1.12

spall

piece of material broken and ejected upon high-velocity impact, usually by stress waves, mainly on brittle material

NOTE If the resulting tensile stress caused by the reflection of the compression wave on the surface (front or back) exceeds the tensile strength of the material, a thin sheet of material separates from the target and is ejected.

3.1.13

specimen

target

representative sample of a spacecraft material that is used in impact experiments

3.1.14**stress**

force exerted on a body that tends to strain or to deform its shape.

3.1.15**tensile strength**

power to resist tensile stress

NOTE The tensile strength of brittle materials is about two orders of magnitude less than the tensile strength of metals.

3.1.16**tensile stress**

stress on a material produced by pulling forces along an axis, which tends to extend or break the material

3.1.17**witness plate**

flat sheet of ductile material used in impact experiments to capture ejecta and characterize the resulting damage

3.2 Abbreviated terms

CFRP carbon-fibre-reinforced polymer

HVI hypervelocity impact

LGG light gas gun

MLI multilayer insulation

PVDF polyvinidylene fluoride

3.3 Symbols

M_e total ejecta mass

K material-type-dependent coefficient (ductile or brittle)

β ratio of the mass ejected from the cone to the total ejected mass from the impact crater

t thickness of test sample

d diameter of projectile

4 General requirements

4.1 If this International Standard is applied during the design of a spacecraft or launch vehicle orbital stage, then the test procedure and results shall be approved by approving agents and documented in accordance with the space debris mitigation plan specified by ISO 24113.

4.2 Tests shall be performed at a hypervelocity impact facility that can fully satisfy the experimental procedure.

4.3 Before performing the experimental procedure, a calibration of the hypervelocity impact facility shall be carried out to provide a reference data point for the subsequent tests at the facility.

4.4 The calibration tests will be used to confirm the facility independencies of the test procedure.