
Textiles — Determination of dynamic hygroscopic heat generation

*Textiles — Détermination de la production de chaleur dynamique
hygroscopique*





COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Testing condition	2
5.1 Low humidity air	2
5.2 High humidity air	2
6 Reagents and materials	2
7 Apparatus	2
8 Conditioning atmosphere for sampling	6
9 Preparation of specimens	6
10 Test procedure	6
10.1 Mounting of test specimens	6
10.2 Pretreatment process immediately before measurement	6
10.3 Measurement process	6
11 Calculation	7
12 Test report	8
Annex A (normative) Determination of the air flow rate for high humidity air	9
Annex B (informative) Interlaboratory test results	11
Annex C (informative) Example of a practical testing apparatus	15
Annex D (informative) Example of an interpretation of the test result	16
Bibliography	17

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 38, *Textiles*.

This second edition cancels and replaces the first edition (ISO 18782:2015), which has been technically revised.

The main changes are as follows:

- in [Clause 3](#), temperature definitions have been added;
- in [Clause 7](#), [Figure 1](#) has been changed from one testing position to 4 testing positions;
- in [7.2.5.5](#), rectifying plate was introduced for more stable testing;
- in [Clause 10.2](#), the pretreatment process has been added;
- in [Annex A](#), the pretreatment process has been added to the testing method for the determination of air flow rate for high humidity.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

In the apparel and clothing market, warm heat-comfort textile material is attracting consumers' attention. It offers comfortable warmth through the combined technology of the hygroscopic heat generation and heat insulation.

The phenomenon of the hygroscopic heat generation is known as a common function of natural fibres especially, but not so much for synthetic fibres. Therefore, the synthetic fibre producers have been developing fibres and textiles with an appropriate warm-feeling property.

This document provides a test method to obtain the practical heat generation of textiles under wearing conditions.

The apparatus used in this test method has multiple test positions. So, this method is practical and economical with high accuracy.

Textiles — Determination of dynamic hygroscopic heat generation

1 Scope

This document specifies a test method for the determination of hygroscopic heat generated by flowing low to high humidity air on one side of a surface. It is applicable to all kinds of sheet-shaped textile materials.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 105-F02, *Textiles — Tests for colour fastness — Part F02: Specification for cotton and viscose adjacent fabrics*

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

generated hygroscopic heat

hygroscopic heat generated by the loss of kinetic energy when gaseous water molecules are adsorbed on a surface of textile material

3.2

temperature at low humidity

T_{initial}

initial equilibrium temperature at measurement side of a specimen when the low humidity air is supplied

3.3

generated hygroscopic heat temperature

ΔT

temperature difference between the initial equilibrium temperature and the temperature when the high humidity air is supplied on measurement side of a specimen

3.4

maximum temperature at high humidity

T_{max}

maximum temperature at measurement side of a specimen when high humidity air is supplied

3.5

maximum generated hygroscopic heat temperature

$\Delta T_{\max}$

maximum value of the generated hygroscopic heat temperature ΔT

4 Principle

When the air supply is switched from low humidity to high humidity in instant, the temperature at the specimen increases and reaches a peak due to the hygroscopic heat generation. The temperature at one side of specimen is measured during this air change and the peak temperature is determined as $\Delta T_{\max}$. In this test method, the high humidity air flow rate is determined by a cotton control specimen in which the $\Delta T_{\max}$ becomes $2,8\text{ °C} \pm 0,3\text{ °C}$.

5 Testing condition

5.1 Low humidity air

The air is taken from the atmosphere of the constant temperature and humidity chamber (7.1) in which the temperature is controlled at $20\text{ °C} \pm 2\text{ °C}$ and the relative humidity at $(40 \pm 3)\%$. The air flow rate is set at $1,0\text{ l/min} \pm 0,1\text{ l/min}$.

5.2 High humidity air

The air in the constant temperature and humidity chamber (7.1) is passed through bubbling bottle (7.2.2) and supplied to specimen as a high humidity air.

NOTE High humidity air is controlled by the air flow rate only; therefore, humidity measurements are not essential. However, the humidity of high humidity air has been known as $(90 \pm 5)\%$ RH.

6 Reagents and materials

6.1 Water, distilled water, ion exchanged water, grade 3 water according to ISO 3696 or equivalent for humidifying air in a bubbling bottle (7.2.2).

6.2 Control specimen, a cotton adjacent fabric as specified in ISO 105-F02.

7 Apparatus

7.1 Constant temperature and humidity chamber or room, capable of maintaining the temperature at $20\text{ °C} \pm 2\text{ °C}$ and the relative humidity at $(40 \pm 3)\%$. The hygroscopic heat generation testing apparatus (7.2) is placed in the chamber or room.

7.2 Hygroscopic heat generation testing apparatus, shown in Figure 1. All devices are placed in the chamber (7.1) in case of cabin type. If in case the oven type, the switching valve and control device