

INTERNATIONAL STANDARD

ISO
2023

Second edition
1994 12 01

Rubber footwear — Lined industrial vulcanized-rubber boots — Specification

*Articles chaussants en caoutchouc — Bottes doublées en caoutchouc
vulcanisé à usage industriel — Spécifications*



Reference number
ISO 2023:1994(E)



Documents

Document Sharing Hub

Contents

Page

1	Scope	1
2	Normative references.....	1
3	Definitions	1
4	Design requirements.....	1
5	Physical properties	2
6	Leakage and immersion requirements.....	3
7	Marking.....	3

Annexes

A	Measurement of minimum thickness	5
B	Determination of resistance to abrasion of laces	7
C	Determination of breaking force of laces	9
D	Determination of breaking force of boot upper	10
E	Determination of resistance to flexing	11
F	Boot heights	14

Tables

1	Minimum thickness.....	2
2	Minimum breaking force of boot upper.....	2
3	Minimum number of flex cycles of boot upper	3
4	Tensile strength and elongation at break of outsole and heel.....	3
5	Changes in value of tensile strength and elongation at break after ageing of outsole and heel.....	3
F.1	Boot heights	14

Figures

A.1	Centreline of boot.....	6
B.1	Lace-abrading machine.....	8
E.1	Test piece for flexing test.....	12
E.2	Arrangement of apparatus and test piece during the flexing cycle	13

© ISO 1994

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 2023 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*.

This second edition cancels and replaces the first edition (ISO 2023:1973), which has been technically revised.

Annexes A, B, C, D and E form an integral part of this International Standard. Annex F is for information only.

Rubber footwear — Lined industrial vulcanized-rubber boots — Specification

1 Scope

This International Standard specifies requirements for lined industrial vulcanized-rubber ankle, half-knee, short-knee and knee-height boots, for men and women, and lined rubber boots of three-quarter and full-thigh height for men.

The standard does not cover the style of boot.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 37:1994, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*.

ISO 132:1983, *Rubber, vulcanized — Determination of flex cracking (De Mattia)*.

ISO 188:1982, *Rubber, vulcanized — Accelerated ageing or heat-resistance tests*.

ISO 815:1991, *Rubber, vulcanized or thermoplastic — Determination of compression set at ambient, elevated or low temperatures*.

ISO 10335:1990, *Rubber and plastics footwear — Nomenclature*.

3 Definitions

For definitions of footwear terms, see ISO 10335.

4 Design requirements

4.1 Boot upper

The boot upper shall consist of one or more plies of rubber and fabric.

4.2 Minimum thickness

At no point shall the thickness of the boot be less than the appropriate value given in table 1, when measured as described in annex A.

In the case of heels with internal cavities, the thickness from the outer surface of the heel to the start of the cavity, over any cleat, including pattern, shall be not less than 9,0 mm.

4.3 Materials and components

4.3.1 Mandatory requirements

4.3.1.1 Laces

When tested in accordance with the method described in annex B, laces shall have an average abrasion resistance of not less than 11 000 cycles.

When tested in accordance with the method described in annex C, laces shall have an average breaking force of not less than 500 N.

Table 1 — Minimum thickness

Dimensions in millimetres

Measurement	Height			
		Over cleat	Between cleats	Non-cleat
Boot upper	4,5			
Foxing strip at the toe	3,0			
Foxing strip at the heel	4,0			
Foxing strip in other areas	2,5			
Insole, filler and soling (men's)		13,0		9,0
Insole, filler and soling (women's)		11,0		9,0
Cleated soling (men's)		9,0	3,0	
Cleated soling (women's)		7,0	2,5	
Non-cleated soling				5,0
Cleated heel (men's)		25,0		
Cleated heel (women's)		20,0		
Non-cleated heel				20,0

4.3.1.2 Metal components

If footwear is to be used in potentially flammable or explosive atmospheres, no metal component shall be of aluminium, magnesium or titanium; neither shall any alloy containing one or more of these constituents be used unless both the total content of these three constituents does not exceed 15 % by mass, and the content of magnesium and titanium together does not exceed 6 % by mass.

NOTE 1 These limitations have been imposed to avoid the hazards of sparking due to friction between rusted steel or iron and the metals described.

4.3.2 Optional requirements

Boot heights

Suggested ranges for heights of boots are given in annex F.

5 Physical properties

5.1 Breaking force of the boot upper

When tested as described in annex D, the breaking force shall be in accordance with table 2.

Table 2 — Minimum breaking force of boot upper

	Minimum breaking force — length and breadth directions N/25 mm
Woven material	250
Knitted fabric	180

5.2 Resistance to flexing of boot upper after ageing

Four test pieces shall be cut from the boot length, two along the length and two across the breadth, and, after ageing for 168 h at 70 °C ± 1 °C in accordance with the ISO 188 air-oven method, shall be tested as described in annex E.

All four test pieces shall withstand the number of continuous flex cycles shown in table 3 without showing pinholes or cracking when viewed with the unaided eye, and shall meet the requirements of grade 1 or grade 2 of ISO 132.

For this purpose, only those parts of the test piece shall be observed which are under tension during the test, i.e. the folds which form a diamond shape. The centre fold of the test piece, pinholes or cracking associated with machine damage shall be ignored.

Table 3 — Minimum number of flex cycles of boot upper

Thicknesses of individual test piece mm	Number of flexes	
	Hand-built type	Moulded type
≤ 2,0	125 000	75 000
> 2,0 but ≤ 2,25	110 000	50 000
> 2,25	90 000	40 000

5.3 Tensile strength and elongation at break of outsole and heel

The outsole and heel shall be reduced to sheets or pieces either by careful buffing or by careful slitting. The sheets or pieces shall be of sufficient size and thickness to be able to stamp a maximum of ten standard-size test pieces. The tensile strength and elongation at break of the outsole and heel shall then be determined in accordance with ISO 37. The type of dumb-bell used shall be stated when quoting results. Of the ten test pieces, five shall be aged prior to testing.

Three test pieces shall be tested and the median value of the three test results shall be in accordance with table 4. If the median value of the results is below the appropriate value given in table 4, and at the same time the highest value is above the appropriate value given in table 4, then the other two test pieces shall be tested.

Table 4 — Tensile strength and elongation at break of outsole and heel

Outsole thickness mm	Tensile strength (min.) MPa	Elongation at break (min.) %
≤ 9,0	8,5	250
> 9,0 but ≤ 10,0	8,0	225
> 10,0 but ≤ 11,0	7,5	200
> 11,0	7,0	200
Heel	7,0	200

After submission to the ageing treatment described in table 5, the median value for tensile strength and elongation at break shall not show changes, from the corresponding unaged median values, greater than the amount given in table 5.

Table 5 — Changes in value of tensile strength and elongation at break after ageing of outsole and heel

Ageing treatment	Maximum change after ageing	
	Tensile strength	Elongation at break
168 h at 70 °C ± 1 °C in accordance with ISO 188 air-oven method	± 20 % of unaged value	– 30 % to + 10 % of unaged value

5.4 Compression set of heel

When tested in accordance with ISO 815 at 70 °C ± 1 °C for 24 h using lubricated small test pieces, samples taken from the heel shall have a compression set of not more than 50 %.

6 Leakage and immersion requirements

6.1 Requirements

When boots are tested as described in 6.2, there shall be no leakage of air. In the case of ankle boots, leakage of air in the vicinity of either the eyelets or gusset shall not constitute a failure but such boots shall then be subjected to an immersion test as described in 6.3, when there shall be no water penetration to the inside of the boot.

6.2 Leakage test procedure

Seal the top of the boots and force air into the boot at a pressure of 10 kPa. Immerse the boot in water to within 75 mm of the top and examine the boot for escape of air bubbles.

6.3 Immersion test for ankle boots

Immerse the boot in water to within 75 mm of the top for a period of 16 h. Remove the boot and examine to see if water has penetrated to the inside.

7 Marking

Each article of footwear shall be indelibly and legibly marked with the following:

- size, stamped on the inside or moulded or impressed on the waist of the outsole;
- manufacturer's or supplier's identification mark;