



**International
Standard**

ISO 20351

**Fine ceramics (advanced ceramics,
advanced technical ceramics) —
Test method for optical properties
of ceramic phosphors for white
light-emitting diodes using an
integrating sphere**

**Second edition
2024-10**

Reference number
ISO 20351:2024(en)

Full document details: [ISO 20351-2024](#)

© ISO 2024  **Documents**
Document Sharing Hub



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	v
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Measurement apparatus	2
4.1 Apparatus configuration	2
4.2 Light source unit	4
4.3 Sample unit	4
4.3.1 Cell	4
4.3.2 White diffuser or reference cell	4
4.3.3 Integrating sphere	4
4.4 Detection unit	5
4.4.1 Directing optical system	5
4.4.2 Spectrometer and detector	5
4.4.3 Amplifier	5
4.5 Signal and data processing unit	5
5 Calibration, inspection and maintenance of measurement apparatus	5
5.1 General	5
5.2 Wavelength calibration of light source unit	5
5.3 Cells and cover glasses	5
5.4 Integrating sphere walls and white diffusers	5
5.5 Wavelength calibration of detection unit	5
5.6 Spectral responsivity correction	6
6 Samples	6
6.1 Reference material	6
6.2 Storage and pre-processing	6
6.3 Filling cells with samples	6
7 Procedure, calculation and report for absolute measurement	6
7.1 Measurement method	6
7.1.1 Measurement environment	6
7.1.2 Light spectrum without phosphor sample	7
7.1.3 Light spectrum with phosphor sample	7
7.2 Calculations	7
7.2.1 Conversion to photon-number-based spectra	7
7.2.2 Fluorescence spectrum	8
7.2.3 Internal quantum efficiency	8
7.3 Test report	8
8 Procedure, calculation and report for substitution measurement	9
8.1 Measurement procedures	9
8.1.1 Measurement environment	9
8.1.2 Spectrometer setup for substitution measurement	9
8.1.3 Measurement for reference material	10
8.1.4 Measurement for phosphor material under test	10
8.2 Calculation	10
8.2.1 Spectral responsivity correction	10
8.2.2 Conversion to photon number-based spectral distribution	10
8.2.3 Calculation of scattered light and fluorescence photon numbers	11
8.2.4 External quantum efficiency	12
8.2.5 Absorptance	12
8.3 Test report	12

Bibliography **14**

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 206, *Fine ceramics*.

This second edition cancels and replaces the first edition (ISO 20351:2017), which has been technically revised.

The main changes are as follows:

- scope of the document is expanded by additionally implementing the reference material-based substitution measurement method to measure external quantum efficiency and absorptance.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

White light-emitting diode (LED) based solid-state lighting (SSL) has been widely used for a variety of applications as alternatives for incandescent and fluorescent lamps. Initially, white LEDs (comprising blue LEDs and yellow phosphors) became popular as backlight sources for small-size liquid-crystal displays (LCDs) used in mobile phones and digital cameras. These were followed by white LEDs (consisting of blue LEDs combined with green and red phosphors) applied to backlight sources for large-area LCDs. Subsequently, LED lamps were commercialised for general lighting, replacing conventional luminaires and capitalising on their advantages, such as compactness, high luminous efficiency, high brightness below 0 °C or higher ambient temperatures, long life, and controllability of light intensity and colour temperature.

The previous edition of this document (ISO 20351:2017) was developed based on the need for standardizing a test method for internal quantum efficiency of phosphors using an integrating sphere. This standard test method has the advantage of a short measurement time and being available to those with no expertise in precise optical measurement. The external quantum efficiency and absorptance were out of the scope of ISO 20351:2017 due to an insufficient understanding of the source of variation in these measurement values.

ISO 23946 was then developed to provide alternative absolute measurement methods for the external quantum efficiency, internal quantum efficiency and absorptance using a gonio-spectrofluorometer. The application of ISO 23946 is assumed to be limited to those who intend to determine the optical properties of phosphor materials to be utilized as reference materials due to its complicated equipment and time-consuming procedure. ISO 13915 was developed following ISO 23946 and provides substitution measurement methods comparing with reference materials with values evaluated in accordance with ISO 23946 to provide external quantum efficiency, internal quantum efficiency and absorptance by using a commercially available fluorescence spectrophotometer.

It was found that the external quantum efficiency and absorptance of a phosphor material under test can also be appropriately obtained using an integrating sphere-based spectrometer with the substitution measurement method as described in ISO 13915, where the measurement using an integrating sphere-based equipment is excluded.

Therefore, the revised second edition of this document is intended to expand the scope by additionally implementing the substitution measurement method for obtaining external quantum efficiency and absorptance using an integrating sphere to the existing absolute method to obtain internal quantum efficiency. This expanded scope will benefit those who routinely use integrating sphere-based equipment.

In this document, measurement conditions and procedures that can affect the measurement values are described in detail, helping those who address high-performance phosphors for competitive SSL products to obtain appropriate information on their competitiveness.

This document can also be adopted for phosphors used in non-white LEDs, e.g. green, orange, pink and purple.

Fine ceramics (advanced ceramics, advanced technical ceramics) — Test method for optical properties of ceramic phosphors for white light-emitting diodes using an integrating sphere

1 Scope

This document specifies test methods for the use of an integrating sphere to measure the optical properties of ceramic phosphor powders, which are used in white light-emitting diodes (LEDs) and emit visible light when excited by UV or blue light. This document specifies an absolute method to measure internal quantum efficiency and a substitution method to measure external quantum efficiency and absorptance. The substitution method uses reference materials whose external quantum efficiency and absorptance have been obtained in accordance with ISO 23946.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 23946, *Fine ceramics (advanced ceramics, advanced technical ceramics) — Test methods for optical properties of ceramic phosphors for white light-emitting diodes using a gonio-spectrofluorometer*

CIE S 017/E:2020, *ILV: International Lighting Vocabulary, 2nd edition*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 23946 and CIE S 017/E and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

internal quantum efficiency

ratio of the number of photons emitted in free space from the phosphor to the number of excitation light photons absorbed by the phosphor

3.2

external quantum efficiency

ratio of the number of photons emitted in free space from the phosphor to the number of excitation light photons incident on the phosphor

3.3

absorptance

ratio of the number of excitation light photons absorbed by the phosphor to the number of excitation light photons incident on the phosphor