
INTERNATIONAL STANDARD



2040

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Strontium chromate pigments for paints

First edition — 1972-06-15

JUN 29 1972

ANSI Internet Doc Sect

UDC 667.622 : 661.843

Ref. No. ISO 2040-1972 (E)

Descriptors : chemical analysis, chromates, materials specifications, pigments, strontium compounds, tests.

AVA Documents
Price based on 5 pages
Document Sharing Hub

FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO Member Bodies). The work of developing International Standards is carried out through ISO Technical Committees. Every Member Body interested in a subject for which a Technical Committee has been set up has the right to be represented on that Committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the Technical Committees are circulated to the Member Bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 2040 was drawn up by Technical Committee ISO/TC 35, *Paints and varnishes*.

It was approved in February 1971 by the Member Bodies of the following countries:

Egypt, Arab Rep. of	Italy	Spain
France	Netherlands	Sweden
Germany	Poland	Switzerland
India	Portugal	United Kingdom
Israel	South Africa, Rep. of	

No Member Body expressed disapproval of the document.

© International Organization for Standardization, 1972 •

Printed in Switzerland

Strontium chromate pigments for paints

1 SCOPE AND FIELD OF APPLICATION

This International Standard lays down the requirements and test methods for strontium chromate pigments of approximate composition SrCrO_4 suitable for use in paints and corrosion-inhibiting coatings.

2 REFERENCES

ISO/R 787, *General methods of test for pigments*.
ISO/R 842, *Sampling raw materials for paints and varnishes*.

3 REQUIRED CHARACTERISTICS AND THEIR TOLERANCES

Strontium chromate pigments for paints shall have the characteristics shown in the Table below.

4 SAMPLING

A representative sample of the pigment shall be taken in accordance with ISO/R 842.

TABLE — Required characteristics and their tolerances

Characteristic ¹⁾		Requirement	Test method
Strontium content	% SrO	min. 48	clause 5.1
Total chromate content	% CrO_3	min. 46	clause 5.2
Water-soluble chloride content	% Cl	max. 0.1	clause 5.3.2
Water-soluble nitrate content	% NO_3	max. 0.1	clause 5.3.3 or 5.3.4
Chromate content in 100 ml of extract from 10 g of pigment	g CrO_3 /100 ml	0.04 to 0.1	clause 5.3.5
Volatile matter at 105 °C	%	max. 1.0	ISO/R 787, Part II
Oil absorption value, com- pared with value agreed between the interested parties		within ± 15 %	ISO/R 787, Part V
Residue on sieve (63 μm)	oil method %	max. 0.5	ISO/R 787, Part VI
	water method %	max. 0.3	ISO/R 787, Part VII

1) If a value for density is agreed between the interested parties, the method for determination shall be that given in ISO/R 787, Part X.