
Paper — Requirements for stability for general graphic applications

*Papier — Exigences pour évaluer la stabilité pour les applications
graphiques générales*





COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Sampling	2
6 Requirements for paper stability	2
6.1 Tearing resistance	2
6.1.1 Conditioning	2
6.1.2 Tear testing	2
6.2 Retention of tearing resistance	3
6.3 Alkali reserve	3
6.4 pH value of aqueous extract	3
7 Precision	3
8 Test report	3
9 Statement of compliance	4
10 Related information	4
Annex A (informative) Precision	5
Annex B (informative) Effect of accelerated ageing on optical properties	9
Annex C (informative) International Standards on paper permanence, archival paper permanence and durability, and on stability for general graphic applications	10
Annex D (informative) Accelerated ageing tests	12
Annex E (informative) Statement of compliance	13
Bibliography	14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 2, *Test methods and quality specifications for paper and board*.

Introduction

This document is intended for papers used for general graphic applications. Paper meeting the requirements of this document will not undergo any significant loss of mechanical properties under normal use and storage conditions. Typical applications include paper products, such as copy paper, brochures, maps and books, which can tolerate some changes in optical properties over time, the magnitude of which may vary with the type of paper and papermaking conditions. Such changes, if any, will not affect the legibility or reproducibility of the information.

This document effectively responds to market needs and environmental requirements. In recent years, there have been an increased trend and interest worldwide in the use of bleached chemithermomechanical pulp (BCTMP), alkaline peroxide mechanical pulp (APMP) and secondary fibre pulp for general applications, such as copy paper, brochures, maps and books which are not intended for permanent storage. Thus, this document will open up opportunities for high-yield pulp producers and paper manufacturers to develop and market a wide range of products containing mechanical fibre, as well as most types of recycled fibre. In particular, coated and uncoated printing and writing papers containing high-yield pulps, such as BCTMP or most types of recycled fibre, can be classified as stable paper, as long as they meet the specifications described in this document. This document will also be of benefit to paper customers and consumers as it provides them with options depending on their end-use applications.

The benefits of using mechanical fibre and/or most types of recycled fibre in paper products may range from improvement in some paper attributes, such as opacity, and lower production costs, to higher sustainability and a greatly reduced environmental footprint. In particular, the amount of virgin fibre, energy consumption, use of water resources, levels of greenhouse gas and other emissions, and solid discharge are significantly lower with the utilization of high-yield pulp and/or most types of recycled pulp in paper production.

Paper — Requirements for stability for general graphic applications

1 Scope

This document specifies the requirements for the stability of paper for general graphic applications. It is applicable to all types of uncoated, coated and filled papers.

NOTE For information on International Standards on paper permanence (see ISO 9706), archival paper permanence and durability (see ISO 11108) and on paper stability for general graphic applications (see ISO 20494), refer to [Annex C](#).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 187, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples*

ISO 536, *Paper and board — Determination of grammage*

ISO 1974, *Paper — Determination of tearing resistance — Elmendorf method*

ISO 5630-3, *Paper and board — Accelerated ageing — Part 3: Moist heat treatment at 80 degrees C and 65 % relative humidity*

ISO 6588-1, *Paper, board and pulps — Determination of pH of aqueous extracts — Part 1: Cold extraction*

ISO 10716, *Paper and board — Determination of alkali reserve*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

paper stability

ability of paper to retain its intended functionality for *general graphic applications* ([3.2](#)), under normal use and storage conditions

Note 1 to entry: Stability for the purpose of this document differs from permanence which is required for paper used for documents to be stored over long periods of time, as in libraries, archives and other protected environments (see ISO 9706).